

Analysis	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Co	Ti	V
1	0.0339	1.691	0.0230	0.0204	0.56	0.270	10.475	17.07	0.28	0.0435	0.350	0.069
2	0.0346	1.702	0.0234	0.0208	0.563	0.271	10.491	17.08	0.286	0.044	0.360	0.073
3	0.0349	1.71	0.0235	0.0211	0.566	0.273	10.52	17.08	0.291	0.0455	0.379	0.073
4	0.0349	1.72	0.0235	0.0212	0.57	0.274	10.526	17.08	0.294	0.047	0.382	0.074
5	0.0350	1.722	0.0244	0.0218	0.576	0.275	10.545	17.11	0.301	0.047	0.385	0.077
6	0.035	1.723	0.0245	0.0218	0.58	0.277	10.552	17.13	0.302	0.047	0.388	0.078
7	0.036	1.73	0.0248	0.0218	0.582	0.280	10.568	17.16	0.304	0.0488	0.389	0.078
8	0.0365	1.73	0.025	0.022	0.582	0.280	10.58	17.164	0.307	0.0494	0.39	0.080
9	0.0367	1.734	0.025	0.0220	0.584	0.280	10.626	17.191	0.308	0.0495	0.390	0.080
10	0.0370	1.734	0.0259	0.0222	0.586	0.284	10.63	17.194	0.308	0.0504	0.391	0.080
11	0.0383	1.738	0.0267	0.0226	0.588	0.286	10.659	17.20	0.308	0.0512	0.391	0.082
12	0.0384	1.74	0.0271	0.0228	0.588	0.286	10.66	17.20	0.309	0.0515	0.392	0.082
13	0.0384	1.744	0.0273	0.0232	0.588	0.287	10.66	17.21	0.310	0.0535	0.393	0.082
14	0.0398		0.0276	0.0242	0.589	0.289		17.24	0.313		0.395	0.083
15	0.0400			0.0244	0.589	0.292		17.241	0.313		0.396	0.085
16	0.0405				0.596	0.303		17.242			0.40	0.090
Average	0.0369	1.724	0.0251	0.0221	0.580	0.2817	10.576	17.162	0.3023	0.0483	0.3857	0.0791
Std Dev	0.0021	0.016	0.0016	0.0011	0.011	0.0087	0.065	0.062	0.0101	0.0030	0.0131	0.0052
Certified	0.037	1.72	0.025	0.022	0.58	0.28	10.58	17.16	0.30	0.048	0.38	0.079

Analysis	Al	N	Nb	Sn	As	B	Ca	O	W
1	0.0385	0.00755	0.004	0.0049	0.002	0.0003	0.0001	0.0005	0.0093
2	0.040	0.0079	0.005	0.0053	0.0048	0.00038	0.0001	0.00051	0.023
3	0.0395	0.00795	0.006	0.0055	0.0049	0.0006	0.00013	0.00108	0.029
4	0.042	0.00817	0.006	0.006	0.0052	0.0006	0.00015	0.0012	0.0358
5	0.042	0.0083	0.0063	0.0062	0.0052			0.00128	0.036
6	0.043	0.00875	0.0073	0.0075				0.0014	0.0410
7	0.045	0.00913	0.0075					0.00155	0.044
8	0.045		0.0076						
9	0.045		0.0078						
10	0.045		0.008						
11	0.046		0.009						
12	0.047		0.009						
13	0.0475		0.0101						
14			0.011						
15			0.0115						
Average	0.0435	0.00825	0.0077	0.0059	0.0044	0.00047	0.00012	0.00107	0.0312
Std Dev	0.0029	0.00054	0.0021	0.0009	0.0014	0.00015	0.00002	0.00042	0.0119
Certified	0.044	0.0082	0.008	0.006	(0.004)	(0.0005)	(0.0001)	(0.0011)	(0.03)

Data in parentheses are not certified but provided for information only.

Analysis: Chemical analyses were made on chips prepared by a lathe from the certified portion of the discs. The laboratories participating in the testing normally followed the requirements of ISO Guide 25. The individual values listed above are the average of each analyst's results. Methods of analysis used were a combination of ASTM Standard Methods E 350, E 353, E 572, E 1019, E 1086, plus additional ICP and AA spectrometric methods. The following Certified Reference Materials were used to validate the analytical data listed above: NIST SRM 15h, 73c, 101f, 101g, 121d, 123c, 131c, 160b, 344, 345, 348a, 362; ECRM 284-1, 286-1; BCS 466/1, 467/1, 475; JK 37; IMZ 1.27/3.

Co-operating Laboratories: Some of the co-operating laboratories were:

Allegheny Ludlum Steel Corp., Brackenridge, Pennsylvania
 Allegheny Ludlum Steel Corp., Lockport, New York
 Analytical Associates, Inc., Detroit, Michigan
 Atlas Specialty Steels, Welland, Ontario, Canada
 Brammer Standard Co., Inc., Houston, Texas
 Crucible Specialty Steel, Syracuse, New York
 J. Dirats and Co., Inc., Westfield, Massachusetts
 Andrew S. McCreath & Son, Inc., Harrisburg, Pennsylvania
 VHG Laboratories, Inc., Manchester, New Hampshire

Additional analytical data: This material was used as an unknown test specimen in the Brammer Standard Company's Stainless Steel Proficiency Testing Program (PTP). The participating laboratories used a combination of combustion instruments, XRF spectrometers, and optical emission spectrometers. The data shown below are the results from the PTP.

	C	Mn	P	S	Si	Cu	Ni		
Number of Labs	22	25	24	21	25	25	25		
Grand Average	0.0383	1.726	0.0248	0.0222	0.584	0.281	10.547		
Standard Deviation	0.0056	0.040	0.0022	0.0015	0.019	0.008	0.117		
	Cr	Mo	Al	Co	Nb	Ti	V	N	
Number of Labs	24	23	21	23	18	25	23	15	
Grand Average	17.185	0.303	0.0446	0.0512	0.0091	0.387	0.0784	0.0090	
Standard Deviation	0.077	0.012	0.0064	0.0048	0.0046	0.020	0.0070	0.0010	

Homogeneity: This Reference Material was tested for homogeneity using ASTM Standard Practice E 826 and found acceptable.

Traceability: This Reference Material was also examined by optical emission spectrometry and found to be compatible with the following Certified Reference Materials: NIST SRM C1151, C1152, C1153, C1154; SS 467; JSS 655-8.

Source: This material was produced by Talley Metals. The material was made in an electric arc furnace and cast into ingots. The bar stock was hot rolled and annealed.

Available Form: This Reference Material is available only in the form of a disc, approximately 38 mm (1.50") in diameter and 12 mm (0.50") thick.

Use: This Reference Material is intended for use in optical emission and x-ray spectrometric methods of analysis. The entire depth of the disc may be used.

Caution: As with any bar material, avoid optical emission spectrometric burns in the center of the disc (5 mm radius), as some segregation may be present.

Because this Reference Material contains a high percent of nickel and chromium, care must be taken in its application. Make certain that corrections are made for possible element interference and dilution effects.

Sample Preparation: For best analytical results, use the same method for preparing the analytical surface on all reference materials as you use for production specimens. Avoid overheating the disc during surface preparation.

Safety Notice: A Material Safety Data Sheet (MSDS) is not required for this material. This material will not release or otherwise result in exposure to a hazardous chemical, under normal conditions of use. Inquiries concerning this Reference Material should be directed to:

Brammer Standard Co., Inc. Phone: (713) 440-9396
14603 Benfer Road
Houston, Texas 77069-2895 USA Fax: (713) 440-4432

Certified by: _____ on July 28, 1994.
G. R. Brammer

Certificate Number 321C-072894

References:

ASTM documents available from ASTM, 1916 Race Street, Philadelphia, PA, 19103.

E 350-90 Standard Test Methods for Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

E 353 - 93 Standard Test Methods for Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

E 572 - 88 Standard Test Method for X-Ray Emission Spectrometric Analysis of Stainless Steel

E 826 - 85 (Reapproved 1990) Standard Practice for Testing Homogeneity of Materials for the Development of Reference Materials

E 1019-93 Standard Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel and in Iron, Nickel, and Cobalt Alloys

E 1086 - 85 Standard Method for Optical Emission Vacuum Spectrometric Analysis of Stainless Steel by the Point-to-Plane Excitation Technique

ISO Guides available from American National Standards Institute, 11 West 42nd St., 13th Floor, New York, NY 10036.

ISO Guide 25 (Third edition, 1990), General requirements for the competence of calibration and testing laboratories.

ISO Guide 30 (Second edition, 1991), Terms and definitions used in connection with reference materials.

ISO Guide 31 (First edition, 1981), Contents of certificates of reference materials.

ISO Guide 33 (First edition, 1989), Uses of certified reference materials.

ISO Guide 35 (Second edition, 1989), Certification of reference materials - General and statistical principles.

Other useful documents available at no cost from NIST, U.S. Department of Commerce, Gaithersburg, MD 20899.

NBS Special Publication 260-100, Handbook for SRM Users

NIST Special Publication 829, Use of NIST Standard Reference Materials for Decisions on Performance of Analytical Chemical Methods and Laboratories

Certificate Number 321C-072894