

Brammer Standard Company, Inc.
Certificate of Analysis

B.S. 41

Reference Material for O-6 Tool Steel

	Certified Value ¹	Estimate of Uncertainty ²		Uncertified Value ³
Carbon	1.41	0.02	Aluminum	(0.007)
Manganese	0.89	0.02	Tin	(0.008)
Phosphorus	0.013	0.002		
Sulfur	0.011	0.001		
Silicon	1.02	0.02		
Copper	0.038	0.005		
Nickel	0.15	0.01		
Chromium	0.22	0.01		
Molybdenum	0.23	0.01		
Vanadium	0.046	0.007		
Tungsten	0.035	0.005		

(analysis listed as percent by weight)

¹ The certified value listed is the present best estimate of the true value based on the results of an interlaboratory testing program.

² The uncertainties listed are based on value judgments of the material inhomogeneity and the 95% confidence interval. The half-width confidence interval C(95%) is shown on page 2.

³ Values in parentheses are not certified and are provided for information only.

Some of the co-operating laboratories were:

Alpha Research Laboratory, Stevensville, MI
Dirats Laboratories, Westfield, MA
Herron Testing Laboratories, Cleveland, OH
Turret Alloys Ltd., Analytical Services, Sheffield, England
VHG Labs, Andover, MA

See the following pages for more information.

Original Certificate Number 41-033186
New Certificate Number REV-41-120409

New Certificate Number REV-41-120409 Revised to show uncertainty values on December 4, 2009

Brammer Standard Company, Inc., 14603 Benfer Road, Houston, TX 77069
Telephone (281) 440-9396 Fax (281) 440-4432

Analysis	C	Mn	P	S	Si	Cu	Ni	Cr	Mo
1	1.383	0.85	0.010	0.009	0.98	0.030	0.140	0.207	0.200
2	1.395	0.87	0.011	0.010	1.00	0.034	0.145	0.216	0.215
3	1.400	0.89	0.012	0.010	1.01	0.036	0.150	0.220	0.220
4	1.402	0.89	0.012	0.010	1.02	0.040	0.150	0.220	0.230
5	1.410	0.90	0.013	0.011	1.02	0.040	0.160	0.220	0.230
6	1.410	0.91	0.014	0.011	1.03	0.042	0.160	0.230	0.230
7	1.420	0.91	0.015	0.012	1.04	0.044	0.170	0.230	0.230
8	1.430	0.92	0.016	0.012	1.05				0.231
9									0.240
Average	1.4063	0.893	0.0129	0.0106	1.019	0.0380	0.1536	0.2204	0.2251
Std Dev	0.0147	0.023	0.0020	0.0011	0.022	0.0049	0.0103	0.0080	0.0118
Certified	1.41	0.89	0.013	0.011	1.02	0.038	0.15	0.22	0.23
t	2.36	2.36	2.36	2.36	2.36	2.45	2.45	2.45	2.31
C (95%)	0.0123	0.019	0.0017	0.0009	0.019	0.0045	0.0095	0.0074	0.0091

Analysis	V	W	Al	Sn
1	0.039	0.030	0.003	0.004
2	0.040	0.032	0.005	0.005
3	0.045	0.033	0.007	0.009
4	0.049	0.035	0.011	0.010
5	0.050	0.038		0.010
6	0.050	0.040		
7	0.051	0.040		
Average	0.0463	0.0354	0.0065	0.0076
Std Dev	0.0050	0.0040	0.0034	0.0029
Certified	0.046	0.035	(0.007)	(0.008)
t	2.45	2.45	3.18	2.78
C (95%)	0.0046	0.0037	0.0054	0.0036

$C(95\%) = (t \times sd) / \sqrt{n}$ The half-width confidence interval, where t is the appropriate Student's t value, sd is the interlaboratory standard deviation, and n is the number of acceptable mean values. For further information regarding the confidence interval for the certified value see ISO Guide 35:2006 section 6.

ISO Guides and Standards available from Global Engineering - www.global.ihs.com

Data in parentheses are not certified but provided for information only.

Analysis: Chemical analyses were performed on chips taken from cross-sections of the discs. The individual values listed above are the average of each analyst's results.

Form: This Reference Material is machined in the form of a disc, approximately 42 mm diameter and 18 mm thick by Brammer Standard Company. The bar stock used for this material was produced by hot-rolling billets and annealing.

Certificate Number: The unique identification number for this certificate of analysis is REV-41-120409. This BS 41 Certificate of Analysis was revised to show the estimate of uncertainty for the certified values.

Refer to the "Certificates" section of the Brammer Standard Company website for any revision to this or other Brammer Standard Company's Certificates of Analysis.

Use: This Reference Material is intended for use in spark atomic emission and x-ray spectrometric methods of analysis.

Certified area: The entire depth of the disc may be used.

Caution: As with any bar material, avoid spark atomic emission spectrometric burns in the center of the disc (5 mm radius), as some segregation may be present.

Sample Preparation: For best analytical results, use the same method for preparing the analytical surface on all reference materials as you use for production specimens. Avoid overheating the disc during surface preparation.

Safety Notice: A Material Safety Data Sheet (MSDS) is not required for this material. This material will not release or otherwise result in exposure to a hazardous chemical, under normal conditions of use. Inquiries concerning this Reference Material should be directed to:

Brammer Standard Co., Inc. 14603 Benfer Road Houston, Texas 77069 USA	Phone: (281) 440-9396 Fax: (281) 440-4432	web: brammerstandard.com email: contact@brammerstandard.com
---	--	--

Revision Certified by: _____ on December 4, 2009.
Beau R. Brammer

**Brammer Standard Company, Inc., is accredited to ISO Guide 34 as a Reference Material Producer for the production of Certified Reference Materials and Reference Materials by A2LA (Certificate Number 656.02)
The scope of accreditation is listed on the website: www.brammerstandard.com**

**Brammer Standard Company's Chemical Laboratory is accredited to ISO Standard 17025 by A2LA.
(Certificate Number 656.01)**

By Certificate Number 10539, the Quality System of Brammer Standard Company, Inc., is registered to ISO 9001:2000 by National Quality Assurance, U.S.A.

Certificate Number REV-41-120409p3