

Brammer Standard Company, Inc.
Certificate of Analysis

B.S. 48A

Reference Material for F-9 Grade Cr-Mo Steel Alloy

	Certified Value ¹	Estimate of Uncertainty ²		Certified Value ¹	Estimate of Uncertainty ²
Analysis listed as percent by weight					
C	0.121	0.004	Al	0.018	0.002
Mn	0.43	0.01	Co	0.022	0.003
P	0.012	0.002	N	0.021	0.001
S	0.011	0.001	Sn	0.014	0.002
Si	0.68	0.01	Ti	0.002	0.001
Cu	0.133	0.006	V	0.014	0.002
Ni	0.29	0.01			
Cr	8.75	0.02			
Mo	0.95	0.01			

¹ The certified value listed is the present best estimate of the true value based on the results of an interlaboratory testing program.

² The uncertainties listed are based on value judgments of the material inhomogeneity and possible bias in the determined analytical values. No attempt is made to derive exact statistical measurements of imprecision because several methods were used in the determination of most constituents.

See the following pages for more information.

Original Certificate Number REV-48A-032092
New Certificate Number REV2-48A-120409

New Certificate Number REV2-48A-120409 Revised to show uncertainty values on December 4, 2009

Brammer Standard Company, Inc., 14603 Benfer Road, Houston, TX 77069-2895
Telephone (281) 440-9396 Fax (281) 440-4432

Analysis	C	Mn	P	S	Si	Cu	Ni	Cr	Mo
1	0.116	0.415	0.010	0.0089	0.67	0.124	0.27	8.70	0.94
2	0.117	0.417	0.010	0.010	0.67	0.127	0.289	8.72	0.943
3	0.118	0.418	0.011	0.010	0.683	0.128	0.29	8.73	0.95
4	0.119	0.42	0.012	0.0104	0.683	0.129	0.292	8.74	0.95
5	0.121	0.422	0.012	0.011	0.686	0.13	0.292	8.74	0.95
6	0.121	0.429	0.0128	0.011	0.69	0.13	0.294	8.75	0.95
7	0.124	0.43	0.013	0.011	0.69	0.133	0.295	8.76	0.95
8	0.126	0.43	0.014	0.0112	0.69	0.133	0.30	8.76	0.95
9	0.127	0.431	0.015	0.012	0.702	0.134	0.301	8.78	0.955
10		0.438				0.14	0.302	8.78	0.955
11		0.443				0.14	0.313		
12		0.45				0.146			
Average	0.1210	0.429	0.0122	0.0106	0.685	0.1328	0.294	8.746	0.949
Std Dev	0.0039	0.011	0.0017	0.0009	0.010	0.0064	0.011	0.025	0.005
Certified	0.121	0.43	0.012	0.011	0.68	0.13	0.29	8.75	0.95
t	2.31	2.20	2.31	2.31	2.31	2.20	2.23	2.26	2.26
C (95%)	0.0030	0.007	0.0013	0.0007	0.008	0.0040	0.007	0.018	0.003

continued from above

Analysis	Al	Co	N	Sn	Ti	V
1	0.0159	0.018	0.0196	0.012	0.001	0.012
2	0.018	0.019	0.0200	0.013	0.002	0.013
3	0.019	0.019	0.0204	0.0131	0.002	0.014
4	0.019	0.019	0.0207	0.014	0.003	0.014
5	0.019	0.0227	0.0207	0.0157		0.014
6	0.020	0.024	0.0212			0.014
7		0.024	0.0216			0.014
8		0.025				0.015
9		0.026				0.0152
10						0.0166
Average	0.0185	0.0219	0.0206	0.0136	0.0020	0.0142
Std Dev	0.0014	0.0031	0.0007	0.0014	0.0008	0.0012
Certified	0.018	0.022	0.0210	0.014	0.002	0.014
t	2.57	2.31	2.45	2.78	3.18	2.31
C (95%)	0.0015	0.0024	0.00063	0.0017	0.0013	0.0010

$C(95\%) = (t \times sd) / \sqrt{n}$ The half-width confidence interval, where t is the appropriate Student's t value, sd is the interlaboratory standard deviation, and n is the number of acceptable mean values. For further information regarding the confidence interval for the certified value see ISO Guide 35:2006 section 6.

Some of the co-operating laboratories were:

- Allegheny Ludlum Steel Corporation, Brackenridge, PA
- Allegheny Ludlum Steel Corporation, Lockport, NY
- Brammer Standard Co., Inc., Houston, TX
- Crobaugh Laboratories, Cleveland, OH
- Crucible Specialty Metals, Syracuse, NY
- Hoesch Stahl AG, Dortmund, Germany
- J. Dirats and Co., Inc., Westfield, MA
- Jessop Steel Company, Washington, PA
- Midstates Analytical Laboratories, Inc., Tulsa, OK
- VHG Laboratories, Inc., Manchester, NH

Analysis: Chemical analyses were made on millings from cross-sections of the bars. The individual values listed on the previous page are the average of each analyst's results.

Analytical Methods: Methods of analysis used were a combination of ASTM Standard Methods E 350, E 415, E 1019, plus additional ICP, and AA spectrometric methods.

Traceability: The following Certified Reference Materials were used to validate the analytical data listed above: NIST SRM 32e, 125b, 361 to 365; BAM 039-2, 044-1; BCS 455/1, 456/1, 458/1; ECRM 085-1, 088-1, 096-1, 184-1, 481-1; GBW 01402; IMZ 1.22, 1.74

Homogeneity: This Reference Material was tested for homogeneity using ASTM Standard Method E 826 and found acceptable. It was also examined by spark atomic emission spectrometry and found to be compatible with the following NIST Certified Reference Materials: SRM 1222, 1224, 1225, 1261A to 1265A, 1761 to 1767

Form: This Reference Material is machined in the form of a disc, approximately 38 mm diameter and 19 mm thick by Brammer Standard Company. The bar stock used for this material was produced by hot-rolling billets and annealing.

Certified area: The entire depth of the disc may be used.

Caution: As with any bar material, avoid spark atomic emission spectrometric burns in the center of the disc (5 mm radius), as some segregation may be present.

Sample Preparation: For best analytical results, use the same method for preparing the analytical surface on all reference materials as you use for production specimens. Avoid overheating the disc during surface preparation.

Certificate Number: The unique identification number for this certificate of analysis is REV2-48A-120409. This BS 48A Certificate of Analysis was revised to show the estimate of uncertainty for the certified values. After reviewing the analytical data, a third decimal place was added to the certified value of copper.

This Reference Material was first revised after retesting by additional laboratories in 1991 and 1992. Additional elements were certified. Also, as a result of the retesting, the certified analysis was revised slightly for C, Mn, S, Si, Al, Co, Sn, and V.

Refer to the "Certificates" section of the Brammer Standard Company website for any revision to this or other Brammer Standard Company's Certificates of Analysis.

Safety Notice: A Material Safety Data Sheet (MSDS) is not required for this material. This material will not release or otherwise result in exposure to a hazardous chemical, under normal conditions of use. Inquiries concerning this Reference Material should be directed to:

Brammer Standard Co., Inc.	Phone: (281) 440-9396	website: brammerstandard.com
14603 Benfer Road	Fax: (281) 440-4432	email: contact@brammerstandard.com
Houston, Texas 77069-2895 USA		

Certified by: _____ on December 4, 2009
Beau R. Brammer

Certificate Number REV2-48A-120409

Referenced Documents

ASTM documents available from ASTM, 1916 Race Street, Philadelphia, PA, 19103.

Versions available at time of interlaboratory testing

E 350 - 90 Standard Test Methods for Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

E 415 - 85 (Reapproved 1989) Standard Test Method for Optical Emission Vacuum Spectrometric Analysis of Carbon and Low-Alloy Steel

E 826 - 85 (Reapproved 1990) Standard Practice for Testing Homogeneity of Materials for the Development of Reference Materials

E 1019-93 Standard Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel and in Iron, Nickel, and Cobalt Alloys

ISO Guides and Standards available from Global Engineering - www.global.ihs.com

ISO Guide 35 Reference Materials - General and statistical principles for certification

Certificate Number REV2-48A-120409