

# BRAMMER STANDARD COMPANY, INC.

## Certificate of Analysis

### BS 642C

Certified Reference Material for Aluminum Silicon Bronze- UNS Number C64200

	Certified Value <sup>1</sup>	Estimate of Uncertainty <sup>2</sup>	Certified Values <sup>3</sup>
<b>Al</b>	<b>7.13</b>	0.04	
<b>As</b>	<b>0.0008</b>	0.0002	
<b>Cr</b>	<b>0.0009</b>	0.0002	
<b>Cu</b>	<b>90.4</b>	0.4	
<b>Fe</b>	<b>0.11</b>	0.02	
<b>Mg</b>	<b>0.0014</b>	0.0002	
<b>Mn</b>	<b>0.0148</b>	0.0005	
<b>Ni</b>	<b>0.0363</b>	0.0008	
<b>P</b>	<b>0.0040</b>	0.0003	
<b>Pb</b>	<b>0.0109</b>	0.0004	
<b>Si</b>	<b>2.20</b>	0.01	
<b>Sn</b>	<b>0.0061</b>	0.0003	
<b>Zn</b>	<b>0.039</b>	0.001	

### Informational Values<sup>3,4</sup>

Be (<0.005)	C (<0.005)	Co (<0.005)	N (<0.005)	O (<0.0005)
S (<0.005)	Sb (<0.0005)	Zr (<0.0005)		

<sup>1</sup> For each element, the certified value listed is the present best estimate of the true value based on the mean of the weighted results of an interlaboratory testing program. See page 3 for more information on its calculation.

<sup>2</sup> For each element, the uncertainty listed is based on a statistical evaluation of the contributions of homogeneity and the interlaboratory testing program. See page 3 for more information on its calculation.

<sup>3</sup> Values are given in weight percent.

<sup>4</sup> Values in parentheses are not certified and are provided for information only.

Trace element information values for Ag, B, Bi, Ga, Se, Te, Ti, and V are shown on page 3.

The requirements of ISO Guides 31, 34, and 35 were followed for the preparation of this Certified Reference Material and certificate of analysis. This is a Certified Reference Material as defined by ISO Guide 30.

Analysis	*	Al	*	As	*	Cr	*	Cu	*	Fe	*	Mg	*	Mn	*	Ni
1	4	7.02	5	0.00057	14	0.0005	4	89.9	4	0.098	3	0.0012	10	0.0130	3	0.0319
2	4	7.04	5	0.00067	5	0.0007	13	90.2	5	0.098	5	0.0012	3	0.0133	3	0.0323
3	3	7.05	5	0.00077	5	0.0009	6	90.2	4	0.100	3	0.0013	5	0.0138	4	0.0327
4	4	7.06	5	0.00080	5	0.0009	3	90.2	5	0.102	5	0.0014	4	0.0139	14	0.0349
5	14	7.09	5	0.00080	5	0.0009	4	90.3	10	0.105	4	0.0015	5	0.0140	5	0.0350
6	5	7.10	4	0.00082	5	0.0010	3	90.3	4	0.105	4	0.0015	4	0.0144	4	0.0357
7	3	7.22	5	0.00084	3	0.0012	6	90.4	3	0.108	5	0.0016	7	0.0148	10	0.0360
8	4	7.22	5	0.00100	3	0.0013	4	90.4	4	0.109	14	0.0018	3	0.0150	4	0.0361
9	4	7.24			4	0.0013	4	90.5	14	0.109			3	0.0153	4	0.0369
10	3	7.24					5	90.5	5	0.111			4	0.0154	5	0.0370
11							10	91.2	4	0.111			5	0.0156	3	0.0380
12									3	0.112			14	0.0157	4	0.0380
13													5	0.0158	5	0.0389
14													4	0.0159		
15													5	0.0162		
Average		7.128		0.000767		0.00087		90.40		0.1053		0.00142		0.01485		0.03630
Std dev		0.033		0.000095		0.00012		0.13		0.0021		0.00016		0.00050		0.00083
H		0.046		0.00021		0.00022		0.55		0.0019		0.00025		0.00065		0.0010
U <sub>1</sub>		0.056		0.00023		0.00025		0.56		0.0028		0.00030		0.00082		0.0013
t-statistic		2.26		2.36		2.31		2.23		2.20		2.36		2.14		2.18
U <sub>2</sub>		0.13		0.00054		0.00057		1.25		0.0062		0.00070		0.0018		0.0029
U <sub>3</sub>		0.040		0.00019		0.00019		0.38		0.0018		0.00025		0.00046		0.00080
<b>Certified</b>		<b>7.13</b>		<b>0.0008</b>		<b>0.0009</b>		<b>90.4</b>		<b>0.11</b>		<b>0.0014</b>		<b>0.0148</b>		<b>0.0363</b>
<b>Uncertainty</b>		<b>0.04</b>		<b>0.0002</b>		<b>0.0002</b>		<b>0.4</b>		<b>0.02</b>		<b>0.0002</b>		<b>0.0005</b>		<b>0.0008</b>
Tolerance		0.13		0.0005		0.0006		1.3		0.01		0.0007		0.0018		0.0029

Analysis	*	P	*	Pb	*	Si	*	Sn	*	Zn
1	4	0.0030	5	0.0098	5	2.14	5	0.0050	4	0.0357
2	3	0.0031	5	0.0099	3	2.15	5	0.0053	5	0.0364
3	3	0.0034	5	0.0100	6	2.17	14	0.0055	4	0.0366
4	5	0.0035	5	0.0101	4	2.17	5	0.0055	4	0.0375
5	7	0.0036	14	0.0108	6	2.19	5	0.0058	3	0.0375
6	4	0.0037	9	0.0109	4	2.19	4	0.0060	5	0.0380
7	5	0.0042	5	0.0110	3	2.20	4	0.0065	14	0.0385
8	5	0.0043	10	0.0110	6	2.21	5	0.0066	4	0.0398
9	4	0.0045	4	0.0113	4	2.22	3	0.0069	4	0.0403
10	5	0.0046	3	0.0120	4	2.25	5	0.0072	8	0.0410
11	3	0.0047	4	0.0123	3	2.25	3	0.0076	5	0.0426
12	7	0.0049	5	0.0124						
13			3	0.0128						
Average		0.00400		0.01092		2.195		0.00606		0.03875
Std dev		0.00026		0.00045		0.014		0.00028		0.00095
H		0.00037		0.00056		0.017		0.00043		0.0011
U <sub>1</sub>		0.00045		0.00072		0.022		0.00052		0.0014
t-statistic		2.20		2.18		2.23		2.23		2.23
U <sub>2</sub>		0.0010		0.0016		0.049		0.0012		0.0032
U <sub>3</sub>		0.00029		0.00044		0.015		0.00035		0.0010
<b>Certified</b>		<b>0.0040</b>		<b>0.0109</b>		<b>2.20</b>		<b>0.0061</b>		<b>0.039</b>
<b>Uncertainty</b>		<b>0.0003</b>		<b>0.0004</b>		<b>0.01</b>		<b>0.0003</b>		<b>0.001</b>
Tolerance		0.0010		0.0016		0.05		0.0012		0.003

Analysis	* Be	* C	* Co	* N	* O	* S	* Sb	* Zr
1	3 0.001000	1 0.0015	3 0.0010	2 0.0005	2 0.00010	3 0.0002	5 0.00020	5 0.00010
2	4 0.001000	1 0.0016	5 0.0016	2 0.0007	2 0.00020	3 0.0004	5 0.00026	5 0.00010
3		1 0.0018	4 0.0020		2 0.00025	1 0.0006	5 0.00027	5 0.00010
4		1 0.0019	3 0.0023		2 0.00033	3 0.0008	5 0.00030	4 0.00023
5		3 0.0022				1 0.0010	5 0.00037	4 0.00027
6		1 0.0024					5 0.00053	14 0.00030
Average	0.00100	0.00187	0.00163	0.00059	0.000322	0.00063	0.000308	0.000181
Std dev	0.00026	0.00019	0.00028	0.00018	0.000084	0.00014	0.000058	0.000062
H	0.00023	0.00028	0.00026	0.00019	0.00017	0.00020	0.00017	0.00015
U <sub>1</sub>	0.00034	0.00033	0.00038	0.00027	0.00019	0.00024	0.00018	0.00016
t-statistic	12.71	2.57	3.18	12.71	2.78	2.78	2.57	2.57
U <sub>2</sub>	0.0043	0.00086	0.0012	0.0034	0.00052	0.00068	0.00045	0.00041
U <sub>3</sub>	0.0031	0.00035	0.00061	0.0024	0.00023	0.00030	0.00018	0.00017
	(<0.005)	(<0.005)	(<0.005)	(<0.005)	(<0.0005)	(<0.005)	(<0.0005)	(<0.0005)

For each element, in accordance with the requirements of ISO Guides 34 and 35, an effort must be made to account for the effects on the certified value of the uncertainty estimate from homogeneity testing (H) and the uncertainties of the contributing laboratories. The average (A) is calculated using a weighted mean where the reciprocal of the square of each laboratory's combined uncertainty (C<sub>L</sub>), calculated from its standard deviation (S<sub>L</sub>) and its uncertainty estimate (U<sub>L</sub>), is used as the weight (W<sub>L</sub>) for its mean (M<sub>L</sub>). The standard deviation (S) is calculated as the square root of the reciprocal of the sum of the weights. U<sub>1</sub> is the combined uncertainty from homogeneity and labs. U<sub>2</sub> is U<sub>1</sub> times the coverage factor (95 % t-statistic). U<sub>3</sub> is U<sub>2</sub> divided by the square root of the number of determinations (n). Thus:

$$C_L = \sqrt{S_L^2 + U_L^2} \quad W_L = \frac{1}{C_L^2} \quad A = \frac{\sum_{i=1}^n W_L M_L}{\sum_{i=1}^n W_L} \quad S = \frac{1}{\sqrt{\sum_{i=1}^n W_L}} \quad U_1 = \sqrt{H^2 + S^2} \quad U_2 = t \times U_1 \quad U_3 = \frac{U_2}{\sqrt{n}}$$

All but the final reported values are taken to two significant figures as determined by each quantity's uncertainty estimate. The final reported Uncertainty is U<sub>3</sub> rounded to one significant figure and represents the half width of the 95 % confidence interval for the **Certified** value. The final reported **Certified** value is A rounded to the same decimal place as the Uncertainty. The Tolerance is the half width of the 95 % confidence interval for measurements rounded to the same decimal place as the Uncertainty. The Uncertainty is a measure of the quality of the **Certified** value. The Tolerance is a measure of the expected performance of an analysis.

For further information regarding the confidence interval for the certified value see ISO Guide 35:2006 section 6.

Analysis	* Ag	* B	* Bi	* Ga	* Se	* Te	* Ti	* V
1	5 9	4 11	5 0.3	5 10	5 0.8	5 0.5	4 128	5 0.8
2	5 15							

#### Analytical Method Codes:

1	Combustion (ASTM E1019)	7	Photometric	13	Titrimetric
2	Fusion (ASTM E 1019)	8	Flame Atomic Absorption	14	DCP Atomic Emission
3	Spark Atomic Emission	9	GF Atomic Absorption	15	HG Atomic Fluorescence
4	ICP Atomic Emission	10	X-Ray Fluorescence		
5	ICP Mass Spectrometry	11	GD Atomic Emission		
6	Gravimetric	12	GD Mass Spectrometry		

ICP = Inductively Coupled Plasma      GF = Graphite Furnace      GD = Glow Discharge

DCP = Direct Current Plasma      HG = Hydride Generation

<u>Laboratory</u>	<u>Location</u>	<u>Registrar</u>	<u>Accreditation</u>
Anderson Laboratories, Inc.	Greendale, WI	A2LA	17025
Andrew S. McCreath & Son, Inc.	Harrisburg, PA	A2LA	17025
APL, Inc	Milwaukee, WI	A2LA	17025
Brammer Standard Company, Inc.	Houston, TX	A2LA	17025, Guide 34
Dirats Laboratories	Westfield, MA	ACLASS	17025
Elemental Analysis, Inc.	Lexington, KY	A2LA	17025
Exova	Glendale Heights, IL	A2LA	17025
Laboratory Testing, Inc.	Hatfield, PA	PRI/Nadcap	17025
LECO Corporation	St. Joseph, MI	BSI	9001
Luvak Inc.	Boylston, MA	PRI/Nadcap	17025
National Analysis Center For Iron And Steel	Beijing, China	CNAS	17025
Northern Analytical Laboratory, Inc.	Londonderry, NH	PRI/Nadcap	17025
NSL Analytical	Cleveland, OH	ACLASS	17025

A2LA = American Association for Laboratory Accreditation

ACLASS = ANSI-ASQ National Accreditation Board

BSI = British Standards Institution

CNAS = China National Accreditation Service

Nadcap = National Aerospace and Defense Contractors Accreditation Program

PRI = Performance Review Institute

**Analysis:** Chemical analyses were made on solid pieces and chips prepared by an end mill from representative samples of the certified portion of the lot in accordance with ASTM Standard Practice E 1806. The laboratories participating in the testing followed the requirements of ISO Standard 17025. Methods of analysis used were those listed on page 3.

**Traceability:** The following Certified Reference Materials were used to validate the analytical data listed on page 2 — 31XWSB2, 32XLB10, 32XLB12, 32XSEB2, 32XSEB5, 32XSEB7, 33XGM5, 34XNS3; 501-147, 501-644, 501-646, 501-673, 502-102, 502-193, 502-403; BAS 180/1, 183/4, 304/1, 390; BS 110S; IARM 80B, 81B, 82A, 83A, 86B, 88A, 92B, 94B, 150A, 151B, 190A; SRM 158A, 164, 164A, 494, 1253A, 3105A, 3113, 3131A, 3136, 3169.

**Homogeneity:** This Certified Reference Material (CRM) was tested for homogeneity using ASTM Standard Method E 826 and found acceptable. It was also examined by spark atomic emission spectrometry and found to be compatible with the following Reference Materials — BS 642, 655, 655A, 876, 954A; CSB 1566, 1567; IARM 82B.

**Validity statement:** ISO Guide 31 states that the certification should contain an expiration date for all materials where instability has been demonstrated or is considered possible, after which the certified value is no longer guaranteed by the certifying body. The certification of BS 642C is valid indefinitely. The certification is nullified if this CRM is damaged, contaminated, or otherwise modified.

**Source:** The bar stock for this CRM was produced by LDM B.V., Drunen, The Netherlands

**Form:** This CRM is machined in the form of a disc, approximately 38 mm in diameter and 19 mm thick by Brammer Standard Company, Inc.

**Use:** This CRM is intended for use in spark atomic emission and x-ray spectrometric methods of analysis. Refer to ISO Guide 33 for information about the use of Certified Reference Materials.

**Certified Area:** The entire depth of the CRM may be used.

Caution: As with any bar material, avoid spark atomic emission spectrometric burns in the center of the CRM (5 mm radius), as some segregation may be present.

**Sample Preparation:** For best analytical results, use the same method for preparing the analytical surface on all reference materials as you use for production specimens. Avoid overheating the sample during surface preparation.

**Certificate Number:** The unique identification number for this certificate of analysis is 642C-031513. You may obtain information on revisions of certificates from the internet at [www.brammerstandard.com](http://www.brammerstandard.com).

**Safety Notice:** A Material Safety Data Sheet (MSDS) is not required for this material. This material will not release or otherwise result in exposure to a hazardous chemical, under normal conditions of use. Inquiries concerning this Reference Material should be directed to:

**Brammer Standard Co., Inc.**                      **Phone: (281) 440-9396**    **Web: [www.brammerstandard.com](http://www.brammerstandard.com)**  
**14603 Benfer Road**  
**Houston, Texas 77069-2895 USA**              **Fax: (281) 440-4432**              **Email: [contact@brammerstandard.com](mailto:contact@brammerstandard.com)**

**Brammer Standard Company, Inc., is accredited by the American Association For Laboratory Accreditation (A2LA) to ISO Guide 34 as a Reference Material Producer for the production of Certified Reference Materials and Reference Materials (Certificate Number 656.02)**

**Brammer Standard Company's Chemical Laboratory is accredited by A2LA to ISO Standard 17025. (Certificate Number 656.01)**

**By Certificate Number 10539, the Quality System of Brammer Standard Company, Inc., is registered to ISO 9001:2008 by National Quality Assurance (NQA), U.S.A.**

**The scopes of accreditation are listed on the website: [www.brammerstandard.com](http://www.brammerstandard.com)**

### **References:**

Versions used were those available at the time of testing and characterization

- E 826            Standard Practice for Testing Homogeneity of a Metal Lot or Batch in Solid Form by Spark Atomic Emission Spectrometry
- E 1019        Standard Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Fusion Techniques
- E 1806            Standard Practice for Sampling Steel and Iron for Determination of Chemical Composition
  
- ISO Standard 17025:2005    General requirements for the competence of testing and calibration laboratories
- ISO Standard 9001:2008    Quality Management Systems - Requirements
- ISO Guide 30:1992    Terms and definitions used in connection with reference materials + 2008 amendment
- ISO Guide 31:2000    Reference materials - Contents of certificates and labels
- ISO Guide 33:2000    Uses of certified reference materials
- ISO Guide 34:2009    General requirements for the competence of reference material producers
- ISO Guide 35:2006    Reference Materials - General and statistical principles for certification

*ASTM documents available from ASTM, 1916 Race Street, Philadelphia, PA, 19103.*

*ISO Guides and Standards available from Global Engineering - [www.global.ihs.com](http://www.global.ihs.com)*

*Other useful documents available from NIST, U.S. Department of Commerce, Gaithersburg, MD 20899.*

NIST Special Publication 260-100, Handbook for SRM Users

NIST Special Publication 829, Use of NIST Standard Reference Materials for Decisions on Performance of Analytical Chemical Methods and Laboratories

Certified by: \_\_\_\_\_ on March 15, 2013.

Beau R. Brammer