

Brammer Standard Company, Inc.

Certificate of Analysis

B.S. 81V-1

AISI Stainless Steel Grade 304 Reference Material

	Certified Value ¹	Estimate of Uncertainty ²		Certified Value ¹	Estimate of Uncertainty ²
Analysis listed as percent by weight					
C	0.032	0.004	Co	0.056	0.004
Mn	1.76	0.04	N	0.048	0.01
P	0.023	0.003	Nb	0.011	0.002
S	0.0012	0.0003	Sn	0.003	0.0015
Si	0.55	0.015	Ti	0.002	0.001
Cu	0.10	0.01	V	0.072	0.004
Ni	9.13	0.05	W	0.023	0.005
Cr	19.14	0.05			
Mo	0.134	0.01			
Al	0.003	0.001			

¹ The certified value listed is the present best estimate of the true value based on the results of an interlaboratory testing program.

² The uncertainties listed are based on value judgments of the material inhomogeneity and possible bias in the determined analytical values. No attempt is made to derive exact statistical measurements of imprecision because several methods were used in the determination of most constituents.

The requirements of ISO Guide 31 and ISO Guide 35 were generally followed for the preparation of this reference material and certificate of analysis. This is a reference material as defined by ISO Guide 30.

See reverse side for more information.

Certificate Number REV-81V-1-020697

Brammer Standard Company, Inc., 14603 Benfer Road, Houston, TX 77069-2895
Telephone (281) 440-9396 Fax (281) 440-4432

Analysis	C	Mn	P	S	Si	Cu	Ni	Cr	Mo
1	0.0308	1.72	0.0209	0.0010	0.539	0.097	9.08	19.09	0.13
2	0.031	1.73	0.022	0.00108	0.543	0.098	9.08	19.13	0.13
3	0.031	1.73	0.0227	0.0012	0.55	0.10	9.13	19.15	0.133
4	0.0315	1.76	0.025	0.0014	0.553	0.10	9.138	19.15	0.133
5	0.0327	1.78			0.56	0.106	9.15	19.178	0.133
6	0.033	1.79			0.561	0.112	9.155		0.135
7		1.797			0.57		9.17		0.146
Average	0.0317	1.758	0.0227	0.00117	0.554	0.102	9.129	19.140	0.134
Std Dev	0.0010	0.032	0.0017	0.00017	0.011	0.006	0.036	0.033	0.005
Certified	0.032	1.76	0.023	0.0012	0.55	0.10	9.13	19.14	0.134

Analysis	Al	Co	N	Nb	Sn	Ti	V	W
1	0.002	0.054	0.0481	0.009	0.0015	0.002	0.068	0.020
2	0.0032	0.054	0.0482	0.011	0.002	0.002	0.070	0.020
3	0.0032	0.0553	0.0484	0.011	0.0038	0.0021	0.070	0.021
4	0.004	0.0568	0.0494	0.0113	0.004	0.003	0.072	0.022
5		0.057		0.0115		0.0035	0.074	0.023
6		0.060					0.0755	0.0262
7								0.031
Average	0.0031	0.0562	0.0485	0.0108	0.0028	0.0025	0.0716	0.0233
Std Dev	0.0008	0.0023	0.0006	0.0010	0.0013	0.0007	0.0028	0.0040
Certified	0.003	0.056	0.048	0.011	0.003	0.002	0.072	0.023

Analysis: Chemical analyses were made on chips prepared by a lathe from the certified portion of the discs. The laboratories participating in the testing normally followed the requirements of ISO Guide 25. The individual values listed above are the average of each analyst's results. Methods of analysis used were a combination of ASTM Standard Methods E 350, E 353, E 572, E 1019, E 1086, plus additional ICP and AA spectrometric methods. The following Certified Reference Materials were used to validate the analytical data listed above: NIST SRM 73c, 101g, 121d, 160b, 344, 345, 348a; BCS 466/1, 467/1, 475; ECRM 252-1, 284-1, 286-1; IMZ 127/3; JK 37.

Co-operating Laboratories: Some of the co-operating laboratories were:

Allegheny Ludlum Steel Corp., Brackenridge, Pennsylvania
 Allegheny Ludlum Steel Corp., Lockport, New York
 Brammer Standard Co., Inc., Houston, Texas
 Crucible Specialty Steel, Syracuse, New York
 J. Dirats and Co., Inc., Westfield, Massachusetts
 Hoesch Stahl AG, Dortmund, Germany
 VHG Laboratories, Inc., Manchester, New Hampshire

Homogeneity: This Reference Material was tested for homogeneity using ASTM Standard Practice E 826 and found acceptable.

Traceability: This Reference Material was also examined by optical emission spectrometry and found to be compatible with the following Certified Reference Materials: NIST SRM C1151, C1152, C1153, C1154, 1155.

Source: This material was produced by Crucible Specialty Metals, Syracuse, New York. The material was made in an electric arc remelting furnace and cast into ingots. The bar stock was hot rolled, cold finished and annealed.

Available Form: This Reference Material is available only in the form of a disc, approximately 38 mm (1.50") in diameter and 12 mm (0.50") thick.

Use: This Reference Material is intended for use in optical emission and x-ray spectrometric methods of analysis. The entire depth of the disc may be used.

Caution: As with any bar material, avoid optical emission spectrometric burns in the center of the disc (5 mm radius), as some segregation may be present.

Because this Reference Material contains a high percent of nickel and chromium, care must be taken in its application. Make certain that corrections are made for possible element interference and dilution effects.

Sample Preparation: For best analytical results, use the same method for preparing the analytical surface on all reference materials as you use for production specimens. Avoid overheating the disc during surface preparation.

Certificate of Analysis Revisions: The original BS 81V Reference Material was certified on March 25, 1992. Revised certificate of analysis numbered 81V-REV010594 was issued to list more details about the reference material, as outlined in ISO Guide 31. This certificate, numbered REV-81V-1-020697, was issued for bar number one of a two-bar batch that was tested for use as a reference material. Bar two contains approximately 1.68% manganese and will be certified in late 1997 as BS 81V-2.

Safety Notice: A Material Safety Data Sheet (MSDS) is not required for this material. This material will not release or otherwise result in exposure to a hazardous chemical, under normal conditions of use. Inquiries concerning this Reference Material should be directed to:

Brammer Standard Co., Inc. Phone: (281) 440-9396
14603 Benfer Road
Houston, Texas 77069-2895 USA Fax: (281) 440-4432

Certified by: _____ on February 6, 1997.
G. R. Brammer

Certificate Number REV-81V-1-020697

References:

ASTM documents available from ASTM, 1916 Race Street, Philadelphia, PA, 19103.

E 350-90 Standard Test Methods for Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

E 353 - 93 Standard Test Methods for Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

E 572 - 88 Standard Test Method for X-Ray Emission Spectrometric Analysis of Stainless Steel

E 826 - 85 (Reapproved 1990) Standard Practice for Testing Homogeneity of Materials for the Development of Reference Materials

E 1019-93 Standard Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel and in Iron, Nickel, and Cobalt Alloys

E 1086 - 85 Standard Method for Optical Emission Vacuum Spectrometric Analysis of Stainless Steel by the Point-to-Plane Excitation Technique

ISO Guides available from American National Standards Institute, 11 West 42nd St., 13th Floor, New York, NY 10036.

ISO Guide 25 (Third edition, 1990), General requirements for the competence of calibration and testing laboratories.

ISO Guide 30 (Second edition, 1991), Terms and definitions used in connection with reference materials.

ISO Guide 31 (First edition, 1981), Contents of certificates of reference materials.

ISO Guide 33 (First edition, 1989), Uses of certified reference materials.

ISO Guide 35 (Second edition, 1989), Certification of reference materials - General and statistical principles.

Other useful documents available at no cost from NIST, U.S. Department of Commerce, Gaithersburg, MD 20899.

NBS Special Publication 260-100, Handbook for SRM Users

NIST Special Publication 829, Use of NIST Standard Reference Materials for Decisions on Performance of Analytical Chemical Methods and Laboratories

Certificate Number REV-81V-1-020697