

# BRAMMER STANDARD COMPANY, INC.

## Certificate of Analysis

### BS 863B

Certified Reference Material for CDA 863 - UNS Number C86300

	Certified Value <sup>1</sup>	Estimate of Uncertainty <sup>2</sup>	Certified Values <sup>3</sup>	Certified Value <sup>1</sup>	Estimate of Uncertainty <sup>2</sup>	
<b>Al</b>	<b>5.25</b>	0.03		<b>Zn</b>	<b>26.1</b>	0.1
<b>As</b>	<b>0.0004</b>	0.0002				
<b>C</b>	<b>0.0028</b>	0.0003				
<b>Co</b>	<b>0.0009</b>	0.0002				
<b>Cr</b>	<b>0.0042</b>	0.0004				
<b>Cu</b>	<b>[62.4]</b>	0.2				
<b>Fe</b>	<b>2.84</b>	0.02				
<b>Mn</b>	<b>2.97</b>	0.02				
<b>Ni</b>	<b>0.081</b>	0.002				
<b>P</b>	<b>0.0010</b>	0.0003				
<b>Pb</b>	<b>0.0205</b>	0.0008				
<b>S</b>	<b>0.0007</b>	0.0003				
<b>Sb</b>	<b>0.0012</b>	0.0003				
<b>Si</b>	<b>0.0103</b>	0.0007				
<b>Sn</b>	<b>0.033</b>	0.002				

### Informational Values<sup>3,4</sup>

Ag (0.003)	B (0.0003)	Mg (0.0002)	N (0.0003)	O (0.0003)
Se (0.0009)				

<sup>1</sup> For each element, the certified value listed is the present best estimate of the true value based on the mean of the weighted results of an interlaboratory testing program. See page 3 for more information on its calculation.

<sup>2</sup> For each element, the uncertainty listed is based on a statistical evaluation of the contributions of homogeneity and the interlaboratory testing program. See page 3 for more information on its calculation.

<sup>3</sup> Values are given in weight percent.

<sup>4</sup> Values in parentheses are not certified and are provided for information only.

Trace element information values for Bi, Ca, Cd, Cl, Ga, Ge, K, Mo, Na, Nb, Pd, Te, Ti, Tl, V, and Zn are shown on page 3.

The requirements of ISO Guides 31, 34, and 35 were followed for the preparation of this Certified Reference Material and certificate of analysis. This is a Certified Reference Material as defined by ISO Guide 30.

## BS 863B

\* Code for method Certified values listed as weight percent

Analysis	*	Al	*	As	*	C	*	Co	*	Cr	*	Cu	*	Fe	*	Mn
1	4	5.0303	5	0.000157	1	0.001433	5	0.000793	3	0.0030	4	62.2	10	2.80	10	2.73
2	3	5.06	5	0.000193	1	0.0024	5	0.0008	5	0.003667	3	62.20667	14	2.81	4	2.878333
3	14	5.11	4	0.0002	1	0.002567	4	0.0008	12	0.0038	10	62.26667	4	2.825667	3	2.91
4	4	5.16	5	0.00024	3	0.00265	4	0.000833	4	0.003827	16	62.29	4	2.843333	14	2.94
5	4	5.195333	12	0.00026	1	0.002767	4	0.001	14	0.0039	16	62.38667	4	2.846667	4	2.972
6	4	5.22	5	0.00047	1	0.0028	12	0.0010	5	0.004033	10	62.52	3	2.846667	10	2.98
7	4	5.227	5	0.0005	1	0.00284	5	0.0010	5	0.004233	16	62.7553	4	2.854733	4	2.986367
8	4	5.23667	9	0.000553	1	0.0032	5	0.001013	4	0.0043	13	62.813	4	2.863333	4	2.99
9	3	5.29	1	0.004517	4	0.00104	4	0.005	16	62.855	10	2.876667	4	3.006667	4	3.04
10	4	5.4079	1	0.005	14	0.0012			4	62.93333	4	2.8817	4	3.04		
11	4	5.43							16	63.06667	4	2.889333	4	3.061		
12									6	63.19667			3	3.075		
13									16	63.31333						
14									4	63.85333						
Average		5.247		0.000441		0.00278		0.000867		0.00425		62.390		2.840		2.968
Std dev		0.030		0.000016		0.00014		0.000076		0.00010		0.090		0.026		0.020
H		0.034		0.00023		0.00040		0.00028		0.00047		0.31		0.021		0.021
U <sub>1</sub>		0.045		0.00023		0.00043		0.00029		0.00048		0.32		0.033		0.029
t-statistic		2.23		2.36		2.26		2.26		2.31		2.16		2.23		2.20
U <sub>2</sub>		0.10		0.00055		0.0010		0.00065		0.0011		0.70		0.073		0.065
U <sub>3</sub>		0.030		0.00020		0.00030		0.00021		0.00037		0.19		0.022		0.019
<b>Certified</b>		<b>5.25</b>		<b>0.0004</b>		<b>0.0028</b>		<b>0.0009</b>		<b>0.0042</b>		<b>[62.4]</b>		<b>2.84</b>		<b>2.97</b>
<b>Uncertainty</b>		<b>0.03</b>		<b>0.0002</b>		<b>0.0003</b>		<b>0.0002</b>		<b>0.0004</b>		<b>0.2</b>		<b>0.02</b>		<b>0.02</b>
Tolerance		0.10		0.0004		0.0010		0.0007		0.0011		0.7		0.07		0.06

Analysis	*	Ni	*	P	*	Pb	*	S	*	Sb	*	Si	*	Sn	*	Zn
1	3	0.073533	7	0.000727	4	0.015	3	0.00035	5	0.000937	12	0.0085	10	0.029	4	25.7
2	14	0.0738	4	0.00085	14	0.018933	1	0.000367	5	0.0010	4	0.008567	14	0.0305	10	25.76667
3	10	0.077333	5	0.000997	5	0.020167	1	0.000433	5	0.001033	5	0.008933	5	0.0335	10	25.79
4	5	0.077833	5	0.001033	5	0.020233	1	0.000833	12	0.0011	5	0.0096	4	0.033733	4	25.8
5	5	0.079333	12	0.0012	4	0.020733	12	0.0010	5	0.0011	7	0.0104	4	0.0342	14	25.91333
6	4	0.081167	5	0.0020	4	0.020967			4	0.0012	4	0.010533	5	0.034933	4	26.07
7	4	0.0816	5	0.002367	3	0.0210			5	0.0016	4	0.010667	12	0.0365	4	26.09667
8	8	0.081967	4	0.002433	5	0.0210			4	0.002	5	0.012233	5	0.0380	3	26.135
9	4	0.082			5	0.021933					14	0.0136	3	0.038733	4	26.19333
10	4	0.083			4	0.022933							4	0.039033	4	26.2221
11	4	0.0832			12	0.0250										
12	5	0.0840														
13	10	0.089														
Average		0.0813		0.001026		0.02053		0.000699		0.001238		0.01029		0.0328		26.117
Std dev		0.0017		0.000076		0.00069		0.000073		0.000066		0.00064		0.0011		0.055
H		0.0019		0.00029		0.0009		0.00026		0.00031		0.00067		0.0012		0.14
U <sub>1</sub>		0.0025		0.00030		0.0012		0.00027		0.00031		0.00093		0.0016		0.15
t-statistic		2.18		2.36		2.23		2.78		2.36		2.31		2.26		2.26
U <sub>2</sub>		0.0055		0.00071		0.0026		0.00075		0.00074		0.0021		0.0036		0.33
U <sub>3</sub>		0.0015		0.00025		0.00077		0.00034		0.00026		0.00071		0.0011		0.11
<b>Certified</b>		<b>0.081</b>		<b>0.0010</b>		<b>0.0205</b>		<b>0.0007</b>		<b>0.0012</b>		<b>0.0103</b>		<b>0.033</b>		<b>26.1</b>
<b>Uncertainty</b>		<b>0.002</b>		<b>0.0003</b>		<b>0.0008</b>		<b>0.0003</b>		<b>0.0003</b>		<b>0.0007</b>		<b>0.002</b>		<b>0.1</b>
Tolerance		0.006		0.0007		0.0026		0.0007		0.0007		0.0021		0.004		0.3

**BS 863B** \* Code for method Informational values listed as weight percent

Analysis	* Ag	* B	* Mg	* N	* O	* Se
1	12 0.0022	12 0.0003	8 0.0000267	2 0.0000333	2 0.0002	5 0.000137
2	5 0.0024	5 0.000357	12 0.00010	2 0.0001	2 0.00022	12 0.00075
3	5 0.0037	5 0.00038	5 0.00010	2 0.0001	2 0.000233	5 0.001767
4			5 0.00015	2 0.0004	2 0.000233	
5			4 0.0002	2 0.00051	2 0.000367	
6			5 0.000227	2 0.000523	2 0.000387	
7			14 0.000227	2 0.00053	2 0.00047	
8			4 0.000233		2 0.0007	
Average	0.0028	0.000335	0.0001518	0.000317	0.000337	0.00088
Std dev	0.0012	0.000043	0.0000090	0.000026	0.000032	0.00021
H	0.00040	0.00022	0.00019	0.00022	0.00022	0.00028
U <sub>1</sub>	0.0013	0.00022	0.00019	0.00022	0.00022	0.00035
t-statistic	4.30	4.30	2.36	2.45	2.36	4.30
U <sub>2</sub>	0.0054	0.0010	0.00044	0.00053	0.00052	0.0015
U <sub>3</sub>	0.0031	0.00055	0.00016	0.00020	0.00018	0.00086
(Informational)	(0.003)	(0.0003)	(0.0002)	(0.0003)	(0.0003)	(0.0009)

For each element, in accordance with the requirements of ISO Guides 34 and 35, an effort must be made to account for the effects on the certified value of the uncertainty estimate from homogeneity testing (H) and the uncertainties of the contributing laboratories. The average (A) is calculated using a weighted mean where the reciprocal of the square of each laboratory's combined uncertainty (C<sub>L</sub>), calculated from its standard deviation (S<sub>L</sub>) and its uncertainty estimate (U<sub>L</sub>), is used as the weight (W<sub>L</sub>) for it's mean (M<sub>L</sub>). The standard deviation (S) is calculated as the square root of the reciprocal of the sum of the weights. U<sub>1</sub> is the combined uncertainty from homogeneity and labs. U<sub>2</sub> is U<sub>1</sub> times the coverage factor (95 % t-statistic). U<sub>3</sub> is U<sub>2</sub> divided by the square root of the number of determinations (n). Thus:

$$C_L = \sqrt{S_L^2 + U_L^2} \quad W_L = \frac{1}{C_L^2} \quad A = \frac{\sum_{i=1}^n W_L M_L}{\sum_{i=1}^n W_L} \quad S = \frac{1}{\sqrt{\sum_{i=1}^n W_L}} \quad U_1 = \sqrt{H^2 + S^2} \quad U_2 = t \times U_1 \quad U_3 = \frac{U_2}{\sqrt{n}}$$

All but the final reported values are taken to two significant figures as determined by each quantity's uncertainty estimate. The final reported Uncertainty is U<sub>3</sub> rounded to one significant figure and represents the half width of the 95 % confidence interval for the **Certified** value. The final reported **Certified** value is A rounded to the same decimal place as the Uncertainty. The Tolerance is the half width of the 95 % confidence interval for measurements rounded to the same decimal place as the Uncertainty. The Uncertainty is a measure of the quality of the **Certified** value. The Tolerance is a measure of the expected performance of an analysis.

For further information regarding the confidence interval for the certified value see ISO Guide 35:2006 section 6.

**BS 863B** \* Code for analytical method Trace analysis listed as mg/kg (ppm)

Analysis	* Bi	* Ca	* Cd	* Cl	* Ga	* Ge	* K	* Mo	* Na	* Nb
1	12 2.4	12 0.12	12 0.31	12 0.10	12 3.0	5 1.2	12 0.097	5 2.8	5 2.4	12 3.8
2		5 11			5 6.1	5 1.3		5 2.8	5 3.9	
3		5 12			5 6.1	5 1.3		5 3.6	5 4.2	
4		5 13			5 6.2	12 2.2		12 10		
5					5 7.3					
6					5 7.4					
7					5 7.6					

Analysis	* Pd	* Te	* Ti	* Tl	* V	* Zr
1	5 2.1	5 1.1	12 0.44	12 0.19	12 0.79	12 2.4
2	5 2.2	5 1.3	5 3.8	5 1.2	5 1.6	
3	5 2.2	5 1.4	5 4.2	5 1.2	5 1.6	
4		12 2.4	5 4.3	5 1.3	5 1.6	
5					5 1.6	
6					5 1.6	
7					5 1.6	

## **Analytical Method Codes:**

1 Combustion (ASTM E1019)	7 Photometric	13 Titrimetric
2 Fusion (ASTM E 1019)	8 Flame Atomic Absorption	14 DCP Atomic Emission
3 Spark Atomic Emission	9 GF Atomic Absorption	15 HG Atomic Fluorescence
4 ICP Atomic Emission	10 X-Ray Fluorescence	16 Difference
5 ICP Mass Spectrometry	11 GD Atomic Emission	
6 Gravimetric	12 GD Mass Spectrometry	

ICP = Inductively Coupled Plasma      GF = Graphite Furnace      GD = Glow Discharge

DCP = Direct Current Plasma      HG = Hydride Generation

<b><u>Laboratory</u></b>	<b><u>Location</u></b>	<b><u>Registrar</u></b>	<b><u>Accreditation</u></b>
Brammer Standard Company, Inc.	Houston, TX	A2LA	17025, Guide 34
LECO Corporation	St. Joseph, MI	A2LA	17025
Evans Analytical Group	Liverpool, NY	A2LA	17025
NSL Analytical	Cleveland, OH	ACCLASS	17025
Dirats Laboratories	Westfield, MA	ACCLASS	17025
Elemental Analysis, Inc.	Lexington, KY	A2LA	17025
Exova	Glendale Heights, IL	A2LA	17025
Laboratory Testing, Inc.	Hatfield, PA	PRI/Nadcap	17025
Luvak Inc.	Boylston, MA	PRI/Nadcap	17025
National Analysis Center For Iron And Steel	Beijing, China	CNAS	17025
Northern Analytical Laboratory, Inc.	Londonderry, NH	PRI/Nadcap	17025

A2LA = American Association for Laboratory Accreditation

ACCLASS = ANSI-ASQ National Accreditation Board

CNAS = China National Accreditation Service

Nadcap = National Aerospace and Defense Contractors Accreditation Program

PRI = Performance Review Institute

**Analysis:** Chemical analyses were made on solid pieces and chips prepared by an end mill from representative samples for the certified portion of the lot in accordance with ASTM Standard Practice E 1806. The laboratories participating in the testing followed the requirements of ISO Standard 17025. Methods of analysis used are those listed on pages 2-3.

**Traceability:** The following Certified Reference Materials were used to validate the analytical data listed on pages 2-3 — 31XMNB5; 501-149, 501-550, 501-643, 501-646, 501-673, 501-676, 501-952, 501-953, 501-991, 502-257, 502-348, 502-403, 502-416; AR 147, 645, 662, 673, 1652, 1656; BAS 180/1, 180/2, 183/4, 345, 390, 431/1; BS CC423, CC954, 145, 630C, 863, 954, 954A; ECRM 284/1, 285/1, 287/1, 327/2; IARM 80B, 86D, 88A, 88B, 242A; IMZ CS1, CS2, CS3, CS4, CS45; KMS HOCS-001; SRM C1100, 37B, 37D, 62, 62D, 131E, 158A, 164, 885, 1108, 1119, 1253A, 2168, 3102A, 3103A, 3112A, 3113, 3128, 3131A, 3161A.

**Homogeneity:** This Certified Reference Material (CRM) was tested for homogeneity using ASTM Standard Method E 826 and found acceptable. It was also examined by spark atomic emission spectrometry and found to be compatible with the following Reference Materials — 502-416, 501-676; BAS 431/1; BS CC423, CC954, 630C, 863, 954, 954A; ECRM 284/1, 285/1, 287/1, 327/2; KMS HOCS-001; SRM 131E, 1108, 1119, 2168.

**Validity statement:** ISO Guide 31 states that the certification should contain an expiration date for all materials where instability has been demonstrated or is considered possible, after which the certified value is no longer guaranteed by the certifying body. The certification of BS 863B is valid indefinitely. The certification is nullified if this CRM is damaged, contaminated, or otherwise modified.

**Source:** The bar stock for this CRM was produced by National Bronze & Metals, Inc. Lorain, OH

**Form:** This CRM is machined in the form of a disc, approximately 38 mm in diameter and 19 mm thick by Brammer Standard Company, Inc.

**Use:** This CRM is intended for use in spark atomic emission and x-ray spectrometric methods of analysis. Refer to ISO Guide 33 for information about the use of Certified Reference Materials.

**Brammer Standard Company, Inc., 14603 Benfer Road, Houston, TX 77069-2895**  
**Telephone: (281) 440-9396    Fax: (281) 440-4432    Website: [www.brammerstandard.com](http://www.brammerstandard.com)**  
Certificate Number 863B-072814 Page 4/6

**Certified Area:** The entire depth of the CRM may be used.

Caution: As with any bar material, avoid spark atomic emission spectrometric burns in the center of the CRM (5 mm radius), as some segregation may be present.

**Sample Preparation:** For best analytical results, use the same method for preparing the analytical surface on all reference materials as you use for production specimens. Avoid overheating the sample during surface preparation.

**Certificate Number:** The unique identification number for this certificate of analysis is 863B-072814. You may obtain information on revisions of certificates from the internet at [www.brammerstandard.com](http://www.brammerstandard.com).

**Safety Notice:** A Material Safety Data Sheet (MSDS) is not required for this material. This material will not release or otherwise result in exposure to a hazardous chemical, under normal conditions of use. Inquiries concerning this Reference Material should be directed to:

**Brammer Standard Co., Inc.**                      **Phone: (281) 440-9396**    **Web: [www.brammerstandard.com](http://www.brammerstandard.com)**  
**14603 Benfer Road**  
**Houston, Texas 77069-2895 USA**              **Fax: (281) 440-4432**              **Email: [contact@brammerstandard.com](mailto:contact@brammerstandard.com)**

**Brammer Standard Company, Inc., is accredited by the American Association For Laboratory Accreditation (A2LA) to ISO Guide 34 as a Reference Material Producer for the production of Certified Reference Materials and Reference Materials (Certificate Number 656.02)**

**Brammer Standard Company's Chemical Laboratory is accredited by A2LA to ISO Standard 17025. (Certificate Number 656.01)**

**By Certificate Number 10539, the Quality System of Brammer Standard Company, Inc., is registered to ISO 9001:2008 by National Quality Assurance (NQA), U.S.A.**

**The scopes of accreditation are listed on the website: [www.brammerstandard.com](http://www.brammerstandard.com)**

## References:

Versions used were those available at the time of testing and characterization

- E 826 Standard Practice for Testing Homogeneity of a Metal Lot or Batch in Solid Form by Spark Atomic Emission Spectrometry
- E 1019 Standard Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Fusion Techniques
- E 1806 Standard Practice for Sampling Steel and Iron for Determination of Chemical Composition
- ISO Standard 17025:2005 General requirements for the competence of testing and calibration laboratories
- ISO Standard 9001:2008 Quality Management Systems - Requirements
- ISO Guide 30:1992 Terms and definitions used in connection with reference materials + 2008 amendment
- ISO Guide 31:2000 Reference materials - Contents of certificates and labels
- ISO Guide 33:2000 Uses of certified reference materials
- ISO Guide 34:2009 General requirements for the competence of reference material producers
- ISO Guide 35:2006 Reference Materials - General and statistical principles for certification

*ASTM documents available from ASTM, 1916 Race Street, Philadelphia, PA, 19103.*

*ISO Guides and Standards available from Global Engineering - [www.global.ihs.com](http://www.global.ihs.com)*

*Other useful documents available from NIST, U.S. Department of Commerce, Gaithersburg, MD 20899.*

NIST Special Publication 260-100, Handbook for SRM Users

NIST Special Publication 829, Use of NIST Standard Reference Materials for Decisions on Performance of Analytical Chemical Methods and Laboratories

Certified by: \_\_\_\_\_ on July 28, 2014.

Beau R. Brammer