Brammer Standard Company, Inc.

Provisional Certificate of Analysis **BS 9310**

Certified Reference Material for AISI Steel Grade 9310 - UNS Number G93106

Analysis listed as percent by weight

	Estimated Analysis ¹		Estimated Analysis ¹				
ΑI	0.028	Nb	0.002				
As	0.005	Ni	3.04				
В	0.0001	0	<0.005				
C	0.090	Р	0.009				
Ca	0.0001	Pb	0.0003				
Co	0.014	S	0.005				
Cr	1.16	Sb	0.002				
Cu	0.14	Si	0.22				
Fe	94.5	Sn	0.008				
Н	< 0.005	Ti	0.001				
Mn	0.64	V	0.004				
Мо	0.095	W	0.004				
N	<0.5	Zr	0.001				

<u>Form:</u> This CRM is machined in the form of a disc, approximately 41mm in diameter and 19mm thick by Brammer Standard Company, Inc.

A detailed final certificate of analysis will be supplied by September 29, 2025

¹ The estimated value listed is the present best estimate of the true value. Values are given in weight percent.

9310	Al	As	В	Be	Bi	С	Са	Ce	Со	Cr	Cu	Fe	Н	Mg
CSONH						0.0938								
BSC SAES	0.0285	0.0046	0.000075			0.0857	0.0001		0.0144	1.16	0.145	94.54		
BSC GDS	0.0286		0.0001			0.0897	0.0001		0.0146	1.14	0.146	94.55		
MTR	0.028	0.005	0.0002			0.09	0.0002		0.014	1.19	0.14		0.00011	
Average	0.02837	0.0048	0.000125			0.0898	0.00013		0.01433	1.16333	0.14367	94.545	0.00011	
Certificate	0.028	0.005	0.0001			0.090	0.0001		0.014	1.16	0.14	94.5	<0.005	
9310	Mn	Mo	N	Nb	Ni	0	P	Pb	S	Sb	Si	Sn	Та	Ti
CSONH			0.0111			0.00086			0.0053					
BSC SAES	0.644	0.0908		0.0022	3.01		0.0095	0.0003	0.0058	0.0025	0.222	0.0076		0.0011
BSC GDS	0.637	0.0936		0.0019	3.04		0.0092	0.0004	0.0054	0.0021	0.219			0.0009
MTR	0.63	0.10		0.002	3.08		0.009	0.0001	0.005	0.001	0.22	0.008		0.001
Average	0.637	0.0948	0.0111	0.00203	3.04333	0.00086	0.00923	0.00027	0.00538	0.00187	0.22033	0.0078		0.001
Certificate	0.64	0.095	<0.5	0.002	3.04	<0.005	0.009	0.0003	0.005	0.002	0.22	0.008		0.001
9310	V	W	Zn	Zr										
CSONH														
BSC SAES	0.0035	0.0031		0.0013										
BSC GDS		0.0011		0.0014										
MTR	0.004	0.008		0.001										
Average				0.00123										
Certificate	0.004	0.004		0.001										

<u>Homogeneity:</u> This Certified Reference Material (CRM) was tested for homogeneity using ASTM Standard Method E826 and found acceptable. It was also examined by spark atomic emission spectrometry and found to be compatible with the following Reference Materials: AR 4340; BS 58C, 58D, 58E, 3310, 4330MOD, 4330V.

<u>Validity statement:</u> ISO Guide 31 states that the certification should contain an expiration date for all materials where instability has been demonstrated or is considered possible, after which the certified value is no longer guaranteed by the certifying body. The certification of BS 9310 is valid indefinitely. The certification is nullified if this CRM is damaged, contaminated, or otherwise modified.

Storage: This CRM must be stored in a cool, dry, non-corrosive environment.

Source: The bar stock for this CRM was produced by Timken Steel; Canton, OH.

Certified Area: The entire depth of the CRM may be used.

Caution: As with any bar material, avoid spark atomic emission spectrometric burns in the center of the CRM (5 mm radius), as some segregation may be present.

<u>Sample Preparation:</u> For best analytical results, use the same method for preparing the analytical surface on all reference materials as used for production specimens. Avoid overheating the sample during surface preparation.

Caution: CRM contains significant insoluble soft metal inclusions. Surface smearing may occur. Spark atomic emission spectrometers may require extended preburns to compensate.

<u>Safety Notice:</u> A Safety Data Sheet (SDS) is not required for this material. This material will not release or otherwise result in exposure to a hazardous chemical, under normal conditions of use. Inquiries concerning this Reference Material should be directed to:

Brammer Standard Co., Inc. Phone: (281) 440-9396 Web: <u>www.brammerstandard.com</u>

14603 Benfer Road

Houston, Texas 77069-2895 USA Fax: (281) 440-4432 Email: contact@brammerstandard.com

The scopes of accreditation and ISO certificates are listed on the website: www.brammerstandard.com

References:

Reference	55.					
	Versions used were those available at the time of testing and characterization					
	Standard Practice for Testing Homogeneity of a Metal Lot or Batch in Solid Form by Spark Atomic Emission Spectrometry					
	Standard Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Fusion Techniques					
E1806	Standard Practice for Sampling Steel and Iron for Determination of Chemical Composition					
ISO Standard 17025:2017 General requirements for the competence of testing and calibration laboratories						
ISO Standar	rd 9001:2015 Quality Management Systems - Requirements					
ISO Guide 30:2015 Terms and definitions used in connection with reference materials + 2008 amendment						
ISO Guide 31:2015 Reference materials - Contents of certificates and labels						
ISO Guide 33:2015 Uses of certified reference materials						
ISO Standard 17034:2016 General requirements for the competence of reference material producers						
ISO Guide 3	5:2017 Reference Materials - General and statistical principles for certification					
ASTM docui	ments available from ASTM, 100 Barr Harbor Dr., West Conshohocken, PA 19428.					
ISO Guides	and Standards available from Global Engineering - <u>www.global.ihs.com</u>					
Other useful	documents available from NIST, U.S. Department of Commerce, Gaithersburg, MD 20899.					
NIST Specia	al Publication 260-100, Handbook for SRM Users					
	al Publication 829, Use of NIST Standard Reference Materials for Decisions on Performance of Analytical ethods and Laboratories					
Certified by:	on September 29, 2023.					
Beau R. Brammer						

President