

BRAMMER STANDARD

www.brammerstandard.com - contact@brammerstandard.com
 14603 BENFER ROAD - HOUSTON, TX 77069 - USA
 ph 281-440-9396 - fx 281-440-4432

COPPER ALLOYS

Part Number: **BS-CU-22** Set of 22 ~7 mm THICK DISCS (BS 938-1 & 922B-3 ~12mm thick)

CDA Nr.	Number	Cu	Sn	Pb	Zn	Fe	Ni	Al	Si	Mn	P	As	Sb	C	S
110	BS 110B	99.4	<0.0002	0.00052	<0.0003	0.0005	<0.0002	<0.0002	<0.0004	<0.0001	<0.0006	<0.0001	<0.0005	0.0007	0.00030
172	BS 172Be-1	97.68	0.033	(0.002)	0.007	0.052	0.039	(0.02)	0.055	0.001	0.003	(0.001)	----	(0.001)	----
360	BS 360A	61.42	0.13	2.51	35.63	0.151	0.058	<0.001	<0.005	0.0007	0.001	0.002	0.008	(0.0032)	(0.0003)
464	BS 464A	60.6	0.62	0.056	38.73	0.013	0.004	(0.001)	<0.01	0.0002	0.012	<0.002	(0.001)	(0.0006)	0.001
482	BS 482A	60.0	0.65	0.50	38.8	0.020	(0.007)	(0.003)	(0.002)	<0.002	<0.003	<0.002	0.0012	(0.0015)	<0.002
510	BS 510A	96.10	4.6	0.016	0.21	0.005	0.020	<0.002	<0.003	<0.002	0.11	0.0008	(0.003)	(0.0006)	0.008
544	BS 544A	88.4	4.42	4.16	3.42	0.092	0.16	(0.0005)	<0.002	<0.002	0.021	0.011	0.040	0.003	0.038
623	BS 623A	88.13	0.002	0.001	0.008	2.19	0.146	9.12	0.014	0.273	<0.002	(0.006)	<0.002	(0.002)	(<0.0005)
630	BS 630A	81.0	0.019	0.0069	0.17	3.73	4.81	10.05	0.037	0.11	<0.01	(0.002)	<0.001	0.005	(0.001)
642	BS 642A	91.0	0.018	0.001	0.011	0.17	0.025	6.70	1.80	0.005	0.001	<0.002	(<0.002)	0.001	<0.001
655	BS 655A	95.74	0.07	0.008	0.02	0.075	0.008	(0.002)	3.14	0.91	(0.004)	<0.002	<0.002	(0.0006)	(0.0003)
675	BS 675A	58.5	0.80	0.074	39.1	1.12	0.019	<0.002	(0.005)	0.32	0.010	0.003	0.0011	(0.0007)	(0.0005)
706	BS 706A	87.60	0.011	0.008	0.13	1.30	10.18	(0.002)	<0.005	0.66	0.006	<0.0005	0.0006	0.004	0.012
715	BS 715A	69.0	0.008	(0.007)	0.10	0.61	30.22	(0.01)	0.10	0.82	0.006	(0.0014)	(0.003)	0.03	0.001
863	BS 863A	64.1	0.013	0.022	24.8	2.41	0.29	5.21	0.034	3.00	(0.007)	0.010	0.003	0.003	<0.0005
903	BS 903B	86.7	7.9	0.10	4.39	0.049	0.50	(0.001)	0.002	0.0004	0.073	0.003	0.003	(0.0004)	0.006
922	BS 922B-1	88.4	5.8	1.33	3.95	0.010	0.61	(0.001)	(0.001)	(0.002)	0.037	0.001	0.002	----	----
929	BS 929	85.3	9.07	1.98	0.0055	0.0030	3.37	(<0.00005)	(<0.001)	(<0.00005)	0.119	0.0017	0.0146	(<0.005)	0.0026
938	BS 938-1	77.1	7.16	14.8	0.26	0.015	0.49	(<0.002)	(<0.004)	(0.001)	0.059	(0.004)	0.033	----	0.009
954	BS 954A	85.64	0.033	0.016	0.30	3.50	0.20	10.17	0.029	0.10	0.012	(0.006)	0.001	0.004	<0.0001
955	BS 955C	80.6	0.003	0.003	0.15	4.04	4.31	10.68	0.025	0.06	0.012	(<0.002)	(<0.002)	----	----
14500	BS 14500	99.4	0.0002	0.0008	0.004	0.0041	(<0.0003)	(<0.0002)	(<0.002)	0.00004	0.0075	(<0.0005)	(<0.001)	0.0005	0.0033

Be: 1.89
Co: 0.206

Ag: (0.001)

CDA Nr. = Copper Development Association Grade Number

Certificates of Analysis are supplied for each certified reference material listed in the set.

