

INDEX

ALLOY LISTING 23
ALLOY SPECIFICATIONS 24
ALUMINUM BRASS 12
ALUMINUM BRONZE 17, 18

BERYLLIUM-COBALT 4
BISMUTH BRASS 12
BISMUTH BRONZE 18
BRASS 10, 11, 12, 13, 14, 15, 16
BRONZE 16, 17, 18

CADMIUM ALLOY 4
CARTRIDGE BRASS 12, 13
CHROMIUM COPPER 4
CONTINUOUS CAST 4
CONVERTER COPPER 5
COPPER 2, 3
COPPER ALLOYS 22
COPPER WIRE 2
COPPER-TIN BINARIES 9

ENVIROBRASS 8

FEDERALLOY 8
FREE CUTTING BRASS 13

GILDING METAL 5
GLOBULE ARC 2
GUN METAL 5

HIGH TENSILE BRASS 16

LEADED BRASS 13
LEADED BRONZE 20, 21
LEADED TIN BRONZE 20, 21

MANGANESE ALLOY 6
MANGANESE BRASS 14
MANGANESE BRONZE 18

NAVAL BRASS 14
NICKEL ALLOY 7, 8
NICKEL BRASS 15
NICKEL BRONZE 18

PHOSPHOR BRASS 15
PHOSPHOR BRONZE 19
PHOSPHORUS ALLOY 8
PHOSPHORUS DEOXIDIZED 2

ROD 2, 5, 14, 21

SEBILOY 8
SILICON BRASS 15
SILICON BRONZE 19
SILVER ALLOY 9

TIN BRONZE 20, 21
TIN COPPER 9

WIRE 2

**There are now
Alloy Specifaions
on the last pages.**

CRM PURITY COPPER DISC AND ROD SETS

available in SETS only, as grouped listed in mg/kg IMN CP: Disc 40 mm Ø x 23 mm IMN CS: Disc 40 mm Ø x 25 mm or Rod 6 mm Ø x 100 mm

Number	Ag	As	B	Bi	Cd	Co	Cr	Fe	Mn	Ni	P	Pb	S	Sb	Se	Si	Sn	Te	Zn
IMN CS1	53.1	2.0	(1.1)	1.1	1.0	0.6	(0.3)	18.4	29.0	46.8	57.7	60.5	65.9	3.0	61.5	(3.0)	52.9	2.1	24.1
IMN CS2	45.6	7.4	(2.8)	6.2	7.4	3.6	35.8	30.5	35.3	26.7	33.8	38.6	44.9	7.5	39.0	(9.4)	33.7	5.6	8.9
IMN CS3	38.9	13.8	(4.2)	12.2	13.4	7.4	10.9	28.3	12.6	11.1	12.1	13.3	18.8	13.0	15.4	(22.2)	13.3	10.6	31.3
IMN CS4	237	42.2	(21.7)	39.6	35.5	24.3	7.0	82.0	8.3	7.2	6.3	7.6	41.3	36.8	6.7	(46.5)	6.2	32.9	44.0
IMN CS5	320	70.5	(35.2)	59.7	66.1	37.5	1.0	90.9	4.3	4.4	2.0	5.0	12.0	63.9	0.9	(54.8)	0.9	49.8	101
IMN CP1	12	0.4	.	1.0	0.6	0.2	0.3	10	1.3	3.4	2.0	1.7	6.3	11	<1	.	5.6	3.0	1.9
IMN CP2	36	140	.	.	72	39	0.5	8.1	5.9	20	11	120	35	160	77	(4)	4.8	12	92
IMN CP3	60	63	.	47	35	20	45	15	30	13	44	81	60	120	43	(8)	17	46	33
IMN CP4	110	14	.	13	11	4.2	86	44	55	3.4	130	28	94	48	10	(3)	40	75	17
IMN CP5	31	65	.	9.4	2.5	34	48	77	49	39	110	13	21	27	35	(82)	2.1	7.8	38
IMN CP6	20	0.85	.	.	.	<1	0.3	6.4	0.6	2.7	1.7	2.7	7.5	0.4	<1	.	0.7	.	1.4

CRM COPPER RODS

analysis listed in mg/kg N.F. = Not Found CAN: rod 7.9 mm Ø x 300 mm IMN: 6 mm Ø x 100 mm

Number	Ag	As	B	Bi	Cd	Co	Cr	Fe	Mn	Ni	O	P	Pb	S	Sb	Se	Si	Sn	Te	Zn
CAN SSC-1	18.8	1.16	.	1.15	N.F.	.	.	39.2	.	17.6	216.0	.	65.3	19.6	2.64	7.28	.	54.9	4.57	33.3
IMN CS7 R	13.7	0.9	<0.5	<0.5	(0.02)	0.09	19.7	4.9	2.2	4.4	.	(2.4)	(0.9)	7.0	1.0	<1.0	<1.0	0.5	<0.05	1.2

CRM ELECTROLYTIC COPPER ROD SET

available in SET/6 ONLY listed in mg/kg 3 or 6 mm Ø x 100 mm

Number	Ag	As	Bi	Fe	Ni	Pb	Sb	Sn	Zn	Cu
IMN CF1	45.0	6.7	12.5	42.0	29.0	33.0	24.0	21.0	57.0	Rem
IMN CF2	9.0	1.1	.	2.8	0.7	0.6	1.4	.	2.2	Rem
IMN CF3	3.2	1.8	.	20.0	6.4	8.9	2.2	3.2	3.4	Rem
IMN CF4	18.0	43.0	1.2	3.7	7.8	1.1	11.0	1.0	31.0	Rem
IMN CF5	12.0	2.3	0.25	98.0	3.0	3.2	1.9	1.3	4.7	Rem
IMN CF6	12.0	0.32	(0.012)	1.0	(0.4)	1.8	0.2	(0.06)	.	Rem

COPPER WIRE FOR GLOBULE ARC WORK

analysis listed in mg/kg These Reference Materials are in wire form, intended for globule arc work. 5 rods 3 mm Ø x 80 mm

Number	Ag	As	Bi	Cd	Co	Cr	Fe	Mn	Ni	Pb	Sb	Se	Sn	Te	Zn	O	P	S	Si
CRM																			
38X C1C	11	0.19	0.10	<0.01	.	<0.005	1.7	(0.005)	0.27	(0.05)	0.10	(0.25)	(0.01)	(0.21)	<0.1	266	<0.05	2.0	<0.1
RM																			
38X C6	104	98	22	32	33	1	107	0.3	166	111	45	.	120	30	40
38X C4	21.0	19.0	5.0	8.0	3.0	3.0	19.0	2.7	29.0	23.0	9.0	.	21.0	8.0	22.0
38X C1B	13	0.8	0.1	<0.01	0.03	0.06	1.2	1.2	1.0	0.8	0.6	.	<0.3	0.3	0.45
38X C1A	8	<1	<1	<1	<1	<1	3	<1	1	0.3	<1	.	<1	<1	<2

CHILL CAST PHOSPHORUS DEOXIDIZED COPPER

= Class, where 1 = CRM and 2 = RM, typical analysis

#	Number	P	Cu	Ag	Fe	Al	As	Co	Mn	Ni	Pb	Sb	Sn	Zn
2	CURM 09.01	0.151	99.82	0.011	0.0019	<0.0005	<0.001	<0.0003	<0.0003	<0.0003	<0.0003	<0.0005	<0.0005	0.0008
2	CURM 09.02	0.078	99.90	0.055	0.0042	<0.0005	<0.001	<0.0005	<0.0005	<0.0005	<0.0005	<0.0005	<0.0005	<0.001
1	SRM C1253a	0.0561	99.46	0.0494	0.0290	0.0176	0.0436	0.0454	0.0357	0.0491	0.0243	0.0139	0.0499	0.0329
2	CURM 09.03	0.056	99.82	0.012	0.0033	<0.0003	<0.001	<0.0003	<0.0003	<0.0003	<0.0005	<0.0005	<0.0005	<0.001
1	SRM C1251a	0.0420	99.89	0.0080	0.0285	(<0.0020)	0.0016	0.00132	0.00046	0.00236	0.00235	0.00149	0.0016	0.0024
2	CURM 09.04	0.0174	99.96	0.0033	0.0047	<0.0005	<0.001	<0.0005	<0.0005	<0.0005	<0.001	<0.0005	<0.001	<0.001
1	SRM C1252a	0.0125	99.87	0.0158	0.0072	(<0.0020)	0.0118	0.0087	0.0043	0.0128	0.0060	0.0042	0.0120	0.00694

Number	Au	Bi	Cd	Cr	Mg	S	Se	Si	Te	Units
CURM 09.01	.	<0.0003	<0.001	.	50 mm Ø x 10-12 mm
CURM 09.02	.	<0.0005	<0.002	.	50 mm Ø x 10-12 mm
SRM C1253a	0.0072	(0.0056)	0.0070	0.0260	(0.0150)	(0.0050)	0.0136	(0.0580)	0.0168	32 mm x 32 mm x 19 mm
CURM 09.03	.	<0.0003	<0.001	.	50 mm Ø x 10-12 mm
SRM C1251a	0.00155	0.00037	(<0.0003)	(0.0003)	(<0.0020)	(0.0035)	0.0011	(<0.0050)	0.0016	32 mm x 32 mm x 19 mm
CURM 09.04	.	<0.0005	<0.002	.	50 mm Ø x 10-12 mm
SRM C1252a	0.00339	(0.0019)	0.00169	0.0019	(<0.0020)	(0.0070)	0.0056	(<0.0100)	0.00546	32 mm x 32 mm x 19 mm

CRM COPPER

analysis listed in mg/kg 40 mm Ø x 30 mm

Number	Fe	P	Sn
BAM 391	0.90	3.3	(<0.1)
BAM 390	0.79	1.3	(<0.1)
BAM 392	0.80	7.0	(<0.1)

COPPER

= class, where 1 = CRM and 2 = RM

39X: 40-42 mm Ø x 15-17 mm BS: 38 mm Ø x 12 mm IARM: 31 mm Ø x 2 or 18 mm
 BAM, BCR, ERM: 40 mm Ø x 30 mm CTIF: 40 mm Ø x 18 mm IMN: 40 mm Ø x 25-27 mm

#	Number	Al	As	Bi	Cd	Co	Cr	Fe	Mg	Mn	Ni	P	Pb	S
1	BAM 376	(0.01815)	0.01999	0.0200	0.01861	0.02079	(0.0400)	0.02346	0.0124	0.02059	0.0209	0.0203	0.0236	0.0133
1	39X 17869	0.0109	0.0121	0.066	0.0037	0.0119	0.0290	0.057	0.0068	0.112	0.0174	0.0449	0.0455	0.0107
1	39X 17873	0.015	0.0209	0.0233	0.0052	0.0233	0.0231	0.019	0.011	0.0182	0.0173	0.078	0.065	0.0206
1	39X 17872	0.0118	0.0203	0.0240	0.0013	0.0102	.	(0.045)	.	0.0055	0.0537	0.0045	0.293	0.0242
1	BAM EB386	0.00365	0.00242	0.00096	0.00078	0.000520	0.00124	0.00647	0.00361	0.00133	0.00250	0.00072	0.00234	0.00219
1	BAM EB385	0.00286	0.00114	0.000581	0.00058	0.000693	0.000981	0.00454	0.00291	0.00101	0.00119	0.00129	0.00113	0.00313
1	IARM 279A	(0.002)	(0.002)	(0.001)	.	(0.002)	0.86	0.025	.	(0.002)	0.014	(0.005)	(0.01)	0.0015
1	BAM 384	0.00130	<0.00050	0.000334	0.000395	0.000388	0.000653	0.00328	0.00146	0.000688	0.00057	.	0.00057	(0.00041)
1	BAM 370	0.00126	0.00117	0.0016	.
1	39X 17866	0.0011	0.0541	0.0056	0.0252	0.0395	0.0284	0.0102	0.0011	0.0047	0.0503	0.0102	0.0052	0.051
1	39X 17868	0.0002	0.0196	0.0202	0.0023	0.0002	.	0.0015	.	0.0023	0.0211	(0.0020)	0.046	0.0056
1	39X 17870	(0.0004)	0.0084	0.0334	0.0036	0.0025	(0.0002)	(0.0009)	(0.0001)	0.00013	0.0065	0.0014	0.0296	0.0044
1	39X 17867	(0.0003)	0.0417	0.0122	0.0173	0.0003	(0.0002)	0.0009	(0.0002)	0.0003	0.0339	(0.0012)	0.0058	0.0041
1	BAM 383	(0.00023)	0.000193	0.000102	0.000148	0.000137	0.000103	0.00109	0.000237	0.000124	0.000359	.	0.000131	(0.00028)
1	BAM 382	<0.00025	(0.0053)	0.000053	0.000090	0.000073	0.000056	0.00060	(0.00014)	0.000076	0.00017	.	0.00010	(0.00032)
1	IARM 278A	<0.002	(0.001)	(0.001)	.	(0.001)	(0.001)	0.004	.	(0.0004)	<0.005	0.011	(0.003)	0.002
1	BS 14500	(<0.0006)	(<0.0005)	.	.	(<0.0001)	(<0.0001)	0.0041	(<0.0003)	0.00004	(<0.0003)	0.0075	0.0008	0.0033
1	BS 110B	<0.0002	<0.0001	.	.	<0.0001	<0.0001	0.0005	<0.0001	<0.0001	<0.0002	<0.0006	0.00052	0.00030
1	39X 17871	.	0.0288	0.069	0.0037	0.0040	(0.0005)	0.0080	(0.0005)	0.0007	0.0329	(0.0005)	0.0131	0.0072
1	IMN CT6	.	0.0054	0.0040	.	0.011	.	0.014	.	.	0.011	0.011	0.0014	0.0069
1	BAM 372	.	0.00103	.	0.000163	0.00114	0.0012	.	.	.
1	BAM 366	.	0.000111	(<0.00003)	0.000027	.	.	0.00234	.	.	0.00032	0.0263	0.00108	0.00087
1	IMN CS7 D	.	0.00009	0.00005	(0.000002)	0.000009	0.00197	0.00049	.	0.00022	0.00044	(0.00024)	(0.00009)	0.00070
1	BCR 074A	.	0.000078	(0.000010)	<0.000002	<0.000005	<0.00001	0.000114	.	0.000127	0.000104	.	0.000097	.
1	IMN CS6	.	0.00002	<0.00005	(0.000006)	0.000002	0.00002	0.00208	.	0.00007	0.00008	(0.00015)	(0.00004)	0.00054
1	BAM 381	.	<0.0001	<0.0001	<0.00004	<0.00004	0.000013	0.00028	(0.000034)	0.000027	0.000073	.	0.00005	(0.00029)
1	IARM 70B	.	(0.0001)	<0.0002	.	<0.003	.	<0.001	.	<0.0003	<0.0002	0.002	(0.003)	(0.0005)
1	BCR 017A	0.00069	.	0.00104
1	BAM 369	.	.	0.00097	.	0.00104	0.00092	.	0.00036
1	BAM 371	0.0018	0.0013
2	CTIF CuCrZr 1*	0.75	0.06	.	0.005	0.02	0.02	.	.

#	Number	Al	As	Bi	Cd	Co	Cr	Fe	Mg	Mn	Ni	P	Pb	S
---	--------	----	----	----	----	----	----	----	----	----	----	---	----	---

continued analysis listed in mass % except * which is mg/kg

Number	Sb	Se	Si	Sn	Te	Ti	Zn	Zr	Ag*	Au*	C*	Be*	Cu	In*	O*	Other	
BAM 376	0.0202	0.0210	.	0.02473	0.0215	(0.00045)	0.02173	0.00422	.	.	.	40.6	
39X 17869	0.0416	0.030	0.045	0.0197	0.038	.	0.160	.	432	366	.	.	.	158	.	.	
39X 17873	0.0229	0.0114	0.030	0.0274	0.0070	.	0.0231	.	228	212	.	.	
39X 17872	0.0217	0.0103	.	0.180	0.0208	.	0.107	(0.0024)	214	(15)	.	.	.	241	.	.	
BAM EB386	0.00312	0.00116	.	0.00283	0.00383	0.00331	0.00495	
BAM EB385	0.00191	0.00072	.	0.00180	0.00100	0.000383	0.0058	
IARM 279A	(0.004)	.	0.020	0.021	0.53	.	(0.01)	0.012	(30)	(20)	.	.	99.1	(10)	.	.	
BAM 384	0.00120	0.000424	(0.00050)	(0.00102)	0.00070	(0.000210)	(0.00127)	<0.0009	
BAM 370	0.0015	.	(0.0019)	0.00165	
39X 17866	0.0113	0.0030	0.0156	0.070	0.027	.	0.268	.	55	51	(1)	.	518	.	.	.	
39X 17868	0.020	0.0120	.	(0.0037)	0.024	.	(0.0024)	.	323	1290	.	.	.	9	.	.	
39X 17870	0.0337	0.0208	.	0.0044	0.0052	.	0.0048	.	456	484	.	.	.	31	.	.	
39X 17867	0.0145	0.0087	0.0010	0.0053	0.0104	.	(0.0010)	.	117	120	.	.	.	29	.	.	
BAM 383	0.000144	(0.00016)	<0.0010	0.00047	0.000140	0.000156	(0.00078)	<0.0009	
BAM 382	0.00007	0.00006	<0.0006	0.000429	0.000061	(0.00006)	0.00060	<0.0003	1.8	
IARM 278A	<0.005	.	(0.002)	(0.001)	0.53	.	(0.002)	.	(10)	(30)	.	.	99.5	(4)	.	.	
BS 14500	(<0.001)	.	(<0.002)	0.0002	0.53	.	0.004	.	(2)	5	(<1)	.	99.4	7	.	.	
BS 110B	<0.0005	.	<0.0004	<0.0002	<0.0002	.	<0.0003	.	<2	7	<1	.	99.94	363	Ca*	<3	
39X 17871	0.0147	0.0360	.	0.0119	0.0101	.	0.028	.	222	51	
IMN CT6	0.011	0.011	.	0.013	0.012	.	0.030	.	39	B*	60
BAM 372	.	0.00076
BAM 366	0.000099	(<0.00011)	.	0.0111	(<0.00003)	.	0.00156
IMN CS7 D	0.00010	<0.00010	<0.00010	0.00005	<0.00005	.	0.00012	.	137	B*	<0.5
BCR 074A	0.000058	0.000037	.	<0.000007	(0.000021)	.	0.000046
IMN CS6	0.00010	<0.00010	.	0.00106	<0.00005	.	0.00014	.	85	B*	<0.5
BAM 381	<0.00015	<0.0001	<0.0005	0.00040	.	<0.00005	0.000522	<0.0009
IARM 70B	(0.0002)	<0.0002	<0.0005	(0.0002)	.	.	<0.001	99.9
BCR 017A
BAM 369	0.0022
BAM 371	0.0014	0.00132	11.5
CTIF CuCrZr 1*	0.01	0.06	99.2

Number	Sb	Se	Si	Sn	Te	Ti	Zn	Zr	Ag*	Au*	C*	Be*	Cu	In*	O*	Other
--------	----	----	----	----	----	----	----	----	-----	-----	----	-----	----	-----	----	-------

BERYLLIUM-COBALT ALLOY

= class, where 1 = CRM and 2 = RM
F = Form, where w = wrought and c = cast

36X: 40-41 mm Ø x 15-17 mm

CTIF: 60 mm Ø x 5 mm

BS: 38 mm Ø x 12 mm
IARM: 31 mm Ø x 2 or 18 mm

#	F	Number	Be	Co	Cu	Al	Cr	Fe	Mn	Ni	Pb	Si	Sn	Zn	mass % except * = ppm
2	c	CTIF 4868	2.92	0.246	96.15	0.044	.	0.203	0.019	0.038	0.023	0.211	0.022	0.056	
2	c	CTIF 4584	2.53	0.04	97.05	0.033	.	0.120	(0.002)	0.015	(0.002)	0.166	0.022	0.022	
2	c	CTIF 4872	1.93	0.400	97.00	0.059	(0.04)	0.106	0.008	0.103	0.019	0.16	0.044	0.119	
2	w	BS 172 Be-1	1.89	0.206	97.68	(0.02)	0.003	0.052	0.001	0.039	(0.002)	0.055	0.033	0.007	
1	w	36X CBC4	1.865	0.207	97.46	0.018	.	0.026	.	0.004	0.318	0.041	0.003	0.005	Mg: 0.0070
1	w	36X CBC3	1.840	0.209	97.77	0.019	.	0.046	.	0.007	0.0025	0.039	0.0021	0.004	Mg: 0.0040
1	w	IARM 71B	1.84	0.21	97.7	0.040	0.0030	0.042	0.0010	0.021	0.006	0.060	0.005	0.005	C: 0.003 P: 0.004
2	c	CTIF 4766	1.58	0.64	96.83	0.027	(0.2)	0.165	0.007	0.203	0.053	0.11	0.100	0.070	
2	c	CTIF 4583	0.84	(0.002)	96.35	0.029	.	(0.15)	0.064	2.02	0.084	0.08	0.25	0.094	
1	w	36X CBC 2	0.450	2.47	96.96	0.0231	0.0044	0.0208	0.0015	0.0472	0.0099	0.0205	0.009	0.0103	Ag: 20*
1	w	BS 17500	0.43	2.31	(97.1)	0.0210	0.0015	0.0262	0.081	0.095	0.0005	0.0641	(0.0002)	0.0065	Ca: 54* C: 20* P: 31* Mg: 76* Sb: 1*
1	w	36X CBC 5	0.32	0.14	97.6	0.021	0.006	0.028	(0.001)	1.69	0.009	0.036	0.01	0.038	
2	c	CTIF 4873	0.17	0.98	98.40	0.094	0.105	0.078	(0.002)	0.049	(0.003)	0.088	(0.007)	(0.003)	
2	c	CTIF 4594	0.129	2.96	95.55	0.029	0.066	(0.12)	.	0.055	(0.005)	0.114	(0.003)	(0.006)	Ag: 0.978

CRM

CADMIUM ALLOY

30 mm Ø x 15 mm

Number	Ag	Cd	Sn	Zn
36X CCD1	(0.0014)	1.01	<0.001	(0.0017)
36X CCD2	(0.0012)	1.18	0.200	(0.0019)
36X CCD3	(0.0011)	1.10	0.473	(0.0018)

CHROMIUM COPPER

= class, where 1 = CRM and 2 = RM

#	Number	Cr	Ag	Al	Fe	Mn	Ni	Pb	Si	Sn	Zn	Zr	Cu
1	IARM 158C	1.04	(0.01)	0.002	0.090	0.019	0.32	0.01	0.02	0.01	0.014	.	98.5
1	36X CCR1	0.948	0.0016	(0.001)	0.0378	0.0010	0.0035	0.0017	0.015	0.0049	0.008	0.067	98.95
1	IARM 158B	0.85	(0.01)	0.002	0.090	0.019	0.32	0.01	0.02	0.01	0.014	.	98.5
1	36X CCZ	0.667	0.0019	0.0003	0.033	0.0008	0.0084	0.0023	0.0031	0.0045	0.0076	0.049	99.22

Number	As	Bi	C	Cd	Co	Mg	N	O	P	S	Sb	Units
IARM 158C	(0.001)	.	0.002	.	0.002	.	<0.0005	0.002	0.005	0.003	0.002	31 mm Ø x 2 or 18 mm
36X CCR1	0.0015	.	.	.	0.0018	.	50 mm Ø x 17 mm
IARM 158B	(0.001)	.	0.002	.	0.002	.	<0.0005	0.002	0.005	0.003	0.002	31 mm Ø x 2 or 18 mm
36X CCZ	.	.	(0.002)	0.0027	0.0012	.	.	.	0.0016	0.0010	.	50 mm Ø x 17 mm

RM

CONTINUOUS CAST COPPER ALLOY

38 mm Ø x 12 mm

informational values

Number	Grade	As	Cu	Fe	Mn	Ni	P	Pb	S	Sb	Sn	Zn	Ag	Al	Si
BS 932E	CDA 932	0.048	82.15	0.029	0.0001	0.16	0.022	7.3	0.053	0.145	7.33	2.86	0.007	<0.001	<0.005

CRM CONVERTER COPPER DISC AND ROD SETS

analysis listed in mass %		AVAILABLE IN SETS ONLY, AS GROUPED										IMN CT: 45 mm Ø x 12 or 27 mm		IMN CG, CH: 10 mm Ø x 100 mm			
Number	Ag	As	B	Bi	Co	Cu	Fe	Ni	P	Pb	S	Sb	Se	Sn	Te	Zn	
IMN CT1	0.057	0.32	0.024	0.018	0.051	.	0.17	0.48	0.082	0.013	0.054	0.33	0.062	0.24	0.053	0.28	
IMN CT2	0.042	0.22	0.033	0.013	0.033	.	0.10	0.29	0.059	0.086	0.036	0.24	0.041	0.14	0.036	0.19	
IMN CT3	0.026	0.11	0.00093	0.0067	0.013	.	0.083	0.12	0.038	0.31	0.012	0.11	0.018	0.070	0.022	0.11	
IMN CT4	0.016	0.050	0.0042	0.0043	0.011	.	0.045	0.049	0.020	0.88	0.0060	0.049	0.011	0.025	0.011	0.045	
IMN CT5	0.0062	0.0056	(0.011)	0.0011	0.0061	.	0.016	0.0095	0.0059	(1.48)	0.0024	0.010	0.0069	0.0070	0.0064	0.0098	
IMN CH6	0.18	.	.	.	0.18	Rem	0.028	0.40	.	0.50	0.19	
IMN CH7	0.40	.	.	.	0.11	Rem	0.11	0.18	.	1.01	0.047	
IMN CH8	0.039	.	.	.	0.020	Rem	0.0012	0.036	.	1.49	0.077	
IMN CH9	0.010	.	.	.	0.0060	Rem	0.0060	0.010	.	1.97	0.015	
IMN CG1	0.011	.	.	.	0.17	Rem	0.013	0.036	.	0.60	0.016	
IMN CG2	0.25	.	.	.	0.098	Rem	0.015	0.011	.	0.30	0.026	
IMN CG3	0.040	.	.	.	0.045	Rem	0.030	0.39	.	0.22	0.14	
IMN CG4	0.10	.	.	.	0.057	Rem	0.25	0.23	.	0.11	0.12	
IMN CG5	0.41	.	.	.	0.0079	Rem	0.069	0.10	.	0.053	0.18	

CRM GILDING METAL

Number	Cu	Fe	Ni	P	Pb	Sn	Zn	method	Units
SRM 1114	96.4	0.01	0.021	0.009	0.012	0.02	3.4	wrought	31 mm Ø x 19 mm
SRM C1114	96.4	0.01	0.021	0.009	0.012	0.02	3.4	cast	31 mm x 31 mm x 19 mm
SRM 1113	95.0	0.04	0.057	0.008	0.026	0.06	4.8	wrought	31 mm Ø x 19 mm
SRM C1113	95.0	0.04	0.057	0.008	0.026	0.06	4.8	cast	31 mm x 31 mm x 19 mm
SRM 1112	93.3	0.07	0.10	0.009	0.057	0.12	6.3	wrought	31 mm Ø x 19 mm
SRM C1112	93.3	0.07	0.10	0.009	0.057	0.12	6.3	cast	31 mm x 31 mm x 19 mm

CRM GILDING METAL SET

available in SET/5 only

wrought 40 mm Ø x 25 mm

Number	Ag	Al	As	Be	Bi	Cd	Cu	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Te	Zn
IMN MI1	0.0038	0.0400	0.0720	0.000091	0.00063	0.0230	95.69	0.2500	0.0030	0.0059	0.0280	0.0060	0.0430	0.000044	0.0032	0.1500	0.0065	3.57
IMN MI2	0.0090	0.0550	0.0540	0.00085	0.00056	0.0160	93.35	0.1600	0.0081	0.0180	0.0220	0.0160	0.0490	0.0019	0.0120	0.1000	0.0110	6.19
IMN MI3	0.0200	0.0150	0.0340	0.0019	0.0026	0.0110	91.46	0.0860	0.0350	0.0730	0.0150	0.0420	0.0230	.	0.0310	0.0670	0.0031	8.01
IMN MI4	0.0260	0.0079	0.0031	0.0065	0.0026	0.0054	88.35	0.0410	0.0500	0.1400	0.0073	0.0700	0.0120	0.0006	0.0600	0.0130	0.0021	11.13
IMN MI5	0.0330	0.0021	0.0150	0.0072	0.0043	0.0012	94.71	0.0150	0.0690	0.2500	0.0026	0.0960	0.0019	0.0096	0.0820	0.0040	.	4.44

GUN METAL

C, CURM: 50 mm Ø x 10 - 12 mm

GM24: wrought 44 mm Ø x 17 mm

GM29: wrought 33 mm Ø x 19 mm

other GM: chill cast 40-42 mm Ø x 15-18 mm

Number	Zn	Sn	Pb	Ni	Fe	Cu	Ag	Al	As	Bi	Cr	Mn	P	S	Sb	Si
CRM																
33X GM4	7.13	2.56	4.69	1.795	0.053	82.96	0.0265	(0.001)	0.287	0.084	Co: 0.259	0.0007	0.0088	0.112	0.0261	(0.0006)
33X GM8	5.45	4.13	6.11	0.148	0.098	83.81	0.097	0.0005	0.0159	0.0248	(0.0004)	0.0008	0.0029	0.0119	0.0146	(0.001)
33X GM5	4.19	5.22	5.13	1.008	0.136	83.98	0.0099	(0.007)	0.059	0.0225	Co: 0.0662	0.0018	0.0112	0.061	0.093	(0.0005)
33X GM7	2.29	9.97	0.97	0.500	0.0278	85.49	0.0574	0.051	0.133	0.085	0.0146	0.151	0.034	0.0139	0.111	0.065
33X GM6	2.01	6.56	3.90	0.833	0.0338	85.99	0.0065	0.0098	0.180	0.0313	Co: 0.0056	0.0307	0.0406	0.093	0.279	0.069
RM typical analysis																
CURM 71.32	6.52	6.46	4.43	0.70	0.35	80.48	0.34	0.12	0.25	0.051	0.05	0.046	0.016	0.08	0.26	0.022
CURM 71.31	4.27	4.38	6.44	2.07	0.098	82.30	0.052	0.045	0.11	0.027	<0.01	0.010	0.060	0.050	0.11	0.006
33X GM29	4.23	6.12	0.050	0.0289	0.0102	89.36	0.0026	(0.0004)	0.0017	0.0019	(0.0004)	(0.0005)	0.138	0.0024	0.0015	0.0027
33X GM24	3.67	3.85	3.35	0.0087	0.0083	88.88	0.0046	(0.0001)	0.0010	0.0009	(0.0013)	<0.0005	0.190	0.003	0.0012	0.0028
CURM 71.33	3.60	4.96	6.84	0.938	0.018	83.60	<0.002	<0.001	<0.001	<0.002	<0.0005	<0.0005	<0.001	<0.001	<0.002	<0.005
C71.34	1.55	8.20	2.47	<0.01	0.29	.	0.025	0.007	0.18	0.029	0.03	0.05	0.020	0.16	0.071	0.04
Number	Zn	Sn	Pb	Ni	Fe	Cu	Ag	Al	As	Bi	Cr	Mn	P	S	Sb	Si

* Provisional Analysis

CRM MANGANESE ALLOY SET

AVAILABLE IN SET/6 ONLY

40 mm Ø x 13 mm

Number	Ag	As	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN CK1	0.012	0.013	0.029	1.06	0.44	0.0011	0.0021	0.0049	0.049	0.13	0.24
IMN CK2	0.0094	0.010	0.11	1.51	0.38	0.0022	0.0062	0.0015	0.091	.	0.14
IMN CK3	0.0066	0.0095	0.17	1.78	0.27	0.0043	0.0098	0.0026	0.033	0.075	0.095
IMN CK4	0.0041	0.0055	0.26	1.91	0.13	0.0056	0.017	0.0041	0.0025	0.042	0.065
IMN CK5	.	0.0015	0.29	2.30	0.011	.	.	0.0051	0.011	0.0048	0.033
IMN CK6	0.0012	0.0039	0.40	2.64	0.073	0.013	.	0.0052	0.21	0.025	0.034

NICKEL ALLOY

#	Number	Ni	Ag	Al	Bi	Co	Cr	Cu	Fe	Mn	Nb	P	Pb	S	Si	Sn	Zn
1	36X CN6	33.46	.	(0.0023)	0.0058	0.0440	1.10	63.34	0.878	0.451	0.51	0.031	0.0066	0.0109	0.144	0.0307	0.026
1	36X CN5	32.26	.	0.006	.	0.018	0.118	65.1	0.791	0.090	0.441	0.041	0.027	0.074	0.80	0.015	0.232
1	IARM 85C	31.3	<0.002	<0.01	.	0.016	0.002	67.3	0.63	0.65	.	(0.003)	0.004	(0.002)	0.01	0.005	0.057
1	SRM 1276a	30.8	(0.004)	.	(<0.0001)	0.045	(0.0002)	67.5	0.56	1.01	.	0.006	0.004	(0.008)	(0.001)	0.023	0.038
1	36X CN8	30.61	.	0.0009	0.103	0.104	1.28	65.51	0.86	0.881	0.18	0.046	0.095	0.022	0.132	0.046	0.159
2	BS 715A	30.22	.	(0.01)	.	.	.	68.0	0.61	0.82	.	0.006	(0.007)	0.001	0.10	0.008	0.10
1	IARM 236A	30.0	.	0.003	0.003	0.004	0.002	66.7	0.91	1.04	.	0.003	0.004	0.003	0.19	0.005	0.002
1	36X CN7	29.95	.	.	(0.014)	0.108	1.51	65.58	1.021	0.659	0.58	(0.021)	0.028	0.0151	0.304	0.039	0.203
2	C62.11	29.9	.	.	.	<0.002	.		<0.005	0.33	.	.	<0.002	<0.002	0.32	.	.
2	CTIF CN 33	29.75	.	(0.01)	0.0212	.	.	87.1	1.6	0.45	0.06	0.02	0.053	0.013	0.47	(0.003)	0.37
1	IARM 85B	29.60	.	(<0.01)	.	0.034	.		0.53	0.53	.	0.007	0.005	0.010	(<0.01)	0.014	0.12
1	36X CN10	29.3	.	1.23	0.014	0.081	1.59	61.01	4.28	0.262	0.89	(0.020)	0.004	0.055	1.02	(0.009)	0.026
1	36X CN9	28.90	.	(0.094)	.	0.323	1.84	64.96	0.722	1.019	1.40	0.008	0.020	0.0130	0.413	0.0291	0.060
2	C62.15	27.5	.	.	.	0.008	.		1.5	0.43	.	.	0.01	0.009	0.06	.	.
1	36X CN4	27.49	.	0.0013	0.0077	0.052	0.022	69.48	2.67	0.164	0.0139	0.0078	(0.023)	0.0076	0.025	0.009	0.041
1	BAM 389	24.7	.	.	0.0044	0.0770	0.0153	74.3	0.107	0.415	.	0.0093	0.0098	.	.	0.0262	0.1125
2	C62.14	20.8	.	.	0.05	0.072	0.050		1.54	0.76	.	.	0.008	0.03	0.03	.	.
1	36X CN3	19.95	.	0.0055	.	0.072	0.050	76.3	1.07	0.920	0.15	0.032	0.053	0.029	0.490	0.063	0.80
2	C65.30	19.8	.	.	.	0.09	.	55.0	1.0	0.09	.	0.05	0.25	0.04	0.10	0.04	Rem
1	34X NS5	17.16	0.0102	0.674	.	0.197	0.0014	55.11	0.717	0.127	.	0.067	1.29	.	0.158	0.194	(23.1)
1	34X NS4	16.96	0.0298	.	.	0.222	0.0005	66.71	0.351	0.0100	.	0.0099	0.152	0.012	(0.0009)	0.020	15.58
2	C65.29	16.8	58.9	0.39	0.17	.	0.07	0.11	0.06	0.02	0.08	Rem
1	36X SP2	15.72	0.0181	0.0003	(0.0027)	0.119	.	74.91	(0.09)	0.0019	.	(0.0006)	0.026	0.0030	(0.0023)	8.92	0.029
1	36X CN2	15.47	.	0.005	0.0045	0.264	0.240	80.78	1.70	1.26	(0.032)	0.015	0.048	0.035	0.044	0.061	0.0358
1	36X CN24	15.41	0.0466	(0.0010)	.	0.0096	0.0065	52.56	0.127	23.60	.	0.0037	0.0056	.	.	(0.0023)	8.00
2	C65.28	15.3	56.9	0.13	0.57	.	0.06	0.06	0.03	0.01	0.15	Rem
1	36X CN11	14.96	.	1.457	.	0.0049	0.380	77.56	0.992	4.34	0.124	(0.002)	(0.003)	0.0012	0.083	(0.002)	(0.006)
1	34X NS3	14.86	0.111	0.038	.	0.102	0.0022	66.30	0.201	0.129	.	0.013	0.155	0.063	0.018	0.031	17.99
1	36X CN23	14.38	0.042	0.007	.	0.0509	0.0029	70.22	0.140	0.0095	.	0.0299	0.115	0.01	0.102	0.148	.
2	C62.13	13.9	.	.	.	0.04	.		0.93	1.2	.	.	0.01	0.05	0.08	.	.
2	C65.27	13.9	57.0	0.26	0.13	.	0.02	0.04	0.03	<0.002	0.01	Rem
1	34X NS2	13.39	0.0026	.	.	0.0118	(0.001)	61.09	0.085	0.0013	.	0.0091	0.063	(0.020)	(0.003)	0.019	25.31
2	C65.26	11.9	56.7	<0.01	0.70	.	0.11	0.06	0.0006	<0.002	<0.01	Rem
2	CTIF CN4	11.2	.	(0.02)	.	.	.	84.0	1.8	1.5	0.7	.	0.006	(0.001)	(0.01)	0.058	0.07
2	BS 706B	10.9	.	<0.003	.	0.005	.	87.00	1.56	0.61	.	0.009	0.006	0.009	<0.002	0.006	0.054
2	BS 706	10.49	.	<0.005	.	.	.	(87.3)	1.61	0.55	.	0.005	<0.01	0.015	<0.01	0.016	0.08
2	BS 706A	10.18	.	(0.002)	.	0.007	.	87.80	1.30	0.66	.	0.006	0.008	0.012	<0.005	0.011	0.13
1	36X CN1	10.11	.	0.006	.	0.154	0.0258	84.90	2.15	1.80	.	0.0436	0.160	0.0070	0.089	0.0578	0.412
2	CTIF CuNi 10	10.08	87.4	1.69	0.70	.	.	0.0027	(0.002)	.	(<0.01)	0.033
1	IARM 84B	10.03	0.005	(0.002)	.	0.013	(0.003)	87.9	1.30	0.62	.	0.004	0.008	0.008	0.01	0.014	0.082
1	BAM 367	9.72	.	.	.	0.0498	.	87.88	1.443	0.723	.	0.0124	0.0298	.	.	0.0105	0.0715
1	36X CN1	9.31	.	<0.001	.	0.131	0.118	85.3	2.41	2.27	(0.019)	0.008	0.008	0.010	0.058	0.006	0.331
2	CTIF CN3 *	9	.	0.1	.	.	.	87.5	0.7	1.5	0.6	.	0.02	0.01	0.2	<0.01	0.1
1	36X SP1	8.33	0.005	0.0020	0.0039	0.057	.	84.90	0.45	0.084	(0.031)	(0.003)	0.0115	0.005	0.004	5.75	0.344
2	C62.12	8.3	.	.	.	<0.002	.		1.8	1.8	.	.	0.02	0.08	0.04	.	.
2	CURM 62.12	7.94	.	.	.	0.081	.	89.42	0.45	1.59	.	.	0.053	0.034	0.109	0.111	0.180
1	34X NS1	7.81	0.069	(0.003)	.	0.052	0.0003	58.63	0.064	0.0009	.	0.0140	0.0141	(0.0004)	(0.002)	0.0110	33.41
2	CTIF CN2	7.80	.	(0.012)	.	.	.	88.40	1.68	1.19	(0.007)	.	0.055	0.028	0.26	(0.0065)	0.515
1	36X CN21	5.50	0.0064	1.95	.	0.0079	0.0050	92.17	0.316	0.0391	.	0.053	0.051	.	.	0.038	0.0203
1	36X 274	2.54	.	0.0013	.	0.0028	0.531	96.23	0.0779	0.0148	.	0.0011	0.0021	0.0035	0.594	0.0140	0.0395
1	37X 218	2.52	.	0.0022	.	0.0013	0.032	96.57	0.074	0.0883	.	0.0014	0.0025	0.007	0.58	0.015	0.027
1	36X CN22	1.806	0.0196	6.09	.	0.0231	0.0144	91.80	0.088	(0.016)	.	0.0178	0.0260	.	.	0.0371	0.0175

Number	As	B	Be	C	Cd	Mg	Sb	Te	Ti	Zr	Units
36X CN6	.	(0.0016)	.	0.0180	0.0066	0.004	40 mm Ø x 15 mm
36X CN5	.	0.0091	0.011	0.0253	.	0.014	40 mm Ø x 15 mm
IARM 85C	0.0009	.	.	0.008	.	0.01	31 mm Ø x 2 or 18 mm
SRM 1276a	(<0.001)	(0.0001)	.	0.002	0.002	0.12	0.0004	0.005	(0.0002)	.	32 mm Ø x 19 mm
36X CN8	.	0.0025	.	0.0225	.	0.021	40 mm Ø x 15 mm
BS 715A	(0.0014)	.	.	0.03	.	.	(0.003)	.	.	.	38 mm Ø x 12 mm
IARM 236A	.	.	.	0.010	.	.	<0.005	.	.	.	31 mm Ø x 2 or 18 mm
36X CN7	.	(0.004)	.	0.0106	0.0024	0.0041	.	.	(0.037)	(0.003)	40 mm Ø x 17 mm
C62.11	<0.002	60 mm Ø x 10 mm
CTIF CN 33	.	.	.	0.02	0.006	<0.06	.	0.0224	.	.	60 mm Ø x 5 mm
IARM 85B	.	.	.	0.011	.	.	(<0.01)	.	.	.	31 mm Ø x 2 or 18 mm
36X CN10	.	0.0029	.	0.064	.	0.0026	.	.	.	(0.055)	40 mm Ø x 15 mm
36X CN9	.	0.0065	.	0.0098	0.150	0.0019	40 mm Ø x ~15 mm
C62.15	<0.002	60 mm Ø x 10 mm
36X CN4	.	.	.	0.0053	.	(0.0004)	.	.	(0.004)	.	40 mm Ø x 17 mm
BAM 389	0.0016	0.067	0.0046	.	0.0660	0.098	40 mm Ø x 30 mm
C62.14	0.002	60 mm Ø x 10 mm
36X CN3	.	0.0064	0.0163	0.035	.	0.012	40 mm Ø x 15 mm
C65.30	0.01	50 mm Ø x 10 - 12 mm
34X NS5	0.704	42 mm Ø x 17 mm
34X NS4	<0.0001	42 mm Ø x 17 mm
C65.29	<0.01	50 mm Ø x 10 - 12 mm
36X SP2	.	0.0005	.	.	.	0.0002	0.006	.	(0.0008)	.	40 mm Ø x 15 mm
36X CN2	.	.	.	0.004	.	0.0006	.	.	0.0102	.	40 mm Ø x 17 mm
36X CN24	(0.0011)	.	.	0.0436	38 mm x 13 mm x 13
C65.28	0.01	50 mm Ø x 10 - 12 mm
36X CN11	.	.	.	(0.001)	.	0.0241	40 mm Ø x ~17 mm
34X NS3	.	.	.	0.014	.	0.0011	42 mm Ø x 18 mm
36X CN23	0.047	.	.	.	0.0021	40 mm Ø x ~17 mm
C62.13	0.006	60 mm Ø x 10 mm
C65.27	<0.01	50 mm Ø x 10 - 12 mm
34X NS2	<0.0005	42 mm Ø x 17 mm
C65.26	<0.01	50 mm Ø x 10 - 12 mm
CTIF CN4	.	.	.	(0.001)	60 mm Ø x 5 mm
BS 706B	<0.0005	.	.	(0.004)	.	.	<0.002	.	.	.	38 mm Ø x 12 mm
BS 706	<0.005	.	.	(0.003)	.	.	<0.005	.	.	.	38 mm Ø x 12 mm
BS 706A	<0.0005	.	.	0.004	.	.	0.0006	.	.	.	38 mm Ø x 12 mm
36X CN1	.	0.0013	.	(0.0026)	40 mm Ø x ~17 mm
CTIF CuNi 10	.	.	.	(0.009)	40 mm Ø x 18 mm
IARM 84B	.	.	.	(0.01)	.	.	(0.002)	.	.	.	31 mm Ø x 2 or 18 mm
BAM 367	0.0347	40 mm Ø x 30 mm
36X CN1	.	(0.0008)	(0.0001)	0.008	.	(0.0003)	40 mm Ø x 15 mm
CTIF CN3 *	.	.	.	0.05	60 mm Ø x 5 mm
36X SP1	.	0.0007	0.0177	.	(0.0004)	.	40 mm Ø x 15 mm
C62.12	.	.									

CRM NICKEL ALLOY SETS

available in SETS only, as grouped		analysis listed in mass %											NA: 28 mm Ø x 25 mm		MN: 35 mm Ø x 30 mm NB: 40 mm Ø x 25 mm		N: 35 mm Ø x 30 mm NC: 40 mm Ø x 12 mm	
Number	Ni	Al	As	Bi	C	Cd	Co	Cu	Fe	Mg	Mn	P	Pb	S	Sb	Si	Sn	Zn
IMN NC1	23.17	.	0.0056	0.0011	0.0320	0.0142	0.0062	.	0.0501	0.0016	0.552	0.0147	0.0025	0.0709	0.0024	0.0854	0.0374	0.776
IMN NC2	24.21	0.0219	0.0104	0.0046	(0.0026)	0.0189	0.0115	.	0.290	0.0024	0.413	.	0.0021	0.0837	0.0049	0.196	0.0457	0.508
IMN NC3	24.68	0.229	0.0167	0.0077	(0.0036)	0.0120	0.0282	.	0.106	0.0561	0.148	0.0312	0.0027	(0.0202)	0.0084	0.0609	0.0171	0.244
IMN NC4	25.39	0.332	0.0251	0.0117	0.0500	0.0049	0.101	.	0.426	0.0170	0.0172	0.0113	0.0120	0.0022	0.0113	0.0197	0.0087	0.0099
IMN NC5	25.82	0.0749	0.0427	0.0213	0.0050	0.0018	0.151	.	0.369	0.0861	0.0623	0.0222	0.0409	.	0.0161	0.0198	0.0044	0.0152
IMN NB1	23.77	0.071	0.024	0.011	0.040	0.016	0.010	75.71	0.11	0.017	0.029	0.025	0.011	0.0019	0.0025	0.093	0.0038	0.052
IMN NB2	24.38	0.043	0.0045	0.0082	0.019	0.0053	0.023	74.73	0.085	0.0059	0.46	0.030	0.014	0.0084	0.0036	0.13	0.014	0.037
IMN NB3	25.87	0.12	0.0076	0.0070	0.034	0.0082	0.017	73.20	0.14	0.013	0.23	0.019	0.011	0.011	0.0057	0.068	0.040	0.20
IMN NB4	25.78	0.013	0.0097	0.0040	0.018	0.0064	0.013	73.45	0.21	0.028	0.015	0.0085	0.0084	0.015	0.0092	0.024	0.065	0.33
IMN NB5	24.94	0.0014	0.011	0.0010	0.012	0.0012	0.0067	73.42	0.28	0.036	0.57	0.0036	0.0060	0.028	0.012	0.0057	0.10	0.57
IMN N1	25.38	0.0050	Rem	0.0056	.	0.0018	.	0.0019	.	.	0.0070	0.0089	0.019
IMN N2	24.28	0.023	Rem	0.35	.	0.21	.	0.011	.	.	0.025	0.012	0.16
IMN N3	22.57	0.055	Rem	0.77	.	0.50	.	0.020	.	.	0.062	0.023	0.33
IMN N4	21.39	0.080	Rem	1.07	.	0.71	.	0.039	.	.	0.13	0.038	0.47
IMN NA1	7.19	.	.	.	(0.020)	.	.	Rem	2.52	.	1.51	.	0.081	(0.081)	.	.	.	0.80
IMN NA2	9.05	.	.	.	(0.023)	.	.	Rem	2.03	.	1.03	.	0.056	(0.065)	.	.	.	0.55
IMN NA3	10.35	.	.	.	(0.019)	.	.	Rem	1.15	.	0.60	.	0.035	(0.036)	.	.	.	0.30
IMN NA4	12.15	.	.	.	(0.012)	.	.	Rem	0.50	.	0.21	.	0.0066	(0.0069)	.	.	.	0.019
IMN MN1	3.21	.	0.0007	0.00011	.	.	.	Rem	0.0041	.	.	(0.00027)	0.0062	.	0.00019	.	.	.
IMN MN2	4.50	.	0.0011	0.00071	.	.	.	Rem	0.033	.	.	0.010	0.012	.	0.00078	.	.	.
IMN MN3	5.29	.	0.0017	0.0012	.	.	.	Rem	0.062	.	.	0.016	0.016	.	0.0013	.	.	.
IMN MN4	5.90	.	0.0038	0.0018	.	.	.	Rem	0.083	.	.	0.026	0.024	.	0.0019	.	.	.

CRM PHOSPHORUS ALLOY SET

cast	SOLD IN SET/4 ONLY											40 mm Ø x 25 mm	
Number	P	As	Bi	Fe	Ni	Pb	Sn	Sb	Se	Te	Zn	Cu	
IMN CO2	11.60	0.0050	0.0049	0.096	0.013	0.070	0.35	0.065	(0.0045)	(0.0055)	0.15	REM	
IMN CO5	9.45	0.0023	0.00095	0.11	0.0082	0.0044	0.55	0.034	(0.0015)	(0.0023)	0.061	REM	
IMN CO3	8.56	0.011	0.015	0.11	0.10	0.10	0.037	0.14	(0.0073)	(0.0080)	0.24	REM	
IMN CO4	5.54	0.016	0.0086	0.29	0.25	0.29	0.13	0.092	(0.010)	(0.012)	0.029	REM	

CRM SEBILOY / ENVIROBRASS / FEDERALLOY

Number	Sn	Zn	Bi	Se	As	Co	Fe	Ni	P	Pb	Sb	Cu
32X SEB2	9.34	3.73	4.36	0.026	0.0094	0.0121	0.078	0.028	0.013	0.424	0.0120	(81.8)
32X SEB4	9.26	8.60	2.65	0.105	0.0012	0.48	0.366	0.0091	(0.006)	0.011	0.0056	78.6
32X SEB6	7.14	4.55	0.615	0.322	0.083	0.231	0.151	0.860	0.0118	0.0463	0.235	85.66
IARM 266A	6.9	3.48	2.37	0.001	0.004	(0.001)	0.035	0.46	0.032	0.010	0.010	(87)
32X SEB5	5.28	6.64	1.17	0.512	0.0121	0.0048	0.360	0.308	0.183	0.0149	0.0344	85.5
IARM 226A	5.1	4.8	1.7	0.93	0.003	0.001	0.054	0.54	0.005	0.040	0.004	86.7
IARM 227A	5.1	4.70	2.3	1.21	0.003	0.001	0.060	0.53	0.003	0.042	<0.01	85.9
IARM 265A	4.4	2.45	2.4	(0.002)	(0.005)	(0.001)	0.013	0.69	0.024	0.011	0.015	(90)
32X SEB1	4.23	8.79	5.31	0.97	0.043	0.0089	0.0293	0.101	0.0054	0.209	0.355	79.6
IARM 228A	4.1	4.1	1.53	0.67	0.003	0.001	0.052	0.45	0.032	0.026	0.010	89.0
IARM 263A	3.5	15.8	2.55	(0.002)	0.003	0.001	0.047	0.66	0.040	0.022	0.06	(78)
32X SEB7	3.20	4.42	3.58	1.19	0.038	0.119	0.074	1.165	0.0206	0.343	0.262	85.46
IARM 264A	3.03	5.33	3.6	(0.001)	(0.004)	(0.001)	0.048	0.54	0.027	0.057	0.074	(87.3)
32X SEB3 **	2.07	0.85	(5.4)	1.42	0.0161	0.025	0.082	1.52	0.040	0.109	0.054	(88.4)

Number	Ag	Al	B	C	Cd	Cr	Mn	N	O	S	Si	Units
32X SEB2	40 mm Ø x 17 mm
32X SEB4	.	.	0.0021	.	0.0004	42 mm Ø x 17 mm
32X SEB6	0.0036	40 mm Ø x 15 mm
IARM 266A	(0.001)	0.002	.	(0.002)	.	(0.002)	(0.002)	.	.	(0.002)	0.002	31 mm Ø x 2 or 18 mm
32X SEB5	.	.	0.0028	.	0.0067	40 mm Ø x 17 mm
IARM 226A	0.004	0.002	.	0.003	.	(0.001)	0.002	<0.0005	(0.001)	0.005	0.002	31 mm Ø x 2 or 18 mm
IARM 227A	0.004	0.002	.	0.003	.	(0.001)	0.001	(0.0002)	0.0013	0.005	0.002	31 mm Ø x 2 or 18 mm
IARM 265A	(0.002)	0.003	.	.	.	(0.001)	(0.002)	.	.	(0.002)	0.003	31 mm Ø x 2 or 18 mm
32X SEB1	(0.0002)	0.0011	.	40 mm Ø x 17 mm
IARM 228A	0.003	0.002	.	0.003	.	0.001	0.001	<0.0005	(0.002)	0.004	0.002	31 mm Ø x 2 or 18 mm
IARM 263A	(0.006)	(0.002)	.	<0.005	.	(0.002)	(0.002)	.	.	(0.002)	0.003	31 mm Ø x 2 or 18 mm
32X SEB7	0.0074	0.067	.	42 mm Ø x 17 mm
IARM 264A	(0.005)	0.003	.	(0.004)	.	(0.002)	(0.002)	.	.	0.0013	0.003	31 mm Ø x 2 or 18 mm
32X SEB3 **	.	.	0.0021	.	0.0016	** Bi and Cu are inhomogeneous in this sample	40 mm Ø x 17 mm

RM SILVER ALLOY

31 mm Ø x 2 or 18 mm

Number	Ag	C	P	S	Zr
IARM 159A	3.48	(0.002)	(<0.01)	(<0.01)	.
IARM 160A	3.03	0.003	(0.004)	(<0.003)	0.40
Al, Co, Cr, Fe, Mn, Ni, Pb, Si, Sn, and Zn: (<0.01)					

RM COPPER-TIN BINARIES

cast typical analysis

Number	Sn	Units
C 11.04	9.3	50 mm Ø x 10 - 12 mm
32X 14956	7.35	40 mm Ø x 15 mm
C 11.03	7.3	50 mm Ø x 10 - 12 mm
C 11.02	5.4	50 mm Ø x 10 - 12 mm
32X 14955	5.25	40 mm Ø x 15 mm
C 11.01	3.3	50 mm Ø x 10 - 12 mm
32X 14954	3.15	40 mm Ø x 15 mm
32X 14953	1.37	40 mm Ø x 15 mm

CRM TIN COPPER

available in SET/5 only

40 mm Ø x 30 mm

Number	Ag	As	Bi	Cu	Fe	Ni	P	Pb	Sb	Sn	Zn
IMN CM1	0.010	0.0098	0.010	Rem	0.019	0.0086	0.0088	0.012	0.012	0.61	0.021
IMN CM2	0.0061	0.0068	0.0072	Rem	0.0064	0.0055	0.0058	0.0067	0.0068	0.84	0.0061
IMN CM3	0.0029	0.0036	0.0033	Rem	0.012	0.0031	0.0041	0.0038	0.0040	1.06	0.0060
IMN CM4	0.0011	0.0011	0.00093	Rem	0.0042	0.0011	0.0009	0.0023	0.0019	1.30	0.0020
IMN CM5	.	(0.015)	0.014	Rem	0.0094	0.014	0.015	0.019	0.018	1.14	0.013

CRM BRASS SETS

wrought available in SETS only, as grouped MB: 40 mm Ø x 18 mm MD, WC: 40 mm Ø x 12 mm ME, MG: 40 mm Ø x 30 mm

Number	Cu	Zn	Al	As	Bi	Fe	Mn	Ni	P	Pb	Sb	Si	Sn
IMN MG1	91.14	Rem	0.040	.	0.00058	0.0081	0.0013	0.048	(0.0019)	0.049	0.00077	.	0.0062
IMN MG2	90.08	Rem	(0.0026)	.	0.00039	0.0067	0.0007	0.0022	0.0012	0.0048	(0.00084)	.	0.018
IMN MG3	93.19	Rem	0.020	.	0.0014	0.062	0.0096	0.013	0.018	0.015	0.0026	.	0.033
IMN MG4	94.00	Rem	.	.	0.0017	0.091	0.024	0.0042	0.012	0.008	0.0045	.	0.023
IMN MG5	95.09	Rem	0.0011	.	0.0026	0.149	0.0036	0.0021	0.0069	0.0054	0.0061	.	0.013
IMN MG6	92.27	Rem	0.0067	.	0.00088	0.028	0.045	0.030	0.0026	0.031	0.0015	.	0.053
IMN WC1	75.10	Rem	0.0034	0.0043	0.0028	0.031	.	.	0.015	0.046	0.0034	0.26	0.0032
IMN WC2	75.05	Rem	0.0016	0.0024	0.0020	0.015	.	.	0.011	0.031	0.0023	0.41	0.0025
IMN WC3	75.28	Rem	0.0018	0.0011	0.00093	0.021	.	.	0.0058	0.0085	0.0010	0.89	0.0011
IMN WC4	75.32	Rem	0.00096	.	0.00047	0.0067	.	.	0.0048	0.0051	0.00080	0.76	0.0010
IMN WC5	75.03	Rem	0.00084	0.0022	0.0019	0.18	.	.	.	0.0055	0.0011	0.48	0.0044
IMN WC6	75.32	Rem	0.0019	0.00097	0.0012	0.051	.	.	0.0037	0.0036	0.00057	0.58	0.0028
IMN MD1	67.92	Rem	.	0.0015	0.0026	0.043	0.097	0.021	0.0082	0.19	0.0096	0.078	0.0013
IMN MD2	68.99	Rem	.	0.072	0.0025	0.18	0.082	0.050	0.0061	0.015	0.0011	0.059	0.0054
IMN MD3	69.43	Rem	.	0.055	0.0018	0.085	0.062	0.070	0.0043	0.010	0.012	0.097	0.010
IMN MD4	71.53	Rem	.	0.038	0.00053	0.018	0.015	0.091	.	0.054	0.0038	0.0066	0.21
IMN MD5	71.06	Rem	.	0.018	(0.00004)	0.081	0.017	0.064	0.00089	0.0023	0.0065	0.016	0.021
IMN MD6	70.77	Rem	.	(0.00022)	0.000044	.	0.00073	0.039	.	0.044	0.00058	.	0.019
IMN ME2	71.29	Rem	0.87
IMN ME3	70.70	Rem	1.11
IMN ME4	69.40	Rem	1.21
IMN ME5	68.53	Rem	1.42
IMN MB1	60.66	39.39
IMN MB2	67.17	32.80
IMN MB3	73.26	26.67
IMN MB4	78.77	21.20
IMN MB5	84.25	15.63
IMN MB6	90.07	9.95
IMN MB7	95.00	4.99

RM TRACE ELEMENTS IN BRASS

cast 50 mm Ø x 10 - 12 mm

Number	Cu	Zn	Al	As	Bi	Fe	Mn	Ni	Pb	Sb	Si	Sn
C30.10	95.3	rem	<0.002	.	.	<0.005	<0.005	<0.01	<0.01	.	<0.005	<0.01
C30.09	89.5	rem	<0.002	<0.005	<0.002	<0.005	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
C30.08	85.1	rem	<0.002	.	.	<0.005	<0.005	<0.01	<0.01	.	<0.005	<0.01
C30.07	79.8	rem	<0.002	.	.	<0.005	<0.005	<0.01	<0.01	.	<0.005	<0.01
C30.06	75.0	rem	<0.005	.	.	<0.005	<0.005	<0.01	0.05	.	<0.005	<0.01
CURM 30.05	69.48	30.53	<0.001	<0.001	<0.003	<0.003	<0.0005	<0.0005	0.002	<0.005	0.001	<0.001
C30.19	67.4	rem	5.0	.	.	<0.005	<0.005	<0.01	<0.01	.	<0.005	1.0
C30.04	64.8	rem	<0.005	.	.	<0.005	<0.005	<0.005	0.005	.	<0.005	<0.005
CURM 30.04	64.34	35.62	<0.001	<0.001	<0.003	0.009	<0.001	<0.001	0.003	<0.005	0.016	0.009
C30.17	61.7	rem	<0.002	.	.	1.6	<0.005	<0.01	<0.01	.	<0.005	<0.01
C30.12	61.3	rem	<0.002	.	.	<0.005	1.0	0.52	<0.005	.	<0.005	<0.005
C38.01	61.0	rem	0.003	0.03	<0.001	0.01	0.009	0.01	0.20	0.02	<0.001	0.20
C38.02	61.0	rem	0.005	0.06	0.005	0.09	0.14	0.03	0.10	0.06	0.01	0.09
C38.03	61.0	rem	0.06	0.08	0.008	0.05	0.07	0.13	0.05	0.08	0.07	0.05
C38.04	61.0	rem	0.02	0.04	0.008	0.04	0.22	0.06	0.02	0.12	0.12	0.02
C38.05	61.0	rem	0.12	0.01	0.01	0.008	0.02	0.18	0.01	0.01	0.14	0.01
C38.06	61.0	rem	<0.001	<0.001	<0.001	<0.005	<0.001	<0.005	0.002	<0.002	<0.001	<0.005
C30.16	61.2	rem	<0.002	<0.005	<0.002	0.90	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
C30.15	60.6	rem	<0.002	<0.005	<0.002	0.55	<0.005	<0.01	<0.01	<0.005	<0.005	<0.01
C30.13	60.6	rem	<0.002	.	.	<0.005	1.9	<0.01	<0.01	.	<0.005	<0.01
C30.03	60.2	rem	0.002	.	.	<0.005	<0.005	0.01	<0.01	.	<0.005	<0.01
C30.14	59.6	rem	<0.002	.	.	<0.005	2.6	0.99	<0.01	.	<0.005	<0.01
C30.22	58.1	rem	<0.002	.	.	<0.005	<0.005	<0.01	1.0	.	<0.005	<0.01
C30.02	55.6	rem	<0.002	.	.	<0.005	<0.005	<0.01	<0.01	.	<0.005	<0.01
C30.01	51.5	rem	<0.001	.	.	0.05	<0.001	<0.001	<0.001	.	<0.001	<0.001

RM BRASS MUSHROOMS

chill cast typical analysis 60 mm Ø x 5 mm

Number	Zn	Cu	Al	As	Be	Fe	Ni	Mg	Mn	P	Pb	Sb	Si	Sn
CTIF L 7	42.45	55.6	0.308	.	.	0.031	0.020	.	0.62	.	0.71	.	0.13	0.038
CTIF L 1-1	39.7	59.60	0.015	.	.	0.017	0.106	.	.	0.080	0.062	.	0.36	0.046
CTIF L 2	35.55	61.55	0.485	.	.	0.216	0.71	.	0.350	.	0.408	.	0.202	0.48
CTIF L 4-1	34.55	61.75	0.100	.	.	0.466	0.227	.	0.109	.	2.017	.	0.12	0.693
CTIF L 3	32.70	62.35	0.91	.	.	0.36	0.90	.	0.205	.	1.02	.	0.034	1.50
CTIF L 5-1	31.5	60.9	0.64	0.13	.	(1.0)	0.494	.	0.50	(0.15)	2.99	0.174	(0.47)	0.88
CTIF L 6	30.26	66.55	0.139	.	.	0.085	1.21	.	0.055	.	0.205	.	1.25	0.250
CTIF L 23	17.90	81.20	.	0.051	.	0.246	0.033	.	.	0.05	0.058	.	0.280	0.20
CTIF UZ 52	16.90	81.18	.	.	0.014	0.32	0.084	0.04	0.002	0.068	0.11	0.08	0.12	1.06
CTIF UZ 53	16.67	82.60	.	0.01	.	0.255	0.025	.	<0.001	0.055	0.025	.	0.145	0.205
CTIF L 21	15.40	82.50	.	0.103	.	0.086	0.156	.	0.004	0.05	0.209	0.10	0.036	1.5
CTIF L 22	15.0	84.3	<0.02	<0.006	.	0.20	0.10	.	<0.01	.	0.10	.	<0.05	1.0
CTIF L 20	13.10	85.55	0.008	0.122	.	0.115	0.205	.	0.043	.	0.27	.	0.035	0.56

ALUMINUM BRASS

= class, where 1 = CRM and 2 = RM

#	Number	Al	Zn	Cu	As	Bi	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Units
2	CTIF LH 1-1	7.99	16.75	65.05	.	.	4.48	5.18	0.0944	0.079	0.022	0.081	0.205	(0.007)	60 mm Ø x 5 mm
2	CTIF LH 2	6.20	21.95	61.98	.	.	2.98	3.65	3.00	.	0.080	.	0.086	0.055	60 mm Ø x 5 mm
2	CTIF LH 6-1	6.09	18.98	63.18	.	.	(3.1)	4.54	3.19	.	0.25	.	0.20	0.257	60 mm Ø x 5 mm
1	BAM 388	4.972	4.81	89.27	.	.	0.0303	0.0512	0.00736	.	0.000969	.	.	0.857	40 mm Ø x 30 mm
2	CTIF LH 5-1	3.65	25.72	66.0	.	.	1.26	1.37	1.57	.	0.110	.	0.114	0.141	60 mm Ø x 5 mm
2	CTIF LH 7	3.16	(26.85)	63.40	.	.	(2.35)	2.96	0.70	.	0.327	.	0.055	0.227	60 mm Ø x 5 mm
2	C30.18	2.91	rem	64.36	<0.005	<0.003	<0.005	<0.005	<0.005	.	<0.01	<0.005	0.10	0.65	50 mm Ø x 10-12 mm
2	CURM 43.01	2.75	22.44	74.36	0.118	<0.002	0.008	0.064	0.121	.	<0.002	<0.001	0.063	0.116	50 mm Ø x 10-12 mm
2	CTIF LH 10	2.66	28.90	59.05	.	.	(1.0)	3.57	1.49	.	1.76	.	1.30	0.203	60 mm Ø x 5 mm
2	CURM 43.02	2.40	20.82	76.21	0.083	<0.001	0.128	0.035	0.068	.	0.064	<0.001	0.038	0.060	50 mm Ø x 10-12 mm
2	CTIF LH 13	2.00	31.8	55.75	.	.	(2.00)	3.14	3.22	.	0.67	.	0.21	1.19	60 mm Ø x 5 mm
2	C43.03	1.6	rem	79.7	<0.005	<0.005	0.07	<0.002	<0.005	.	0.10	<0.01	<0.005	<0.005	50 mm Ø x 10-12 mm
1	BAM 368 *	1.972	rem	77.049	0.0246	.	0.0193	0.0203	0.0258	0.00899	0.01313	(0.002)	.	0.0147	40 mm Ø x 30 mm
2	C30.21	1.44	rem	56.0	<0.005	.	<0.005	<0.005	<0.005	.	<0.005	<0.01	0.18	1.96	50 mm Ø x 10-12 mm
2	CTIF LH 12	1.13	33.15	62.75	.	.	(1.2)	0.125	0.505	.	0.21	.	(0.06)	0.83	60 mm Ø x 5 mm
2	CTIF LH 11	0.46	26.20	66.80	.	.	0.36	0.71	2.91	.	1.26	.	0.88	0.44	60 mm Ø x 5 mm

* BAM 368 also contains 62.1 ppm Mg

CRM ALUMINUM BRASS SET

available in SET/4 only

40 mm Ø x 35 mm

Number	Al	As	Bi	Cd	Cr	Cu	Fe	Mg	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN W01	1.33	0.056	0.0003	0.013	0.013	78.85	0.13	0.00060	0.014	0.0043	0.0023	0.15	0.0083	0.044	0.011	Rem
IMN W02	1.76	0.041	0.0014	0.032	0.0098	77.80	0.050	0.0066	0.16	0.031	0.0090	0.098	0.00098	0.013	0.056	Rem
IMN W03	2.15	0.015	0.0047	0.039	0.0027	77.58	0.029	0.0055	0.051	0.11	0.0062	0.054	0.0035	0.007	0.0071	Rem
IMN W04	2.50	0.030	0.0098	0.0063	0.00034	76.20	0.022	0.013	0.074	0.077	0.015	0.020	0.0058	0.001	0.13	Rem

CRM BISMUTH BRASS

cast and chill cast

analysis listed in mass % except * which is mg/kg

40-42 mm Ø x ~15-18 mm

Number	Bi	Zn	Cu	Al	As	B*	Cd*	Fe	Mn	Ni	P	Pb	S*	Sb	Se	Si	Sn
31X BIB3	4.05	32.46	62.48	0.0298	0.057	.	29	0.099	0.243	0.098	0.0175	0.149	(5)	0.0417	0.003	0.061	0.111
31X BIB1	1.948	36.67	59.93	0.0718	0.0282	.	82	0.113	0.0479	0.313	0.0637	0.211	(10)	0.0154	0.0064	0.099	0.488
31X BIB4	0.980	36.89	60.88	0.358	.	8	5	0.148	0.0039	0.175	0.0064	0.091	(7)	0.0144	0.0162	0.0018	0.400
31X BIB2	0.921	33.85	62.05	0.411	0.084	.	20	0.379	0.0451	0.466	0.0358	0.0617	(14)	0.119	0.0142	0.322	1.186

RM CARTRIDGE BRASS

cast typical analysis listed in mass %

50 mm Ø x 10 - 12 mm

Number	Zn	Cu	Al	As	Bi	Cd	Cr	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Sn	Si
CURM 48.01	32.6	66.98	<0.001	0.067	0.038	<0.0003	*	0.049	0.0008	<0.001	0.134	0.016	0.106	<0.001	0.047	<0.002	0.041
CURM 48.02	32.58	67.16	0.013	0.025	0.004	*	0.004	0.053	*	0.067	<0.001	0.012	0.084	0.007	0.037	0.035	0.010
CURM 48.05	31.0	68.69	<0.002	<0.001	.	<0.0003	*	0.066	*	0.016	0.117	0.007	<0.003	0.013	*	0.083	0.026
C48.03	Rem	70.4	0.003	0.04	0.006	.	0.001	0.01	0.003	0.04	0.02	<0.001	0.05	0.006	0.07	0.05	<0.001
C48.06	Rem	71.6	0.002	0.008	0.004	.	0.0006	0.01	0.001	0.006	0.11	0.002	0.02	0.006	0.006	0.02	0.006
CURM 48.04	26.99	72.68	<0.001	0.034	0.014	<0.0003	<0.002	0.008	0.0005	0.012	0.096	0.006	0.043	0.011	0.026	0.018	0.004

* For the above chart, * indicates a value of <0.0005

CRM CARTRIDGE BRASS SET

available in SET/5 only

remainder is Zinc

wrought 40 mm Ø x 25 mm

Number	Ag	Al	As	Be	Bi	Cd	Cu	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Te
IMN MH1	0.0029	0.0010	0.0670	0.0088	0.0037	0.0260	65.93	0.0170	0.0350	0.2600	0.0160	0.0065	0.0034	0.0004	0.0740	0.1400	0.0004
IMN MH2	0.0110	0.0190	0.0410	0.0015	0.0022	0.0180	68.25	0.0270	0.0110	0.2200	0.0055	0.0210	0.0055	0.0240	0.0540	0.0970	0.0015
IMN MH3	0.0065	0.0081	0.0160	0.0003	0.0011	0.0089	71.28	0.0810	0.0850	0.1000	0.0035	0.0780	0.0090	0.0130	0.0310	0.0240	0.0046
IMN MH4	.	0.0027	0.0011	0.0045	0.0006	0.0029	69.94	0.1300	0.0017	0.0520	0.0022	0.3300	0.0043	0.0170	0.0160	0.0110	0.0035
IMN MH5	0.0250	0.0140	0.0038	0.00004	.	0.0012	72.87	0.1900	0.0720	0.0072	0.0011	0.2000	0.0180	0.0035	0.0039	0.0021	0.0047

CRM CARTRIDGE BRASS SETS

available in SETs only, as grouped

40 mm Ø x ~28 mm

Number	Cd	Cr	Cu	Se	Zn	Zr
IMN MJ1	0.00355	0.0120	67.77	0.00062	Rem	.
IMN MJ2	0.00377	0.00440	66.40	0.00037	Rem	.
IMN MJ3	0.00165	0.00158	67.39	0.00035	Rem	.
IMN MJ4	0.00130	0.00374	68.06	0.0124	Rem	.
IMN MJ5	0.000360	0.00065	(67.82)	0.00288	Rem	.
IMN MJJ1	.	.	67.82	.	Rem	0.0454
IMN MJJ2	.	.	(68.03)	.	Rem	0.00017
IMN MJJ3	.	.	67.87	.	Rem	0.00070
IMN MJJ4	.	.	67.75	.	Rem	0.0074

CRM FREE CUTTING BRASS SET

available in SET/5 only

40 mm Ø x 25 mm

Number	Al	As	Bi	Cu	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN WN1	0.33	0.035	0.023	58.44	0.23	0.57	0.29	0.031	0.51	0.099	0.16	1.00	Rem
IMN WN2	0.24	0.011	0.035	60.38	0.29	0.73	0.19	0.051	1.58	0.10	0.22	0.68	Rem
IMN WN3	0.14	0.032	0.020	62.32	0.062	0.39	0.098	0.034	2.62	0.020	0.12	0.39	Rem
IMN WN4	0.047	0.021	0.0094	57.97	0.11	0.13	0.050	0.014	0.86	0.061	0.036	0.13	Rem
IMN WN5	(0.0004)	0.030	0.0028	64.36	0.0085	0.0020	0.0049	0.0051	3.78	0.0035	(0.0013)	0.019	Rem

CRM LEADED BRASS

= class, where 1 = CRM and 2 = RM

#	Number	Pb	Sn	Zn	Cu	Al	As	Bi	Co	Fe	Mn	Ni	P	Sb	Si
1	IARM 250A	7.2	2.46	9.7	80.2	(0.002)	.	0.02	(0.002)	0.17	<0.002	0.33	0.003	0.052	0.003
2	BS 836A-1	5.32	4.59	4.52	84.64	(0.001)	0.008	.	.	0.023	(0.002)	0.46	0.08	0.068	0.003
1	IARM 86C	5.03	4.37	5.38	84.6	0.002	<0.005	(0.01)	<0.005	0.24	0.002	0.27	0.003	0.143	0.003
1	33X RB1	5.02	2.137	7.95	83.25	0.0048	0.0030	0.0029	0.0558	0.928	0.0167	0.0539	0.020	0.432	0.063
1	33X RB2	3.85	3.19	9.14	82.67	0.0362	0.0211	0.101	0.0352	0.493	0.0028	0.255	0.0208	0.019	0.0116
1	BAM 375	2.90	0.2090	38.02	58.32	0.0270	0.0231	0.00686	0.01964	0.207	0.0222	0.1053	(0.00086)	0.0122	0.0211
2	BS 360B	2.77	0.15	35.7	(61.2)	(0.001)	0.002	.	(0.002)	0.117	0.0094	0.040	(0.002)	0.017	0.002
1	31X 7835-1	2.75	0.382	34.04	62.30	0.067	0.0161	0.0118	0.0154	0.135	.	0.136	0.0221	0.0207	0.029
1	31X 7835-7	2.29	0.137	7.50	88.87	0.0084	.	0.048	0.0120	0.030	.	0.943	0.080	0.0327	0.039
1	31X 7835-2	2.08	0.211	31.86	64.03	0.172	0.0225	0.0084	0.0279	0.094	.	1.35	0.0276	0.0240	0.0217
1	31X 7835-5	1.64	0.116	6.23	91.25	0.078	0.104	.	.	0.126	.	0.249	0.018	0.114	.
1	IARM 87B	1.58	0.78	36.1	60.9	0.20	0.007	0.003	0.007	0.29	0.006	0.095	0.008	0.014	0.004
1	31X 7835-6	1.498	0.080	38.05	59.67	0.546	0.0006	0.0026	0.0005	0.091	.	0.0173	<0.0005	0.0127	(0.001)
1	31X 7835-3	1.274	0.0912	35.34	62.10	0.384	0.098	0.0257	0.0053	0.299	.	0.282	0.042	0.104	0.022
2	BS 857B-1	1.22	1.14	34.91	61.3	0.35	(0.001)	.	.	0.30	0.003	0.61	0.004	(0.002)	0.004
1	31X 7835-4	1.049	0.070	30.36	67.13	0.525	0.142	0.0169	0.0027	0.0350	.	0.477	0.121	0.068	.

Number	Ag	B	Be	C	Cd	Cr	Mg	O	S	Se	Te	Units
IARM 250A	0.02	.	.	<0.005	.	<0.003	.	.	0.046	.	.	31 mm Ø x 2 or 18 mm
BS 836A-1	0.023	0.042	.	.	cont. cast 38 mm Ø x 12 mm
IARM 86C	(0.02)	.	.	0.003	0.035	.	.	31 mm Ø x 2 or 18 mm
33X RB1	0.0174	0.0013	0.0153	.	0.0044	.	.	chill cast 42 mm Ø x 17 mm
33X RB2	0.0029	0.0017	0.0008	.	0.078	.	.	chill cast 42 mm Ø x 17 mm
BAM 375	0.0166	.	.	.	0.00859	0.00538	wrought 40 mm Ø x 30 mm
BS 360B	0.006	.	(0.001)	(0.002)	.	(0.0001)	.	0.0007	(0.0005)	.	(0.002)	38 mm Ø x 12 mm
31X 7835-1	.	0.0011	.	.	0.0018	(0.003)	.	chill cast 42 mm Ø x 17 mm
31X 7835-7	0.0047	.	.	.	0.0075	.	.	chill cast 40 mm Ø x ~15 mm
31X 7835-2	.	(0.0016)	.	.	0.0026	0.003	.	chill cast 42 mm Ø x 18 mm
31X 7835-5	chill cast 42 mm Ø x 18 mm
IARM 87B	(0.01)	.	.	0.003	.	(0.002)	.	.	(0.001)	.	.	31 mm Ø x 2 or 18 mm
31X 7835-6	.	0.0005	.	.	0.0010	.	.	.	0.0017	0.0007	.	chill cast 42 mm Ø x 18 mm
31X 7835-3	.	0.0014	.	.	0.0030	0.0010	.	chill cast 40 mm Ø x 15 mm
BS 857B-1	(0.002)	cont. cast 38 mm Ø x 12 mm
31X 7835-4	.	0.0021	.	.	0.0088	chill cast 40 mm Ø x ~15 mm

CRM LEADED BRASS SET

available in SET/6 only

40 mm Ø x 30 mm

Number	Al	Bi	Cu	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN WG1	0.096	0.0013	60.99	0.0084	0.16	0.20	0.029	0.71	(0.062)	(0.0046)	0.29	Rem
IMN WG2	(0.00095)	0.016	56.99	0.42	(0.0024)	0.0051	.	2.66	(0.0024)	(0.021)	(0.0025)	Rem
IMN WG3	0.041	0.0057	58.20	0.31	0.037	0.029	0.013	2.29	0.018	(0.014)	0.091	Rem
IMN WG4	0.073	0.014	60.05	0.10	0.12	0.16	0.020	1.41	(0.042)	(0.016)	0.21	Rem
IMN WG5	0.058	0.0094	59.32	0.18	0.074	0.078	0.016	1.66	0.034	(0.022)	0.14	Rem
IMN WG6	0.020	0.023	60.67	0.18	0.21	0.29	0.044	3.70	(0.0078)	(0.019)	0.40	Rem

MANGANESE BRASS

= class, where 1 = CRM and 2 = RM chill cast analysis listed in mass % except * which is mg/kg CTIF: 60 mm Ø x 5 mm
31X: 40-42 mm Ø x 15-18 mm

#	Number	Mn	Zn	Cu	Al	Fe	Ni	Pb	Si	Sn	As	Co	P	Sb	Ag*	Bi*	Cd*	Cr*
1	31X MNB12	17.88	22.12	56.16	0.749	0.335	0.491	1.99	0.013	0.231	0.0022	0.0012	0.019	0.0056	.	21	12	38
1	31X MNB11	11.99	22.85	57.36	1.19	0.337	4.46	1.610	0.071	0.161	0.0010	0.0046	0.0186	0.0051	.	21	9	46
2	CTIF UZHR 9	5.90	27.70	60.20	3.85	2.20	<0.005	<0.005	0.01
1	31X MNB4	4.14	27.12	58.95	2.16	1.73	3.23	0.640	0.90	1.080	0.0068	0.057	0.0252	(0.006)	171	.	.	.
1	31X MNB3	2.77	24.10	68.20	0.98	1.306	0.208	0.458	1.36	0.549	0.0052	0.048	0.0170	0.0054	103	.	.	.
1	31X MNB2	2.23	32.19	63.02	0.268	0.66	0.118	1.02	0.233	0.319
1	31X MNB1	0.188	29.37	67.77	0.599	0.268	0.053	1.44	0.128	0.105
1	31X MNB5	0.175	37.11	55.14	3.24	0.898	1.32	0.157	0.528	1.228	0.0021	0.066	0.0399	(0.006)	195	.	.	116

CRM MANGANESE BRASS DISC AND ROD SETS

available in SETS ONLY, as grouped IMN MA: 10 mm Ø x 100 mm IMN WF: 44 mm Ø x 30 mm

Number	Al	As	Bi	Cu	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN MA1	1.51	0.085	0.0020	55.50	0.073	3.37	0.39	0.10	0.16	0.0061	0.071	1.04	Rem
IMN MA2	3.35	0.0081	0.0029	60.88	1.27	1.30	0.011	0.015	0.020	0.0019	0.042	0.41	Rem
IMN MA3	.	0.029	0.028	57.04	0.55	0.78	0.13	0.040	0.049	0.14	0.50	0.74	Rem
IMN MA4	0.33	.	.	57.40	0.20	2.75	0.69	0.15	.	0.20	0.27	0.015	Rem
IMN MA5	1.04	0.11	0.020	58.51	0.70	1.97	1.01	0.062	1.20	0.072	0.65	0.046	Rem
IMN MA6	2.15	0.013	0.0072	60.45	1.72	0.90	0.056	0.019	0.60	0.016	0.013	0.13	Rem
IMN WF1	.	.	0.00059	56.47	0.097	2.16	0.010	(0.0012)	0.010	0.00058	.	0.012	Rem
IMN WF2	.	.	0.00091	57.66	0.21	1.79	0.040	(0.0032)	0.040	0.0018	.	0.045	Rem
IMN WF3	.	.	0.0015	58.66	0.29	1.36	0.10	0.0075	0.070	0.0036	.	0.072	Rem
IMN WF4	.	.	0.0021	60.50	0.42	0.57	0.15	0.0095	0.10	0.0045	.	0.11	Rem
IMN WF5	.	.	0.0030	58.77	0.68	0.52	0.18	0.014	0.14	0.0061	.	0.16	Rem
IMN WF6	.	.	0.00095	59.78	0.05	0.98	0.074	0.0020	0.026	.	.	0.028	Rem

NAVAL BRASS

= class, where 1 = CRM and 2 = RM 31X NB: 42 mm Ø x 17-18 mm BS: 38 mm Ø x 12 mm CURM: 50 mm Ø x 10-12 mm IARM 74: 31 mm Ø x 2 or 18 mm

#	Number	Sn	Pb	Zn	Cu	Al	As	Bi	Fe	Mn	Ni	P	S	Sb	Si	Ag	B	Co
2	CURM 42.25	2.72	0.0023	39.20	57.78	0.021	0.118	<0.001	0.003	0.169	<0.001	0.050	0.005	<0.001	<0.001	.	.	.
2	CURM 42.24	2.25	0.91	33.75	62.45	0.067	0.065	0.054	0.066	0.065	0.025	0.226	0.012	0.060	0.093	.	.	.
2	C42.25	2.2	<0.01	rem	58.5	0.02	0.10	<0.002	<0.005	0.13	<0.005	0.06	0.001	<0.005	<0.002	.	.	.
1	31X NB 4	2.01	0.067	32.57	63.71	0.178	0.0062	0.104	0.235	0.0053	0.230	0.230	(0.0032)	0.450	0.203	.	0.0009	.
1	31X NB 3	1.67	0.197	24.64	72.45	0.094	0.074	0.093	0.113	0.0166	0.0299	0.150	(0.006)	0.265	0.145	.	0.0026	.
2	CURM 42.23	1.63	0.575	22.13	74.36	0.008	0.168	0.034	0.354	0.019	0.168	0.128	0.045	0.356	0.015	.	.	.
2	CURM 42.22	1.10	1.10	26.32	70.46	0.042	0.217	0.046	0.23	0.122	0.061	0.177	<0.001	0.173	0.042	.	.	.
1	31X NB 2	1.06	0.293	28.82	68.93	0.085	0.105	0.052	0.095	0.116	0.065	0.091	<0.002	0.115	0.096	.	.	.
1	IARM 74B	0.70	0.017	38.9	60.4	0.003	<0.01	.	0.011	<0.01	0.006	(0.008)	(0.003)	0.003	0.003	.	.	.
1	IARM 76C	0.66	1.6	37.2	60.4	(0.004)	(0.003)	.	0.013	(0.001)	0.003	0.003	(0.001)	(0.004)	(0.003)	(0.002)	.	.
2	BS 482A	0.65	0.50	38.8	60.0	(0.003)	<0.002	0.020	<0.002	(0.007)	<0.003	<0.002	0.0012	(0.002)
2	BS 464A	0.62	0.056	38.73	60.6	(0.001)	<0.002	0.013	0.0002	0.004	0.012	0.001	(0.001)	<0.01
2	CURM 42.21	0.60	0.259	31.61	66.78	0.003	<0.003	0.013	0.119	<0.001	0.120	0.087	0.034	0.25	0.15	.	.	.
2	BS 464	0.61	0.034	39.0	Rem.	<0.005	<0.005	0.08	<0.005	0.02	0.009	(0.001)	0.007	<0.005
1	IARM 75B	0.59	0.63	38.0	60.63	(0.005)	(0.004)	(0.001)	0.06	(0.003)	0.02	0.003	(0.001)	(0.004)	(0.003)	.	.	.
2	C42.21	0.54	0.23	rem	66.1	0.005	<0.005	0.012	0.06	<0.005	0.096	0.081	0.007	0.19	0.081	.	.	.
1	31X NB 1	0.535	0.504	29.73	68.35	(0.0004)	0.161	0.0065	0.037	0.051	0.520	0.0223	0.0024	0.0057	0.004	.	.	(0.0006)
1	IARM 74A	0.50	0.02	38.14	.	<0.01	.	.	0.01	<0.01	0.01	0.006	0.001	<0.01

CRM NAVAL BRASS SET

available in SET/5 only 40 mm Ø x 25 mm

Number	Al	Bi	Cu	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN WK1	0.11	0.014	59.97	0.28	0.13	0.28	0.030	0.17	0.024	0.30	0.11	Rem
IMN WK2	0.080	0.011	60.54	0.16	0.088	0.21	0.017	0.33	0.018	0.29	1.34	Rem
IMN WK3	0.045	0.0088	62.09	0.066	0.046	0.13	0.017	0.11	0.012	0.16	0.49	Rem
IMN WK4	0.013	0.0052	63.28	0.085	0.020	0.070	0.010	0.050	0.0056	0.082	1.04	Rem
IMN WK5	0.0042	0.0011	64.92	0.0092	0.0056	0.0055	0.0056	0.0062	0.0027	0.0064	0.47	Rem

CRM NICKEL AND PHOSPHOR BRASS

analysis listed in mass %

Number	Ni	P	Cu	Zn	Al	Cd	Cr	Fe	Mn	Pb	Sn	Units
31X B29	4.11	3.33	67.08	24.75	0.219	0.0144	0.062	0.144	0.0625	0.146	0.0328	40 mm Ø x ~15 mm
BAM 387	5.020	.	75.18	19.57	.	.	.	0.0617	0.0796	0.00108	0.00301	40 mm Ø x 30 mm

CRM NICKEL BRASS SETS

available in SETS ONLY, as grouped analysis listed in mass % except * which is mg/kg IMN WH, WM: 40 mm Ø x 25 mm IMN WP: 40 mm Ø x 30 mm

Number	Ni	Zn	Cu	Al	As	Bi	C*	Cd	Co	Fe	Mg	Mn	P	Pb	S	Sb	Si	Sn
IMN WP1	5.45	Rem	67.15	0.020	0.0012	0.00080	.	0.0019	.	0.020	.	0.0069	0.020	0.52	.	0.0010	(0.01)	0.0042
IMN WP2	7.79	Rem	65.08	0.0090	0.0049	0.0052	.	0.0052	.	0.12	.	0.040	0.0067	0.82	.	0.0052	(0.009)	0.11
IMN WP3	10.24	Rem	63.05	0.0020	0.011	0.012	.	0.011	.	0.20	.	0.15	0.0079	1.52	.	0.012	(0.03)	0.18
IMN WP4	12.38	Rem	60.91	0.039	0.015	0.016	.	0.016	.	0.31	.	0.35	0.011	(2)	.	0.015	(0.04)	0.26
IMN WP5	15.63	Rem	58.70	0.049	0.021	0.021	.	0.026	.	0.026	.	0.49	0.0027	(1.8)	.	0.028	(0.03)	0.33
IMN WP6	4.27	Rem	69.37	2.41
IMN WM1	5.03	25.35	69.06	0.083	0.00026	0.011	44	0.0046	0.021	0.011	0.0054	0.38	0.0018	0.018	0.017	0.00098	0.0026	0.0036
IMN WM2	6.66	24.18	68.41	0.050	0.0030	0.014	52	0.022	0.017	0.022	0.019	0.53	0.023	0.011	0.0058	0.013	0.0067	0.11
IMN WM3	6.09	23.57	69.85	0.033	0.0053	0.0055	58	0.0024	0.011	0.077	0.0042	0.19	0.0052	0.0073	0.0073	0.0043	0.037	0.098
IMN WM4	5.36	23.19	71.10	0.0080	0.0072	0.0029	72	0.0021	0.0099	0.13	0.0027	0.011	0.0057	0.0044	0.0058	0.0059	0.071	0.075
IMN WM5	4.68	25.90	68.99	0.0012	0.0089	0.0007	90	0.00077	0.0021	0.22	0.00056	0.0024	0.016	0.0020	0.0030	0.0068	0.094	0.035
IMN WH1	5.70	Rem	68.16	.	.	.	(46)	.	0.0061	0.0052	.	0.56	0.0029	.	(0.0055)	.	0.010	.
IMN WH2	6.34	Rem	69.14	.	.	.	(58)	.	0.017	0.038	.	0.36	0.0072	.	(0.0071)	.	0.038	.
IMN WH3	3.44	Rem	70.18	.	.	.	(70)	.	0.031	0.11	.	0.25	0.013	.	(0.011)	.	0.072	.
IMN WH4	4.14	Rem	71.15	.	.	.	(75)	.	0.048	0.13	.	0.11	0.015	.	(0.017)	.	0.12	.
IMN WH5	4.89	Rem	72.28	.	.	.	(87)	.	0.028	0.22	.	0.011	0.017	.	(0.021)	.	0.17	.

SILICON BRASS

= class, where 1 = CRM and 2 = RM

Number	Si	Zn	Cu	Al	Pb	Fe	Mn	Ni	P	Sb	Sn
1 31X WSB5	6.07	0.343	90.06	0.218	0.100	0.79	0.496	0.492	0.080	0.124	1.05
2 CTIF LS2	4.91	11.60	79.60	0.156	0.886	1.022	0.220	1.110	0.064	0.0103	0.338
1 31X WSB1	4.58	6.14	84.61	0.957	0.435	0.557	0.964	0.229	0.044	0.048	0.525
1 31X WSB4	4.40	5.61	86.09	0.290	0.204	0.592	1.45	0.228	0.042	0.0335	0.802
2 CTIF LS1	4.35	16.3	77.7	(0.02)	0.213	0.448	0.039	0.55	0.128	.	0.243
1 31X WSB7	4.25	7.58	72.74	3.87	0.025	1.95	3.39	3.03	0.188	0.636	1.93
1 31X WSB2	3.92	13.94	79.22	0.760	0.621	0.393	0.330	0.154	0.021	0.0202	0.402
1 37X 226	3.55	2.82	91.58	0.0020	(0.001)	1.51	0.577	0.0024	0.0022	.	0.0030
1 31X WSB3	3.44	11.96	81.14	0.509	0.397	0.22	1.06	0.371	0.033	0.028	0.607
2 CTIF LS3	3.3	19	76	0.43	0.58	0.10	0.15	0.11	0.011	0.107	0.15
1 IARM 151B	3.11	12.94	84.0	0.002	0.013	0.024	0.002	0.011	0.003	.	0.009
1 IARM 313 *	3.09	21.4	75.4	.	0.04	0.011	(0.001)	(0.004)	0.09	0.016	0.006
1 31X WSB6	2.48	0.881	94.74	0.059	0.95	0.032	0.248	0.117	(0.020)	0.007	0.056

Number	As	Bi	C	Cd	Co	Cr	Mg	S	Zr	Units
31X WSB5	0.0284	0.030	.	0.0047	0.057	0.0087	0.0012	0.0081	.	43 mm Ø x 20 mm
CTIF LS2	60 mm Ø x 5 mm
31X WSB1	0.063	0.0387	.	0.0115	0.210	0.184	0.0258	.	.	42 mm Ø x 17 mm
31X WSB4	0.0286	0.0318	.	0.0012	0.096	0.103	0.006	(0.002)	.	43 mm Ø x 20 mm
CTIF LS1	60 mm Ø x 5 mm
31X WSB7	0.103	0.190	.	0.0077	0.0118	0.0145	.	.	.	42 mm Ø x ~17 mm
31X WSB2	0.077	0.0102	.	0.0015	0.174	0.096	0.0098	(0.0011)	.	43 mm Ø x 20 mm
37X 226	.	.	0.006	.	.	0.0023	.	0.0005	(0.0002)	57 mm Ø x 17 mm
31X WSB3	0.053	0.0195	.	0.0028	0.129	0.0480	(0.004)	(0.0024)	.	43 mm Ø x 20 mm
CTIF LS3	60 mm Ø x 5 mm
IARM 151B	(0.003)	.	<0.001	.	31 mm Ø x 2 or 18 mm
IARM 313 *	(0.001)	.	(0.001)	.	31 mm Ø x 2 or 18 mm * Provisional Analysis
31X WSB6	0.0051	0.0056	.	0.0071	0.247	0.058	(0.001)	(0.002)	.	43 mm Ø x 20 mm

CRM SILICON BRASS SET

available in SET/7 only OES only, small holes bad for XRF

40 mm Ø x 28 mm

Number	Al	As	Bi	Cu	Fe	Mn	Ni	P	Pb	Sb	Si	Sn	Zn
IMN WB1	0.062	0.013	0.0076	78.41	0.049	0.69	0.032	0.00098	0.20	0.025	4.80	0.13	Rem
IMN WB2	0.072	0.043	0.0094	78.97	0.13	0.64	0.096	0.0084	0.42	0.055	3.86	0.0041	Rem
IMN WB3	0.035	0.026	0.0029	79.45	0.28	0.44	0.025	0.023	0.23	0.010	3.55	0.22	Rem
IMN WB4	0.083	0.020	0.0056	80.48	0.35	0.14	0.051	0.060	0.099	0.031	3.06	0.018	Rem
IMN WB5	0.018	0.0075	0.0023	80.88	0.46	0.050	0.019	0.083	0.012	0.0038	2.79	0.27	Rem
IMN WB6	0.0075	0.0043	0.0011	81.11	0.66	0.011	0.0068	0.12	0.0037	0.0025	1.99	0.049	Rem
IMN WB7	0.041	0.052	0.0084	77.69	0.033	0.88	0.068	0.017	0.098	0.031	3.95	0.39	Rem

CRM HIGH TENSILE BRASS

Number	Cu	Zn	Al	Fe	Mn	Si	As	C	Ni	P	Pb	S	Sb	Sn	Units
31X HT31	66.67	18.19	6.70	2.90	5.27	0.041	0.0006	0.006	0.196	0.0032	0.020	(0.0003)	(0.0011)	0.0149	50 mm Ø x 18 mm
31X HT37	60.33	34.69	0.0004	0.0344	2.88	1.38	0.0011	0.003	0.0105	0.003	0.623	<0.0005	0.0007	0.0116	40 mm Ø x 18 mm
31X HT38	58.77	36.66	0.960	0.0530	2.60	0.869	0.0008	0.003	0.0242	0.0024	0.051	(0.001)	(0.0006)	0.039	50 mm Ø x 18 mm

RM BRONZE MUSHROOMS

chill cast typical analysis 60 mm Ø x 5 mm

Number	Sn	Zn	Cu	Al	As	Fe	Mn	Ni	P	Pb	S	Sb	Si
CTIF B 1	15.15	0.92	82.90	0.072	.	0.088	.	0.063	0.037	0.202	0.030	0.444	0.055
CTIF B 2	13.55	0.11	85.90	(0.002)	.	0.041	.	(0.003)	0.17	0.0206	0.048	(<0.002)	0.17
CTIF B 3	12.8	2.2	80.2	0.1	.	0.2	0.20	1.5	0.45	1.6	0.04	0.2	0.07
CTIF B 4	11.10	1.34	83.75	.	.	0.021	.	0.57	0.52	2.53	0.019	0.10	0.015
CTIF B 14	10.75	0.15	87.00	<0.01	0.04	0.11	0.02	0.30	0.64	0.50	0.02	0.08	0.075
CTIF B 13	10.05	1.09	86.35	0.016	0.065	0.250	0.046	0.50	0.210	0.99	0.070	0.243	0.085
CTIF B 5	9.90	0.42	85.95	0.039	.	0.18	0.082	2.28	0.041	0.48	0.067	0.47	0.049
CTIF B 30	9.80	1.05	77.45	0.063	.	0.115	0.150	0.97	0.063	10.0	0.048	0.22	0.066
CTIF B 12	9.57	0.61	85.65	0.120	0.111	0.162	0.235	2.63	0.525	0.201	0.013	0.117	0.050
CTIF B 11	8.04	2.10	84.75	.	.	0.170	.	2.0	0.057	1.93	0.09	0.70	0.14
CTIF B 31	7.65	0.79	78.65	(0.031)	.	(0.015)	.	0.489	.	11.79	0.028	0.475	(0.047)
CTIF B 23	7.18	1.46	83.45	0.020	.	(0.040)	.	0.086	0.070	7.20	0.019	0.384	0.025
CTIF B 10	6.95	2.75	83.65	0.205	0.0075	0.165	(0.0045)	1.01	0.014	4.07	0.050	1.14	.
CTIF B 30	6.35	3.77	83.35	0.040	.	0.165	.	0.51	0.072	5.10	0.115	0.520	0.055
CTIF B 22	5.92	1.17	74.80	0.075	0.0056	0.11	.	1.49	0.039	16.10	0.027	0.13	0.070
CTIF B 21	5.13	6.17	83.05	0.13	.	0.285	.	1.21	(0.004)	3.79	0.047	0.18	.
CTIF B 22	3.5	4.0	83.0	.	.	<0.10	.	2.5	.	6.0	0.03	0.05	<0.1
CTIF UN 3S	0.215	1.62	92.65	0.11	.	0.30	0.073	3.45	.	0.20	.	.	1.24
Number	Sn	Zn	Cu	Al	As	Fe	Mn	Ni	P	Pb	S	Sb	Si

CRM BRONZE SETS

AVAILABLE IN SETS ONLY, as grouped

IMN: 40 mm Ø x ~30 mm

VS: 40 mm x 40 mm x 25 mm

Number	Al	Be	Bi	Cu	Fe	Ni	P	Pb	S	Sb	Se	Si	Sn	Zn
IMN BM1	0.596	.	0.538	Rem	1.08	0.518	0.00443	0.0241	0.0630	0.00431	0.0125	1.40	0.00551	0.351
IMN BM2	0.188	.	0.201	Rem	0.507	1.27	0.00973	0.0163	0.191	0.549	0.0956	0.985	0.0162	0.0565
IMN BM3	0.109	.	0.104	Rem	0.00679	2.18	0.0941	0.00784	0.480	0.110	0.454	0.565	0.104	0.0198
IMN BM4	0.00840	.	0.0110	Rem	0.102	2.93	0.213	0.00231	0.0201	0.200	0.200	0.398	0.196	0.119
IMN BM5	0.00276	.	0.00658	Rem	0.0107	3.67	0.578	0.00134	0.0104	0.0152	(0.00554)	0.105	0.539	0.281
VS 3152-85	(0.19)	1.71	.	(97.5)	0.036	0.092	.	0.0028	.	.	.	0.086	0.18	(0.035)
VS 3153-85	(0.11)	1.92	.	(97.2)	0.084	0.19	.	0.0045	.	.	.	0.14	0.104	0.049
VS 3154-85	(0.064)	2.44	.	(96.7)	0.28	0.23	.	0.0023	.	.	.	0.12	0.033	0.041
VS 3155-85	(0.027)	2.64	.	(96.2)	0.079	0.35	.	0.0060	.	.	.	0.23	0.083	0.13
VS 3156-85	(0.054)	3.2	.	(95.4)	0.14	(0.081)	.	0.011	.	.	.	0.30	0.061	0.23

CRM BRONZE

Number	Cu	Fe	Ni	P	Pb	Sn	Zn	method	Units
SRM 1115	87.9	0.13	0.074	0.005	0.013	0.10	11.7	wrought	31 mm Ø x 19 mm
SRM C1115	87.9	0.13	0.074	0.005	0.013	0.10	11.7	cast	31 mm x 31 mm x 19 mm
SRM 1116	90.3	0.046	0.048	0.008	0.042	0.04	9.4	wrought	31 mm Ø x 19 mm
SRM 1117	93.0	0.014	0.020	0.002	0.069	0.02	6.8	wrought	31 mm Ø x 19 mm
SRM C1117	93.0	0.014	0.020	0.002	0.069	0.02	6.8	cast	31 mm x 31 mm x 19 mm

ALUMINUM BRONZE

= class, where 1 = CRM and 2 = RM

#	Number	Al	Cu	As	Cr	Fe	Mg	Mn	Ni	P	Pb	Si	Sn	Zn
1	32X ALB 9	13.86	79.24	0.0275	(0.064)	3.13	0.205	0.090	1.21	(0.054)	0.377	0.282	0.061	1.17
1	32X ALB 10	11.25	74.28	0.017	0.0103	4.23	0.0029	1.73	7.58	0.040	0.107	0.169	0.202	0.315
1	32X ALB 3	11.20	80.31	0.0114	0.0060	3.97	0.0117	0.297	3.47	0.022	0.105	0.173	0.110	0.311
1	IARM 94B	10.8	80.6	<0.01	0.017	3.99	.	0.071	4.31	0.011	0.004	0.028	(0.003)	0.14
2	C52.53	10.7	Rem	.	0.19	5.5	0.07	0.38	4.1	.	0.04	0.10	0.07	0.11
2	CURM 52.52	10.69	79.26	.	0.004	6.02	0.007	0.145	3.56	.	0.074	0.011	0.044	0.094
2	BS 955C	10.68	80.6	(<0.002)	.	4.04	.	0.06	4.31	0.012	0.003	0.025	0.003	0.15
1	IARM 204A	10.55	83.3	(<0.01)	0.008	3.87	.	0.052	1.95	0.007	0.004	0.034	0.005	0.22
2	BS 955 MOD	10.37	(74.9)	(<0.003)	.	5.46	.	1.61	6.28	(<0.002)	0.035	0.054	0.096	1.05
1	IARM 93B	10.33	85.4	<0.01	(0.007)	3.87	.	0.024	0.088	(0.002)	0.012	0.024	0.009	0.17
2	BS 955B	10.30	81.5	(0.002)	.	3.79	.	0.12	4.11	0.017	0.051	0.05	0.024	0.052
2	BS 954C	10.21	83.9	(0.006)	.	3.9	.	0.29	1.38	0.011	0.050	0.07	0.08	0.09
2	BS 954B	10.20	83.9	(0.005)	.	3.90	.	0.27	1.38	0.012	0.047	0.07	0.07	0.10
2	BS 954A	10.17	85.64	(0.006)	.	3.50	.	0.10	0.20	0.012	0.016	0.029	0.033	0.30
1	IARM 80C *	10.1	80.6	0.005	0.013	3.87	.	0.58	4.71	0.0036	(0.003)	0.076	0.003	0.097
2	BS 630A	10.05	81.0	(0.002)	.	3.73	.	0.11	4.81	<0.01	0.0069	0.037	0.019	0.17
2	C52.51	10.0	Rem	.	<0.01	4.3	<0.01	<0.01	5.1	.	<0.01	<0.01	<0.01	0.02
1	32X CA 1	9.79	80.03	.	0.0049	4.63	0.0003	0.296	4.94	0.003	0.007	0.090	0.0180	0.162
1	32X ALB 2	9.60	80.70	0.0066	0.0031	4.05	0.0035	0.056	4.53	0.048	0.266	0.295	0.103	0.247
1	32X CA 7	9.37	88.06	.	0.0028	2.09	0.0004	0.151	0.234	.	(0.004)	0.017	0.0172	0.006
2	C52.55	9.3	Rem	.	0.05	4.9	0.13	1.1	4.6	.	0.14	0.03	0.03	0.10
2	BS CC954	9.28	84.0	0.003	.	3.61	.	0.353	1.12	0.013	0.13	0.092	0.061	1.30
2	BS 623	9.24	(88.1)	<0.01	.	2.25	.	0.16	0.10	0.013	<0.01	0.046	0.01	0.05
1	IARM 79C	9.20	87.6	0.003	(0.002)	2.28	.	0.20	0.55	0.006	<0.005	0.033	0.010	0.014
1	32X CA23	9.19	81.05	.	0.0018	3.63	0.0003	1.298	4.71	0.0011	(0.0026)	0.026	0.0164	0.031
1	IARM 79B	9.19	88.4	.	(0.003)	2.13	.	0.16	0.075	0.005	(0.003)	0.019	0.017	0.013
2	BS 623A	9.12	88.13	(0.006)	.	2.19	.	0.273	0.146	<0.002	0.001	0.014	0.002	0.008
1	32X CA31	8.95	82.24	.	0.0026	4.06	0.0008	0.336	4.28	(0.003)	(0.0024)	0.036	0.0037	0.041
2	C52.56	8.9	Rem	.	0.14	4.6	0.09	0.74	5.6	.	0.17	0.15	0.11	0.28
1	IARM 235A	8.9	81.2	<0.005	0.01	4.07	.	1.17	4.44	0.012	0.012	0.061	0.018	0.083
1	32X ALB11B	8.85	80.38	.	.	3.99	0.072	1.290	4.44	0.0249	0.0316	0.015	0.0062	0.508
1	32X ALB 1	8.83	81.85	0.0083	0.0052	3.11	0.0092	0.057	5.74	0.0145	0.207	0.106	0.0314	0.0228
1	32X ALB11A	8.80	80.58	.	.	3.81	0.075	1.13	4.33	0.045	0.118	0.069	0.0289	0.576
2	CURM 51.14	8.42	88.57	0.44	.	0.72	.	0.55	0.219	0.012	0.003	0.286	0.113	0.656
1	32X ALB 6	8.05	81.98	0.012	0.0097	2.53	0.0019	0.904	5.31	0.0101	0.096	0.295	0.147	0.685
1	32X ALB 4	7.87	79.61	0.0130	0.022	3.55	0.153	1.028	7.03	0.036	0.120	0.252	0.085	0.264
2	CURM 52.54	7.85	81.59	<0.005	.	3.31	<0.005	1.20	5.40	.	0.086	0.022	0.135	0.39
2	CURM 51.13	7.30	88.79	0.215	.	1.81	.	0.898	0.057	0.022	0.104	0.174	0.270	0.335
2	C51.13	6.93	Rem	0.21	.	2.05	.	0.77	0.053	0.021	0.12	0.16	0.19	0.30
1	32X ALB 5	6.91	84.61	0.064	0.0056	2.22	0.0176	1.21	4.14	0.048	0.093	0.086	0.062	0.487
1	IARM 81B	6.70	91.2	0.058	0.002	0.047	.	0.012	0.003	0.004	0.006	1.84	0.008	0.176
1	32X ALB 8	6.60	76.29	0.155	0.046	5.58	0.0152	1.67	6.50	0.218	0.359	0.736	0.699	1.051
2	CURM 51.12	6.36	88.29	0.111	.	2.87	.	1.33	0.112	<0.001	0.219	0.005	0.196	0.45
1	32X CA12	6.14	90.48	.	0.0008	0.657	0.0005	0.0290	0.088	.	(0.0017)	2.57	0.0157	0.0405
2	C51.12	6.06	Rem	0.11	.	2.90	.	1.25	0.11	<0.005	0.25	<0.01	0.18	0.42
2	CURM 51.11	5.27	93.95	<0.001	.	0.060	.	<0.001	0.012	0.035	0.33	0.159	0.027	0.111
2	C51.11	5.0	Rem	<0.01	.	0.07	.	<0.005	0.15	0.03	0.31	0.11	0.025	0.07
1	32X ALB 7	4.01	84.40	0.056	0.061	4.82	0.0039	0.383	4.96	0.057	0.029	0.399	0.30	0.527

Number	Al	Cu	As	Cr	Fe	Mg	Mn	Ni	P	Pb	Si	Sn	Zn
Number	Ag	Be	Bi	C	Co	S	Sb	Se	Units				
32X ALB 9	0.042	.	.	(0.006)	0.0259	42 mm	Ø x 18 mm		
32X ALB 10	.	.	.	(0.0022)	42 mm	Ø x 18 mm		
32X ALB 3	42 mm	Ø x 18 mm		
IARM 94B	0.017	.	.	(0.006)	0.011	0.002	(0.011)	.	.	31 mm	Ø x 2 or 18 mm		
C52.53	50 mm	Ø x 10 - 12 mm		
CURM 52.52	50 mm	Ø x 10 - 12 mm		
BS 955C	0.014	(0.002)	.	.	38 mm	Ø x 12 mm		
IARM 204A	0.009	.	.	0.006	0.008	(0.002)	(0.01)	.	.	31 mm	Ø x 2 or 18 mm		
BS 955 MOD	(0.003)	.	.	40 mm	Ø x 17 mm		
IARM 93B	(0.004)	.	.	0.007	0.006	0.002	(0.012)	.	.	31 mm	Ø x 2 or 18 mm		
BS 955B	(0.009)	0.002	(0.002)	.	.	38 mm	Ø x 12 mm		
BS 954C	.	.	.	(0.004)	.	(0.0005)	<0.003	.	.	38 mm	Ø x 12 mm		
BS 954B	.	.	.	(0.005)	.	(0.0005)	(0.001)	.	.	38 mm	Ø x 12 mm		
BS 954A	.	.	.	0.004	.	<0.0001	0.001	.	.	38 mm	Ø x 12 mm		
IARM 80C *	.	.	.	0.008	0.008	(0.001)	(0.01)	.	.	31 mm	Ø x 2 or 18 mm		* Provisional Analysis
BS 630A	.	.	.	0.005	.	(0.001)	<0.001	.	.	38 mm	Ø x 12 mm		
C52.51	50 mm	Ø x 10 - 12 mm		
32X CA 1	0.0012	.	.	(0.007)	42 mm	Ø x 18 mm		
32X ALB 2	42 mm	Ø x 18 mm		
32X CA 7	0.0009	.	.	0.0028	0.0003	42 mm	Ø x 18 mm		
C52.55	50 mm	Ø x 10 - 12 mm		
BS CC954	.	.	.	(0.007)	.	(0.002)	0.004	.	.	32 mm	Ø x 17 mm		
BS 623	.	.	.	(0.002)	.	(0.001)	<0.01	.	.	37 mm	Ø x 12 mm		
IARM 79C	<0.005	.	.	0.003	<0.005	<0.001	<0.005	.	.	31 mm	Ø x 2 or 18 mm		
32X CA23	0.0008	.	.	(0.0050)	50 mm	Ø x 18 mm		
IARM 79B	0.002	.	.	0.002	(0.002)	(0.001)	.	.	.	31 mm	Ø x 2 or 18 mm		
BS 623A	.	.	.	(0.002)	.	(0.0005)	<0.002	.	.	38 mm	Ø x 12 mm		
32X CA31	0.0008	.	.	0.006	0.0029	42 mm	Ø x 18 mm		
C52.56	50 mm	Ø x 10 - 12 mm		
IARM 235A	<0.005	.	.	0.009	0.01	0.002	(0.004)	.	.	31 mm	Ø x 2 or 18 mm		
32X ALB11B	.	0.064	0.082	.	0.0180	.	0.203	0.007	.	40 mm	Ø x 15 mm		
32X ALB 1	42 mm	Ø x 18 mm		
32X ALB11A	.	0.0194	0.120	.	0.089	.	0.093	0.006	.	40 mm	Ø x -15 mm		
CURM 51.14	50 mm	Ø x 10 - 12 mm		
32X ALB 6	.	.	.	(0.0025)	42 mm	Ø x 18 mm		
32X ALB 4	42 mm	Ø x 18 mm		
CURM 52.54	50 mm	Ø x 10 - 12 mm		
CURM 51.13	50 mm	Ø x 10 - 12 mm		
C51.13									

CRM ALUMINUM BRONZE SETS

available in SETS only, as grouped analysis listed in mass % except * which is mg/kg 40 mm Ø x ~25 mm

Number	Al	As	Bi	Cd	Co	Cr*	Fe	Mg*	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn
IMN BF1	10.90	0.061	0.00042	.	.	.	(6.2)	.	0.0059	2.49	(0.012)	0.23	.	(0.002)	0.26	0.011	0.57
IMN BF2	9.96	0.050	0.0025	.	.	.	(5.4)	.	0.12	3.54	0.053	0.15	.	(0.013)	0.25	0.081	0.40
IMN BF3	9.58	0.038	0.0039	.	.	.	4.50	.	0.28	4.43	0.098	0.111	.	0.028	0.20	0.17	0.27
IMN BF4	9.12	0.022	0.0057	.	.	.	3.25	.	0.39	5.24	0.13	0.059	.	0.037	0.097	0.25	0.10
IMN BF5	8.35	0.0039	0.010	.	.	.	2.44	.	0.50	6.03	0.16	0.014	.	0.048	0.028	0.35	0.018
IMN B01	3.16	0.00033	0.00030	0.00035	.	32.7	0.0158	.	0.0167	0.00517	(0.0004)	0.00384	.	0.00035	(0.00471)	2.54	7.10
IMN B02	4.03	0.00199	0.00197	0.00182	.	3.7	0.00569	.	0.00102	0.00204	0.00227	(0.00214)	.	0.00226	0.00979	1.83	6.26
IMN B03	4.67	0.00662	0.00660	0.00570	.	54.8	0.0752	.	0.00884	0.0683	0.00550	0.0537	.	0.00568	0.0552	1.17	5.07
IMN B04	6.15	0.0115	0.0107	0.00881	.	91	0.137	.	0.00612	0.111	0.0100	0.102	.	0.0104	0.0951	0.704	4.28
IMN B05	7.02	0.0161	0.0152	0.0134	.	145	0.218	.	0.0772	0.0355	0.0155	0.0299	.	0.0152	0.0135	0.117	3.08
IMN B11	2.88	0.011	0.013	0.016	0.027	.	0.011	58	0.60	6.97	0.0022	0.0025	0.021	0.0012	(0.11)	(0.11)	0.020
IMN B12	2.46	0.0089	0.0095	0.011	0.020	.	0.038	98	0.42	6.47	0.011	0.0043	0.014	0.0030	(0.091)	(0.080)	0.038
IMN B13	1.97	0.0072	0.0071	0.0076	0.014	.	0.12	65	0.21	5.87	0.014	0.0081	0.0082	0.0056	(0.047)	(0.049)	0.22
IMN B14	1.50	0.0031	0.0042	0.0048	0.0076	.	0.20	35	0.013	5.49	0.013	0.010	0.0049	0.0088	(0.015)	(0.014)	0.36
IMN B15	1.09	0.0018	0.0013	0.00075	0.0024	.	0.28	17	0.0030	5.00	0.019	0.017	0.0023	0.010	(0.0071)	(0.0034)	0.51

RM ALUMINUM BRONZE MUSHROOMS

chill cast typical analysis 60 mm Ø x 5 mm

Number	Al	Cu	Fe	Mn	Ni	Pb	Si	Sn	Zn	Bi	Cd	Cr	Mg
CTIF CA 36	12.60	77.25	2.93	0.131	6.33	0.0154	0.113	0.201	0.244	0.058	.	0.041	0.130
CTIF 2158-W	11.95	85.00	2.53	0.26	0.10	<0.005	0.015	<0.01	<0.01
CTIF 4065-P	11.85	81.20	3.40	0.075	3.18	0.03	0.034	0.18	0.03
CTIF CA 35	11.4	75.6	6.1	1.6	3.80	0.10	0.25	0.30	0.55
CTIF 2154-V	11.25	85.00	3.05	0.12	0.41	<0.005	0.015	<0.01	<0.01
CTIF CA 13	11.20	82.45	3.82	1.22	0.50	0.0230	0.11	(0.01)	0.65
CTIF CA 3	10.9	86.5	0.80	0.06	0.80	0.15	0.08	0.20	0.30
CTIF CA 21	10.82	81.9	3.45	0.30	3.09	0.05	0.07	0.07	0.100	.	0.0095	.	.
CTIF CA 22	10.45	80.50	2.51	0.745	4.54	0.0243	0.32	0.30	0.605
CTIF 3011-G	10.35	84.80	1.98	0.165	2.00	0.10	0.16	0.125	0.25
CTIF CA 27	10.25	81.1	2.81	1.195	3.88	0.11	0.127	0.054	0.428	.	0.012	.	.
CTIF CA 10	10.15	80.65	4.55	0.333	3.39	0.16	0.46	0.16	0.067
CTIF 3299-J	10.10	87.60	0.38	1.12	0.21	0.110	0.136	0.106	0.19
CTIF 3297-Y	10.00	87.45	1.88	0.03	.	0.11	0.15	0.10	0.27
CTIF 4149-G	9.84	84.95	2.00	0.21	1.96	0.15	0.18	0.34	0.37
CTIF 2152-S	9.78	85.05	3.99	0.42	0.68	<0.005	0.015	.	<0.01
CTIF 2151-R	9.43	84.75	4.48	0.73	0.56	<0.005	0.015	<0.01	<0.01
CTIF 3296-L	9.40	88.55	0.07	0.37	0.41	0.30	0.20	0.06	0.62
CTIF CA 31	9.15	76.5	3.18	3.27	7.51	0.020	0.064	0.063	0.145	.	.	.	0.02
CTIF CA 26	9.10	81.25	4.36	0.188	4.87	0.058	0.035	0.005	0.038	.	0.034	.	.
CTIF 3300-M	8.73	89.5	0.45	0.165	0.205	0.205	0.415	0.205	0.085
CTIF 3301-Z	8.10	87.30	4.00	0.26	0.125	0.032	0.057	0.028	0.06
CTIF 2794-H	8.0	90.3	0.82	<0.01	0.69	<0.01	0.048	0.105	<0.01
CTIF CA 20	8.00	87.15	0.79	1.85	1.18	0.18	0.17	0.19	0.41	.	0.05	.	.
CTIF CA 12	8.0	84.1	2.77	3.09	1.385	0.047	0.058	0.036	0.45
CTIF CA 25	7.97	79.12	6.10	0.51	5.74	0.03	0.084	0.177	0.252
CTIF CA 30	7.55	81.6	5.2	2.05	3.10	0.142	0.15	0.099	0.066
CTIF 3018-F	7.25	81.90	4.45	1.57	4.50	0.02	0.085	0.06	0.06
CTIF 3610-Q	7.10	82.32	3.98	0.045	5.40	0.23	0.065	0.25	0.51	.	0.090	.	.
Number	Al	Cu	Fe	Mn	Ni	Pb	Si	Sn	Zn	Bi	Cd	Cr	Mg

CRM BISMUTH BRONZE

31 mm Ø x 2 or 18 mm

Number	Ag	Al	As	Bi	Co	Cr	Cu	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn
IARM 211A	0.005	0.002	(0.01)	5.0	(0.001)	(0.002)	88.4	0.004	(0.003)	0.003	0.19	0.014	0.002	0.057	0.003	6.23	0.006

MANGANESE BRONZE

= class, where 1 = CRM and 2 = RM BS CC: 32 Ø x 20 mm other BS: 38 mm Ø x 12 mm IARM: 31 Ø x 2 or 18 mm

#	Number	Mn	Al	Fe	Sn	Zn	Cu	As	C	Ni	P	Pb	S	Sb	Si
1	IARM 88B	2.93	5.66	2.12	0.020	25.1	63.9	.	0.003	0.065	0.011	0.066	<0.001	<0.005	0.09
2	BS CC865	0.32	0.70	1.06	0.71	37.92	58.69	0.010	(0.002)	0.28	0.004	0.46	(0.002)	0.01	0.011
2	BS 675A	0.32	<0.002	1.12	0.8	39.1	58.5	0.003	(0.0007)	0.019	0.010	0.074	(0.0005)	0.0011	(0.005)
1	IARM 83A	0.22	<0.01	0.99	0.57	39.81	.	.	(0.007)	0.01	0.005	0.058	0.002	0.008	<0.01
1	IARM 83B	0.13	0.002	0.97	0.85	39.3	58.7	.	0.003	0.010	0.004	0.017	(0.001)	(0.004)	(0.003)
2	BS 675	0.11	<0.01	0.73	0.92	39.7	Rem.	<0.005	(0.0004)	<0.01	<0.01	<0.01	(0.0013)	<0.01	<0.02

RM NICKEL BRONZE - XRF ONLY

Number	Ni	Cu	Fe	Pb	Sn	Zn	Units
37X HK7	30.7	59.3	1.72	5.32	2.30	0.38	40 mm Ø x 10 mm

PHOSPHOR BRONZE

= class, where 1 = CRM and 2 = RM

#	Number	P	Sn	Zn	Cu	Mn	Ni	Pb	Al	As	Fe	Mg	S	Sb	Si
2	CURM 54.03	0.954	7.30	0.003	91.74	<0.005	0.0019	0.003	<0.001	0.006	0.005	<0.0003	<0.001	0.0007	<0.002
1	32X PB 11	0.799	3.75	1.43	90.55	0.111	0.768	0.900	(0.001)	0.199	0.75	0.0022	0.007	0.502	0.099
2	CURM 54.05	0.501	11.36	0.554	84.78	0.078	1.28	1.14	0.055	0.063	0.051	0.0021	0.063	0.111	0.006
1	32X PB 23	0.319	7.56	0.0020	92.04	<0.005	0.0033	0.0042	<0.005	0.0011	<0.005	.	0.0015	0.0025	0.0016
2	CURM 54.04	0.250	9.47	1.09	86.54	0.419	0.536	0.79	0.074	0.106	0.316	0.0009	0.046	0.33	0.065
1	32X PB 20	0.196	4.55	0.007	95.22	<0.005	0.0090	0.0045	<0.005	0.0011	0.0013	.	0.0030	0.0012	0.0046
1	IARM 78B	0.19	4.73	3.55	87.7	(0.002)	0.077	3.87	(0.002)	<0.003	0.02	.	0.010	0.01	<0.002
1	32X PB 4	0.178	9.75	0.107	88.4	1.17	0.081	0.114	(0.0005)	<0.01	0.014	.	.	(0.0032)	0.099
1	32X PB 12	0.172	5.25	0.546	93.29	0.0110	0.221	0.102	0.0067	0.087	0.032	0.0033	0.0127	0.160	0.0099
1	IARM 77B	0.148	4.66	0.007	95.2	(0.002)	0.002	0.016	(0.001)	(0.001)	0.002	.	0.002	0.005	(0.003)
1	32X PB 13	0.128	7.09	0.240	91.88	0.0300	0.111	0.104	0.039	0.081	0.057	0.0144	0.015	0.117	0.073
2	BS 510A	0.11	4.6	0.21	95.10	<0.002	0.020	0.016	<0.002	0.0008	0.005	.	0.008	(0.003)	<0.003
2	CURM 54.02	0.107	5.53	0.410	92.87	0.101	0.109	0.663	0.020	0.023	0.102	0.0020	0.030	0.026	0.012
1	32X PB15	0.0873	2.21	0.76	96.07	0.125	0.212	0.174	0.045	0.123	0.116	0.0275	.	0.026	0.043
2	CURM 54.01	0.053	3.17	0.346	95.42	0.158	0.348	0.307	0.040	0.044	0.028	0.008	0.023	0.070	0.039
2	C54.01	0.05	3.2	0.31	rem	0.13	0.26	0.29	0.009	0.04	0.01	<0.001	0.03	0.08	0.006
2	BS 544A	0.021	4.42	3.42	(88.4)	<0.002	0.16	4.16	(0.0005)	0.011	0.092	.	0.038	0.040	<0.002
1	32X PB 14	(0.008)	9.00	0.038	90.26	(0.0002)	0.144	0.048	(0.0009)	0.0331	0.0056	0.0003	0.065	0.055	(0.0025)
1	32X PB 10	0.003	11.87	0.0494	87.85	0.0005	0.054	0.067	(<0.001)	0.0138	0.014	0.004	0.0162	0.0201	(0.0036)

#	Number	P	Sn	Zn	Cu	Mn	Ni	Pb	Al	As	Fe	Mg	S	Sb	Si
---	--------	---	----	----	----	----	----	----	----	----	----	----	---	----	----

Number	Bi	C	Co	Se	Units
CURM 54.03	50 mm Ø x 10-12 mm
32X PB 11	0.0065	.	0.091	.	40 mm Ø x 17 mm
CURM 54.05	50 mm Ø x 10-12 mm
32X PB 23	.	0.004	.	.	49 mm Ø x 17 mm
CURM 54.04	50 mm Ø x 10-12 mm
32X PB 20	38 mm Ø x 17 mm
IARM 78B	31 mm Ø x 2 or 18 mm
32X PB 4	40 mm Ø x 15 mm
32X PB 12	0.057	.	0.0142	.	40 mm Ø x ~17 mm
IARM 77B	.	0.003	.	.	31 mm Ø x 2 or 18 mm
32X PB 13	0.0137	.	0.0052	.	40 mm Ø x ~17 mm
BS 510A	.	(0.0006)	.	.	38 mm Ø x 12 mm
CURM 54.02	50 mm Ø x 10-12 mm
32X PB15	.	.	0.0509	.	40 mm Ø x ~15 mm
CURM 54.01	50 mm Ø x 10-12 mm
C54.01	50 mm Ø x 10-12 mm
BS 544A	.	(0.003)	.	.	38 mm Ø x 12 mm
32X PB 14	0.224	.	0.0013	.	40 mm Ø x 17 mm
32X PB 10	0.0128	.	.	0.0058	40 mm Ø x ~17 mm

Number	Bi	C	Co	Se	Units
--------	----	---	----	----	-------

SILICON BRONZE

= class, where 1 = CRM and 2 = RM

BS: 38 mm Ø x 12 mm

IARM: 31 Ø x 2 or 18 mm

#	Number	Si	Cu	Al	As	C	Cr	Fe	Mn	Ni	P	Pb	S	Sb	Sn	Zn
1	IARM 82B	3.22	95.3	0.002	.	.	0.004	0.080	1.04	0.011	0.004	0.011	0.003	.	0.017	0.38
2	BS 655A	3.14	95.74	(0.002)	<0.002	(0.0006)	.	0.075	0.91	0.008	(0.004)	0.008	(0.0006)	<0.002	0.07	0.02

CRM SILICON BRONZE SET

available in SET/7 ONLY, as grouped

40 mm Ø x 25 mm

Number	Al	As	Bi	Cu	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn
IMN BH1	0.027	0.0047	0.018	Rem	1.67	0.0065	0.25	0.96	0.0047	0.74	0.012	0.066	4.77	0.044	2.03
IMN BH2	0.079	0.015	0.014	Rem	1.28	0.0066	0.54	0.74	0.023	0.57	0.0092	0.042	4.14	0.21	2.99
IMN BH3	0.14	0.022	0.0091	Rem	0.96	0.0075	1.00	0.53	0.039	0.40	0.0062	0.026	3.07	0.37	3.84
IMN BH4	0.22	0.054	0.006	Rem	0.55	0.0057	1.46	0.28	0.059	0.24	0.0064	0.016	2.29	0.55	4.91
IMN BH5	0.29	0.071	0.0019	Rem	0.093	0.0024	1.80	0.047	0.073	0.015	0.0055	0.0054	1.45	0.69	5.58
IMN BH6	0.32	0.078	0.018	Rem	0.35	0.01	0.80	0.39	0.078	0.017	0.016	0.056	1.51	0.32	6.27

CRM LEADED, TIN, AND LEADED TIN BRONZE DISC AND ROD SETS

available in SETS ONLY, as grouped

IMN BB: 10 mm Ø x 100 mm
IMN BL: 40 mm Ø x 27 mmIMN BI, WL: 40 mm Ø x 25 mm
VS: 40 mm x 40 mm x 25 mm

Number	Al	As	Bi	C	Cd	Co	Cu	Fe	Mg	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn
IMN BL1	0.11	0.058	0.024	.	0.060	.	Rem	0.38	0.051	0.062	0.25	0.49	0.25	(0.0081)	0.053	0.059	2.58	0.68
IMN BL2	0.15	0.039	0.014	.	0.040	.	Rem	0.21	0.11	0.055	0.37	0.29	0.14	(0.0063)	0.039	0.031	4.04	0.40
IMN BL3	0.019	0.025	0.0099	.	0.022	.	Rem	0.10	.	0.026	0.13	0.084	0.065	.	0.021	0.015	6.12	0.15
IMN BL4	.	0.0089	0.0058	.	0.0092	.	Rem	0.014	.	0.0092	0.015	0.010	0.013	(0.022)	0.0095	0.011	8.38	0.017
IMN BL5	0.00052	0.00057	0.0015	.	0.0015	.	Rem	0.0061	0.0030	0.0011	0.0074	0.0042	0.0069	0.031	0.0039	(0.0038)	11.05	0.0078
VS 2807-83	(0.0029)	.	(0.025)	.	.	.	(78.7)	0.062	.	.	0.81	0.55	12.5	.	0.80	(0.045)	6.3	1.17
VS 2808-83	(0.0034)	.	(0.031)	.	.	.	(79.7)	0.100	.	.	0.50	0.30	10.6	.	0.50	(0.025)	7.3	0.71
VS 2809-83	(0.0049)	.	(0.039)	.	.	.	(81.1)	0.209	.	.	0.31	0.20	9.0	.	0.34	(0.011)	8.3	0.38
VS 2810-83	(0.0084)	.	(0.041)	.	.	.	(81.9)	0.35	.	.	0.21	0.088	7.3	.	0.27	(0.0017)	9.4	0.26
VS 2811-83	(0.021)	.	(0.062)	.	.	.	(83.0)	0.60	.	.	0.110	(0.059)	5.4	.	(0.12)	(0.0021)	10.5	(0.14)
IMN BB1	0.019	0.086	0.032	.	.	.	84.82	0.33	.	0.081	0.061	0.055	1.55	.	0.60	0.037	8.10	3.90
IMN BB2	0.032	0.12	0.024	.	.	.	84.09	0.28	.	0.12	0.097	0.085	2.64	.	0.49	0.055	7.11	4.70
IMN BB3	0.0021	0.0079	0.0021	.	.	.	80.88	0.037	.	0.0012	2.42	(0.014)	6.73	.	0.052	0.0044	3.36	6.23
IMN BB4	0.0062	0.029	0.011	.	.	.	81.32	0.086	.	0.020	1.20	0.030	6.14	.	0.21	0.018	2.58	8.11
IMN BB5	0.015	0.051	0.018	.	.	.	82.25	0.14	.	0.054	0.49	0.037	5.18	.	0.31	0.028	4.11	7.21
IMN BB6	0.040	0.16	0.041	.	.	.	83.54	0.31	.	0.15	0.23	0.12	3.52	.	0.62	0.083	5.47	5.40
IMN BB7	0.011	0.016	0.0054	.	.	.	82.24	0.095	.	0.011	1.73	0.016	7.31	.	0.098	0.012	4.92	3.26
IMN BI1	0.15	0.14	0.12	.	.	.	Rem	0.42	.	0.26	2.41	0.70	6.97	(0.011)	0.58	0.23	3.19	3.55
IMN BI2	0.077	0.11	0.070	.	.	.	Rem	0.31	.	0.15	1.46	0.59	5.39	(0.0055)	0.43	0.13	4.18	5.73
IMN BI3	0.034	0.052	0.028	.	.	.	Rem	0.17	.	0.082	0.29	0.32	4.52	(0.003)	0.24	0.075	5.01	7.16
IMN BI4	0.0020	0.010	0.0030	.	.	.	Rem	0.083	.	0.025	0.088	0.029	3.82	(0.002)	0.075	0.014	7.69	10.22
IMN WL1	0.082	0.0010	0.0093	0.0050	0.0017	0.0010	95.54	0.072	0.00036	0.0041	0.44	0.012	0.013	0.020	.	0.057	0.22	3.52
IMN WL2	0.057	0.0078	0.0073	0.0082	0.0023	0.0065	97.49	0.13	0.00097	0.0038	0.32	0.016	0.011	0.0070	0.0050	0.046	0.32	1.56
IMN WL3	0.0034	0.020	0.0050	0.010	0.010	0.0096	96.51	0.20	0.0016	0.38	0.22	0.021	0.0083	0.0088	0.0085	0.0037	0.37	2.21
IMN WL4	.	0.0034	0.0026	0.0032	0.0068	0.013	96.41	0.012	.	.	0.019	.	0.0066	0.0050	.	0.0019	0.55	2.97
IMN WL5	0.0014	0.0011	0.0011	.	0.0038	0.019	97.62	0.0025	.	0.00073	0.0014	.	0.0030	0.0019	0.0006	0.0009	0.73	1.61
IMN WL6	0.10	0.024	0.012	0.016	0.025	0.019	95.76	0.31	0.015	0.14	0.091	0.032	0.016	0.017	0.011	0.13	0.80	2.48

RM COPPER ALLOY XRF SET

Part Number: BS CU-22 Set of 19 samples, each 30 - 45 mm Ø x 7 mm discs

CDA	Number	Cu	Al	Fe	Mn	Ni	Pb	Si	Sn	Zn	As	C	P	S	Sb	Be	Co
110	BS 110A	99.9	0.002	0.003	<0.0003	0.002	0.003	0.001	0.002	(0.001)	(0.001)	0.0018	0.001	0.0008	0.0004	.	.
172	BS 172Be-1	97.68	(0.02)	0.052	0.001	0.039	(0.002)	0.055	0.033	0.007	(0.001)	(0.001)	0.003	.	.	1.89	0.206
314	BS 314A	89.75	0.002	0.019	0.001	0.009	1.47	(0.006)	0.0019	8.7	<0.003	0.002	<0.003	0.003	<0.002	.	.
360	BS 360A	61.42	<0.001	0.151	0.0007	0.058	2.51	<0.005	0.13	35.63	0.002	(0.0032)	0.001	(0.0003)	0.008	.	.
464	BS 464A	60.6	(0.001)	0.013	0.0002	0.004	0.056	<0.01	0.62	38.73	<0.002	(0.0006)	0.012	0.001	(0.001)	.	.
482	BS 482A	60.0	(0.003)	0.020	<0.002	(0.007)	0.50	(0.002)	0.65	38.8	<0.002	(0.0015)	<0.003	<0.002	0.0012	.	.
510	BS 510A	96.10	<0.002	0.005	<0.002	0.020	0.016	<0.003	4.6	0.21	0.0008	(0.0006)	0.11	0.008	(0.003)	.	.
544	BS 544A	88.4	(0.0005)	0.092	<0.002	0.16	4.16	<0.002	4.42	3.42	0.011	0.003	0.021	0.038	0.040	.	.
623	BS 623A	88.13	9.12	2.19	0.273	0.146	0.001	0.014	0.002	0.008	(0.006)	(0.002)	<0.002	<0.0005	<0.002	.	.
630	BS 630A	81.0	10.05	3.73	0.11	4.81	0.0069	0.037	0.019	0.17	(0.002)	0.005	<0.01	(0.001)	<0.001	.	.
642	BS 642A	91.0	6.70	0.17	0.005	0.025	0.001	1.80	0.018	0.011	<0.002	0.001	0.001	<0.001	<0.002	.	.
655	BS 655A	95.74	(0.002)	0.075	0.91	0.008	0.008	3.14	0.07	0.02	<0.002	(0.0006)	(0.004)	(0.0003)	<0.002	.	.
675	BS 675A	58.5	<0.002	1.12	0.32	0.019	0.074	(0.005)	0.80	39.1	0.003	(0.0007)	0.010	(0.0005)	0.0011	.	.
706	BS 706A	87.60	(0.002)	1.30	0.66	10.18	0.008	<0.005	0.011	0.13	<0.0005	0.004	0.006	0.012	0.0006	.	.
715	BS 715A	69.0	(0.01)	0.61	0.82	30.22	(0.007)	0.10	0.008	0.10	(0.0014)	0.03	0.006	0.001	(0.003)	.	.
863	BS 863A	64.1	5.21	2.41	3.00	0.29	0.022	0.034	0.013	24.8	0.010	0.003	(0.007)	<0.0005	0.003	.	.
903	BS 903B	86.7	(0.001)	0.049	0.0004	0.50	0.10	0.002	7.9	4.39	0.003	(0.0004)	0.073	0.006	0.003	.	.
932	BS 932A	82.9	<0.01	0.068	<0.002	0.12	7.09	<0.01	6.26	3.35	0.014	(0.006)	0.005	(0.05)	0.097	.	.
954	BS 954A	85.64	10.17	3.50	0.10	0.20	0.016	0.029	0.033	0.30	(0.006)	0.004	0.012	<0.0001	0.001	.	.

CDA	Number	Cu	Al	Fe	Mn	Ni	Pb	Si	Sn	Zn	As	C	P	S	Sb	Be	Co
-----	--------	----	----	----	----	----	----	----	----	----	----	---	---	---	----	----	----

ALLOY	NUMBER	ALLOY	NUMBER	ALLOY	NUMBER
110	IARM 70B	675	BS 675A	954	BS 954B
122	BAM 366	675	IARM 83A	954	BS 954C
122	CURM 09.04	675	IARM 83B	954	BS CC954
122.2	CURM 09.03	687	BAM 368	954	IARM 93B
125	CURM 09.01	693	IARM 313A	954 MOD	IARM 204A
125	CURM 09.02	697	CTIF L3	955	BS 955B
145	BS 14500	702.6	37X 218	955	BS 955C
145	IARM 278A	706	BAM 367	955	IARM 94B
162	36X CCD1	706	BS 706A	955 MOD	BS 955 MOD
162	36X CCD2	706	BS 706B	955 MOD	CTIF CA10
162	36X CCD3	706	CTIF CuNi 10	955.1 MOD	CTIF CA22
170	SRM C1122	706	IARM 84B	955.2	C52.53
172	BS 172Be-1	710	36X CN3	956	32X CA12
172	CTIF 4872	713	BAM 389	958	IARM 235A
172	IARM 71B	715	36X CN5	958.2	32X CA1
175	36X CBC2	715	BS 715A	964	IARM 236A
175	BS 17500	715	IARM 85B	997.5	31X MNB12
175.1	36X CBC5	715	IARM 85C	Coinage Alloy	36X CN21
180	36X 274	715	SRM 1276a	Coinage Alloy	36X CN23
181.5	36X CCZ	762	34X NS2	Envirobrass 2-1	IARM 226A
182	36X CCR1	767	C65.28	Envirobrass 2-2	IARM 227A
182	IARM 279A	812	39X 17869	Envirobrass 2-3	IARM 228A
210	31X B24	815	IARM 158B	Federalloy I-836	IARM 265A
210	31X B9	815	IARM 158C	Federalloy I-844	IARM 264A
240	31X B6	836	33X GM5	Federalloy I-848A	IARM 263A
240	C30.07	836	BS 836A-1	Federalloy III-932	IARM 266A
260	C48.06	836	IARM 86C	NARloy-A	IARM 159A
260	CURM 48.04	838	33X GM8	NARloy-Z	IARM 160A
260 MOD	31X B4	838.1	33X RB1	Red Brass	33X RB2
261.3	C48.03	844	IARM 250A	Sebiloy 3	31X BIB2
268	31X B28	855	31X B2	Spinodal Alloy	36X SP1
268	31X TB4	855	31X TB2	Spinodal Alloy	36X SP2
270	31X B3	855	31X TB3		
272	C30.04	855	C38.01		
274	C38.06	855	C38.02		
280	C30.03	855	C38.03		
280	C30.12	855	C38.04		
314	BS 314B	855	C38.05		
314	IARM 72B	857	BS 857B-1		
316	31X 7835-7	857	IARM 87B		
360	BS 360B	862	CTIF LH7		
370	31X B18	863	IARM 88B		
371	C30.22	865	BS CC865		
377	31X B19	874	31X WSB2		
464	BS 464	875	31X WSB3		
464	BS 464A	875	IARM 151B		
464	IARM 74A	893.2 Magnolia B	IARM 211A		
464	IARM 74B	902	BAM 377		
482	BS 482A	903	BS 903B		
482	IARM 75B	905	BS 905A-1		
485	IARM 76C	905	BS CC905		
510	32X PB20	907	32X PB10		
510	BS 510A	910 MOD	CTIF B1		
510	IARM 77B	922	BS 922B-3		
521	32X PB23	922	IARM 90B		
544	BS 544A	924 MOD	33X GM7		
544	IARM 78B	925	CURM 54.05		
615.5	36X CN22	927	32X LB11		
622	CTIF 2154-V	927.1	32X SN1		
623	32X CA7	931 MOD	C71.34		
623	BS 623A	932	BS 932E		
623	IARM 79B	932	IARM 91D		
623	IARM 79C	932 MOD	CTIF B23		
624	32X ALB3	936	CTIF B31		
624	C52.51	937	BS 937		
624	CTIF 3011-G	937	BS 937B-1		
624	CTIF CA21	937	BS CC937		
630	32X CA23	937	CURM 50.02		
630	BS 630A	937 MOD	32X LB3		
630	IARM 80C	938	BS 938-1		
632	32X CA31	941	IARM 184A		
642	IARM 81B	944 MOD	32X LB10		
655	BS 655A	945 MOD	CTIF B32		
655	IARM 82B	947	IARM 267A		
673	31X HT37	952.2	CTIF 2152-S		
674	31X HT38	953	CTIF CA3		
675	BS 675	954	BS 954A		

Please use the Adobe Acrobat "search" function to find the complete chemistry of these samples listed within this catalog.

The best efforts have been made in the construction of this chart. Some samples do not perfectly fit the alloy specifications, but are considered acceptable for the purposes of calibration and type standardization.

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
197.1	Ni<0.10	rem			0.30-1.20	<0.05	<0.05	0.10-0.40	<0.05				<0.02	<0.20				<0.05		0.01-0.20		
197.2	Ni<0.10	rem			0.05-0.40	<0.05	<0.10	0.07-0.15	<0.05				<0.20	<0.20						0.02-0.06		
197.5		rem			0.35-1.20	<0.05	<0.05	0.05-0.40	<0.05				0.05-0.40	<0.20						0.05-0.20		
198		rem			0.02-1.20	<0.05	<0.05	0.01-0.10	<0.05				0.10-1.00	0.30-1.50						0.01-0.20		
198.1		rem			1.5-3.0			<0.10						1.0-5.0					<0.10	<0.10	2.9-3.4	<0.10
199	>99.50													rem								
205		97.0-98.0			<0.05				<0.02					rem								
210		94.0-96.0			<0.05				<0.03					rem								
220		89.0-91.0			<0.05				<0.05					rem								
226		86.0-89.0			<0.05				<0.05					rem								
230		84.0-86.0			<0.05				<0.05					rem								
230.3		81.5-85.5			<0.05				<0.05			0.20-0.40		rem								
234		81.0-84.0			<0.05				<0.05					rem								
240		78.5-81.5			<0.05				<0.05					rem								
240.8		78.0-82.0		<0.10	<0.05				<0.20					rem								
250		74.0-76.0			<0.05				<0.05					rem								
256		71.0-73.0			<0.05				<0.05					rem								
260		68.5-71.5			<0.05				<0.07					rem								
261		68.5-71.5			<0.05			0.02-0.05	<0.05					rem								
261.3		68.5-71.5			<0.05				<0.05					rem	0.02-0.08							
262		67.0-70.0			<0.05				<0.07					rem								
263.8		68.0-72.0		<0.10	<0.05				<0.30					rem								
268		64.0-68.5			<0.05				<0.15					rem								
270		63.0-68.5			<0.07				<0.10					rem								
272		62.0-65.0			<0.07				<0.10					rem								
274		61.0-64.0			<0.05				<0.10					rem								
280		59.0-63.0			<0.07				<0.30					rem								
282		58.0-61.0		<0.005	<0.05			0.12-0.22	<0.03				<0.05	rem								
285.8		49.0-52.0		<0.10	<0.10				<0.50					rem								
298		49.0-52.0		<0.10	<0.10				<0.50					rem								
310		89.0-91.0			<0.10				0.30-0.70					rem								
312		87.5-90.5			<0.10		<0.25		0.7-1.2					rem								
314		87.5-90.5			<0.10		<0.7		1.3-2.5					rem								
316		87.5-90.5			<0.10		0.7-1.2	0.04-0.10	1.3-2.5					rem								
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
320		83.5-86.5			<0.10		<0.25		1.5-2.2					rem								
325		72.0-74.5			<0.10				2.5-3.0					rem								
325.1		69.0-72.0			<0.07				0.30-0.70					rem	0.02-0.06							
330		65.0-68.0			<0.06				0.25-0.70					rem								
331		65.0-68.0			<0.06				0.8-1.5					rem								
332		65.0-68.0			<0.07				1.5-2.5					rem								
335		62.0-65.0			<0.15				0.25-0.70					rem								
335.3		62.5-66.5			<0.10				0.30-0.80					rem	0.02-0.06							
340		62.0-65.0			<0.15				0.8-1.5					rem								
342		62.0-65.0			<0.15				1.5-2.5					rem								
344		62.0-66.0			<0.10				0.50-1.00					rem								
345		62.0-65.0			<0.15				1.5-2.5					rem								
347		62.5-64.5			<0.10				1.0-1.8					rem								
348		61.5-63.5			<0.10				0.40-0.80					rem								
349		61.0-64.0			<0.10				0.10-0.50					rem								
350		60.0-63.0			<0.15				0.8-2.0					rem								
353		60.0-63.0			<0.15				1.5-2.5					rem								
353.3		60.5-64.0			<0.10				1.5-3.5					rem	0.02-0.25							
353.4		60.0-63.0			0.10-0.30				1.5-2.5					rem								
356		60.0-63.0			<0.15				2.0-3.0					rem								
360		60.0-63.0			<0.35				2.5-3.7					rem								
362		60.0-63.0			<0.15				3.5-4.5					rem								
365		58.0-61.0			<0.15				0.25-0.70				<0.25	rem								
366		58.0-61.0			<0.15				0.25-0.70				<0.25	rem	0.02-0.06							
367		58.0-61.0			<0.15				0.24-0.70		0.02-0.10			rem								
368		58.0-61.0			<0.15			0.02-0.10	0.25-0.70				<0.25	rem								
370		59.0-62.0			<0.15				0.8-1.5				<0.25	rem								
371		58.0-62.0			<0.15				0.6-1.2					rem								
377		58.0-61.0			<0.30				1.5-2.5					rem								
377.1		56.5-60.0			<0.30				1.0-2.5					rem								
378		56.0-59.0			<0.30				1.5-2.5					rem								
380		55.0-60.0		<0.50	<0.35				1.5-2.5				<0.30	rem								
380.1		0.10-0.60			<0.30				1.5-3.0					rem								
385		55.0-59.0			<0.35				2.5-3.5					rem								
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr	
385.1		56.0-60.0							2.5-4.5					rem									
385.9		<0.35			<0.35				2.0-3.5					rem									
386		<0.35			<0.35				2.5-3.5		<0.02			rem									
404		<0.05			<0.05				<0.05				0.35-0.70	2.0-3.0									
405		<0.05			<0.05				<0.05				0.7-1.3	rem									
408		<0.05			<0.05				<0.05				1.8-2.2	rem									
408.1		0.08-0.12			0.08-0.12				<0.05				1.8-2.2	rem									
408.2		>94.00			>94.00				<0.05				1.0-2.5	0.20-2.50									
408.5		0.05-0.20			0.05-0.20				<0.05				2.6-4.0	rem									
408.6		0.01-0.05			0.01-0.05				<0.05				1.7-2.3	rem									
409		<0.05			<0.05				<0.05				0.50-0.80	rem									
410		<0.05			<0.05				<0.05				2.0-2.8	rem									
411		<0.05			<0.05				<0.10				0.30-0.70	rem									
411.2		0.05-0.20			0.05-0.20				<0.10				0.30-0.70	rem									
413		<0.05			<0.05				<0.10				0.7-1.3	rem									
415		<0.05			<0.05				<0.10				1.5-2.2	rem									
419		<0.05			<0.05				<0.10				4.8-5.5	rem									
420		<0.05			<0.05				<0.10				1.5-2.0	rem									
421		<0.05			<0.05				<0.05				2.2-3.0	rem									
422		<0.05			<0.05				<0.05				0.8-1.4	rem									
422.2		0.05-0.20			0.05-0.20				<0.05				0.7-1.4	rem									
425		<0.05			<0.05				<0.05				1.5-3.0	rem									
425.2		0.05-0.20			0.05-0.20				<0.05				1.5-3.0	rem									
426		0.05-0.20			0.05-0.20				<0.05				2.5-4.0	rem									
430	Ni = Ni+Co	<0.05			<0.05				<0.10				1.7-2.7	rem									
432		<0.05			<0.05				<0.05				0.40-0.60	rem									
434		<0.05			<0.05				<0.05				0.40-1.00	rem									
435		<0.05			<0.05				<0.10				0.6-1.2	rem									
436		<0.05			<0.05				<0.10				0.20-0.50	rem									
438		<0.05			<0.05				<0.05				1.0-1.5	rem									
442.5		<0.20			<0.20				<0.07				0.50-1.50	rem									
443		<0.06			<0.06				<0.07				0.8-1.2	rem									
444		<0.06			<0.06				<0.07				0.8-1.2	rem									
445		<0.06			<0.06				<0.07				0.8-1.2	rem									
454.5		0.20-0.40			0.20-0.40				<0.10				0.10-0.30	rem									
462		<0.10			<0.10				<0.20				0.50-1.00	rem									
462.1		<0.03			<0.03				<0.05				<1.00	rem									
464		<0.10			<0.10				<0.20				0.50-1.00	rem									
464.2		<0.10			<0.10				<0.20				1.0-1.4	rem									
465		<0.10			<0.10				<0.20				0.50-1.00	rem									
466		<0.10			<0.10				<0.20				0.50-1.00	rem									
467		<0.10			<0.10				<0.20				0.50-1.00	rem									
470		<0.01			<0.01				<0.05				0.25-1.00	rem									
472		<0.10			<0.10				<0.50				3.0-4.0	rem									
476		<0.05			<0.05				1.8-2.2				1.8-2.2	rem									
479.4	Ni = Ni+Co	0.10-1.00			0.10-1.00				1.0-2.0				1.2-2.0	rem									
482		<0.10			<0.10				0.40-1.00				0.50-1.00	rem									
485		<0.10			<0.10				1.3-2.2				0.50-1.00	rem									
485.1		<0.10			<0.10				1.0-2.5				0.7-1.5	rem									
486		<0.10			<0.10				1.0-2.5				0.8-1.5	rem									
490.8		<0.10			<0.10				<0.50				3.0-4.0	rem									
501		<0.05			<0.05				<0.05				0.50-0.80	rem									
502		<0.10			<0.10				<0.05				1.0-1.5	rem									
505		<0.10			<0.10				<0.05				1.0-1.7	rem									
505.1		<0.10			<0.10				<0.05				1.0-1.5	0.10-0.25									
505.8		0.05-0.20			0.05-0.20				<0.05				1.0-1.7	<0.30									
505.9		>97.00			>97.00				<0.02				0.5-1.5	<0.50									
507		<0.10			<0.10				<0.05				1.5-2.0	rem									
507.05		>96.50			>96.50				<0.02				1.5-2.0	<0.50									
507.1		<0.10			<0.10				<0.02				1.7-2.3	rem									
507.15		0.05-0.15			0.05-0.15				<0.02				1.7-2.3	rem									
507.25		0.05-0.20			0.05-0.20				<0.02				1.5-2.5	1.5-3.0									
507.8		0.05-0.20			0.05-0.20				<0.05				1.7-2.3	<0.30									
508		<0.10			<0.10				<0.05				2.6-3.4	rem									
509		<0.10			<0.10				<0.05				2.5-3.8	<0.30									
510		<0.10			<0.10				<0.05				4.2-5.8	<0.30									
510.8		0.05-0.20			0.05-0.20				<0.05				4.8-5.8	<0.30									
511		<0.10			<0.10				<0.05				3.5-4.9	<0.30									
511.8		0.05-0.20			0.05-0.20				<0.05				3.5-4.9	<0.30									
511.9		0.05-0.15			0.05-0.15				<0.02				3.0-6.5	rem									
Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr	

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr	
518		rem		<0.01	<0.10			0.10-0.35	<0.02				4.0-6.0	<0.30									
519		rem			0.05-0.20			0.03-0.35	<0.05				5.0-7.0	<0.30									
521		rem			<0.10		0.05-0.20	0.03-0.35	<0.05				5.0-7.0	<0.30									
521.8		rem			0.05-0.20		0.05-0.20	0.02-0.10	<0.05				7.0-9.0	<0.30									
524		rem			<0.10			0.03-0.35	<0.05				9.0-11.0	<0.20									
524.8	Cu+Mn+P+Sn >99.5	rem			0.05-0.20		0.05-0.20	0.02-0.10	<0.05				9.0-11.0	<0.20									
526		rem			<0.10	1.0-2.0		0.03-0.35	<0.05				2.2-3.3	<0.20									
529		rem			<0.10	1.0-2.0		0.03-0.35	<0.05				7.0-9.0	<0.20									
532		rem			<0.10			0.03-0.35	2.5-4.0				4.0-5.5	<0.20									
534		rem			<0.10			0.03-0.35	0.8-1.2				3.5-5.8	<0.30									
544		rem			<0.10			0.01-0.50	3.5-4.5				1.5-4.5	<0.30									
546		rem			<0.10			0.01-0.50	3.5-4.5				1.5-4.5	<0.30									
548	Cu+P+Fe+Sn+Zn >99.5				<0.10			0.03-0.35	4.0-6.0				4.0-6.0	<0.30									
551.8	Cu+P >99.85	rem						4.8-5.2															
551.81	Cu+P >99.85	rem	1.80-2.20					7.0-7.5															
552.8		rem	4.80-5.20					6.8-7.2															
552.81		rem	4.80-5.20					5.8-6.2															
552.82		rem	4.80-5.20					6.5-7.0															
552.83		rem	5.80-6.20					7.0-7.5															
552.84		rem	14.5-15.5					4.8-5.2															
552.85		rem	17.2-18.0					6.0-6.7															
566		rem	29-31		<0.50																		
606		rem		4.0-7.0																			
607		rem		2.3-2.9					<0.01				1.7-2.0										
608		rem		5.0-6.5	<0.10				<0.10					0.20-0.35									
610		rem		6.0-8.5	<0.50				<0.02					<0.10									
613		rem		6.0-7.5	2.0-3.0	<0.20	<0.15	<0.015	<0.02				0.20-0.50	<0.10									
614		rem		6.0-8.0	1.5-3.5	<1.00	1.8-2.2	<0.015	<0.01					<0.20									
615	Cu = Ag+Cu	rem		7.7-8.3					<0.05														
615.5	Cu = Ag+Cu	rem		5.5-6.5	<0.20		1.5-2.5		<0.05					<0.80									
618	Cu = Ag+Cu	rem		8.5-11.0	0.50-1.50				<0.02					<0.10									
619	Cu = Ag+Cu	rem		8.5-11.0	3.0-4.5				<0.02					<0.80									
622	Cu = Ag+Cu	rem		11.0-32.0	2.0-4.2				<0.02					<0.10									
623	Cu = Ag+Cu	rem		8.5-10.0	2.0-4.0	<0.50	<1.0		<0.02					<0.25									
624	Cu = Ag+Cu	rem		10.0-11.5	2.0-4.5	<0.30								<0.25									
625	Cu = Ag+Cu	rem		12.5-13.5	3.5-5.0	<2.00			<0.02					<0.04									
625.8	Cu = Ag+Cu	rem		12.0-13.0	3.0-5.0				<0.02					<0.04									
625.81	Cu = Ag+Cu	rem		13.0-14.0	3.0-5.0				<0.02					<0.02									
625.82	Cu = Ag+Cu	rem		14.0-15.0	3.0-5.0				<0.02					<0.02									
627.3	Cu = Ag+Cu	rem		8.5-11.0	4.0-6.0	<0.50	4.0-6.0		<0.05					<0.40									<0.05
630	Cu = Ag+Cu	rem		9.0-11.0	2.0-4.0	<1.50	4.0-5.5							<0.20									
630.1	Cu = Ag+Cu	rem		9.7-10.9	2.0-3.5	<1.50	4.5-5.5							<0.30									
630.2	Cu = Ag+Cu	rem		10.5-11.5	4.0-5.5	<1.50	4.2-6.0		<0.03					<0.30									
632	Cu = Ag+Cu	rem		8.7-9.5	3.5-4.3	1.2-2.0	4.0-4.8		<0.02					<0.15									<0.20
632.3	Cu = Ag+Cu	75.9-84.5		8.5-9.5	3.0-5.0	<3.50	4.0-5.5		<0.02					<0.10									
632.8	Cu = Ag+Cu	rem		8.5-9.5	3.0-5.0	0.6-3.5	4.0-5.5		<0.02					<0.10									
633	Cu = Ag+Cu	rem		5.0-7.5	2.0-6.0	11.0-13.0	1.0-2.5		<0.02					<1.50									
633.8	Cu = Ag+Cu	rem		7.0-8.5	2.0-4.0	11.0-14.0	1.5-3.0		<0.02					<0.10									
634	Cu = Ag+Cu	rem		2.6-3.2	<0.15		<0.15		<0.05					<0.15									
636	Cu = Ag+Cu	rem		3.0-4.0	<0.15	<0.10	<0.15		<0.05					<0.10									
638	Cu = Ag+Cu	rem		2.5-3.1	<0.20	<0.10	<0.20		<0.05					<0.80									
641.1	Cu = Ag+Cu	rem		8.0-11.0	<0.30	<0.50	<0.25		1.0-2.0					<0.20									
642	Cu = Ag+Cu	rem		6.3-7.6	<0.30	<0.10	<0.25		<0.05					<0.10									
642.1	Cu = Ag+Cu	rem		6.3-7.0	<0.30	<0.10	<0.25		<0.05					<0.10									
642.5	Cu = Ag+Cu	rem		5.5-7.5	<1.00	<0.50	<0.25		<0.05					<0.10									
644	Cu = Ag+Cu	rem		3.5-4.5	<0.05		4.2-5.0		<0.03					<0.20									
647	Cu = Ag+Cu	rem			<0.10		1.6-2.2		<0.10					<0.50									
647.1	Cu = Ag+Cu	>95.00				<0.10	2.9-3.5							0.20-0.90									
647.2	Cu = Ag+Cu	rem					1.6-2.2							0.10-0.40									
647.5	Cu = Ag+Cu	rem			<0.25		1.3-2.7		<0.01					0.20-0.80									
647.25	Cu = Ag+Cu	>95.00	Cs <0.01				2.9-3.5		<0.01					0.50-1.50									
647.3	Cu = Ag+Cu	>93.50				<0.10	1.0-2.0		<0.01					0.20-0.50									
647.4	Cu = Ag+Cu	>95.00	Cs <0.01				1.0-2.0		<0.01					0.05-0.50									
647.5	Cu = Ag+Cu	rem			<1.00		1.0-3.0		<0.02					0.10-0.70									<0.10
647.6	Cu = Ag+Cu	>93.50			0.10-0.40		0.40-2.50		<0.02					0.05-0.60									
647.8	Cu = Ag+Cu	>90.00				0.01-1.00	1.0-3.5		<0.02					0.20-0.90									<0.01
649	Cu = Ag+Cu	rem		<0.10	<0.10		<0.10		<0.05					0.8-1.2									
651	Cu = Ag+Cu	rem			<0.80	<0.70			<0.05					1.2-1.6									
653	Cu = Ag+Cu	rem			<0.80				<0.05					0.8-2.0									
654	Cu = Ag+Cu	rem																					

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
655	Cu = Ag+Cu	rem		<0.01	<0.80	0.50-1.30	<0.6		<0.05			2.8-3.8		<1.50								
656	Cu = Ag+Cu	rem			<0.50	<1.50			<0.02			<1.50	<1.50	<1.50								
656.2	Cu = Ag+Cu	>90.00			1.0-2.0	<1.00		<0.10	<0.05			2.4-4.0		1.5-4.0								
658	Cu = Ag+Cu	rem			<0.25	0.50-1.30	<0.6		<0.05			2.8-3.8										
661	Cu = Ag+Cu	rem			<0.25	<1.50			0.20-0.80			2.8-3.5		<1.50								
662	Cu = Ag+Cu	86.6-91.0			<0.05		0.30-1.00	0.05-0.20	<0.05				0.20-0.70	rem								
663	Cu = Ag+Cu	84.5-87.5			1.3-1.7		<0.05	<0.02	<0.015			<0.05	1.5-3.0	rem				<0.20				
664	Cu = Ag+Cu	rem		<0.05	1.8-2.3		<0.05	<0.02	<0.015			<0.05	<0.05	11.0-12.0	<0.05			0.30-0.70				
664.1	Cu = Ag+Cu	rem			0.50-1.50									12.7-17.0								
664.2	Cu = Ag+Cu	rem																				
667	Cu = Ag+Cu	68.5-71.5			<0.10	0.8-1.5			<0.07					rem								
668	Cu = Ag+Cu	60.0-63.0		<0.25	<0.35	2.0-3.15	<0.25		<0.05			0.50-1.50	<0.30	rem								
669	Cu = Ag+Cu	62.5-64.5			<0.25	11.5-12.5			<0.01					rem								
669.5	Cu = Ag+Cu	rem		1.0-1.5	<0.50	14.0-15.0			<0.01					14.0-15.0								
670	Cu = Ag+Cu	63.0-68.0		3.0-6.0	2.0-4.0	2.5-5.0			<0.20				<0.50	rem								
671.3	Cu = Ag+Cu	56.0-59.0		0.10-1.00	<0.50	0.50-1.50	0.50-1.50		0.50-1.50				0.50-1.50	rem								
671	Cu = Ag+Cu	58.0-63.0		<0.25	<0.50	2.0-3.15	<0.25		0.40-3.00				<0.30	rem								
674	Cu = Ag+Cu	55.0-60.0		0.50-2.00	<0.35	2.0-3.15	<0.25		<0.50				<0.30	rem								
674.1	Cu = Ag+Cu	55.5-59.0		1.3-2.3	<1.00	1.0-2.4	<2.0		<0.8			0.7-1.3	<0.50	rem								
674.2	Cu = Ag+Cu	57.0-58.5		1.0-2.0	0.15-0.55	1.5-2.5	<0.25		0.25-0.80			0.25-0.70	<0.35	rem								
675	Cu = Ag+Cu	57.0-60.0		<0.25	0.8-2.0	0.05-0.50			<0.20				0.50-1.50	rem								
676	Cu = Ag+Cu	57.0-60.0			0.40-1.30	0.05-0.50			0.50-1.00				0.05-1.50	rem								
676.2	Cu = Ag+Cu	55.0-57.0			0.50-1.30	1.0-2.0			<0.07					rem								
677	Cu = Ag+Cu	55.5-58.0			0.7-1.5	0.05-0.30	1.5-2.3		<0.05					21.3-24.1	0.02-0.06			0.25-0.55				
678	Cu = Ag+Cu	56.0-59.0		0.50-1.50	0.7-1.5	0.20-0.60			<0.30				<0.20	rem								
678.1	Cu = Ag+Cu	56.5-59.5		0.40-1.60	<1.00	0.40-1.80	<1.5		<1.0			<0.60	<0.50	rem								
678.2	Cu = Ag+Cu	56.5-59.5		0.30-1.30	0.50-1.20	0.30-2.00	<1.5		<0.10				0.30-1.00	rem								
681	Cu = Ag+Cu	56.0-60.0		<0.01	0.25-1.25	0.01-0.50	0.20-0.80		<0.05			0.04-0.15	0.75-1.10	rem								
681	Cu = Ag+Cu	56.0-60.0		<0.01	0.25-1.25	0.01-0.50			<0.05			0.04-0.15	0.75-1.10	rem								
682	Cu = Ag+Cu	58.0-60.0			0.6-1.0	0.6-1.0			<0.05			0.07-0.15		rem								
686	Cu = Ag+Cu	56.0-60.0		0.30-1.50	0.50-1.20	0.30-2.00			0.50-1.50				0.20-1.00	rem								
687	Cu = Ag+Cu	76.0-79.0		1.8-2.5	0.06				<0.07					rem								
688	Cu = Ag+Cu	3.0-3.8			<0.20				<0.05					rem								
690	Cu = Ag+Cu	3.0-3.8			<0.05		0.50-0.80		<0.025					rem								
690.5	Cu = Ag+Cu	72.0-75.0		3.0-4.0			0.50-1.50					0.10-0.60		rem								0.01-0.20
691	Cu = Ag+Cu	81.0-84.0		0.7-1.2	<0.25	<0.10	0.8-1.4		<0.05			0.8-1.3	<0.10	rem								
694	Cu = Ag+Cu	80.0-83.0			<0.20				<0.30			3.5-4.5		rem								
694.3	Cu = Ag+Cu	80.0-83.0			<0.20				<0.30			3.5-4.5		rem	0.03-0.06							
694.4	Cu = Ag+Cu	80.0-83.0			<0.20				<0.30			3.5-4.5		rem								
694.5	Cu = Ag+Cu	80.0-83.0			<0.20	<0.40		0.03-0.06	<0.30			3.5-4.5		rem								
697	Cu = Ag+Cu	75.0-80.0			<0.20	<0.40			0.50-1.50			2.5-3.5		rem								
697.1	Cu = Ag+Cu	75.0-80.0			<0.20	<0.40			0.50-1.50			2.5-3.5		rem	0.03-0.06							
697.2	Cu = Ag+Cu	75.0-80.0			<0.20	<0.40			0.50-1.50			2.5-3.5		rem								
697.3	Cu = Ag+Cu	75.0-80.0			<0.20			0.03-0.06	<0.8			2.5-3.5		rem								
698	Cu = Ag+Cu	66.0-70.0			<0.4		<0.50		<0.8			0.7-1.3		rem								
699	Cu=Ag+Cu; C, Cd	<0.05		1.4-2.3	<0.10	40.0-48.0	<0.10		<0.02					<0.14	<0.01			<0.20				
699.1	Cu = Ag+Cu	rem		0.25-0.80	1.0-1.4	28.0-32.0	<0.10		<0.01					3.0-5.0								
699.5	Cu = Ag+Cu	51.0-54.0			<0.05	36.0-40.0	8.5-10.5							rem								
701	Cu = Ag+Cu	rem			<0.05	<0.50	3.0-4.0		<0.05					<0.25								
702	Cu = Ag+Cu	rem			<0.10	<0.40	2.0-3.0		<0.05					rem								
702.3	Cu = Ag+Cu	rem			<0.10	<0.10	2.2-3.2		<0.05					0.40-0.80								
702.5	Cu = Ag+Cu	rem			<0.20	<0.10	2.2-4.2		<0.05					0.20-1.20					0.05-0.30			
702.6	Cu = Ag+Cu	rem			<0.20	<0.10	1.0-3.0	<0.01	<0.05					0.20-0.70								
702.7	Cu = Ag+Cu	rem			0.28-1.00	<0.15	1.0-3.0		<0.05					0.20-1.00								
702.8	Cu = Ag+Cu	rem			<0.015		1.3-1.7	0.020-0.040	<0.02					0.22-0.30								
702.9	Cu = Ag+Cu	rem			<0.015		1.3-1.7	0.020-0.040	<0.02					0.22-0.30								
703	Cu = Ag+Cu	>99.50			<0.05	<0.50	4.7-5.7							rem								
703.2	Cu = Ag+Cu	rem		0.20-1.20	1.3-1.7	0.30-0.80	4.8-6.2		<0.05					rem				0.18-0.50				
704	Cu = Ag+Cu	rem			1.0-1.8	0.50-1.50	4.5-6.0		<0.05					rem								
704.4	Cu = Ag+Cu	rem			1.0-1.8	0.50-1.50	4.5-6.0		<0.05					rem								
705	Cu = Ag+Cu	rem			<0.10	<0.15	5.8-7.8		<0.05					rem								
706	Cu = Ag+Cu	rem			1.0-1.8	0.50-1.00	9.0-11.0		<0.05					rem								
706.1	Cu = Ag+Cu	rem			1.0-2.0	1.0-1.00	10.0-11.0		<0.01					rem								
706.2	Cu = Ag+Cu	>86.50			1.0-1.8	<0.10	9.0-11.0	<0.02	<0.02					rem								
706.9	Cu=Ag+Cu, C<0.03, Hsp<0.0005	rem		<0.002	<0.05	<0.001	9.0-11.0	<0.001	<0.001					rem								<0.001
707	Cu = Ag+Cu	rem			<0.05	<0.50	9.5-10.5		<0.05					rem								
708	Cu = Ag+Cu	rem			<0.10	<0.15	10.5-12.5		<0.05					rem								

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
711.1	Cu = Ag+Cu	rem			<0.20	<0.35	21.5-23.5		<0.05					<1.00							<0.05	
713	Cu = Ag+Cu	rem			0.40-1.00	<1.00	23.5-26.5		<0.05					<1.00								
715	Cu = Ag+Cu	>65.00			0.40-1.00	<1.00	29.0-33.0	<0.02	<0.02					<1.50								
715.2	Cu = Ag+Cu			<0.05	0.40-1.00	<0.30	29.0-33.0	<0.03	<0.05	<0.024		<0.15		<0.05								
715.8	Cu = Ag+Cu, C <0.70				<0.50	<0.30	29.0-33.0	<0.03	<0.05	<0.024		<0.15		<0.05								
715.81	Cu = Ag+Cu	rem			0.40-0.70	<1.00	29.0-32.0	<0.02	<0.02	<0.003	<0.001	<0.25	<0.001	<0.001	<0.001	0.30-0.70	<0.001	<0.05	<0.10		0.20-0.50	
715.9	Cu = Ag+Cu, C<0.02, Hg<0.0005	rem		<0.002	0.40-1.00	0.50-1.50	29.0-32.0	<0.001	<0.01	<0.003	<0.001	<0.015	<0.001	<0.001							<0.001	
716.2	Cu = Ag+Cu, C<0.06	rem			0.40-1.00	1.5-2.5	29.0-32.0		<0.01	<0.08												
716.4	Cu = Ag+Cu, C<0.06	rem			1.7-2.3	1.5-2.5	29.0-32.0		<0.01	<0.08												
717	Cu = Ag+Cu	rem			0.40-1.00	29.0-33.0			<0.01	<0.03												
719	Cu = Ag+Cu, C<0.04	rem			<0.50	0.20-1.00	28.0-33.0	<0.02	<0.05	<0.015		<0.25		<0.05			2.2-3.0				0.01-0.20	0.02-0.35
721.5	Cu = Ag+Cu, C<0.10	rem			<0.10	<0.05	43.0-46.0		<0.05			<0.25		<0.20								
723	Cu = Ag+Cu, C<0.03	rem			0.5-1.0	<1.00	15.0-18.0		<0.05			<0.03		<1.00				0.30-0.70				<0.03
724	Cu = Ag+Cu	rem		1.5-2.5	<0.10	<1.00	11.0-15.0		<0.05			<0.03		<1.00								
724.2	Cu = Ag+Cu, C<0.05	rem		1.0-2.0	0.7-1.2	3.5-5.5	13.5-16.5	<0.01	<0.02	<0.15		<0.15		<0.20								0.05-0.40
725	Cu = Ag+Cu	rem			<0.60	<0.20	8.5-10.5		<0.05					<0.50								
726	Cu = Ag+Cu	rem			<0.60	<0.20	3.5-4.5	<0.05	<0.05					<0.50								
729.5	Cu = Ag+Cu	91.0-93.0			<0.10	<0.10	7.0-8.0		<0.01					<0.10								
729.5	Cu = Ag+Cu	rem			<0.50	0.05-0.30	8.5-9.50		<0.02					<0.10								
729.5	Cu=Ag+Cu, Nb 0.1-0.3, B <0.001	rem		<0.10	<0.50	0.05-0.30	9.5-10.5	<0.005	<0.005	<0.0025	<0.02	<0.05		<0.50			<0.001					<0.01
729	Cu = Ag+Cu	rem			<0.50	<0.30	14.5-15.5		<0.02					<0.50								
729.5	Cu = Ag+Cu	rem			<0.60	<0.60	20.0-22.0		<0.05					<0.50								
731.5	Cu = Ag+Cu	rem			<0.25	<0.50	4.0-7.0		<0.10					<0.10								
732	Cu = Ag+Cu	rem			<0.06	<1.00	19.0-23.0		<0.05					<0.10								
735	Cu = Ag+Cu	70.5-73.5			<0.25	<0.50	16.5-19.5		<0.10					rem								
738	Cu = Ag+Cu	rem			<0.25	<0.50	11.0-13.0		<0.05					rem								
740	Cu = Ag+Cu	68.5-71.5			<0.25	<0.50	9.0-11.0		<0.05					rem								
743	Cu = Ag+Cu	69.0-73.5			<0.25	<0.50	14.0-16.0		<0.10					rem								
744	Cu = Ag+Cu	63.0-66.0			<0.25	<0.50	7.0-9.0		<0.10					rem								
744	Cu = Ag+Cu	62.0-66.0			<0.25	<0.50	11.0-13.0		<0.05					rem								
745	Cu = Ag+Cu	63.5-66.5			<0.25	<0.50	9.0-11.0		<0.10					rem								
752	Cu = Ag+Cu	63.5-66.5			<0.25	<0.50	16.5-19.5		<0.05					rem								
754	Cu = Ag+Cu	63.5-66.5			<0.25	<0.50	14.0-16.0		<0.10					rem								
757	Cu = Ag+Cu	63.5-66.5			<0.25	<0.50	11.0-13.0		<0.05					rem								
757.2	Cu = Ag+Cu	60.0-65.0			<0.25	0.05-0.30	11.0-13.0		<0.04					rem								
759	Cu = Ag+Cu, Ni = Ni+Co	60.0-65.0			<0.25	<0.50	17.0-19.0		<0.10					rem								
760	Cu = Ag+Cu, Ni = Ni+Co	60.0-63.0			<0.25	<0.50	7.0-9.0		<0.10					rem								
761	Cu = Ag+Cu, Ni = Ni+Co	59.0-63.0			<0.25	<0.50	7.0-9.0		<0.10					rem								
762	Cu = Ag+Cu, Ni = Ni+Co	57.0-61.0			<0.25	<0.50	11.0-13.5		<0.10					rem								
763	Cu = Ag+Cu, Ni = Ni+Co	60.0-64.0			<0.50	<0.50	17.0-19.0	0.50-2.00	<0.05					rem								
763.9	Cu = Ag+Cu, Ni = Ni+Co	59.0-63.0			<0.50	<0.50	23.0-26.0		0.8-1.1				0.40-0.60	rem								
764	Cu = Ag+Cu, Ni = Ni+Co	58.5-61.5			<0.25	<0.50	16.5-19.5		<0.05					rem								
766	Cu = Ag+Cu, Ni = Ni+Co	55.0-58.0			<0.25	<0.50	11.0-13.5		<0.10					rem								
767	Cu = Ag+Cu, Ni = Ni+Co	55.0-58.0			<0.25	<0.50	14.0-16.0		<0.10					rem								
770	Cu = Ag+Cu, Ni = Ni+Co	53.5-56.5			<0.25	<0.50	16.5-19.5		<0.05					rem								
770.1	Cu = Ag+Cu, Ni = Ni+Co	54.0-56.0			<0.25	0.05-0.35	17.0-19.0		<0.05					rem								
773	Cu = Ag+Cu, Ni = Ni+Co	46.0-50.0		<0.01	<0.30		9.0-11.0	<0.25	<0.05			0.04-0.25		rem								
773.1	Cu = Ag+Cu, Ni = Ni+Co	46.0-56.0		<0.01		<0.50	9.0-11.0	<0.25	<0.05			0.04-0.25		rem								
774	Cu = Ag+Cu, Ni = Ni+Co	43.0-47.0			<0.20	<0.25	12.0-14.0		<0.20				<0.15	rem								
776	Cu = Ag+Cu, Ni = Ni+Co	42.0-45.0			<0.20	<0.25	9.0-11.0		<0.20					rem								
782	Cu = Ag+Cu, Ni = Ni+Co	63.0-67.0			<0.35	<0.50	7.0-9.0		1.5-2.5					rem								
788	Cu = Ag+Cu, Ni = Ni+Co	63.0-67.0			<0.25	<0.50	9.0-11.0		1.5-2.0					rem								
790	Cu = Ag+Cu, Ni = Ni+Co	63.0-67.0			<0.35	<0.50	11.0-13.0		1.5-2.2					rem								
792	Cu = Ag+Cu, Ni = Ni+Co	59.5-66.5			<0.25	<0.50	11.0-13.0		0.8-1.4					rem								
793	Cu = Ag+Cu, Ni = Ni+Co	55.0-59.00			<0.50	<0.50	11.0-13.0		0.50-2.00					rem								
796	Cu = Ag+Cu, Ni = Ni+Co	43.5-46.5				1.5-2.5	9.0-11.0		0.8-1.2					rem								
796.2	Cu = Ag+Cu, Ni = Ni+Co	46.0-48.0				<0.50	8.0-11.0		0.50-2.00					rem								
798	Cu = Ag+Cu, Ni = Ni+Co	45.5-48.5			<0.25	1.5-2.5	9.0-11.0		1.5-2.5					rem								
798.1	Cu = Ag+Cu, Ni = Ni+Co	46.0-48.0			<0.25	<0.50	8.0-11.0		2.0-3.5					rem								
798.2	Ni = Ni+Co	46.0-48.0			<0.50	<0.50	8.0-11.0		2.0-3.5					rem								
798.3	Cu = Ag+Cu, Ni = Ni+Co	45.5-47.0			<0.45	0.15-0.55	9.0-10.5		1.0-2.5					rem								
799	Cu = Ag+Cu, Ni = Ni+Co	47.5-50.5			<0.25	<0.50	6.5-8.5		1.0-1.5					rem								
801	Cu = Ag+Cu, Ni = Ni+Co	>99.95												rem								
803	Cu = Ag+Cu, Ni = Ni+Co	>99.95												rem								
804.1	Cu = Ag+Cu, Ni = Ni+Co	>99.90	>0.034											rem								
805	Cu=Ag+Cu, Ni=Ni+Co, B <0.02	>99.75	>0.034																			

Alloy	Notes	Cu	Ag	Al	Fe	Mn	Ni	P	Pb	S	Sb	Si	Sn	Zn	As	Be	Bi	Co	Cr	Mg	Ti	Zr
958.2		>77.50		9.0-10.0	4.0-5.0	<1.50	4.5-5.8		<0.02			<0.10	<0.20									
959		rem		12.0-13.5	3.0-5.0	<1.50	<0.50		<0.01	<0.02		<0.50										
962	C <0.10, No <1.00	rem		1.0-1.8	1.0-1.8	1.0-1.8	9.0-11.0	<0.02														
963	C <0.15, No 0.50-1.50	rem		0.50-1.50	0.25-1.50	18.0-22.0	18.0-22.0	<0.02	<0.01	<0.02		<0.50										
964	C <0.15, No 0.50-1.50	rem		0.25-1.50	<1.50	28.0-32.0	28.0-32.0	<0.02	<0.03	<0.02		<0.50										
966		rem		0.8-1.1	<1.00	29.0-33.0	29.0-33.0		<0.01			<0.15			0.40-0.70							
967		rem		0.7-1.0	<0.70	29.0-33.0	29.0-33.0		<0.01			<0.15			1.10-1.20						0.01-0.20	0.1-0.2
968	No 0.10-0.30, B <0.01	rem		<0.10	0.05-0.30	9.5-10.5	9.5-10.5	<0.005	<0.005	<0.0025	<0.02	<0.05								0.005-0.15	<0.01	
969.5	No <0.10	rem			0.50-0.30	14.5-15.5	14.5-15.5		<0.02			<0.30										<0.15
	No <0.10	rem			0.05-0.40	11.0-15.5	11.0-15.5		<0.02			<0.30										<0.15
973		53.0-56.0		<0.005	<1.50	<0.50	11.0-14.0	<0.05	8.0-11.0	<0.08	<0.35	<0.15	1.5-3.0	17.0-25.0								
974		58.0-61.0			<1.50	<0.50	15.5-17.0		4.5-5.5				2.5-3.5	rem								
976		63.0-67.0		<0.005	<1.50	<1.00	19.0-21.5	<0.05	3.0-5.0	<0.08	<0.25	<0.15	3.5-4.5	3.0-9.0								
978		64.0-67.0		<0.005	<1.50	<1.00	24.0-27.0	<0.05	1.0-2.5	<0.08	<0.20	<0.15	4.0-5.5	1.0-4.0								
982		73.0-79.0			<0.70		<0.50	<0.10	21.0-27.0		<0.50		0.6-2.0	<0.50								
984		rem	<1.50		<0.70		<0.50	<0.10	26.0-33.0		<0.50		<0.50	<0.50								
986		60.0-70.0	<1.50		<0.35				30.0-40.0				<0.50	<0.10								
988		56.5-62.5	<5.50		<0.35			<0.02	37.5-42.5				<0.25									
988.4		rem			<0.35				40.0-44.0				1.0-5.0									
		rem			<0.35				44.0-56.0				1.0-5.0									
993	Incramet 800	rem		10.7-11.5	0.40-1.00		13.5-16.5		<0.02			<0.02	<0.05				1.0-2.0					
993.5		rem		9.5-10.5	<1.00	<0.25	14.5-16.0		<0.15				7.5-9.5									
994		rem		0.50-2.00	1.0-3.0	<0.50	1.0-3.5		<0.25			0.50-2.00		0.50-5.00								
995		rem		0.50-2.00	3.0-5.0	<0.50	3.5-5.5		<0.25			0.50-2.00		0.50-2.00								
996	C <0.05	rem		1.0-2.8	<0.20	39.0-45.0	<0.20		<0.02			<0.10	<0.10	<0.20				<0.20				
997	No 4.0-6.0	>54.00		0.50-3.00	<1.00	11.0-15.0	4.0-6.0		<2.0				<1.00	19.0-25.0								
997.5		55.0-61.0		0.25-3.00	<1.00	17.0-23.0	<5.0		0.50-2.50				0.50-2.50	17.0-23.0								

These are specifications for reference purposes only, not samples for sale.