

# INDEX

- ALLOY LISTING 49  
ALLOY SPECIFICATIONS 51  
ALLOYED CAST IRON 40, 41, 47, 48  
ALUMINUM IN STAINLESS STEEL 19  
ALUMINUM IN STEEL 2, 6  
ANTIMONY IN STEEL 5  
ARSENIC IN STEEL 5
- BISMUTH STEEL 5, 8  
BORON IN STEEL 2
- CALCIUM IN STAINLESS STEEL 19  
CALCIUM IN STEEL 6  
CARBON STEEL 2, 3, 4, 44  
CARBON STEEL SPECIFICATIONS 51  
CAST IRON  
32, 33, 34, 35, 37, 38, 39, 40, 41, 42, 43, 48  
CAST IRON WITH MAGNESIUM 34, 35, 36  
COBALT ALLOY 9  
COBALT IN STAINLESS STEEL 21  
COPPER IN STAINLESS STEEL 20  
Cr-Mo STEEL 6, 7
- DUCTILE IRON 33
- EPMA SETS 6
- GRAY IRON 33
- HIGH ALLOY STEEL 31, 32, 47  
HIGH ALLOY STEEL SPECIFICATIONS 54  
HIGH CHROMIUM CAST IRON 40, 41, 47, 48
- IRON 2
- LEADED STEEL 8  
LOW ALLOY STEEL  
5, 6, 7, 8, 9, 10, 11, 12, 13, 14, 15, 16, 45, 46  
LOW ALLOY STEEL SPECIFICATIONS 52  
LOW ALLOY STEEL WITH  $0.13\% < C < 0.3\%$  13, 14  
LOW ALLOY STEEL WITH  $C < 0.13\%$  15  
LOW ALLOY STEEL WITH  $C > 0.3\%$  11, 12
- LOW ALLOY STEEL WITH EXTENSIVE ANALYSIS 13
- MAGNETIC ALLOY 9  
MANGANESE STAINLESS STEEL 22  
MANGANESE STEEL 8  
MARAGING STEEL 21
- NICKEL BINARY 22  
NITROGEN IN STEEL 6  
NODULAR IRON 33
- PERMENDUR 2V 9  
PHOSPHORUS IN STAINLESS STEEL 23
- RESULFURIZED STAINLESS STEEL 23  
RESULFURIZED STEEL 9, 44  
RESULFURIZED STEEL SPECIFICATIONS 51
- SELENIUM IN STAINLESS STEEL 23  
SET 2, 6, 8, 9, 16, 30, 32  
Si-Mo CAST IRON 33  
SILICON STEEL 10, 46  
SOLUBLE ALUMINUM 2  
SOLUBLE BORON 2  
STAINLESS STEEL  
19, 20, 21, 22, 23, 24, 25, 26, 27, 28, 29, 30, 31, 47  
STAINLESS STEEL SPECIFICATIONS 54  
STAINLESS STEEL WITH  $C < 0.05\%$  28, 29  
STAINLESS STEEL WITH  $C > 0.05\%$  26, 27  
STAINLESS STEEL WITH  $NI < 5.0\%$  24, 25  
SULFUR IN STAINLESS STEEL 23
- TOOL STEEL 16, 17, 18, 45, 46  
TOOL STEEL SPECIFICATIONS 53  
TUNGSTEN IN STAINLESS STEEL 21
- WHITE IRON 36
- XRF 2, 6, 8, 9, 16, 30, 32

## PURE IRON

# = class, where 1 = CRM and 2 = RM

\* Provisional Analysis

17025

T = total

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	N	O
1	SRM 1265a	0.0067	0.0057	0.0011	0.0055	0.008	0.0058	0.041	0.007	0.0050	(0.0007)	0.007	.	.
1	BS 50F	0.0064	0.082	0.0066	0.0031	0.016	0.0088	0.016	0.022	0.0017	0.003	0.0023	0.0042	(0.0026)
2	CZ LA-0A	(0.006)	0.045	0.005	0.005	0.0015	0.012	0.028	0.022	(0.0044)	0.0015	0.002	0.0023	.
2	CZ LA-0B	(0.003)	0.038	0.0037	0.0023	(0.0043)	0.0074	0.0070	0.009	(0.0016)	(0.0010)	(0.0017)	0.0027	.
1	IARM 27G	(0.003)	(0.003)	(0.003)	0.0011	(0.07)	0.040	0.045	0.043	(0.002)	(0.0013)	(0.0009)	(0.0003)	0.025
1	BS LC-7B	0.0025	0.024	0.013	0.0029	(0.005)	0.0033	0.0081	0.0090	0.0034	0.0194	0.0018	0.0043	0.0020
1	BS LC-7A	0.0025	0.023	0.013	0.0030	0.0056	0.0038	0.0058	0.0074	0.0034	0.0194	0.0017	0.0043	(0.005)
1	BS 50G	0.0023	0.010	0.0088	0.0033	0.009	0.007	0.0045	0.008	(0.001)	0.008	0.0011	0.0019	0.0030
1	VS RG24/1	0.0022	0.015	0.0027	0.0069	0.017	0.011	0.037	0.037	0.0013	.	0.012	.	.
2	TL 1669 **	0.00226	0.0955	0.0137	0.0100	0.0093	0.0217	0.0160	0.0246	0.0011	0.03553T	0.0019	0.0024	.
2	BS 50D	0.0020	0.0008	0.0014	0.00024	0.0018	0.0004	0.0012	0.0003	(0.00004)	(0.0040)	0.0026	0.0024	0.0220
1	ECRM 098-1D	0.00051	0.00008	(0.00006)	0.00031	0.00048	.	.	0.00571	0.00085	.	.	0.00024	.
1	ECRM 097-2D	.	0.012	0.00538	0.00181	0.00285	0.00793	0.0241	0.0213	0.00370	.	0.0139	0.00294	.

Number	As	B	Mg	Nb	Pb	Sn	Ti	V	W	Units	
SRM 1265a	(0.0002)	0.00013	.	.	0.00001	.	(0.0001)	0.0006	.	disc 32 mm Ø x 19 mm	
BS 50F	0.0013	(<0.0002)	(<0.0001)	(<0.0002)	(0.0003)	0.0010	0.0004	0.0004	(0.0003)	(0.0050)	disc 35 mm Ø x -7 or 19+ mm
CZ LA-0A	(0.0015)	.	.	Sb:(0.0007)	(0.001)	(0.001)	0.001	.	.	.	disc -37 mm Ø x 25 mm
CZ LA-0B	0.0024	.	.	.	.	(0.0013)	.	.	.	.	disc -39 mm Ø x -25 mm
IARM 27G	(0.0016)	(0.0006)	(0.0002)	(0.002)	(0.002)	(0.001)	<0.005	(0.001)	<0.005	.	disc 31 mm Ø X 2 or 18 mm
BS LC-7B	0.0026	(0.0001)	(0.00008)	0.0007	(0.0003)	(0.0007)	(0.0001)	(0.0004)	(0.0006)	.	disc 38 mm Ø x 38 mm Fe:99.9
BS LC-7A	0.0024	(0.0001)	(0.0001)	(0.0005)	(0.0004)	(0.0007)	0.0004	(0.0004)	(0.0005)	.	disc 35 mm Ø x 38 mm Fe:99.9
BS 50G	0.0034	(0.0001)	(0.0002)	(0.0004)	(0.00007)	Sb:0.0005	(0.003)	(0.0003)	.	.	disc 38 mm Ø x 38 mm Fe:99.9
VS RG24/1	.	.	.	.	.	.	0.0010	.	.	.	disc -45 mm Ø x -28mm last
TL 1669 **	0.0017	0.00038	.	0.00046	0.00013	0.0071	0.0504	(0.0006)	.	.	disc 38 mm Ø x 25 mm
BS 50D	(0.0001)	0.00004	0.00005	0.0002	0.00005	<0.0001	0.0001	0.0004	(0.0002)	.	disc 35 mm Ø x -7 to 19+mm last
ECRM 098-1D	.	.	.	.	.	.	.	.	.	.	octagon 35 mm Ø x 25 mm
ECRM 097-2D	0.00281	0.00012	Sb:0.00012	Ta:0.00015	Zn:0.00014	0.00043	.	0.00011	0.00386	.	disc 38 mm Ø x 25 or 30 mm

\*\* TL-1669 also contains in ppm Ca: 1.7, Sb: 4.9, Zn: 2.7

## RM CARBON STEEL XRF SET

Part Number: BS CS-10

AVAILABLE INDIVIDUALLY

17025

~7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Co	N	Sn	V
Pure Iron	BS 50F	0.0064	0.082	0.0066	0.0031	0.016	0.0088	0.016	0.022	0.0017	0.003	0.0013	0.0023	0.0042	0.0010	(0.0003)
1018	BS 1018	0.195	0.79	0.012	0.024	0.237	0.130	0.104	0.177	0.044	0.029	0.0041	0.0058	0.0079	0.0099	0.0009
1020	BS 57F	0.196	0.554	0.009	0.027	0.202	0.197	0.070	0.120	0.018	(0.002)	(0.006)	0.007	0.0077	0.008	0.063
1026	BS 4932	0.234	0.76	0.010	0.015	0.25	0.15	0.080	0.144	0.033	(0.001)	(0.005)	0.005	0.0080	0.008	0.060
1035	BS 4931	0.352	0.80	0.011	0.016	0.27	0.217	0.070	0.093	0.024	(0.001)	0.005	0.006	0.0080	0.009	0.058
1040	BS 3941	0.407	0.802	0.016	0.023	0.257	0.053	0.018	0.069	0.0061	0.0019	0.0036	0.0042	0.0069	0.0019	0.0025
1045	BS 56E	0.483	0.72	0.010	0.025	0.24	0.015	0.015	0.021	0.005	0.062	0.0035	0.005	0.0056	(0.0006)	(<0.002)
1095	BS 64C	0.920	0.22	0.015	0.0024	0.22	0.016	0.038	0.261	0.008	(0.005)	.	0.004	0.0084	(0.001)	0.005
1522 (LF2)	BS 2932	0.208	1.20	0.008	0.020	0.186	0.060	0.034	0.077	0.026	0.022	(0.003)	0.004	0.0080	0.005	0.001
1345	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.041	0.007	0.033	0.0023	0.006	0.0056	(0.0004)	(<0.003)

## CRM CARBON STEEL SET

AVAILABLE IN SET/6 ONLY

38 mm Ø x 30 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Al.Sol	Ti	Ti.Sol	V
NCS HS11719-5	1.19	2.20	0.011	0.013	0.751	0.046	0.164	0.439	0.036	0.034	0.029	0.028	0.0082
NCS HS11719-1	0.963	0.586	0.022	0.010	0.241	0.111	0.206	0.131	0.019	0.017	0.016	0.015	0.035
NCS HS11719-3	0.435	1.14	0.045	0.020	0.163	0.160	0.114	0.086	0.019	0.016	0.024	0.023	0.099
NCS HS11719-4	0.140	1.30	0.084	0.020	0.526	0.276	0.344	0.198	0.160	0.155	0.132	0.128	0.153
NCS HS11719-2	0.042	0.048	0.105	0.0053	0.154	0.411	0.432	0.247	0.296	0.292	0.161	0.154	0.207
NCS HS11719-6	0.0060	0.163	0.0053	0.035	0.014	0.0032	0.013	0.021	0.0021	0.0016	0.0010	(0.0008)	0.363

## CRM SOLUBLE ALUMINUM AND SOLUBLE BORON STEEL SET

available in set/6 only as grouped .T = total .S = soluble

37 mm Ø x 30 mm

Number	Al.T	Al.S	B.T	B.S	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo
NCS HS93703-1a	0.59	0.58	0.036	0.034	1.04	2.10	0.023	0.030	0.650	0.033	0.063	4.05	0.0088	0.0040
NCS HS93703-2	0.92	0.91	0.0083	0.0080	0.055	0.021	0.027	0.0033	0.827	0.422	1.09	3.09	0.262	1.56
NCS HS93703-3	0.107	0.103	0.0041	0.0037	0.792	1.34	0.013	0.038	1.09	0.532	0.533	2.11	0.488	0.397
NCS HS93703-4	0.083	0.078	0.0050	0.0048	0.475	0.612	0.015	0.015	2.57	0.687	2.01	1.31	0.403	0.977
NCS HS93703-5	(1.29)	(1.27)	0.0017	0.0015	0.651	1.53	0.036	0.0052	0.024	0.236	2.98	0.021	0.094	0.631
NCS HS93703-6	0.64	0.63	0.0033	0.0030	0.246	0.211	0.045	0.0058	0.274	0.092	3.83	0.505	0.145	0.203

Number	As	Bi	Ca	Nb	Pb	Sb	Sn	Ti	V	W	Zr
NCS HS93703-1a	0.034	0.0013	(0.0001)	0.300	(0.0001)	(0.0004)	0.0035	0.069	0.021	0.313	(0.0005)
NCS HS93703-2	0.0034	0.0006	0.0010	0.254	0.0008	0.0020	0.0069	0.346	0.376	1.97	0.087
NCS HS93703-3	0.0019	0.0004	0.0010	0.506	0.0007	0.0040	0.054	0.016	0.071	0.755	0.014
NCS HS93703-4	0.056	(0.0002)	(0.0001)	0.167	0.0006	0.0095	0.012	0.035	0.709	1.48	0.069
NCS HS93703-5	0.0064	0.0015	0.0007	0.0057	0.0007	0.010	0.015	0.111	0.231	0.050	0.41
NCS HS93703-6	0.011	(0.0002)	(0.0001)	0.070	0.0011	0.0006	0.017	0.246	0.526	1.04	0.22

## CARBON STEEL

## CONTINUED ON THE NEXT PAGE

# = Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	B	Ca	Co	Mo
1	IRSID 1660	1.20	0.280	0.014	0.010	0.173	0.059	0.072	(0.026)	(0.009)	.	.	.	.	.	.
1	ECRM 090-1D	1.05	0.226	0.013	0.0095	0.281	0.053	0.121	.	.	.	.	.	.	.	0.009
1	SRM 1227	0.97	0.402	0.014	0.026	0.215	0.006	0.007	0.019	.	.	.	.	.	0.003	0.003
1	SS 602/2	0.94	0.66	0.023	0.031	0.057	(0.06)	(0.02)	(0.03)	0.096	.	.	.	.	(0.007)	(0.004)
2	BS 64C	0.920	0.22	0.015	0.0024	0.22	0.016	0.038	0.261	(0.005)	.	.	.	.	0.004	0.008
2	HRT FE2014-N	0.91	1.97	0.012	(0.004)	0.24	0.01	0.02	0.35	0.016	.	.	.	.	.	0.01
1	ECRM 056-2D	0.8181	0.5073	0.0103	0.0093	0.2006	0.0129	0.0218	0.0146	0.00024	.	.	.	.	.	.
1	SRM 1224	0.75	0.41	0.009	0.039	0.173	0.072	0.054	0.071	0.060	.	.	.	.	.	0.013
1	BS 54H	0.737	0.829	0.0030	0.0044	0.521	0.046	0.373	0.369	0.032	.	0.0036	(0.0001)	(0.0001)	0.0030	0.0106
1	VS RG28	0.70	0.84	0.031	.	1.161	0.050	0.154	0.135	0.066	.	.	.	.	.	0.090
1	VS RG28/1	0.68	0.91	0.031	0.0071	2.36	0.040	0.168	0.194	0.068	.	.	.	.	0.072	0.104
1	IARM 373A	0.63	0.70	0.0123	0.031	0.22	0.107	0.048	0.096	0.002	.	0.0046	0.0003	0.0005	0.005	0.0176
1	VS UG20/6	0.58	0.473	(0.008)	(0.02)	0.229	0.249	0.360	0.396	.	.	.	.	.	.	.
1	SS 435/1	0.52	0.41	0.033	0.031	0.54	.	0.060	0.14	.	.	.	.	.	.	.
1	SS 435/2	0.489	0.390	0.037	0.042	0.328	.	0.133	0.184	.	.	.	.	.	0.011	.
2	BS 56E	0.483	0.72	0.010	0.025	0.24	0.015	0.015	0.021	0.062	.	0.0035	.	( $<0.0005$ )	0.005	0.005
1	IRSID 1636	0.47	0.78	0.029	0.037	0.40	0.135	0.092	(0.060)	(0.007)	.	.	.	.	.	.
1	SS 459/2	0.467	0.909	0.0482	0.0481	0.640	.	0.015	(0.013)	.	0.0110	.	.	0.0890	.	.
1	BS 1045	0.458	0.796	0.0069	0.023	0.215	0.190	0.060	0.108	(0.001)	.	0.0050	(0.0003)	0.0013	0.0056	0.0170
1	IARM 200D	0.453	0.749	0.0103	0.024	0.225	0.232	0.097	0.109	(0.004)	.	0.0050	.	.	0.007	0.0217
1	VS UG123	0.45	0.552	0.016	0.026	0.216	0.196	0.084	0.111	0.024	.	.	.	.	.	.
1	IRSID 1657	0.445	0.724	0.028	(0.013)	0.274	.	0.048	(0.022)	0.004	.	0.0051	.	.	.	(0.008)
1	NM 306	0.44	0.80	0.043	0.042	0.34	.	.	0.26	.	.	.	.	.	.	.
1	IRSID 1648	0.432	1.41	0.031	(0.070)	0.242	0.408	0.165	0.170	(0.004)	.	(0.038)	.	.	.	(0.028)
1	NM EN-8	0.42	0.82	0.02	0.02	0.21	.	.	.	.	.	.	.	.	.	.
1	IRSID 1642	0.418	0.929	0.031	(0.031)	0.388	0.097	0.068	(0.035)	(0.020)	.	(0.042)	.	.	.	(0.009)
1	IRSID 1647	0.418	0.701	0.019	(0.027)	0.299	(0.104)	0.093	0.490	(0.060)	.	.	.	.	.	.
1	IARM 210D	0.412	0.73	0.0052	0.030	0.230	0.273	0.122	0.096	(0.002)	(0.0555)	0.0059	0.0004	0.0009	0.007	0.034
1	SS 434/1	0.41	1.49	0.050	0.027	0.31	.	0.044	0.055	.	.	.	.	.	.	.
1	IARM 349A	0.41	1.49	0.011	0.025	0.192	0.300	0.178	0.189	0.0020	.	0.005	0.0003	0.0015	0.0085	0.059
1	BS 3941	0.407	0.802	0.016	0.023	0.257	0.053	0.018	0.069	0.0019	.	0.0036	(0.0001)	0.0011	0.0042	0.0061
1	IRSID 1652	0.406	0.931	(0.017)	0.040	0.386	0.345	0.190	0.184	.	(0.0013)	0.038	.	.	.	(0.042)
1	IRSID 1637	0.401	0.940	0.030	0.030	0.378	0.097	0.068	(0.033)	0.022	.	0.042	.	.	.	(0.006)
1	SS 605/2	0.400	0.345	0.054	0.015	0.54	(0.06)	(0.05)	(0.06)	0.027	.	.	.	.	(0.008)	(0.01)
1	IRSID 1644	0.394	0.594	0.021	0.031	0.287	0.265	0.158	0.138	(0.017)	.	.	.	.	.	.
1	ECRM 084-1D	0.391	0.860	.	0.029	0.265	0.267	0.154	.	.	.	.	.	.	.	0.033
1	IRSID 1649	0.384	0.930	0.045	(0.047)	0.250	0.418	0.226	0.321	0.004	.	0.037	.	.	.	0.043
1	SS 460/2	0.383	0.616	0.0374	0.0099	0.126	.	.	0.024	(0.019)	.	.	0.0027	.	0.0106	.
1	VS RG30	0.38	0.357	0.013	0.013	0.45	0.161	0.62	3.06	.	.	.	.	.	0.50	0.62
1	BS 1035	0.362	0.758	0.0100	0.028	0.246	0.241	0.123	0.151	0.0008	.	0.0051	(0.0002)	0.0017	0.0073	0.049
1	IRSID 1655	0.355	1.018	(0.018)	(0.060)	0.443	0.415	0.188	0.157	(0.004)	.	(0.036)	.	.	.	(0.043)
1	IRSID 1663	0.353	0.967	0.0090	0.034	0.235	0.180	0.148	0.206	0.037	.	0.028	.	.	.	0.042
1	VS UG90	0.34	0.286	0.0079	0.012	0.221	0.200	0.265	0.261	0.037	0.032	0.0044	.	.	.	0.046
1	VS UG19/6	0.34	0.274	(0.03)	(0.03)	0.136	0.148	0.262	0.227	.	.	.	.	.	.	.
1	IARM 360A	0.331	0.733	0.008	0.023	0.260	0.235	0.078	0.113	0.0016	.	0.0060	0.0004	0.0017	0.0067	0.024
1	BS 1030	0.331	0.682	0.0101	0.0299	0.261	0.269	0.078	0.124	0.0014	.	0.0055	0.0003	0.0012	0.0069	0.0182
1	IARM 209D	0.322	0.68	0.0084	0.021	0.268	0.243	0.079	0.137	(0.003)	.	0.0060	0.0002	0.002	0.007	0.037
1	IRSID 1653	0.312	0.962	0.034	(0.039)	0.400	0.453	0.218	0.358	$<0.004$	.	(0.039)	.	.	.	(0.038)
1	VS RG27	0.30	0.91	0.054	0.0032	0.42	0.188	0.135	1.53	0.88	.	.	.	.	0.071	0.222
1	SS 434/2	0.275	1.54	0.061	0.0141	0.51	.	0.037	0.238	.	.	.	.	.	.	.
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	B	Ca	Co	Mo
1	IRSID 1654	0.270	0.979	0.036	(0.047)	0.354	0.441	0.241	0.328	.	.	0.040	.	.	.	(0.043)
1	IARM 359A	0.267	0.686	0.0094	0.020	0.233	0.186	0.068	0.121	0.002	.	0.0073	0.0003	0.0013	0.0069	0.023
1	BS 1026	0.260	0.715	0.0171	0.0191	0.268	0.247	0.096	0.163	0.0330	.	0.0100	(0.0002)	0.0017	0.0072	0.0289
1	VS UG94	0.26	0.186	0.0037	0.0026	0.101	0.088	0.178	0.206	0.017	.	.	.	.	.	0.0005
1	VS UG18/6	0.242	0.213	(0.003)	(0.003)	0.20	0.063	0.273	0.237	.	.	.	.	.	.	.
2	HRT FE2016-N	0.23	0.85	0.015	0.011	0.32	0.02	0.15	0.21	0.033	.	.	.	.	.	.
1	BS 1020	0.210	0.568	0.0058	0.0249	0.250	0.184	0.059	0.109	0.0006	.	0.0074	(0.0001)	0.0022	0.0070	0.018
1	IARM 213C	0.201	0.922	0.007	0.025	0.25	0.149	0.068	0.099	0.0019	.	0.0058	0.0003	0.0014	0.0074	0.022
1	IRSID 1664	0.2008	0.472	0.0106	0.0259	0.0616	0.0820	0.0547	0.0707	.	0.0193	0.0115	(0.0002)	(0.0005)	(0.0084)	0.0157
1	VS RG25/1	0.196	0.29	0.019	0.0088	0.100	0.065	0.037	0.060	0.067	.	.	.	.	0.012	0.010
1	BS 1018	0.195	0.79	0.012	0.024	0.237	0.130	0.104	0.177	0.029	.	0.0041	(0.0002)	(0.0004)	0.0058	0.044
1	BS LF2B	0.176	1.05	0.007	0.0067	0.209	0.318	0.115	0.138	0.0287	.	0.0052	(0.0002)	0.0010	0.0071	0.0382
1	IARM 28K	0.174	0.80	0.012	0.027	0.291	0.171	0.0638	0.107	(0.025)	.	(0.005)	0.0005	.	0.0060	0.0210
1	BS 1016	0.172	0.77	0.011	0.030	0.193	0.153	0.107	0.091	0.0200	.	0.0066	(0.0003)	(0.0004)	0.0193	0.040
1	12X 10180C	0.171	0.803	0.0150	0.0200	0.147	0.0500	0.0284	0.0793	0.0198	.	0.0029	.	.	.	0.0047
1	12X 10180B	0.169	0.722	0.0101	0.0056	0.114	0.0544	0.0333	0.0451	0.043	.	0.0059	.	.	.	0.0062
2	TL 1000	0.1692	1.4281	0.0142	0.0164	0.2258	0.0120	0.0312	0.0635	0.0226	.	(0.0016)	0.00018	0.00039	0.0042	0.0076
1	VS RG25	0.167	0.131	0.014	0.0084	.	0.046	0.057	0.015	.	.	.	.	.	.	0.0028
1	VS UG124	0.165	1.41	0.019	0.032	0.384	0.020	0.015	0.035	0.039	.	.	.	.	.	.
1	VS UG109	0.161	0.353	0.020	0.0037	0.151	0.082	0.0053	0.048	0.0093	.	.	.	.	.	.
1	IARM 213D	0.158	0.725	0.0120	0.031	0.226	0.207	0.076	0.093	(0.003)	.	(0.006)	(0.0004)	.	0.0	

## CARBON STEEL CONTINUED FROM THE PREVIOUS PAGE

Number	N	Nb	O	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units
IRSID 1660												37 mm Ø x 30 mm
ECRM 090-1D	0.0146	0.00043		0.00239	0.00090			0.204		0.00209		38 mm Ø x 25 or 30 mm
SRM 1227								0.002				32 mm Ø x 19 mm
SS 602/2								(0.001)			(<0.005)	44 mm Ø X 19 mm
BS 64C	0.0084	(<0.003)				(0.001)	(0.002)	0.005				44 mm Ø X -7 or 19+ mm
HRT FE2014-N	0.0052							0.066				-35mm Ø x 20 mm
ECRM 056-2D												44 mm Ø x 25 or 30 mm
SRM 1224								0.002				32 mm Ø x 19 mm
<b>BS 54H</b>	0.0039	(0.0003)	(0.001)	(0.001)	(0.001)	0.0030	0.0009	0.0008	(0.003)	Fe:97.0	(0.0008)	44 mm Ø x 19+ mm <b>17025</b>
VS RG28		0.029				0.0041	0.022	0.006				-45 mm Ø x ~28 mm
VS RG28/1		0.041					0.022	0.035	0.0041			-45 mm Ø x ~28 mm
IARM 373A	0.0088	0.001	0.002	(0.001)	(0.002)	0.0069	0.0017	0.023	(0.002)	(0.003)	(0.003)	31 mm Ø x 2 or 18 mm
VS UG20/6		0.039										-45 mm Ø x ~28 mm
SS 435/1		0.134										38 mm Ø x 19 mm
SS 435/2												38 mm Ø x 19 mm
BS 56E	0.0056	(<0.002)		(0.0001)	0.0004	(0.0006)	(0.001)	(<0.002)				44 mm Ø x -7 to 19+ mm
IRSID 1636												48 mm Ø x 30 mm
SS 459/2		0.0102		0.0044	0.0121			0.0585			(0.074)	38 mm Ø x 19 mm
<b>BS 1045</b>	0.0113	0.026	0.0040	(0.0005)	0.0017	0.0084	0.0011	(0.002)	(0.0007)	Fe:98.1	(0.0009)	38 mm Ø x -7 or 19+ mm <b>17025</b>
IARM 200D	0.009	0.0010				0.0079	(0.0013)	0.0244	(0.003)			31 mm Ø X 2 or 18 mm
VS UG123	0.0078							0.0019				-45 mm Ø x ~25 mm
IRSID 1657								(0.001)				42 mm Ø x 30 mm
NM 306												40 mm Ø x 25 mm last
IRSID 1648						0.033						40 mm Ø x 28 mm
NM EN-8												40 mm Ø x 20 mm
IRSID 1642								(0.002)				45 mm Ø x 30 mm
IRSID 1647												41 mm Ø x 30 mm
IARM 210D	0.011	0.001	0.0034	0.001	0.002	0.010	0.0104	0.024	(0.002)		(0.001)	31 mm Ø x 2 or 18 mm
SS 434/1		0.078										38 mm Ø x 19 mm
IARM 349A	0.0100	0.0012	0.003	(0.001)	(0.003)	0.015	0.0013	0.027	0.004	(0.003)	(0.002)	31 mm Ø x 2 or 18 mm
<b>BS 3941</b>	0.0069	0.033	0.0055	0.0010	0.0005	0.0019	0.0017	0.0025	(0.0004)	last	(0.0003)	41 mm Ø x -7 - 19 mm <b>17025</b>
IRSID 1652						0.030						45 mm Ø x 30 mm
IRSID 1637								(0.002)				45 mm Ø x 30 mm
SS 605/2								(0.001)			(0.12)	44 mm Ø x 19 mm
IRSID 1644												45 mm Ø x 30 mm
ECRM 084-1D						0.023						38 mm Ø x 25 or 30 mm
IRSID 1649						0.028						40 mm Ø x 28 mm
SS 460/2		0.068		0.0005	(0.0006)			0.0322			(<0.0005)	38 mm Ø x 19 mm
VS RG30		0.139						0.63	0.91			-45 mm Ø x ~28 mm
<b>BS 1035</b>	0.0105	(0.001)	0.0036	(0.001)	(0.002)	0.0027	0.0007	0.026	0.0020	Fe:97.9	(0.0009)	40 mm Ø x -7 or 19+ mm <b>17025</b>
IRSID 1655						0.046						40 mm Ø x 34 mm
IRSID 1663						0.0143	0.051					44 mm Ø x 30 mm
VS UG90	0.015				0.0011		0.039					-47 mm Ø x -30 mm
VS UG19/6												-45 mm Ø x ~28 mm
IARM 360A	0.0102	0.0015	0.004	(0.001)	0.0023	0.010	0.0010	0.039	(0.001)	(0.003)	(0.001)	31 mm Ø x 2 or 18 mm
<b>BS 1030</b>	0.0107	(0.0004)	0.005	0.0005	0.0024	0.0114	0.0005	0.031	0.0012	last	(0.0002)	38 mm Ø x -7 mm <b>17025</b>
IARM 209D	0.0107	0.0014	0.005	0.001	0.004	0.012	0.0011	0.042	(0.002)	(0.003)		31 mm Ø x 2 or 18 mm
IRSID 1653						0.066						40 mm Ø x 34 mm
VS RG27								0.064	0.170			-45 mm Ø x ~28 mm
SS 434/2	0.0104	0.038										38 mm Ø x 19 mm
Number	N	Nb	O	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units
IRSID 1654						0.030						40 mm Ø x 34 mm
IARM 359A	0.0094	0.002	0.0044	(0.001)	(0.002)	0.0100	0.0009	0.027	(0.001)		(0.001)	31 mm Ø x 2 or 18 mm
<b>BS 1026</b>	0.0083	(0.0004)	0.0031	(0.0002)	0.0019	0.0112	(0.0004)	0.0016	0.0021		(0.0002)	38 mm Ø x -7 or 19+ mm <b>17025</b>
VS UG94							0.053	(0.001)				-40 mm Ø x ~28 mm
VS UG18/6												-45 mm Ø x ~28 mm
HRT FE2016-N	0.0055											35 mm Ø x 20 mm
<b>BS 1020</b>	0.0109	(0.0003)	0.0046	(0.0002)	(0.0018)	0.0090	(0.0005)	0.0363	(0.0004)		(0.0005)	44 mm Ø x -7 or 19+ mm <b>17025</b>
IARM 213C	0.0116	0.0011	0.0042	0.0011	0.002	0.0081	0.0010	0.035	(0.002)	(0.006)	(0.0004)	31 mm Ø x 2 or 18 mm
IRSID 1664	0.0072	(0.0002)		0.0002	0.0012	0.0108	0.0013	(0.0005)	<0.002	(0.0007)	(0.0001)	37 mm Ø x 30 mm
VS RG25/1		0.016					0.055	0.0110				-45 mm Ø x ~28 mm
<b>BS 1018</b>	0.0079	(0.0006)	0.0014	(0.0006)	(0.001)	0.0099	0.0009	0.0009	0.0014	Fe:98.2	(0.001)	38 mm Ø x -7 or 19+ mm <b>17025</b>
<b>BS 1F2B</b>	0.0078	(0.0003)	0.0024	(0.0001)	0.0018	0.0092	0.0009	0.0300	0.0027	<b>17025</b>	Fe:97.9	38 mm Ø x -7 or 19+ mm
IARM 28K	(0.008)	0.0017	(0.005)			0.0075	(0.0015)	(0.0014)				31 mm Ø x 2 or 18 mm
<b>BS 1016</b>	0.0113	(0.0009)	(0.003)	(0.004)	Fe:98.4	0.013	0.0010	0.0011	(0.0013)	<b>17025</b>	(0.001)	Hexagon ~60 mm Ø x 19+ mm
12X 10180C	0.0052					0.0024				0.0005		-40 mm Ø x ~15 mm
12X 10180B	0.0071					0.0065				0.0079		-40 mm Ø x ~15 mm
TL 1000	(0.0093)	0.0293		Mg: (0.00005)		(0.00106)	0.0011	(0.0033)	(0.0002)			36 mm Ø x 20 mm
VS RG25							0.039					-45 mm Ø x ~28 mm
VS UG124	0.0072							0.0043				-45 mm Ø x ~25 mm
VS UG109							0.071					-45 mm Ø x ~25 mm
IARM 213D	(0.008)	(0.0012)	(0.01)		(0.0032)	0.0147	0.0011	0.0010	(0.003)	(0.002)	(0.0015)	31 mm Ø x 2 or 18 mm
SS 456/2		0.0057		0.0189	0.0172			0.0221			(0.014)	38 mm Ø x 19 mm
VS UG93							0.075	0.0008				-40 mm Ø x ~28 mm
VS UG17/6												-45 mm Ø x ~28 mm
SS 433/2		0.059										38 mm Ø x 19 mm
IRSID 1661					(0.0005)	(0.0085)						40 mm x 42 mm x 30 mm
VS UG125	0.0112							0.035				-45 mm Ø x ~28 mm
VS UG108							0.071		0.074			-45 mm Ø x ~25 mm
SRM 1228								<0.001				32 mm Ø x 19 mm
ECRM 057-2D	0.0023											38 mm Ø x 25 or 30 mm
NM 305												40 mm Ø x 20 mm
ECRM 083-2D	0.00157									0.00439		39 mm Ø x 28 mm
DSZU C03		(0.002)		(0.009)	(0.003)	0.011	0.002	0.004	(0.009)	(0.0037)	(0.0006)	40 mm Ø x 30 mm
VS RG26							0.121		0.0052			-45 mm Ø x ~28 mm
SS 431/2	0.0052	0.0040										38 mm Ø x 19 mm
VS UG2/11	(0.007)											-45 mm Ø x ~28 mm
RM Fe 1/5	0.002	<0.005		<0.002		0.0008	<0.0005	<0.0005	0.002		<0.005	40 mm Ø x 40 mm
VS UG2/5		(0.002)					(0.01)	0.005	(0.02)			-45 mm Ø x ~28 mm
<b>BS 1005</b>	0.0044	0.0008	0.0058	(0.0003)	(0.0007)	0.0009	0.0010	(0.0007)	(0.0003)	Fe:99.6	(0.0008)	38 mm Ø x -7 or 19+ mm <b>17025</b>
<b>BS 1009</b>	0.0043	(0.0008)	0.0060	(0.0004)	(0.0009)	0.0007	0.0007	(0.0006)	(0.001)	Fe:99.6	(0.0006)	38 mm Ø x -7 or 19+ mm <b>17025</b>
SS 111/1	0.0025					0.0006	0.0004	0.0002				44 mm Ø x 19 mm
VS 005						0.0021	0.0047					-45 mm Ø x ~25 mm
SS 432/2	0.0066	0.0174										38 mm Ø x 19 mm
VS 003						0.0020	0.0063					-45 mm Ø x ~25 mm
CZ LA-1B	0.003	(0.001)		(0.0007)	(0.002)	(0.001)	(0.001)	0.004	0.010		(0.002)	-37 mm Ø x 25 mm
IMZ 110A	0.0037						(0.0006)	(0.0014)				43 mm Ø x 20 mm
VS 004							0.0013					-45 mm Ø x ~25 mm
VS 002						0.00040	0.0005					-45 mm Ø x ~25 mm
Number	N	Nb	O	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units

## ARSENIC AND ANTIMONY IN STEEL

# = Class, where 1 = CRM and 2 = RM analysis listed in mass % except \* which is mg/kg

#	Number	As	Sb	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Sn	Ti
2	CZ CM-2B	0.12	0.020	0.247	0.894	0.082	0.0114	1.95	0.99	1.20	1.53	0.046	.	0.45	0.33	0.091	0.342
1	12X 12749X	0.081	.	0.176	1.41	0.023	0.066	0.48	0.253	0.47	0.453	0.202	.	0.426	0.195	0.018	0.0178
1	12X 120	0.065	0.031	0.60	0.40	(0.049)	0.026	0.34	0.10	0.085	0.20	0.033	.	.	.	0.008	.
1	12X 15266V	0.0640	.	0.455	1.240	0.0344	0.0258	0.674	0.226	1.317	3.49	0.526	.	0.286	0.298	0.0082	.
1	12X 350C	0.057	.	0.159	0.758	0.0296	0.040	0.467	0.196	0.160	0.335	0.290	.	0.030	0.147	0.0382	0.076
1	IRSID 1656	0.055	.	0.477	0.730	0.027	0.013	0.277	.	(0.048)	(0.017)	(0.002)	.	.	(0.007)	.	.
1	12X 355C	0.0331	0.0796	0.159	0.508	0.0214	0.0241	0.494	0.657	0.0710	0.113	0.1104	.	0.0495	0.1010	0.0564	0.153
1	12X 354B	0.023	.	0.252	5.03	0.0478	0.0105	0.200	0.0679	0.082	0.0487	0.0150	.	0.0237	0.0328	0.0154	0.0248
1	BS 1762	0.025	(0.02)	0.363	2.04	0.032	0.037	0.38	0.133	1.16	0.929	0.049	.	0.064	0.347	0.079	0.096
1	ECRM 055-2D	0.0187	0.00376	0.5199	0.687	0.0102	0.0205	0.3094	0.2089	0.3121	0.3217	.	.	0.0257	0.0960	0.0162	0.00104
1	12X 357D	0.0127	0.018	0.312	0.219	0.0101	0.066	0.211	0.203	0.188	0.21	0.138	.	0.198	0.025	0.0145	0.074
1	BS 1030	0.0055	0.0024	0.331	0.682	0.0101	0.0299	0.261	0.269	0.078	0.124	0.0014	.	0.0069	0.0182	0.0114	0.0005
1	VS UG90	0.0044	0.0011	0.34	0.286	0.0079	0.012	0.221	0.200	0.265	0.261	0.037	0.032	.	0.046	.	0.039
1	VS UG89	0.0043	0.0011	0.92	0.76	0.0085	0.01	0.385	0.373	0.51	0.420	0.01	0.007	.	0.044	.	0.012
1	VS UG92	0.0027	0.0005	0.69	0.79	0.05	0.0029	1.98	0.111	0.155	0.200	0.091	0.08	.	0.119	.	0.022
1	IRSID 1670	0.0018	.	0.0011	0.3981	0.0128	0.0075	0.0046	0.0134	0.0142	0.0174	0.0479	.	0.0018	0.0009	0.0017	0.0078
1	VS UG88	0.0007	0.0003	0.62	1.26	0.0026	0.0043	1.22	0.171	0.52	0.474	0.01	0.009	.	0.104	.	0.107
1	VS UG91	0.0004	0.00009	0.49	.	0.0038	0.0021	2.23	0.057	0.039	0.064	0.048	0.048	.	0.058	.	0.038
1	SS 458/2	.	0.089	0.198	0.479	0.0281	0.0314	0.504	.	.	.	0.055	0.053	0.198	.	.	.
1	SS 457/2	.	0.050	0.307	0.327	0.0098	0.0448	0.105	.	.	.	0.088	0.084	0.0217	.	.	.

Number	B	Bi	Ca*	Ce*	Mg*	N	Nb	O*	Pb	Se	Ta	V	W	Zn	Zr	Units
CZ CM-2B	0.0010	.	.	.	.	0.0062	(0.58)	.	0.087	.	.	0.109	0.22	.	0.013	~39 mm Ø x ~25 mm
12X 12749X	.	.	.	.	.	.	.	.	0.016	.	.	0.068	0.036	.	.	~40 mm Ø x ~15 mm
12X 120	.	.	.	.	.	0.0115	.	.	0.077	.	.	.	.	.	.	40 mm Ø x 40 mm
12X 15266V	.	.	.	.	.	.	1.438	.	.	.	0.116	0.106	.	.	.	~40 mm Ø x ~15 mm
12X 350C	.	.	.	.	.	.	.	.	.	.	.	0.0115	0.260	.	.	~40 mm Ø x ~15 mm
IRSID 1656	.	.	.	.	.	.	.	.	.	.	.	(0.002)	.	.	.	40 mm Ø x 35 mm
12X 355C	(0.0012)	.	.	.	.	0.0023	0.023	.	.	0.0395	.	0.1265	0.037	.	0.0192	~40 mm Ø x ~15 mm
12X 354B	.	.	.	.	.	0.0027	0.0802	.	.	.	.	0.0204	0.0248	.	.	~40 mm Ø x ~15 mm
BS 1762	0.0048	.	(20)	.	(3)	0.017	0.074	64	(0.011)	Fe:93.9	(0.03)	0.193	0.029	(0.01)	(0.01)	37 mm Ø x 25 mm 17025
ECRM 055-2D	.	.	.	.	.	0.01069	.	.	.	.	.	0.00245	0.0166	.	.	38 mm Ø x 25 or 30 mm
12X 357D	0.0036	0.0024	.	.	.	0.011	.	0.040	0.0057	.	.	0.127	0.0213	.	0.0049	~40 mm Ø x ~15 mm
BS 1030	0.0003	.	12	.	(2)	0.0107	(0.0004)	50	0.0005	.	(0.001)	0.031	0.0012	last	(0.0002)	38 mm Ø x ~7 mm 17025
VS UG90	.	.	.	.	.	0.015	.	.	.	.	.	.	.	.	.	~47 mm Ø x ~30 mm
VS UG89	.	.	.	.	.	0.017	0.0043	.	0.0003	.	.	0.021	.	.	.	~47 mm Ø x ~30 mm
VS UG92	.	.	.	.	.	0.016	0.034	.	0.00017	.	.	0.024	.	.	.	~47 mm Ø x ~30 mm
IRSID 1670	0.0007	.	.	(2)	.	0.0016	(0.0003)	.	.	.	.	(0.0005)	.	.	.	37 mm Ø x 30 mm
VS UG88	.	.	.	.	.	0.020	0.059	.	0.00015	.	.	0.117	.	.	.	~47 mm Ø x ~30 mm
VS UG91	.	.	.	.	.	0.010	0.097	.	0.00006	.	.	0.049	.	.	.	~47 mm Ø x ~30 mm
SS 458/2	0.0069	.	.	.	.	0.0510	.	0.0140	.	.	.	0.105	.	.	(0.064)	38 mm Ø x 19 mm
SS 457/2	0.0046	.	.	.	.	0.0174	.	0.0098	.	.	.	0.153	.	.	0.025	38 mm Ø x 19 mm

## RM

## BISMUTH STEEL

Number	Bi	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	N
BS 4140A	0.105	0.40	0.84	0.021	0.076	0.21	0.15	0.15	0.97	0.016	0.005	0.010	0.16	0.0098
BS 53MOD	0.102	1.01	0.36	0.011	0.012	0.26	0.070	0.072	1.37	0.019	0.004	0.007	0.024	0.0086
BS 4140B	0.087	0.43	0.76	0.027	0.037	0.20	0.006	0.012	0.84	0.036	(0.002)	0.005	0.16	0.0064
BS 4150MOD	0.070	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.012	0.005	0.012	0.21	0.0087

Number	Ca	O	Pb	Sn	Ti	V	Units
BS 4140A	(0.0003)	(0.0025)	(0.001)	0.011	(0.003)	0.004	38 mm Ø x ~7 tp 19+ mm
BS 53MOD	(0.001)	(0.002)	0.0005	0.008	.	0.005	38 mm Ø x ~7 or 19+ mm
BS 4140B	(0.0002)	(0.002)	0.004	(0.002)	0.003	0.005	38 mm Ø x ~12 mm
BS 4150MOD	0.0010	(0.003)	0.0010	0.013	(0.002)	0.008	38 mm Ø x ~7 mm last

## CALCIUM IN STEEL

# = Class, where 1 = CRM and 2 = RM analysis listed in mass % except \* which is mg/kg

#	Number	Ca	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	V
1	<b>BS HiCal-1</b>	0.0140	0.271	1.00	(0.007)	0.0007	1.29	0.152	3.28	1.55	0.070	.	0.0024	0.379	.	0.0027
1	SS 115	0.0058	0.6224	0.682	0.0123	0.00093	0.2078	.	0.0196	0.0198	0.0527	.	.	.	0.0067	.
1	<b>BS 9325A</b>	0.0039	0.203	0.969	0.0079	0.0045	0.612	0.163	3.29	1.50	0.0056	.	0.0093	0.358	0.0076	(0.0024)
1	SS 116	0.0036	0.617	0.6756	0.0092	0.00176	0.201	.	0.0155	0.0141	0.0587	.	.	.	0.0069	.
1	<b>BS 1020</b>	0.0022	0.210	0.568	0.0058	0.0249	0.250	0.184	0.059	0.109	0.0006	.	0.0070	0.018	0.0109	0.0363
2	HRT FE2009-N	0.0020	0.12	0.55	0.010	0.003	0.32	0.08	0.25	2.56	0.030	.	.	1.02	.	0.015
1	<b>BS 3941</b>	0.0011	0.407	0.802	0.016	0.023	0.257	0.053	0.018	0.069	0.0019	.	0.0042	0.0061	0.0069	0.0025
2	BS 4150MOD	0.0010	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.012	.	0.012	0.21	0.0087	0.008
1	<b>BS 4130</b>	0.0007	0.303	0.541	0.0105	0.0113	0.245	0.221	0.088	0.924	0.0242	.	0.0065	0.168	0.0072	0.0037
2	BS 4942	0.0006	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	(0.004)	.	0.010	0.54	0.0080	0.28
1	<b>BS PP20</b>	0.0003	0.382	1.41	0.018	0.0070	0.262	0.119	1.00	1.94	0.0132	.	0.0145	0.212	0.0080	0.066
1	IMZ 111	0.0003	0.106	0.31	0.010	0.039	0.55	0.036	0.23	0.072	0.017	0.007	.	0.084	0.0133	0.022
2	TL 1669	0.00017	0.00226	0.0955	0.0137	0.0100	0.0093	0.0217	0.0160	0.0246	0.03553 (tot)	.	0.0019	0.0011	0.0024	(0.0006)

Number	As	B	Bi	Nb	O	Pb	Sb	Sn	Ti	W	Zr	Other
<b>BS HiCal-1</b>	0.0022	(0.0001)	.	(0.002)	.	(0.0005)	.	(0.0002)	0.0037	(0.0009)	(0.0008)	~38 mm Ø x ~30 mm <b>17025</b>
SS 115	.	.	.	.	.	.	.	.	0.0027	.	.	38 mm Ø x 19 mm
<b>BS 9325A</b>	0.0024	(0.0001)	.	0.0017	.	(0.0003)	Fe: 92.8	(0.0003)	0.0030	0.024	(0.001)	~40 mm Ø x ~30 mm <b>17025</b>
SS 116	.	.	.	.	.	0.00012	.	.	0.00171	.	.	44 mm Ø x 19 mm
<b>BS 1020</b>	0.0074	(0.0001)	.	(0.0003)	0.0046	(0.0002)	(0.0018)	0.0090	(0.0005)	(0.0004)	(0.0005)	44 mm Ø x ~7 or 19+ mm <b>17025</b>
HRT FE2009-N	.	.	.	.	.	.	.	.	.	.	Zn: 0.004	40 mm Ø x 40 mm
<b>BS 3941</b>	0.0036	(0.0001)	.	0.033	0.0055	0.0010	0.0005	0.0019	0.0017	(0.0004)	(0.0003)	41 mm Ø x ~7 - 19 mm <b>17025</b> last
BS 4150MOD	0.005	.	0.070	(0.003)	0.0010	0.0010	.	0.013	(0.002)	.	.	38 mm Ø x ~7 or 19 mm last
<b>BS 4130</b>	0.0048	(0.0002)	.	0.0015	0.0015	(0.00003)	(0.0021)	0.0099	0.0009	0.0011	Mg:0.0002	38 mm Ø x ~7 or 19+ mm <b>17025</b>
BS 4942	0.005	.	.	.	(0.0021)	.	.	0.014	.	.	.	38 mm Ø x ~7 or 19+ mm last
<b>BS PP20</b>	0.0049	0.00011	.	0.0048	(0.0010)	.	0.0013	0.0069	0.0007	0.0058	.	38 mm Ø x ~7 or 19+ mm <b>17025</b>
IMZ 111	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
TL 1669	0.0017	0.00038	.	0.00046	.	0.00013	0.00049	0.0071	0.0504	.	(0.00021)	38 mm Ø x 25 mm Zn: 2.7*

## CRM Al, Ca, AND N IN LOW ALLOY STEEL

Number	Al	Ca	N	Units
IMZ 133	.	.	<b>0.0360</b>	40 mm Ø x 40 mm
IMZ 131	0.0043	.	<b>0.0333</b>	40 mm Ø x 40 mm
IMZ 135	0.0274	0.0008	<b>0.0238</b>	40 mm Ø x 40 mm
IMZ 169	0.075	.	<b>0.0193</b>	40 mm Ø x 40 mm
IMZ 141	0.0071	.	<b>0.0154</b>	40 mm Ø x 40 mm
IMZ 130	0.0046	0.0024	<b>0.0153</b>	40 mm Ø x 40 mm
IMZ 139	(0.029)	0.0031	<b>0.0113</b>	40 mm Ø x 40 mm
IMZ 132	0.0021	0.0002	<b>0.0097</b>	40 mm Ø x 40 mm
IMZ 137	0.0017	0.00025	<b>0.0083</b>	40 mm Ø x 40 mm
IMZ 140	0.0307	0.0015	<b>0.0083</b>	40 mm Ø x 40 mm
IMZ 138	0.0022	.	<b>0.0063</b>	40 mm Ø x 40 mm
IMZ 134	0.0124	0.0005	.	40 mm Ø x 40 mm
IMZ 136	0.0034	0.00031	.	40 mm Ø x 40 mm

## C-Mo and Cr-Mo STEEL XRF SET

# = class, where 1 = CRM ISO 17025 and 2 = RM, Set Part Number: BS MOLY-5 AVAILABLE INDIVIDUALLY ~7 mm discs

#	Grade	Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	N	Sn	V
2	C-.5Mo	4419	BS 3952	0.208	0.546	0.011	0.021	0.264	0.202	0.112	0.105	0.519	0.048	.	(0.0005)	.	.
1	1.25Cr-.5Mo	F-11	<b>BS 45B</b>	0.140	0.502	0.0068	0.017	0.583	0.101	0.136	1.14	0.60	0.030	0.0090	0.0066	0.0069	0.0083
1	2.25Cr-1Mo	F-22	<b>BS 46B</b>	0.126	0.472	0.0087	0.0187	0.219	0.128	0.081	2.28	1.00	0.020	0.0074	0.0100	0.0073	0.0073
2	5Cr-.5Mo	F-5	BS 47A	0.130	0.44	0.017	0.015	0.27	0.11	0.12	4.22	0.47	0.015	0.011	0.018	0.008	0.016
1	9Cr-1Mo	F-9	<b>BS 48B</b>	0.110	0.365	0.0228	0.0068	0.75	0.070	0.165	8.78	0.949	0.0157	0.0165	0.0088	0.0049	0.033

## CRM EPMA SETS

available in sets only, as grouped 4x10x15mm

Number	Cr	Number	Ni
NMIJ 1001-a	5.00	NMIJ 1006-a	5.04
NMIJ 1002-a	14.96	NMIJ 1007-a	10.05
NMIJ 1003-a	19.87	NMIJ 1008-a	20.02
NMIJ 1004-a	29.84	NMIJ 1009-a	39.92
NMIJ 1005-a	39.69	NMIJ 1010-a	60.07

## Cr-Mo STEEL (Cr &gt; 1, Mo &gt; 0.1)

# = Class, where 1 = CRM and 2 = RM \* Provisional Analysis

#	Number	Cr	Mo	C	Mn	P	S	Si	Cu	Ni	Al	As	Co	N	Sn	V
1	BS 48B	8.78	0.949	0.110	0.36	0.0228	0.0068	0.75	0.070	0.165	0.0157	0.0048	0.0165	0.0088	0.0049	0.033
1	BS 9905A	8.75	0.95	0.113	0.465	0.0133	0.0040	0.34	0.091	0.152	0.0186	0.0065	0.0136	0.034	0.0060	0.216
1	13X 90901A	8.43	0.905	0.102	0.447	0.0148	0.0009	0.429	0.039	0.249	0.021	.	.	0.0472	0.0020	0.208
2	HRT FE2012-H	5.13	2.78	0.37	0.41	0.019	0.002	0.42	0.07	0.20	.	.	.	.	.	0.42
1	BS H-13A	5.11	1.32	0.391	0.445	0.0187	(0.003)	1.13	0.083	0.139	(0.03)	0.0050	0.033	0.034	(0.005)	0.92
2	BS 47B	4.78	0.45	0.122	0.39	0.014	0.022	0.22	0.12	0.105	0.018	0.004	.	0.023	0.006	0.004
1	IARM 37C	4.34	0.500	0.096	0.408	0.014	(0.004)	0.31	0.121	0.148	(0.010)	(0.009)	0.015	0.008	0.009	0.017
2	BS 47A	4.22	0.47	0.130	0.44	0.017	0.015	0.27	0.11	0.12	0.015	.	0.011	0.018	0.008	0.016
1	12X 40CDV12A	3.29	0.946	0.401	0.604	0.0060	0.0013	0.250	0.0978	0.1062	0.0208	0.0040	0.0197	0.0155	0.0049	0.198
1	SRM 1772	3.10	1.39	0.477	0.61	0.008	0.0031	0.264	0.083	0.105	.	.	.	.	.	0.236
1	SS 407/2	3.03	0.83	0.490	0.195	0.038	0.0105	0.66	0.397	0.527	0.040	.	0.0068	(0.011)	.	0.19
1	IMZ 160	2.64	0.98	0.077	0.38	0.023	0.004	0.34	0.42	0.30	0.031	.	.	.	.	0.10
1	IMZ 159	2.64	0.98	0.075	0.39	0.022	0.005	0.33	0.41	0.31	0.024	.	.	.	.	0.10
2	HRT FE2009-N	2.56	1.02	0.12	0.55	0.010	0.003	0.32	0.08	0.25	0.030	.	.	.	.	0.015
1	IARM 36C	2.43	0.98	0.14	0.49	0.009	0.014	0.25	0.142	0.085	(0.017)	(0.005)	(0.008)	0.008	(0.008)	0.0061
1	IARM 196A	2.35	0.129	1.08	2.40	0.040	0.014	0.35	0.25	0.61	0.015	0.025	0.013	0.0084	0.033	0.157
1	SRM 1270	2.34	0.956	0.077	0.626	0.0065	0.0065	0.247	0.114	0.174	.	.	0.038	.	.	0.013
1	BS 46B	2.28	1.00	0.126	0.472	0.0087	0.0187	0.219	0.128	0.081	0.020	0.0041	0.0074	0.0100	0.0073	0.0073
1	IMZ 169	2.20	1.03	0.099	0.54	0.015	0.0155	0.35	0.128	0.073	0.075	.	0.012	0.0193	0.062	(0.016)
1	ECRM 190-1D	2.18	0.410	0.395	1.28	0.0112	0.0044	0.278	.	0.934	.	.	0.034	.	.	.
1	BS PP20	1.94	0.212	0.382	1.41	0.018	0.0070	0.262	0.119	1.00	0.0132	0.0049	0.0145	0.0080	0.0069	0.066
1	BS 55G	1.79	0.421	0.386	0.853	0.010	0.0026	0.58	0.106	0.131	0.0123	0.0062	0.0093	0.0079	0.0074	0.0056
1	IRSID 1749	1.734	0.257	0.411	0.733	0.0104	0.0157	0.193	0.188	0.190	1.034	0.0134	0.0141	0.0066	0.0148	(0.0036)
1	ECRM 129-3D	1.702	0.206	0.3684	0.371	0.0110	0.0165	0.2087	0.0804	1.022	1.016	0.0049	0.0148	0.0046	0.0067	.
1	TL 1100	1.664	0.3349	0.3487	0.6284	0.0124	0.0049	0.2839	0.1767	3.727	0.0374	.	0.0283	0.0116	0.0083	.
1	ECRM 195-1D	1.56	0.77	0.757	0.571	0.017	0.012	0.467	0.036	0.33	.	.	.	0.010	.	0.31
1	SRM 1286	1.53	0.344	0.196	0.152	0.008	0.017	0.130	0.043	2.81	0.109	0.019	0.010	0.012	0.012	0.0057
2	BS 68B	1.51	0.309	0.39	0.52	0.010	0.020	0.26	0.163	0.165	1.08	.	0.016	0.0073	0.010	0.007
1	BS 68E	1.49	0.322	0.406	0.560	0.005	0.0004	0.296	0.134	0.147	1.09	(0.003)	0.007	0.0030	0.0097	0.0010
1	12X 24065A	1.412	0.1716	0.370	0.502	0.0129	0.0044	0.218	0.216	0.271	1.035	0.0074	.	0.0076	0.0120	0.0040
2	BS 58E	1.40	0.110	0.100	0.63	0.009	0.002	0.29	0.154	3.22	0.029	0.003	0.013	0.0033	0.003	0.006
1	12X 15CDV6A	1.397	0.875	0.171	0.839	0.0056	0.0086	0.152	0.0231	0.044	0.019	0.0041	.	0.0069	0.0011	0.242
1	IARM 35L	1.35	0.607	0.119	0.535	0.007	0.014	0.679	0.123	0.071	0.017	0.0045	0.0070	0.0072	0.0088	0.0037
1	SS 112	1.236	0.190	0.394	0.436	0.0043	0.0026	0.289	0.149	1.461	0.0148	0.0021	0.0175	0.0024	0.0086	.
1	12X 43400A	1.181	0.223	0.422	0.592	0.0164	0.0284	0.259	0.177	1.378	0.013	0.0084	.	0.0089	0.007	.
1	BS 45B	1.14	0.60	0.140	0.502	0.0068	0.017	0.583	0.101	0.136	0.030	0.0066	0.0090	0.0066	0.0069	0.0083
1	IRSID 1745	1.130	0.222	0.295	0.850	0.0077	0.081	0.220	0.202	0.188	0.0202	0.0262	.	0.0058	0.0134	(0.004)
1	12X 11572A	1.107	0.499	0.111	0.498	0.0069	0.0025	0.649	0.0576	0.0977	0.0290	0.0030	.	0.0058	0.0049	.
1	12X 14072A	1.061	0.573	0.430	0.680	0.0151	0.0061	0.322	0.203	0.136	0.0039	.	0.0098	0.0103	(0.011)	0.301
2	BS 1962	1.05	0.229	0.41	0.94	0.007	0.011	0.242	0.224	0.16	0.018	0.007	0.008	0.0095	0.010	0.004
1	IPT 501	1.05	0.210	0.277	0.723	0.016	0.030	0.208	0.083	0.063	0.034	.	0.008	0.0076	0.008	.
1	IARM 299A	1.03	0.99	0.469	0.70	0.008	0.002	0.22	0.100	0.57	0.092	0.003	0.0054	0.0028	0.0055	0.120
2	BS 4150MOD	1.01	0.21	0.47	0.90	0.024	0.079	0.21	0.19	0.15	0.012	0.005	0.012	0.0087	0.013	0.008

Number	B	Ca	Nb	O	Pb	Sb	Ta	Ti	W	Zr	Units
BS 48B	(0.0002)	(0.003)	(0.001)	0.0022	(0.0002)	(0.001)	.	0.0031	0.026	(0.002)	38 mm Ø x -7 or 19+ mm 17025 Fe: 88.7
BS 9905A	(0.0005)	(0.0002)	0.074	0.0024	(0.002)	(0.003)	(0.01)	0.0023	0.0024	(0.002)	38 mm Ø x -7 or 19+ mm 17025 Fe: 88.9
13X 90901A	.	.	0.070	.	.	.	.	(0.0025)	0.009	.	-40 mm Ø x -15 mm
HRT FE2012-H	.	.	(0.007)	.	.	.	.	.	.	.	40 mm Ø x 20 mm
BS H-13A	(0.0007)	(0.0006)	0.0052	(0.016)	(0.0004)	(0.002)	.	(0.03)	0.100	(0.002)	38 mm Ø x -7 or 19+ mm 17025 Fe: 90.2
BS 47B	.	.	.	(0.004)	.	.	.	.	.	.	38 mm Ø x -7 or 19+ mm
IARM 37C	.	.	(0.004)	.	.	.	.	(0.0025)	(0.012)	.	31 mm Ø x 2 or 18 mm
BS 47A	.	.	0.002	(0.003)	.	.	.	0.003	.	.	38 mm Ø x -7 or 19+ mm
12X 40CDV12A	.	.	.	.	.	.	.	.	.	.	38 mm Ø x -15 mm
SRM 1772	.	.	.	.	.	.	.	.	.	.	34 mm Ø x 19 mm
SS 407/2	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
IMZ 160	.	.	.	.	.	.	.	.	0.26	.	40 mm Ø x 40 mm
IMZ 159	.	.	.	.	.	.	.	.	0.26	.	40 mm Ø x 40 mm
HRT FE2009-N	.	0.0020	.	.	.	.	.	.	.	Zn: 0.004	40 mm Ø x 40 mm
IARM 36C	.	.	.	.	.	.	.	.	.	.	31 mm Ø x 2 or 18 mm
IARM 196A	0.0017	0.0002	0.087	0.0021	0.001	0.006	.	0.014	0.189	0.006	31 mm Ø x 18 mm
SRM 1270	.	.	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
BS 46B	(0.0006)	0.0009	(0.003)	0.0026	(0.001)	(0.002)	.	(0.001)	0.0008	(0.002)	38 mm Ø x -7 or 19+ mm 17025 Fe: 95.7
IMZ 169	.	.	(0.0045)	.	(0.001)	.	.	0.001	.	.	40 mm Ø x 40 mm
ECRM 190-1D	.	.	.	.	.	.	.	.	.	.	35 mm x 35 mm x 30 mm
BS PP20	0.00011	0.0003	0.0048	(0.0010)	.	0.0013	.	0.0007	0.0058	.	38 mm Ø x -7 or 19+ mm 17025
BS 55G	(0.0003)	0.0016	<0.01	0.0015	<0.01	0.0026	.	0.0044	(0.029)	<0.01	38 mm Ø x -7 or 19+ mm 17025 Fe: 95.6
IRSID 1749	.	(0.0002)	(0.0005)	0.0002	(0.0002)	0.0018	.	0.0031	(0.0030)	(0.0003)	41 mm Ø x 25 mm Mg: 9 ppm
ECRM 129-3D	.	.	.	.	.	0.00059	.	0.0030	.	.	39 mm Ø x 25 mm
TL 1100	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 20 mm
ECRM 195-1D	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 28 to 35 mm
SRM 1286	(0.006)	.	(0.012)	.	(0.0002)	.	.	0.040	(0.013)	(0.021)	32 mm Ø x 19 mm
BS 68B	.	.	.	.	.	.	.	0.005	.	.	41 mm Ø x 15-19 mm last
BS 68E	0.0002	(0.0003)	(0.002)	0.0011	(0.0002)	0.0024	.	0.0012	(0.002)	.	38 mm Ø x -7 or 19+ mm Mg:0.0004 17025
12X 24065A	.	.	.	.	.	.	.	0.0028	.	Zn:0.0034	-40 mm Ø x -15 mm
BS 58E	(0.0002)	(0.0002)	.	0.0008	.	.	.	(0.002)	.	.	38 mm Ø x -7 or 19+ mm
12X 15CDV6A	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
IARM 35L	0.00044	.	(0.0026)	.	.	.	.	(0.0015)	(0.004)	.	31 mm Ø x 2 mm
SS 112	0.0007	.	0.0065	.	.	.	.	0.0100	.	.	44 mm Ø x 19 mm
12X 43400A	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm Zn: 0.0027
BS 45B	(0.0003)	0.0008	(0.002)	0.0015	(0.15)	(0.003)	.	0.0024	(0.0038)	(0.0009)	38 mm Ø x -7 or 19+ mm 17025 Fe: 96.7
IRSID 1745	.	.	.	.	.	.	.	(0.003)	.	.	48 mm Ø x 30 mm
12X 11572A	.	.	.	.	.	.	.	.	.	Zn:0.0009	38 mm Ø x -15 mm
12X 14072A	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -15 mm
BS 1962	.	.	.	.	(0.001)	.	.	0.004	.	last	41 mm Ø x -7 mm 25(pre-17025)
IPT 501	.	.	.	.	.	.	.	0.0015	.	.	34 mm Ø x 18 mm
IARM 299A	0.0003	(0.001)	0.006	(0.002)	(0.001)	(0.002)	.	0.0038	0.010	(0.001)	31 mm Ø x 2 or 18 mm
BS 4150MOD	.	0.0010	.	(0.003)	0.0010	.	.	(0.002)	.	last	38 mm Ø x -7 mm Bi: 0.070



## LEADED STEEL

# = Class, where 1 = CRM and 2 = RM

OES regularly requires extension of preburn time

#	Number	Pb	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	N	Sn	V
1	BS 74C	0.328	0.077	0.94	0.082	0.294	(0.002)	0.005	0.011	0.019	(<0.002)	0.004	.	0.008	0.0040	(<0.002)	0.0016
1	14X 12144A	0.328	0.0800	1.227	0.0630	0.325	0.0093	0.0106	0.0162	0.0807	0.0034	0.0022	.	0.0089	0.0066	.	.
2	CZ CM-15C	0.29	0.075	1.13	0.063	0.32	0.006	0.141	0.072	0.052	.	.	(0.01)	0.021	.	.	.
1	BS 74D	0.282	0.072	1.00	0.073	0.28	(0.007)	0.0057	0.0115	0.0185	(0.008)	0.0047	0.0043	0.0063	0.0040	(0.0010)	0.0012
1	BS 75G	0.247	0.161	1.08	0.0085	0.114	0.011	0.0300	0.045	0.079	0.0016	0.0028	0.0031	0.0174	0.0030	0.0014	0.0005
2	BS 75F	0.202	0.165	1.05	0.009	0.116	0.004	0.030	0.044	0.080	0.002	.	.	0.018	.	.	.
1	BS 73C	0.21	0.206	0.86	0.0111	0.031	0.280	0.025	0.56	0.574	0.028	0.0035	0.0028	0.180	0.0040	(0.002)	0.0031
1	IARM Fe86L20-18	0.20	0.175	0.794	0.009	0.015	0.29	0.242	0.458	0.53	0.025	0.0085	0.0085	0.203	0.0052	0.014	0.0016
1	IARM 182B	0.19	0.21	0.81	0.016	0.037	0.27	0.017	0.47	0.49	0.038	(0.003)	0.006	0.172	0.0040	0.0019	0.004
1	IARM 183C	0.18	0.079	1.06	0.078	0.31	0.004	0.016	0.019	0.055	0.0021	0.003	(0.002)	0.010	0.0049	0.003	0.002
2	BS 72B	0.174	0.497	0.87	0.029	0.029	0.26	0.21	0.169	0.985	0.020	(0.006)	0.012	0.187	0.0081	0.014	0.004
2	BS 73B	0.139	0.200	0.83	0.009	0.030	0.250	0.141	0.416	0.512	0.022	0.004	0.008	0.170	0.0113	0.008	(<0.002)
2	BS 70B	0.135	0.40	0.90	0.009	0.022	0.27	0.13	0.25	1.00	0.024	.	.	0.205	.	.	.
1	BS 70C	0.133	0.387	0.90	(0.009)	0.020	0.27	0.123	0.247	0.99	0.019	0.007	0.0086	0.202	0.0079	0.008	0.0026

Number	B	Ca	Nb	O	Sb	Ti	W	Zn	Grade	Units
BS 74C	.	.	(<0.005)	.	.	.	.	.	12L14	41 mm Ø x ~7 or 19+ mm
14X 12144A	.	.	.	.	.	.	.	.	.	-40 mm Ø x ~15 mm
CZ CM-15C	.	.	.	.	.	.	.	.	.	-39 mm Ø x 25 mm
BS 74D	0.0009	<0.001	(0.0018)	(0.028)	<0.05	(0.0007)	<0.005	Fe:98.2	12L14	41 mm Ø x ~7 or 19+ mm
BS 75G	(0.0002)	(0.0002)	(0.0003)	0.0155	.	(0.0004)	0.0004	.	11L17	41 mm Ø x ~7 or 19+ mm
BS 75F	.	.	.	.	.	.	.	.	11L17	40 mm Ø x ~7 or 19+ mm
BS 73C	(0.0002)	(0.0005)	(0.002)	0.0013	(0.002)	0.0024	(0.006)	.	86L20	38 mm Ø x ~7 or 19+ mm
IARM Fe86L20-18	CRM	.	.	.	.	.	.	.	86L20	38 mm Ø x ~2 or 19 mm
IARM 182B	(0.0003)	(0.0005)	(0.003)	(0.003)	(0.003)	(0.003)	(0.01)	(0.001)	86L20	31 mm Ø x 2 mm
IARM 183C	0.0011	.	0.0010	0.016	(0.001)	0.0009	(0.002)	0.001	12L14	31 mm Ø x 2 mm
BS 72B	.	.	(0.001)	.	.	(0.002)	.	.	41L50	37 mm Ø x ~7 or 19+ mm
BS 73B	.	.	.	.	.	.	.	.	86L20	41 mm Ø x ~12 or ~17 mm
BS 70B	.	.	.	.	.	.	.	.	41L40MOD	41 mm Ø x ~7 or 19+ mm
BS 70C	(0.0003)	.	<0.005	0.0020	(0.003)	0.0020	(0.0006)	.	41L40MOD	41 mm Ø x ~7 or 19+ mm

## RM LEADED AND BISMUTH STEEL XRF SET

Part Number: BS PB-BI-7

AVAILABLE INDIVIDUALLY

~7 mm discs

17025

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Bi	Pb	Sn	V	N
11L17	BS 75F	0.165	1.05	0.009	0.116	0.004	0.030	0.044	0.080	0.018	0.002	.	0.202	.	.	.
12L14	BS 74E	0.08	0.91	0.087	0.316	0.002	0.006	0.012	0.019	0.008	(0.002)	.	0.34	.	.	.
41L40	BS 70B	0.40	0.90	0.009	0.022	0.27	0.13	0.25	1.00	0.205	0.024	.	0.135	.	.	.
41L50	BS 72B	0.497	0.87	0.029	0.029	0.26	0.21	0.169	0.985	0.187	0.020	.	0.174	0.014	0.004	0.0081
4140 + Bi & S	BS 4140A	0.40	0.84	0.021	0.076	0.21	0.15	0.15	0.97	0.16	0.016	0.105	(0.001)	0.011	0.004	0.0098
4150 + Bi & S	BS 4150 MOD	0.47	0.90	0.024	0.079	0.21	0.19	0.15	1.01	0.21	0.012	0.070	0.0010	0.013	0.008	0.0087
8620 + Bi & S	BS 8620A	0.184	0.80	0.008	0.079	0.21	0.15	0.44	0.48	0.16	0.016	0.073	(0.001)	0.009	0.004	0.0107

## MANGANESE STEEL

14X:~40Øx~15-17mm BS:32Øx~15-17mm CZ:~39Øx25mm DSZU:39Øx20mm ECRM:35Øx25mm IMN:50-56Øx15mm NCS:36Øx36mm SS:48x42x12mm VS:~38Øx~18mm

#	Number	Mn	C	P	S	Si	Cu	Ni	Cr	Al	Mo	N	Nb	Sn	V	Other
1	DSZU C013	28.8	0.89	0.025	(0.002)	0.29	0.108	(0.20)	(0.14)	(8.6)	(0.44)	(0.002)	(0.46)	.	(0.1)	.
1	VS LG68	28.8	0.39	(0.02)	0.003	0.11	0.20	0.13	8.6	0.46	.	.	0.46	.	.	.
1	IMZ 199	28.74	0.90	0.022	(0.0006)	0.294	0.110	0.20	0.164	8.65	0.43	.	0.43	.	0.026	B:(0.001) Ti:(0.004)
1	IRSID 1833	22.57	0.605	0.0345	(0.0005)	0.193	0.030	0.0494	0.268	0.0025	0.0133	0.012	0.0026	0.0043	0.203	As, Co, Pb, and Ti **
1	14X MN1AL	22.08	0.597	0.053	0.0054	0.944	0.178	0.692	1.321	(0.23)	0.499	0.0585	0.096	0.0393	0.0226	Ta:(0.011) Ti: 0.0346
1	DSZU C012	20.9	0.39	0.021	0.0072	0.31	0.087	0.103	0.17	(2.9)	(0.03)	(0.013)	.	.	(1.14)	.
2	BS 17	19.59	0.63	0.047	0.007	0.21	0.075	0.03	1.46	(0.02)	0.46	.	.	(0.012)	(0.02)	~15mm height
2	BS 17A	19.38	0.588	0.043	0.005	0.22	0.135	0.060	1.37	0.052	0.52	0.038	0.06	0.012	0.016	Co: 0.013
1	NCS AH37335	18.70	1.30	0.048	0.007	0.457	0.021	0.593	2.00	(0.011)	0.249	0.024	0.077	Ce:0.011	0.201	Ti:0.006
1	VS LG69	18.6	0.45	0.033	0.0048	0.50	0.088	0.178	0.428	2.78	0.020	0.011	.	.	.	.
1	DSZU C011a	17.4	0.45	0.042	0.008	0.43	0.089	0.11	0.36	(2.8)	(0.014)	.	.	.	.	.
1	NCS AH37334	16.90	1.20	0.051	0.011	0.655	0.024	0.200	2.20	0.018	0.180	0.021	0.085	Ce:0.027	0.253	La:0.014 Ti: 0.125
1	IMZ 198	16.10	0.44	0.031	0.0090	0.423	0.104	0.058	0.30	2.80	(0.008)	.	.	.	.	Ti:(0.005)
1	VS LG66	16.1	0.44	0.031	0.010	0.41	0.104	0.059	0.30	2.6	.	.	.	.	.	.
1	DSZU C011	16.09	0.44	0.031	0.0093	0.41	0.105	0.058	0.30	(2.6)	(0.01)	(0.010)	.	.	.	.
2	CZ SP-2C	14.5	1.40	0.037	0.016	0.29	0.35	0.050	1.56	0.030	0.050	0.027	Co:0.044	0.037	0.051	Ti: 0.014 W: 0.033
1	DSZU C023	13.09	0.79	0.052	0.0062	0.291	0.111	3.15	0.313	(0.006)	(0.02)	(0.018)	(0.02)	.	(0.02)	B:(0.001) Ti:(0.004)
1	DSZU C022	12.89	1.15	0.087	0.0057	0.34	0.103	0.122	0.192	(0.007)	(0.03)	(0.013)	(0.01)	.	(0.03)	B:(0.001) Ti:(0.006)
1	NCS AH37333	12.46	1.23	0.061	0.009	0.428	0.017	3.34	1.72	0.022	0.951	0.024	0.108	Ce:0.029	0.085	La:0.017 Ti: 0.064
1	14X MN2S	12.3	0.80	0.024	0.0080	2.20	0.089	0.726	0.364	0.020	1.08	0.038	0.23	0.015	0.089	Ta:(0.006) Ti: 0.018
1	DSZU C010	12.25	1.20	0.082	0.0035	0.49	0.120	0.108	0.187	(0.006)	(0.01)	(0.017)	.	.	.	.
1	DSZU C021	11.23	1.32	0.035	0.010	0.105	0.32	0.36	0.62	(0.003)	0.096	(0.013)	(0.03)	.	0.124	B:(0.002) Ti:(0.005)
1	SS 493/3	11.15	0.819	0.12	0.009	0.861	0.017	3.24	0.259	0.035	1.04	0.025	.	.	0.025	.
1	14X MN3U	10.2	1.09	0.0239	0.015	1.11	0.135	0.387	0.599	0.045	0.343	0.025	0.398	0.0254	0.022	Ta: 0.010 Ti:(0.10)
2	BS 19A	8.76	1.57	0.092	0.009	1.46	0.51	1.48	3.75	0.057	1.97	0.039	0.040	0.037	0.10	Co: 0.014
1	DSZU C020	8.85	0.97	0.024	(0.015)	0.091	0.53	1.36	0.96	(0.004)	0.13	(0.020)	(0.02)	.	0.152	B:(0.002) Ti:(0.003)
1	14X MN5U	8.78	1.36	0.0552	0.0273	1.47	0.691	2.10	3.18	0.0257	1.93	0.0231	0.102	0.0228	0.0490	Ti: 0.93
1	SS 492/3	8.33	1.18	0.0318	0.0093	0.299	0.0211	4.17	1.076	0.131	1.318	0.0225	.	.	(0.04)	Co: 0.0048
1	14X MN5V	8.02	1.42	0.057	0.0207	2.27	0.551	3.09	3.28	0.145	2.26	0.0146	0.041	0.0278	0.0810	Ta:(0.004) Ti: 0.51
2	CZ CM-9B	2.27	0.17	(0.008)	(0.010)	0.89	0.040	0.023	1.36	0.049	(0.002)	.	(0.06)	(0.003)	(0.006)	+7 informational

\*\* IRSID 1833 also contains As: 0.0034, Co: 0.0089, Pb: 0.00007, and Ti: 0.0011. Sample size 35 mm Ø x 25 mm.

## CRM MANGANESE STEEL SET

AVAILABLE IN SET/6 ONLY



**CRM**      **Co/Fe/V MAGNETIC ALLOY PERMENDUR 2V**      analysis listed in mass %

Number	Co	Fe	V	Mn	P	S	Si	Ni	N	Nb	O	Zr	Units
IARM 326A	48.4	49.6	1.94	0.003	0.0013	0.0011	0.029	0.037	0.0004	0.038	0.0082	0.002	31 mm Ø x 2 mm

**RESULFURIZED STEEL**

# = Class, where 1 = CRM and 2 = RM      **OES regularly requires extension of preburn time to analyze correctly**

#	Number	S	C	Mn	P	Si	Cu	Ni	Cr	Al	Co	Mo	N	Sn	Ti	V
1	IMZ 123	0.38	0.25	1.57	0.030	0.23	0.093	0.057	0.16	0.032	.	.	0.0171	(0.007)	.	.
1	ECRM 085-1D	0.336	0.067	0.977	0.062	0.008	0.291	.	0.19	.	.	.	0.0031	(0.0010)	(<0.0010)	0.0021
1	<b>BS 66L</b>	0.315	0.065	0.844	0.061	0.002	0.007	0.015	0.026	0.0008	0.0035	0.0012	0.0097	0.0054	.	0.0006
1	14X 12130A	0.305	0.0871	1.219	0.061	0.022	0.0201	0.0345	0.0505	0.0024	.	0.0102	0.0070	0.0084	0.0016	(0.0037)
1	IARM 199C	0.281	0.469	1.55	0.0155	0.21	0.193	0.085	0.190	0.0019	0.007	0.0293	0.0070	0.0084	0.0016	(0.0037)
1	IMZ 124	0.28	0.10	0.60	0.082	(0.019)	0.060	0.046	0.11	0.005	.	.	0.0059	0.009	.	.
1	<b>BS 1144A</b>	0.271	0.468	1.43	0.0108	0.214	0.147	0.063	0.076	0.0020	0.0064	0.0154	0.0095	0.0079	(0.0008)	0.0015
1	<b>BS 1144</b>	0.243	0.483	1.55	0.022	0.262	0.462	0.097	0.193	(0.002)	0.011	0.017	0.0093	0.0113	0.002	0.0039
1	14X MSFM 4A	0.224	0.226	1.141	0.0386	0.469	0.429	6.22	1.69	(0.007)	0.0253	0.974	0.0220	0.0141	.	0.0151
1	IMZ 122	0.21	0.27	1.33	0.073	0.43	0.25	0.25	0.19	(0.027)	.	.	0.0110	0.12	.	.
1	14X 606M36TA	0.196	0.378	1.574	0.0159	0.167	0.179	0.0931	0.163	0.0071	.	0.272	0.0096	0.0103	.	.
1	14X 11390A	0.190	0.420	1.040	0.0342	0.198	0.0395	0.0239	0.0609	0.0026	.	0.0067	0.0042	0.0022	.	.
1	ECRM 058-2D	0.1712	0.424	1.186	0.0098	0.1080	0.261	0.199	0.1211	.	.	0.0589	0.0107	.	.	.
1	14X MSFM3G	0.147	0.438	1.809	0.0297	0.292	0.205	0.161	0.454	(0.18)	0.0494	0.390	0.0206	0.0378	.	0.0199
1	IARM 29E	0.121	0.193	1.19	0.0157	0.239	0.253	0.082	0.105	0.0032	0.008	0.0269	0.0093	0.0109	0.0014	0.0255
1	14X 11170A	0.120	0.154	1.129	0.0133	0.151	0.1101	0.0877	0.1126	0.0023	.	0.0317	0.0112	0.0110	.	.
2	BS 65C	0.115	0.150	1.19	0.007	0.24	0.24	0.063	0.066	(0.002)	(0.007)	0.012	0.0084	.	.	0.002
2	BS 66B	0.112	0.418	1.56	0.018	0.017	0.028	0.032	0.093	(0.001)	0.005	0.019	0.0056	0.0016	(0.001)	0.0014
1	IARM 348A	0.102	0.384	1.46	0.0121	0.270	0.230	0.081	0.123	(0.002)	(0.010)	0.026	(0.010)	0.0112	0.0015	0.0029
1	IARM 307A	0.096	0.163	1.44	0.0113	0.281	0.190	0.197	0.104	0.032	(0.010)	0.045	0.0108	0.0090	0.0015	(0.0028)
1	<b>BS 3993</b>	0.094	0.152	1.16	0.012	0.260	0.111	0.045	0.072	0.002	0.006	0.010	0.0071	0.006	(0.0008)	0.002
1	IMZ 121	0.097	0.39	1.18	0.057	(0.056)	0.032	0.029	0.036	0.016	.	.	0.0125	0.059	.	.
2	BS 52D	0.088	0.436	0.97	0.068	0.18	0.060	0.18	0.16	0.028	0.012	0.09	0.0025	0.004	(0.004)	0.002
1	12X 15253T	0.0821	0.222	1.208	0.0900	0.347	0.266	0.991	2.022	0.0242	0.265	1.039	0.029	0.309	.	0.276
2	BS 4150MOD	0.079	0.47	0.90	0.024	0.21	0.19	0.15	1.01	0.012	0.012	0.21	0.0087	0.013	(0.002)	0.008
2	BS 42A	0.078	0.52	1.08	0.012	0.258	0.285	0.147	0.80	0.025	(0.007)	0.195	0.008	.	.	0.004
1	12X 15217R	0.078	0.166	0.885	0.064	1.392	0.257	0.860	1.011	0.081	0.193	0.311	0.014	0.058	.	0.607
1	NM 307	0.073	1.03	0.52	0.073	0.22	.	.	1.19	.	.	.	.	.	.	.
2	<b>BS 42</b>	0.073	0.516	1.24	0.021	0.235	0.252	0.183	0.67	0.020	0.012	0.190	0.0080	0.012	(0.003)	0.003
1	12X 15255R	0.067	0.392	1.09	0.080	1.01	0.288	0.317	1.49	0.161	0.045	0.113	0.0058	0.106	0.052	0.491
1	KUT B2/2	0.064	0.065	1.22	0.087	(0.38)	0.32	1.49	.	0.10	.	1.06	.	.	(0.25)	0.87
1	<b>BS 4150MOD-A</b>	0.062	0.503	1.12	0.0172	0.253	0.192	0.095	0.799	0.0023	0.0070	0.170	0.0081	0.0090	0.0018	0.029
1	IMZ 125	(0.057)	0.029	0.95	(0.018)	0.15	0.044	0.023	0.18	(0.007)	.	.	.	0.002	.	.
1	KUT B12	0.048	0.43	0.76	0.028	0.34	0.41	1.62	1.32	0.007	0.011	0.21	.	0.032	0.011	0.026
1	KUT B4	0.043	0.55	1.07	0.047	1.72	0.49	.	.	.	.	.	.	.	.	.
1	IARM 381A	0.043	0.272	1.16	0.013	0.269	0.379	0.185	0.129	0.0023	0.011	0.0341	(0.014)	0.0137	(0.002)	0.0299
1	NM 304	0.033	0.19	0.29	0.093	0.082	.	(0.007)	.	.	.	.	.	.	.	.

  

Number	As	B	Bi	Ca	Nb	O	Pb	Sb	W	Zn	Zr	Units
IMZ 123	0.033	.	.	.	.	.	0.030	0.030	.	.	.	40 mm Ø x 40 mm
ECRM 085-1D	.	.	.	.	.	.	0.0010	0.0073	.	0.0025	.	38 mm Ø x 25 or 30 mm
<b>BS 66L</b>	0.0020	(<0.0003)	.	(<0.0010)	(0.0012)	.	0.0007	0.0021	(<0.0010)	.	.	44 mm Ø x -7 or 19+ mm <b>17025</b>
14X 12130A	0.0016	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
IARM 199C	0.0059	0.0012	0.003	(0.0011)	0.0016	0.0037	(0.001)	(0.003)	0.0023	(0.0006)	.	31 mm Ø x 2 or 18 mm
IMZ 124	0.004	.	.	.	.	.	(0.002)	0.002	.	.	.	40 mm Ø x 40 mm
<b>BS 1144A</b>	0.0052	(0.0003)	Fe:97.3	(0.0005)	(0.002)	0.0019	(0.0006)	(0.002)	(0.0009)	.	(0.0006)	38 mm Ø x -7 or 19+ mm <b>17025</b>
<b>BS 1144</b>	0.009	.	.	.	(0.004)	0.0016	(0.001)	.	(0.003)	.	last	38 mm Ø x -16 mm <b>17025</b>
14X MSFM 4A	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm
IMZ 122	0.007	.	.	.	.	.	(0.020)	0.019	.	.	.	40 mm Ø x 40 mm
14X 606M36TA	0.0085	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
14X 11390A	0.0028	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
ECRM 058-2D	0.0095	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 25 or 30 mm
14X MSFM3G	.	0.0043	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
IARM 29E	0.0085	0.0007	.	0.0012	0.0024	(0.005)	(0.001)	(0.003)	.	(0.004)	.	31 mm Ø x 2 or 18 mm
14X 11170A	0.0044	.	.	.	.	.	0.0011	.	.	.	.	-40 mm Ø x -15 mm
BS 65C	.	.	.	.	.	.	.	.	.	.	.	37 mm Ø x -7 or 19+ mm last
BS 66B	.	0.0003	.	.	.	.	.	.	.	.	.	41 mm Ø x -7 or 19+ mm
IARM 348A	(0.007)	(0.0013)	<0.02	0.0010	0.027	(0.003)	(0.002)	(0.003)	(0.009)	<0.003	(0.003)	31 mm Ø x 2 or 18 mm
IARM 307A	0.008	<0.005	<0.02	<0.0005	(0.002)	(0.003)	(0.002)	<0.004	(0.005)	<0.002	(0.002)	31 mm Ø x 2 or 18 mm
<b>BS 3993</b>	0.004	.	.	(0.0002)	.	(0.0030)	.	.	.	.	.	38 mm Ø x -7 or 19+ mm <b>25(pre-17025)</b>
IMZ 121	0.002	.	.	.	.	.	0.011	0.017	.	.	.	40 mm Ø x 40 mm
BS 52D	.	.	.	.	.	(0.002)	.	.	.	.	last	44 mm Ø x -7 to 19+ mm last
12X 15253T	0.0216	.	.	.	0.374	.	.	Ta:0.007	0.276	.	.	-40 mm Ø x -15 mm
BS 4150MOD	0.005	.	0.070	0.0010	.	(0.003)	0.0010	.	.	.	last	38 mm Ø x -7 mm
BS 42A	.	.	.	.	.	.	.	.	.	.	.	37 mm Ø x -7 or 19+ mm
12X 15217R	.	0.0044	.	.	0.102	.	.	.	0.100	.	.	-40 mm Ø x -15 mm
NM 307	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 25 mm
<b>BS 42</b>	(0.004)	.	.	.	(0.002)	.	.	.	(0.002)	.	.	44 mm Ø x -7 or 19+ mm <b>17025</b>
12X 15255R	.	.	.	.	0.203	.	Ta:0.034	.	0.143	.	(0.011)	-40 mm Ø x -15 mm
KUT B2/2	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 39 mm
<b>BS 4150MOD-A</b>	0.0038	(0.0004)	.	(0.0007)	(0.002)	0.0017	(0.0004)	(0.002)	0.0026	Fe:96.7	(0.0005)	38 mm Ø x -7 or 19+ mm <b>17025</b>
IMZ 125	0.065	.	.	.	.	.	.	0.014	.	.	.	40 mm Ø x 40 mm
KUT B12	0.011	0.0035	.	.	0.022	.	.	.	.	.	(0.002)	30-35 mm Ø x 39 mm
KUT B4	.	.	.	.	.	.	.	.	.	.	0.09	30-35 mm Ø x 39 mm
IARM 381A	0.0055	.	.	.	0.0018	.	.	.	(0.003)	.	.	31 mm Ø x 2 or 18 mm
NM 304	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 25 mm

**RM**      **RESULFURIZED STEEL XRF SET**      Part Number: BS RESUL-4      AVAILABLE INDIVIDUALLY      -7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	Co	N	Sn	V	As
1117	BS 65C	0.150	1.19	0.007	0.115	0.24	0.24	0.063	0.066	0.012	(0.002)	(0.007)	0.0084	0.02	0.002	(0.008)
1140 + P	BS 52D	0.436	0.97	0.068												

## SILICON STEEL

# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Mo	N	Sn	Ti
2	CZ SST-4A	4.73	0.062	0.376	0.031	0.020	0.111	0.082	0.105	0.514	.	0.019	0.0058	0.025	0.035
2	CZ SST-3A	3.27	0.035	0.221	0.007	0.0093	0.096	0.061	0.043	0.009	.	0.036	0.0088	0.015	0.009
1	SRM 1218	(3.2)	0.0029	0.014	(0.002)	0.0011	0.003	(0.002)	0.006	0.005	.	(0.003)	.	.	(0.004)
1	SRM 1135	3.19	0.027	0.094	0.006	0.026	0.056	0.050	0.022	0.0028	.	0.014	.	0.004	.
2	CZ SST-2A	3.07	0.083	0.160	0.026	0.0089	0.205	0.066	0.138	0.010	.	0.054	0.0078	0.055	0.016
1	SRM 1134	2.889	0.0261	0.2751	0.0276	0.0095	0.0707	0.0375	0.0198	(0.329)	.	0.0087	.	0.0034	.
2	CZ SST-1A	2.57	0.072	0.062	0.041	0.0043	0.654	0.155	0.209	0.061	.	(0.002)	0.0059	0.110	0.004
1	VS UG91	2.23	0.49	.	0.0038	0.0021	0.057	0.039	0.064	0.048	0.048	.	0.058	0.010	0.038
1	12X 15251U	2.05	1.017	0.910	0.0253	0.0215	0.1194	0.896	0.612	0.1085	.	0.205	0.0031	0.0108	.
1	VS UG92	1.98	0.69	0.79	0.05	0.0029	0.111	0.155	0.200	0.091	0.08	0.119	0.016	.	0.022
1	KUT T4/1	1.97	0.17	0.23	0.012	0.041	0.16	0.077	0.24	.	.	.	.	.	(<0.005)
1	12X 15259Q	1.81	0.603	0.401	0.0401	0.0704	0.200	4.02	0.512	0.1488	.	0.407	0.0151	0.053	.
1	ECRM 196-2D	1.808	0.0060	0.364	0.00369	0.00065	0.0057	0.0401	0.0282	0.2167	.	0.0142	0.00178	0.00047	0.00253
1	VS UG4/5	1.80	0.56	1.26	(0.008)	(0.006)	0.098	0.68	0.17	0.010	.	0.087	.	.	0.17
1	NCS HS11751a	1.76	0.574	0.792	0.020	0.014	0.011	0.019	0.024	.	.	.	.	.	.
2	CZ LA-2E	1.725	0.081	0.111	0.060	0.044	0.577	2.015	0.149	0.357	.	0.652	0.0071	0.087	0.343
1	ECRM 186-1D	1.72	0.610	0.870	0.022	0.035	0.281	0.190	0.218	0.014	.	0.048	.	.	.
1	BS 300	1.68	0.410	0.721	0.0046	0.0006	0.118	1.867	0.803	0.099	.	0.370	0.0023	0.0053	0.0096
1	12X 44220A	1.662	0.417	0.874	0.0050	0.0009	0.031	1.89	0.846	0.029	.	0.401	0.0030	0.0019	.
3	CZ CM-2A	1.66	0.20	0.97	0.10	0.012	1.01	1.20	1.50	0.03	.	0.33	.	0.08	0.34
1	VS UG111	1.64	0.52	0.625	0.0028	0.0035	0.065	0.036	0.058	0.049	.	0.039	.	.	0.025
1	VS UG1/9	1.63	0.63	0.84	0.030	0.017	0.020	0.105	0.046	0.027	.	0.135	(0.002)	(0.002)	0.069
1	IARM 340A	1.63	0.414	0.755	0.011	0.001	0.103	1.80	0.84	0.062	.	0.39	0.0020	0.005	0.0098
1	IARM 342A	1.63	0.257	1.37	0.006	0.0051	0.110	1.76	0.38	0.019	.	0.42	0.0102	0.021	0.0028
1	VS UG4/10	1.61	0.695	0.834	0.031	0.0060	0.050	0.156	0.130	0.064	.	0.089	0.0192	.	0.0044
1	KUT B1/1	1.58	0.97	0.205	0.017	0.032	0.14	3.96	1.66	.	.	.	.	.	.
1	12X 15261X	1.513	0.546	0.483	0.090	0.0518	0.308	0.0985	0.496	1.648	.	1.594	.	0.0172	0.385
1	VS UG1/10	1.51	0.51	0.659	0.0053	0.0042	0.096	0.190	0.067	0.015	.	0.051	0.0164	0.0030	0.016
1	KUT A11/1	(1.46)	0.043	0.21	0.011	0.0137	0.047	0.04	0.02	0.02	.	1.20	.	0.002	0.17
1	VS UG4/6	1.25	0.59	1.23	(0.003)	0.0008	0.169	0.47	0.400	0.032	.	0.083	(<0.0005)	0.017	0.131
1	VS UG87	1.25	0.59	1.18	0.026	0.022	0.030	0.50	0.260	0.024	0.02	0.044	0.010	.	0.103
1	VS UG1/5	1.23	0.62	0.79	(0.02)	(0.03)	(0.01)	0.048	0.069	0.022	.	0.061	.	.	0.045
1	VS UG88	1.22	0.62	1.26	0.0026	0.0043	0.171	0.52	0.474	0.01	0.009	0.104	0.020	.	0.107
1	DSZU C046	1.21	0.785	0.257	0.025	0.0153	0.211	1.47	2.67	0.47	.	0.69	0.0099	0.0033	0.115
1	KUT A12	1.19	0.031	0.31	0.014	0.082	0.18	2.43	1.25	0.18	.	0.47	.	.	0.05
2	CZ CM-14A	1.15	0.523	1.58	0.051	0.028	0.30	1.14	1.13	0.063	.	0.395	0.0095	0.027	0.40
1	12X 15258P	1.01	0.392	1.23	0.067	0.032	0.109	0.497	0.631	0.087	.	0.361	.	0.071	0.100
1	SS 603/2	0.97	0.79	0.236	0.020	0.056	(0.05)	(0.03)	(0.04)	0.076	.	(0.004)	.	.	.
1	SS 405/2	0.947	0.044	0.903	0.0095	0.058	0.022	0.102	0.206	0.330	.	0.025	(0.011)	.	.
1	SS 113	0.931	0.837	1.207	0.0595	0.0294	0.179	0.0784	1.248	0.0151	.	0.056	0.0109	0.0067	0.0390
1	SS 604/2	0.75	0.199	1.91	0.016	0.072	(0.07)	(0.09)	(0.06)	0.008	.	(0.02)	.	.	.
#	Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Mo	N	Sn	Ti
Number	As	B	Ca	Co	Nb	O	Pb	Sb	Ta	V	W	Zr	Units		
CZ SST-4A	0.004	0.0006	.	0.012	.	.	0.008	(0.003)	.	0.031	0.026	(0.003)	~37 mm Ø x 25 mm	.	.
CZ SST-3A	(0.003)	0.0019	.	0.038	.	Zn:0.011	0.013	.	.	0.041	0.016	.	~37 mm Ø x 25 mm	.	.
SRM 1218	.	.	.	(0.002)	.	.	.	.	.	(<0.001)	.	(0.002)	32 mm Ø x 19 mm	.	.
SRM 1135	.	.	.	.	.	.	.	.	.	<0.01	.	.	31 mm Ø x 19 mm	.	.
CZ SST-2A	.	0.0089	.	0.022	.	Zn:0.011	0.015	0.008	.	0.024	0.019	0.017	~37 mm Ø x 25 mm	.	.
SRM 1134	.	.	.	.	.	.	.	.	.	.	.	.	31 mm Ø x 19 mm	.	.
CZ SST-1A	(0.002)	0.0003	.	0.005	.	.	(0.002)	(0.002)	.	0.006	.	.	~37 mm Ø x 25 mm	.	.
VS UG91	0.0004	.	.	.	0.097	.	0.00006	0.00009	.	0.049	.	.	~47 mm Ø x ~30 mm	.	.
12X 15251U	.	.	.	0.228	0.266	.	.	.	.	0.391	0.0393	.	~40 mm Ø x ~15 mm	.	.
VS UG92	0.0027	.	.	.	0.034	.	0.00017	0.0005	.	0.024	.	.	~47 mm Ø x ~30 mm	.	.
KUT T4/1	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 39 mm	.	.
12X 15259Q	.	.	.	0.141	0.249	.	.	.	.	0.139	0.49	.	~40 mm Ø x ~15 mm last	.	.
ECRM 196-2D	0.00033	0.00014	0.00071	0.0138	Mg:0.00075	.	.	.	.	0.00368	.	Zn:0.00019	38 mm Ø x 25 mm	.	.
VS UG4/5	.	.	.	.	0.053	.	.	.	.	0.054	0.14	.	~45 mm Ø x ~28 mm	.	.
NCS HS11751a	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm	.	.
CZ LA-2E	0.083	0.0043	.	0.268	0.111	.	0.068	0.033	.	0.310	0.307	.	~37 mm Ø x 25 mm	.	.
ECRM 186-1D	.	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 25 or 30 mm	.	.
BS 300	0.0030	0.0003	0.0008	0.0079	0.0031	(0.0004)	(0.00026)	0.0007	(0.0012)	0.070	0.0009	last	38mm Ø x -12 or 19mm Fe:93.8	.	.
12X 44220A	0.0026	.	.	.	.	.	.	.	.	0.0764	.	.	~38 mm Ø x ~15 mm	.	.
CZ CM-2A	0.11	0.0005	.	0.43	0.48	.	0.06	0.008	0.027	0.10	0.23	0.03	~39 mm Ø x 25 mm last	.	.
VS UG111	.	.	.	.	.	.	.	.	.	0.058	0.056	.	~45 mm Ø x ~28 mm	.	.
VS UG1/9	(0.001)	(0.0003)	.	.	0.124	.	(0.002)	.	.	0.024	0.063	.	~45 mm Ø x ~28 mm	.	.
IARM 340A	(0.004)	0.0004	(0.0004)	0.006	0.015	(0.001)	(0.001)	0.0021	.	0.064	(0.005)	(0.002)	31 mm Ø x 2 or 18 mm	.	.
IARM 342A	(0.006)	0.0004	(0.0001)	0.008	(0.002)	0.0006	0.0008	0.0021	.	0.023	(0.005)	(0.002)	31 mm Ø x 2 or 18 mm	.	.
VS UG4/10	.	.	.	.	0.030	.	.	.	.	0.0239	0.006	.	~45 mm Ø x ~28 mm	.	.
KUT B1/1	.	.	.	.	.	.	.	.	.	.	.	0.001	30-35 mm Ø x 39 mm	.	.
12X 15261X	0.0051	.	.	0.333	0.601	.	.	.	.	0.122	0.269	0.0297	~40 mm Ø x ~15 mm	.	.
VS UG1/10	.	.	.	0.091	.	.	.	.	.	0.042	0.074	.	~45 mm Ø x ~28 mm	.	.
KUT A11/1	.	.	.	0.16	.	.	.	.	.	0.46	.	.	30-35 mm Ø x 39 mm	.	.
VS UG4/6	(0.001)	.	.	(0.004)	(0.03)	.	(0.005)	(<0.0005)	.	0.051	0.111	.	~45 mm Ø x ~28 mm	.	.
VS UG87	0.116	.	.	.	.	.	0.00008	0.0012	.	0.0038	.	.	~47 mm Ø x ~30 mm	.	.
VS UG1/5	.	.	.	0.078	.	.	.	.	.	0.070	(0.01)	.	~45 mm Ø x ~28 mm	.	.
VS UG88	0.0007	.	.	0.059	.	.	0.00015	0.0003	.	0.117	.	.	~47 mm Ø x ~30 mm	.	.
DSZU C046	0.0020	(0.0004)	0.0007	0.006	(0.005)	.	.	.	.	0.72	0.47	.	40 mm Ø x 25 mm	.	.
KUT A12	0.007	.	.	0.012	(0.03)	.	.	0.013	.	0.042	.	.	30-35 mm Ø x 39 mm	.	.
CZ CM-14A	0.016	0.0062	(0.004)	0.015	0.115	.	0.013	0.006	0.015	0.345	0.021	0.044	~39 mm Ø x 25 mm last	.	.
12X 15258P	.	0.0100	.	0.310	0.133	.	.	.	(0.002)	0.378	0.125	.	~40 mm Ø x ~15 mm	.	.
SS 603/2	.	.	.	(0.01)	.	.	.	.	.	(0.001)	.	(<0.005)	44 mm Ø x 19 mm	.	.
SS 405/2	.	.	.	.	.	.	.	.	.	0.411	.	.	38 mm Ø x 19 mm	.	.
SS 113	0.0020	0.0066	.	0.0415	0.0487	.	.	.	.	0.201	0.012	0.0029	44 mm Ø x 19 mm	.	.
SS 604/2	.	.	.	(0.01)	.	.	.	.	.	(0.001)	.	(<0.005)	44 mm Ø x 19 mm	.	.
Number	As	B	Ca	Co	Nb	O	Pb	Sb	Ta	V	W	Zr	Units		

LOW ALLOY STEEL WITH C > 0.3%				CONTINUED ON THE NEXT PAGE							# = Class, where 1=CRM, 2=RM, 3=RM no uncertainties					
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti
1	VS UG0/6	1.40	0.329	(0.006)	(0.003)	0.221	0.286	0.55	0.73	0.129	(0.002)	(0.01)	0.079			0.0052
1	VS UG0/9	1.33	0.208	0.0040	0.0045	0.170	0.307	0.36	0.55	0.139	(0.001)		0.024	0.0022	0.041	0.029
1	VS UG0/10	1.321	0.268	0.0090	0.0044	0.244	0.265	0.353	0.596	0.101			0.052	0.0120	0.0033	0.017
1	VS UG0/5	1.32	(0.2)	(0.01)	(0.007)	(0.2)	0.265	0.351	0.60	0.108			(0.05)		(0.01)	(0.01)
1	SS 402/2	1.311	0.288	0.0161	0.0138	0.111	0.302	0.808	0.652	0.161			0.140	0.0069		
1	ECRM 035-2D	1.277	0.305	0.0038	0.011	0.216	0.0085	0.0190	0.0104	0.0193			0.0056	0.0230		0.0030
1	IMZ 65/2	1.19	0.27	0.013	0.007	0.13	0.059	0.067	0.079	0.030						
1	DSZU C049	1.17	0.237	0.0166	0.0147	0.227	0.069	0.044	0.131	(0.005)		(0.003)	(0.002)	(0.007)		(0.003)
1	KUT A18	1.16	(1.99)	0.014	0.007	0.15	0.066	0.125	0.90	(0.02)					0.035	0.011
1	VS UG0/11	1.16	0.196	0.0054	0.0078	0.233	0.134	0.114	0.163	0.009		0.0109	0.011	0.005		0.0041
3	CZ CM-5B	1.09	1.28	0.021	0.012	0.39	0.13	0.23	2.07	0.083		0.022	0.10	0.0135	0.06	0.05
1	14X 72305A	1.085	0.349	0.0128	0.0028	0.206	0.149	0.089	0.425	0.0049			0.0231	0.0068		
2	CZ CM-5C	1.04	1.17	0.029	0.021	0.54	0.151	0.42	2.45	0.063		0.022	0.132	0.014	0.014	0.031
1	VS UG9/9	1.04	0.310	0.0053	0.021	0.219	0.163	0.242	0.310	(0.003)		0.022	0.308	0.0027	0.0046	0.130
1	IMZ 172	1.03	0.71	0.018	0.047	0.12	0.128	0.12	4.47	0.062		0.012	0.96	0.0192		(0.002)
1	IARM 49E	1.03	0.364	(0.006)	(0.002)	0.248	0.076	0.043	1.43	0.024		(0.006)	0.017	(0.003)	(0.003)	0.0060
1	12X 52986A	1.023	0.372	0.0049	0.0011	0.246	0.077	0.0411	1.418	0.0258	(0.002)		0.0169	(0.002)		
2	BS 53G	1.02	0.35	0.014	0.015	0.23	0.160	0.090	1.53	0.019		0.008	0.034	0.0084		(0.002)
1	NILAB 100LA D	1.002	0.333	0.012	0.018		0.019	0.027	1.517	0.005		0.007	0.012	0.0046		0.0007
1	IARM 324A	0.99	1.01	0.009	0.028	0.163	0.22	0.081	0.42	0.002		0.007	0.022	0.0082	0.014	0.0016
2	BS A485-1	0.98	1.10	0.019	0.004	0.62	0.16	0.13	1.07	0.017		0.010	0.029	0.0060		0.003
1	KUT B15	0.98	0.269	0.030	0.031	0.80	0.14	0.15	3.70	0.13		0.21	1.20			(0.32)
1	VS UG75	0.98	0.286	0.0127	0.0089	0.248	0.111	0.201	1.43	(0.01)			(0.01)		(0.01)	(0.01)
2	CZ LA-4C	0.95	1.63	0.021	0.012	0.07	0.056	0.045	1.78	0.048		(0.006)	0.008	0.012	0.053	(0.002)
1	VS UG9/11	0.94	0.895	0.027	0.0085	0.312	0.163	0.354	0.985	(0.04)			0.094	0.0119		0.010
1	12X 19965A	0.936	0.600	0.0196	0.0081	0.247	0.148	0.141	1.713	0.0256			0.210	0.0087		
1	SS 401/2	0.935	1.19	0.026	0.0078	0.60	0.101	0.019	0.138	0.074		0.0042	0.49	0.0159		
1	IMZ 119	0.93	1.15	0.018	0.006	0.16	0.042	0.049	0.062	0.010	0.007			0.0086		(0.0007)
1	VS UG89	0.92	0.76	0.0085	0.01	0.385	0.373	0.51	0.420	0.01	0.007		0.044	0.017	0.0043	0.012
1	VS UG110	0.91	0.86	0.0063	0.0050	0.342	0.377	0.491	0.47	0.006			0.0052			0.0015
1	VS UG21/6	0.83	0.74	(0.02)	(0.02)	0.312	0.346	0.47	0.50							
2	IARM 172A	0.78	0.010	0.007	0.004	1.29	0.40	0.025	3.52	0.39		0.006	0.014	0.0004	0.004	0.003
1	SS 403/2	0.750	1.677	0.055	0.0381	0.209	0.221	0.223	0.463	0.0485			0.088	(0.010)		
1	IMZ 64/2	0.75	0.47	0.012	(0.005)	0.22	0.12	0.081	0.090	0.020						
1	VS UG8/11	0.728	1.97	0.036	0.0019	0.31	0.160	0.291	1.74	(0.01)			0.622	0.0138		
1	ECRM 059-2D	0.721	0.495	0.0046	0.0084	0.188	0.0074	0.0198	0.0090	0.00045	0.00020			0.0018		
2	CZ CM-1C	0.72	1.73	0.023	0.025	0.31	0.18	0.52	0.47	0.034		0.026	0.084	0.009	0.054	0.066
2	CZ CM-4B	0.72	0.50	0.023	0.012	0.80	0.40	1.40	2.23	0.025		0.115	0.33	0.013	0.071	0.12
1	SS 404/2	0.696	0.532	0.0479	0.0228	1.121	0.427	0.393	0.774	0.017			0.307	0.0089		
1	IMZ 118	0.69	1.76	(0.049)	(0.049)	0.30	0.18	0.19	3.0	(0.014)			0.15	0.058		
1	IMZ 116	0.64	0.94	0.025	0.035	0.25	0.33	0.022	0.72	0.025	0.012		0.074	0.0130		(0.0008)
1	VS UG1/11	0.61	0.667	0.0098	0.011	1.74	0.155	0.080	0.108	0.032		0.0195	0.0067	0.0100		0.0047
1	VS UG96	0.60	0.52	0.0046	0.0029	0.290	0.256	0.396	0.399	0.031			0.0042			0.0025
1	VS UG119	0.55	0.70	0.012	(0.02)	1.63	0.207	0.142	0.195	0.039			0.0113	0.0047		0.0030
1	12X 10550	0.549	0.685	0.0184	0.0055	0.281	0.0290	0.0247	0.338	0.0325			0.0086	0.0051		
1	12X 61500A	0.530	0.912	0.0104	0.0102	0.240	0.157	0.0976	1.023	(0.007)	0.0067		0.0195			
2	CZ CM-6A	0.52	0.37	0.016	0.058	0.27	0.05	0.19	0.37	0.02		0.03	0.04	0.009	0.028	0.03
2	CZ BO-2B	0.515	0.745	0.0093	0.0016	0.309	0.100	0.057	0.212	0.0196		0.0055	0.006	0.004		0.0017
1	12X LA3C	0.500	1.693	0.0274	0.0442	0.163	0.213	0.280	0.375	0.0410		0.0475	0.303	0.0039		
1	IARM 34C	0.50	0.739	0.0090	0.0011	0.30	0.078	0.085	0.914	0.068		0.005	0.022	0.0030	0.004	0.0045
2	BS 4941	0.490	0.79	0.012	0.017	0.27	0.106	0.074	0.96	0.024		0.008	0.039	0.0076		
1	BS 43A	0.49	0.82	0.0074	0.025	0.252	0.18	0.24	0.92	(0.003)		0.008	0.059	0.0072	(0.0017)	(0.002)
1	IMZ 103A	0.49	0.78	0.066	0.051	0.42	0.27	0.57	0.58	0.026		0.002	0.18		0.040	0.17
1	IMZ 117	0.49	0.77	0.038	0.015	0.34	0.41	0.29	0.94	0.023	0.013		0.024	0.0154	0.041	(0.0014)
1	BS 1144	0.483	1.55	0.022	0.243	0.262	0.462	0.097	0.193	(0.002)		0.011	0.017	0.0093	(0.004)	0.002
1	IPT 503	0.456	0.682	0.027	0.027	0.218	0.129	0.063	0.160	0.018		0.006	0.020	0.0082		0.0011
1	SRM C1173	0.453	0.174	0.031	0.092	1.38	0.204	4.04	2.63	0.02			1.46			0.037
1	12X 41450A	0.446	1.011	0.0093	0.0031	0.261	0.1318	0.187	1.194	0.0220			0.340	0.0080		
1	VS UG5/11	0.445	0.64	0.010	0.0037	0.29	0.146	1.40	0.912			0.0195	0.269	0.0119		
2	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.041	0.033		0.006	0.007	0.0056	(0.002)	(0.002)
1	12X LA3B	0.439	1.176	0.0215	0.0379	0.16	0.173	0.300	0.357	0.0300		0.0300	0.302	0.0080		
1	NM PC-4	0.43	0.80	0.043	0.045	0.34			0.26							
1	IARM 30H	0.425	0.937	0.015	0.022	0.253	0.131	0.063	0.97	0.020		0.0071	0.199	0.0081	(0.003)	(0.0024)
1	IARM 305B	0.425	0.58	0.011	0.014	0.349	0.214	0.156	1.63	0.92		0.007	0.32	0.0044	0.002	0.0044
1	IARM 252D	0.423	0.842	0.0075	0.0128	0.256	0.270	0.424	0.468	0.024		0.0078	0.204	0.0068	0.0013	0.0012
1	BS 4340A	0.423	0.766	0.0062	(0.0008)	0.253	0.128	1.80	0.879	0.031		0.0111	0.259	0.0102	(0.002)	(0.0011)
1	SRM 1173	0.423	0.19	0.033	0.092	1.28	0.204	4.06	2.70				1.50			
2	HRT FE2015-N	0.42	0.83	0.007	0.028	0.24	0.15	0.32	1.03	0.023			0.21	0.0057		
1	BS 4340	0.418	0.695	0.0119	0.0187	0.279	0.149	1.79	0.807	0.028		0.0068	0.231	0.0080	(0.001)	0.0014
1	IARM 252C	0.416	0.92	0.025	0.008	0.248	0.109	0.505	0.501	0.017		0.008	0.205	0.0083	0.002	0.001
2	BS 4942	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	(0.004)		0.010	0.54	0.0080		
1	IARM 252E	0.413	0.87	(0.009)	(0.012)	0.257	0.164	0.407	0.486	0.028		0.0093	0.204	0.0064		0.0010
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti
2	BS 1962	0.41	0.94	0.007	0.011	0.242	0.224	0.16	1.05	0.018		0.008	0.229	0.0095		0.004
1	VS UG116	0.41	0.59	0.012	0.027	0.246	0.221	1.13	0.89	0.026			0.044	0.0089		0.0022
1	IARM 252F	0.406	0.88	0.011	0.009	0.247	0.182	0.412	0.463	0.026		0.0086	0.210	0.0059	0.0016	0.0010
1	IARM 30J	0.405	0.884	0.010	0.036	0.256	0.173	0.187	0.972	0.023		0.0098	0.205	(0.010)	0.0016	0.0013
1	SS 114	0.403	0.416	0.0044	0.0046	0.295	0.358	1.502	0.187	0.078		0.0171				

Number	LOW ALLOY STEEL WITH C > 0.3%						CONTINUED FROM THE PREVIOUS PAGE						Units	
	As	B	Ca	Fe	Mg	O	Pb	Sb	Sn	Ta	V	W		Zr
VS UG0/6	.	.	.	.	.	.	(<0.0005)	(<0.0005)	0.0032	.	0.0046	.	.	~45 mm Ø x ~28 mm last
VS UG0/9	.	(0.0002)	.	.	.	.	(0.002)	(0.0008)	.	0.0087	0.074	.	.	~45 mm Ø x ~28 mm
VS UG0/10	.	.	.	.	.	.	.	0.0043	.	0.0037	(0.006)	.	.	~45 mm Ø x ~28 mm
VS UG0/5	.	.	.	.	.	.	.	.	.	(0.01)	(0.01)	.	.	~45 mm Ø x ~28 mm
SS 402/2	.	.	.	.	.	.	.	.	.	.	0.194	.	.	38 mm Ø x 19 mm
ECRM 035-2D	0.0017	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 20 mm
IMZ 65/2	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
DSZU C049	(0.004)	(0.0002)	(0.003)	.	.	.	.	(0.004)	.	(0.003)	.	.	.	40 mm Ø x 25 mm
KUT A18	0.003	(0.011)	.	.	.	.	.	0.005	0.016	0.10	.	.	.	30-35mm Ø x 18 mm
VS UG0/11	.	.	.	.	.	.	.	0.0051	.	0.0035	0.0032	.	.	~45 mm Ø x ~28 mm
CZ CM-5B	0.018	0.002	.	.	.	.	0.01	0.006	0.012	0.06	0.03	0.09	.	~37 mm Ø x 25 mm
14X 72305A	.	.	.	.	.	.	.	0.0101	.	0.0045	.	.	.	~40 mm Ø x ~15 mm
CZ CM-5C	0.020	0.0012	(0.0006)	.	.	.	0.009	0.005	0.018	0.106	0.034	(0.07)	.	~39 mm Ø x 25 mm
VS UG9/9	.	(0.0002)	.	.	.	.	(0.002)	.	(0.011)	0.215	1.60	.	.	~45 mm Ø x ~28 mm
IMZ 172	.	.	.	.	.	.	.	.	0.010	0.20	0.011	.	.	40 mm Ø x 40 mm
IARM 49E	0.0029	.	.	.	.	(0.002)	.	.	0.0065	0.066	.	.	.	31 mm Ø x 2 or 18 mm
12X 52986A	.	.	.	.	.	.	.	.	0.0063	0.0615	.	.	.	~38 mm Ø x ~15 mm
BS 53G	0.004	(0.0001)	(0.0001)	.	.	0.001	.	.	0.007	0.006	(0.13)	.	.	44 mm Ø x ~7 or 19+ mm
NILAB 100LA D	0.004	.	.	.	.	.	.	.	.	0.004	.	.	.	34 mm Ø x 20 mm
IARM 324A	0.006	0.0004	0.0009	.	.	0.003	.	(0.002)	0.011	0.0017	(0.003)	(0.001)	.	31 mm Ø x 2 mm
BS A485-1	0.006	.	.	.	.	(0.0008)	.	.	0.011	0.003	.	.	.	39 mm Ø x ~7 or 19+ mm
KUT B15	.	.	.	.	.	.	.	.	.	(0.33)	.	.	.	30-35mm Ø x 2 or 18 mm
VS UG75	.	.	.	.	.	.	.	.	.	(0.006)	(0.02)	.	.	~40 mm Ø x ~25 mm
CZ LA-4C	(0.003)	0.0005	.	.	.	.	.	.	(0.006)	(0.010)	0.008	.	.	~37 mm Ø x 25 mm
VS UG9/11	.	.	.	.	.	.	.	.	0.0064	0.048	1.27	.	.	~45 mm Ø x ~28 mm
12X 19965A	.	.	.	.	.	.	.	.	0.0070	0.0087	.	Zn:0.0008	.	~41 mm Ø x ~15 mm
SS 401/2	.	.	.	.	.	.	.	.	.	0.496	.	.	.	38 mm Ø x 19 mm
IMZ 119	.	.	(0.0002)	.	.	.	.	.	.	0.006	.	.	.	40 mm Ø x 40 mm
VS UG89	0.0043	.	.	.	.	.	0.0003	0.0011	.	0.021	.	.	.	~47 mm Ø x ~30 mm
VS UG110	.	.	.	.	.	.	.	.	.	.	0.004	.	.	~45 mm Ø x ~25 mm
VS UG21/6	.	.	.	.	.	.	.	.	.	.	.	.	.	~45 mm Ø x ~28 mm
IARM 172A	(0.005)	0.0003	.	.	.	0.0006	(<0.01)	.	0.003	0.003	0.038	.	.	31 mm Ø x 2 mm
SS 403/2	.	.	.	.	.	.	.	.	.	0.341	.	.	.	38 mm Ø x 19 mm
IMZ 64/2	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
VS UG8/11	.	.	.	.	.	.	.	.	0.0058	0.181	0.70	.	.	~45 mm Ø x ~28 mm
ECRM 059-2D	.	.	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 25 or 30 mm
CZ CM-1C	0.036	0.0020	0.0007	.	.	.	0.005	0.01	0.012	0.073	0.064	0.051	.	~39 mm Ø x 25 mm
CZ CM-4B	0.015	0.017	.	.	.	.	0.022	0.052	0.028	0.18	0.116	Zn:0.007	.	~39 mm Ø x 25 mm
SS 404/2	.	.	.	.	.	.	.	.	.	0.107	.	.	.	38 mm Ø x 19 mm
IMZ 118	.	.	(0.0002)	.	.	.	.	.	0.22	0.059	.	.	.	40 mm Ø x 40 mm
IMZ 116	.	.	.	.	.	.	.	.	.	0.076	.	.	.	40 mm Ø x 40 mm
VS UG1/11	.	.	.	.	.	.	.	.	0.0035	.	.	.	.	~45 mm Ø x ~28 mm
VS UG96	.	.	.	.	.	.	.	.	.	0.0030	.	.	.	~40 mm Ø x ~28 mm
VS UG119	.	.	.	.	.	.	.	.	.	.	.	.	.	~45 mm Ø x ~25 mm
12X 10550	0.0059	.	.	.	.	.	.	.	0.0018	.	.	Zn:(0.0016)	.	~40 mm Ø x ~15 mm
12X 61500A	.	.	.	.	.	.	.	.	0.0114	0.110	.	Zn: 0.0055	.	~38 mm Ø x ~15 mm
CZ CM-6A	0.025	0.015	.	.	.	.	0.017	0.03	0.017	0.05	0.04	0.04	.	~39 mm Ø x 25 mm
CZ BO-2B	0.0057	.	(0.0008)	.	.	.	.	.	0.0062	(0.001)	(0.005)	.	.	~37 mm Ø x ~25 mm
12X LA3C	0.0301	Zn:(0.004)	.	.	.	.	(0.004)	.	.	0.157	.	0.0197	.	~40 mm Ø x ~15 mm
IARM 34C	0.0024	0.0003	(0.0004)	.	.	0.0008	(0.0003)	(0.001)	0.0058	0.206	(0.003)	(0.001)	.	31 mm Ø x 2 or 18 mm
BS 4941	(0.004)	.	(0.0002)	.	.	0.0017	.	.	0.006	0.164	.	.	.	41 mm Ø x ~7 or 19+ mm
BS 43A	(0.005)	(0.0002)	(0.0006)	[96.8]	(0.0001)	(0.003)	.	(0.002)	0.011	0.145	(0.005)	(0.001)	.	41 mm Ø x ~7 or 19+ mm
IMZ 103A	.	0.006	.	.	.	.	.	.	(0.005)	0.17	.	.	.	40 mm Ø x 40 mm
IMZ 117	.	.	(0.0002)	.	.	.	.	.	.	0.087	.	.	.	40 mm Ø x 40 mm
BS 1144	0.009	.	.	.	.	0.0016	(0.001)	.	0.0113	0.0039	(0.003)	last	.	38 mm Ø x ~16 mm 17025
IPT 503	.	.	.	.	.	.	0.008	.	.	.	.	.	.	35 mm Ø x 20 mm
SRM C1173	.	.	.	.	.	.	.	.	0.42	.	.	.	.	32 mm Ø x 19 mm
12X 41450A	0.0053	.	.	.	.	.	.	.	0.0090	0.0385	.	.	.	~38 mm Ø x ~15 mm
VS UG5/11	.	.	.	.	.	.	.	.	0.0047	0.148	0.049	.	.	~45 mm Ø x ~28 mm
BS XCCV	0.002	.	.	.	.	(0.0018)	(<0.0006)	(0.0003)	(0.0004)	.	(<0.003)	.	(<0.0002)	36 mm Ø x ~7 or 19+ mm
12X LA3B	.	0.0015	.	.	.	.	0.0149	.	.	Zn:0.0098	0.157	.	(0.027)	~40 mm Ø x ~15 mm
NM PC-4	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 20 mm last
IARM 30H	0.0046	(0.0007)	(0.0009)	.	(0.001)	(0.0016)	(0.0005)	0.0013	0.008	.	(0.0040)	(0.007)	(0.002)	31 mm Ø x 2 mm
IARM 305B	(0.006)	0.0006	0.0007	.	(0.002)	0.0006	(0.0003)	(0.004)	0.011	0.004	(0.004)	0.0011	.	31 mm Ø x 2 or 18 mm
IARM 252D	0.0053	(0.0002)	(0.001)	.	(0.0002)	(0.0013)	(0.0004)	0.0024	0.012	0.022	(0.004)	(0.0013)	.	31 mm Ø x 2 or 18 mm
BS 4340A	0.0059	(0.0002)	(0.0002)	95.4	0.0004	0.0007	(0.0003)	(0.0018)	0.0081	0.0024	0.0005	0.0016	.	38 mm Ø x ~7 or 19+ mm 17025
SRM 1173	.	.	.	.	.	.	.	.	.	0.42	.	.	.	32 mm Ø x 19 mm
HRT FE2015-N	.	.	.	.	.	.	.	.	.	0.006	.	.	.	35 mm Ø x 20 mm
BS 4340	0.0043	(0.0002)	0.0005	95.5	(0.0002)	0.0012	(0.0002)	(0.0013)	0.0063	0.0033	0.0012	0.0005	.	38 mm Ø x ~7 or 19+ mm 17025
IARM 252C	0.004	(0.0001)	(0.0003)	.	.	(0.002)	0.001	<0.005	0.007	0.005	<0.005	<0.002	.	31 mm Ø x 2 mm
BS 4942	0.005	.	0.0006	.	.	(0.0021)	.	.	0.014	0.28	.	.	.	38 mm Ø x ~7 or 19+ mm last
IARM 252E	0.0046	.	.	.	.	.	.	.	0.0075	(0.0028)	.	.	.	31 mm Ø x 2 or 18 mm
Number	As	B	Ca	Fe	Mg	O	Pb	Sb	Sn	Ta	V	W	Zr	Units
BS 1962	0.007	.	25(pre-17025)	.	(0.0001)	.	(0.001)	.	0.010	.	0.004	.	.	41 mm Ø x ~7 mm last
VS UG116	.	.	.	.	.	.	.	.	.	.	.	.	.	~45 mm Ø x ~25 mm
IARM 252F	(0.006)	.	.	.	.	.	.	.	0.006	.	(0.003)	(0.003)	.	31 mm Ø x 2 or 18 mm
IARM 30J	(0.002)	.	.	.	.	.	.	.	0.0109	.	0.0045	(0.005)	.	31 mm Ø x 2 mm
SS 114	0.0025	0.0008	.	.	.	.	.	.	0.041	.	0.0086	.	0.0051	44 mm Ø x 19 mm
IMZ 55/1A	.	0.0018	.	.	.	.	.	0.0051	0.017	.	0.107	.	.	38 mm Ø x 20 mm
IARM 31G	(0.004)	0.0004	.	.	.	.	.	.	0.0077	.	0.0036	(0.004)	(0.0012)	31 mm Ø x 2 or 18 mm
IMZ 63/2	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
SS 225/2	.	.	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
IPT 504	.	.	.	.	.	.	.	.	.	.	.	.	.	36 mm Ø x 20 mm
12X 826M40A	0.0056	.	.	.	.	.	.	.	0.0085	.	.	.	.	~38 mm Ø x ~15 mm
BS 4942A	0.0031	(0.0001)	0.0012	96.8	0.0004	0.0020	(0.0007)	(0.001)	0.0044	.	0.280	(0.0009)	(0.001)	38 mm Ø x ~7 or 19+ mm 17025
VS RG30/1	.	.	.	.	.	.	.	.	.	.	0.70	0.89	.	~45 mm Ø x ~28 mm
VS UG79	.	.	.	.	.	.	.	.	.	.	(0.02)	(0.01)	.	~40 mm Ø x ~26 mm
IRSID 1731	.	.	.	.	.	.	.	.	.	.	.	.	.	44 mm Ø x 30 mm
DSZU C045	0.0052	(0.0004)	0.0005	.	.	.	.	.	0.0050	0.004	(0.011)	.	.	40 mm Ø x 25 mm
VS UG3/10	.	.	.	.	.	.	.	.	0.0057	0.0053	0.006	.	.	~45 mm Ø x ~28 mm
12X 605M36A	0.0102	.	0.0033	.	.	.	.	.	0.0101	.	.	.	.	~38 mm Ø x ~15 mm
12X 12700A	0.0060	0.0014	.	.	.	.	.	.	.	.	0.0033	.	Zn:0.0120	~50 mm Ø x ~20 mm
IMZ 115	.	.	.	.	.	.	.	.	.	.	(0.063)	.	.	40 mm Ø x 40 mm
IRSID 1750	0.0188	(0.0002)	(0.0002)	.	(<0.0002)	.	(<0.001)	0.0031	0.114	(<0.0010)	0.114	(0.004)	(0.0002)	38 mm Ø x 25 mm
IMZ 114A	0.0035	0.0019	.	.	.	.	0.021	0.018	0.014	0.096	(0.007)	Zn:(0.006)	.	38 mm Ø x 20 mm
12X 352E	0.													

## LOW ALLOY STEEL WITH 0.13 % &lt; C &lt; 0.3 % - CONTINUED ON THE NEXT PAGE

#=Class, where 1=CRM and 2=RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Sn	V
1	IARM 330A	0.299	1.00	(0.005)	(0.001)	0.273	0.074	1.80	0.90	0.045	.	(0.003)	0.0063	0.404	0.0024	0.0039	0.071
1	12X 16604A	0.299	0.444	0.0064	0.0018	0.239	0.131	1.892	1.912	0.0111	.	.	0.0366	0.334	0.0046	0.0060	0.0069
1	SRM 1269	0.298	1.35	0.012	0.0061	0.189	0.095	0.108	0.201	0.016	.	.	.	0.036	.	.	0.004
1	ECRM 086-1D	0.297	0.879	0.024	0.037	0.206	0.320	0.168	0.150	.	.	0.023	.	.	.	0.026	.
2	CZ CM-3A	0.295	0.37	0.016	0.0013	0.27	0.16	1.82	1.87	0.05	.	0.005	0.012	0.33	0.007	0.007	0.007
1	VS UG9/10	0.294	0.616	.	(0.003)	0.235	0.169	0.144	0.170	0.280	.	.	.	0.282	0.015	0.0017	1.25
1	VS RG27/1	0.290	0.74	0.044	0.0043	0.28	0.208	0.142	1.83	1.07	.	.	0.025	0.191	.	.	0.072
1	IMZ 178	0.29	0.65	0.016	0.003	0.28	0.140	2.09	1.26	0.051	.	.	0.015	0.20	0.0160	0.011	0.011
1	SRM 1225	0.274	0.48	0.007	0.014	0.221	.	0.018	0.91	.	.	.	.	0.166	.	.	0.004
1	BS HiCal-1	0.271	1.00	(0.007)	0.0007	1.29	0.152	3.28	1.55	0.070	.	0.0022	0.0024	0.379	.	(0.0002)	0.0027
1	IARM 380A	0.268	1.24	0.021	0.025	0.181	0.265	0.114	0.192	0.0029	.	(0.007)	(0.010)	0.059	(0.012)	0.0117	0.0475
2	RM Fe 2/4	0.26	0.61	0.039	0.016	0.30	0.30	0.68	0.70	(0.001)	.	0.04	0.29	0.47	0.020	0.04	0.46
2	BS 69B	0.258	1.28	0.008	0.013	1.27	0.086	1.71	0.28	0.024	.	.	0.035	0.39	0.0057	0.006	(0.002)
1	12X 12750U	0.258	0.510	0.0078	0.0053	0.599	0.106	0.786	0.792	0.253	.	.	0.581	0.088	.	0.110	0.102
1	12X 32550A	0.257	1.350	0.0061	0.0054	1.59	0.108	1.750	0.377	0.0178	.	0.0054	.	0.417	0.0101	0.0206	0.0222
2	BS 6418	0.255	1.42	0.010	0.004	1.54	0.11	1.74	0.34	0.027	.	0.0044	0.010	0.42	0.0066	0.006	0.003
1	IARM 380B	0.243	1.27	0.016	0.027	0.238	0.307	0.182	0.153	(0.0021)	.	0.0058	0.014	0.055	(0.013)	0.0132	0.049
2	HRT FE2018-N	0.24	0.74	0.012	(0.003)	0.29	0.06	0.43	1.46	0.017	.	.	.	0.75	0.0066	.	0.30
1	IMZ 113	0.24	0.50	0.022	0.025	0.10	0.11	0.13	1.25	0.007	0.004	.	.	0.050	0.0154	.	0.039
1	12X 722M24A	0.236	0.510	0.0135	0.0199	0.262	0.200	0.208	3.094	0.0187	.	0.0075	.	0.497	.	0.0116	0.0080
1	VS UG6/5	0.232	0.39	(0.006)	(0.008)	0.51	0.257	(0.2)	1.85	(0.4)	.	.	.	(0.2)	.	.	0.34
1	12X 356D	0.228	0.325	0.057	0.040	0.235	0.402	0.070	0.246	0.031	.	0.025	0.110	0.0299	0.0107	0.0372	0.071
2	DSZU C043A	0.222	2.14	0.060	0.064	0.131	0.51	2.93	0.49	0.066	.	(0.001)	.	0.146	(0.009)	0.0023	0.25
1	IARM 229B	0.220	0.858	0.0073	0.0106	0.329	0.0153	0.030	0.017	0.025	.	(0.002)	0.0116	0.495	0.0072	0.0012	0.0059
1	ECRM 197-1D	0.219	0.792	0.0073	0.0232	0.275	0.152	0.148	0.451	0.0313	.	0.0083	0.0135	0.402	0.0114	0.0097	.
2	BS 3961	0.215	0.565	0.016	0.022	0.236	0.133	1.67	0.510	0.022	.	.	(0.010)	0.27	0.0079	(0.008)	(0.002)
2	TL 1668	0.2146	1.643	0.0137	0.0012	1.645	0.0108	0.0164	0.0173	0.0371	.	0.0016	0.0031	(0.0014)	0.0043	0.0047	0.0016
1	BS 8620F	0.212	0.85	0.0090	0.033	0.243	0.234	0.427	0.547	0.040	.	0.0078	0.0089	0.206	0.0106	0.0102	0.0054
1	DSZU C048	0.212	0.467	0.0102	0.0059	0.273	0.262	0.105	0.175	0.0293	.	0.0085	0.015	0.016	(0.011)	0.016	.
2	TL 1001	0.2108	0.8645	0.0141	0.0236	0.2141	0.1902	0.5378	0.5290	0.0191	.	(0.0051)	(0.0070)	0.1987	0.0102	0.0090	.
1	IPT 502	0.210	0.823	0.018	0.026	0.198	0.121	0.408	0.485	0.024	.	.	0.0083	0.155	0.0069	.	.
1	VS UG4/11	0.21	0.59	0.024	0.0069	0.285	0.074	0.173	1.21	0.032	.	.	0.0108	0.87	0.020	.	0.78
1	IARM 33D	0.209	0.593	0.009	0.023	0.207	0.072	1.78	0.139	0.026	.	0.0035	0.008	0.229	0.0053	0.005	0.002
2	BS 3952	0.208	0.546	0.011	0.021	0.264	0.202	0.112	0.105	0.048	.	.	.	0.519	(0.0005)	.	.
1	ECRM 187-2D	0.2038	1.257	0.0066	(0.0300)	0.2111	0.1288	0.1755	1.132	0.0223	.	0.0057	0.0112	0.0623	0.0105	0.0237	0.0122
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Sn	V
1	BS 9325A	0.203	0.969	0.0079	0.0045	0.612	0.163	3.29	1.50	0.0056	.	0.0024	0.0093	0.358	0.0076	(0.0003)	(0.0024)
1	BS 4820A	0.203	0.64	0.008	0.014	0.185	0.212	3.28	0.116	0.029	.	0.006	0.008	0.203	0.0076	0.0097	0.0010
1	12X 12747V	0.201	1.240	0.0648	0.0275	0.298	0.232	0.494	0.58	0.0271	.	0.0075	0.211	0.606	0.025	0.144	0.0272
1	VS RG31/1	0.200	0.191	0.0039	0.0058	0.28	0.39	2.12	1.28	0.30	.	.	0.273	0.30	.	.	0.200
1	KUT B3	0.20	0.14	(0.012)	0.025	0.53	0.25	.	5.94	.	.	.	.	.	.	.	1.16
1	VS UG5/5	(0.2)	0.52	(0.005)	(0.03)	0.145	0.37	0.42	1.42	0.19	.	.	.	0.44	.	.	0.29
1	IARM 155F	0.199	0.617	0.008	(0.013)	0.223	0.219	3.36	0.144	0.0356	.	(0.006)	0.012	0.244	(0.005)	0.0084	0.0015
1	IMZ 112B ##	0.195	0.43	0.022	0.016	0.27	0.055	0.046	0.034	(0.03)	.	.	.	0.043	0.010	0.15	0.045
1	VS UG8/10	0.192	1.81	0.0064	(0.005)	0.61	0.198	0.348	0.729	0.082	.	.	.	0.030	0.0185	0.0052	.
1	VS UG114	0.190	1.65	0.010	0.0074	0.59	0.173	0.345	1.03	0.146	.	.	.	0.016	.	.	0.0031
1	IMZ 162	0.19	1.31	0.021	0.014	0.59	0.077	1.64	0.91	(0.040)	.	.	.	0.52	.	.	0.045
1	VS UG113	0.189	1.55	0.0087	0.0070	0.59	0.185	0.186	1.12	0.263	.	.	.	0.010	.	.	0.040
2	BS 4620	0.189	0.57	0.006	0.018	0.25	0.216	1.75	0.072	0.032	.	0.0084	0.012	0.24	0.0078	0.013	(0.0008)
1	BS 51F	0.188	0.519	0.016	0.017	0.24	0.231	1.68	0.156	0.022	.	(0.005)	0.0086	0.224	0.0061	0.008	0.0030
1	ECRM 192-1D	0.1875	1.377	0.0029	0.0010	0.219	0.0453	0.755	0.0717	0.0306	0.0285	.	0.0055	0.482	0.0118	.	.
1	VS UG112	0.186	1.63	0.0065	0.0050	0.60	0.157	0.185	0.98	0.026	.	.	.	0.021	.	.	0.014
2	BS LF3	0.183	0.52	0.006	0.018	0.206	0.080	3.36	0.098	0.017	.	0.006	0.056	0.056	0.0054	0.006	(0.002)
2	HRT FE2012-N	0.18	0.70	0.010	0.008	0.31	0.14	0.13	0.25	0.030	.	.	.	0.26	.	.	.
1	IMZ 74A	0.179	1.19	0.008	0.010	0.34	0.209	0.130	0.197	0.012	.	.	0.0043	0.047	0.0118	.	0.072
1	12X 19MNV56A	0.174	1.563	0.0114	0.0245	0.357	0.203	0.110	0.1087	0.0101	.	.	.	0.0270	0.0210	0.0214	0.0939
1	ECRM 087-1D	0.174	0.671	0.010	0.046	0.263	0.171	0.118	0.078	.	.	0.024	0.015	0.021	.	0.017	.
1	12X 15180A	0.170	1.196	0.0110	0.0022	0.212	0.141	0.1030	0.118	0.018	.	0.0117	.	0.0231	0.0051	0.0115	.
1	ECRM 194-2D	0.1694	1.282	0.0137	0.00049	0.2974	0.0313	0.3316	0.760	0.0669	.	0.00208	0.00328	0.402	0.00319	.	0.00161
2	BS 3962	0.168	0.58	0.007	0.018	0.244	0.146	1.83	0.138	0.023	.	0.005	0.007	0.219	0.0072	0.007	(0.001)
1	VS UG7/11	0.164	0.293	0.0045	0.0062	0.39	0.468	2.09	1.31	0.276	.	.	0.291	0.298	0.014	.	0.208
2	HRT FE1999-N	0.16	0.59	0.011	0.005	0.22	0.11	0.09	0.87	0.027	.	.	.	0.46	0.0091	.	0.021
2	BS XCOT	0.158	0.52	0.005	0.011	0.28	0.027	1.27	0.65	0.006	.	0.004	0.017	0.020	0.0076	(0.002)	0.031
1	IMZ 176A	0.15	0.75	0.018	0.003	0.35	0.103	3.62	0.41	(0.058)	.	.	(0.010)	0.027	0.0129	0.009	(0.061)
2	BS 15A	0.142	1.12	0.016	0.008	0.058	0.030	0.029	0.044	0.041	.	0.003	0.005				

## LOW ALLOY STEEL WITH 0.13 % &lt; C &lt; 0.3 %

## CONTINUED FROM THE PREVIOUS PAGE

Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
IARM 330A	0.0003	0.0010	.	.	(0.003)	(0.0009)	(0.0004)	(0.001)	.	0.006	(0.004)	.	0.0015	31 mm Ø x 2 mm
12X 16604A	.	.	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
SRM 1269	.	.	.	.	.	.	0.005	.	.	.	.	.	.	32 mm Ø x 19 mm
ECRM 086-1D	.	.	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 25 or 30 mm
CZ CM-3A	0.0002	.	.	.	0.006	.	.	.	.	0.006	0.015	.	.	-39 mm Ø x 25 mm
VS UG9/10	.	.	.	.	.	.	.	.	.	0.163	1.34	.	.	-45 mm Ø x ~28 mm
VS RG27/1	.	.	.	.	.	.	.	.	.	0.110	0.170	.	.	-45 mm Ø x ~28 mm
IMZ 178	.	.	.	.	0.105	.	.	.	.	.	0.017	.	.	40 mm Ø x 40 mm
SRM 1225	.	.	.	.	.	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
<b>BS HiCal-1</b>	(0.0001)	0.0140 [91.9]	(0.0003)	(0.0002)	.	.	(0.0005)	.	.	0.0037	(0.0009)	.	(0.0008)	-38 mm Ø x ~30 mm <b>17025</b>
IARM 380A	.	.	.	.	(0.0020)	.	.	.	.	.	(0.009)	.	.	31 mm Ø x 2 or 18 mm
RM Fe 2/4	(0.0027)	<0.001	.	.	(0.011)	.	<0.02	<0.03	.	(0.0065)	0.19	.	<0.02	40 mm Ø x 40 mm
BS 69B	.	.	.	.	.	.	.	.	.	(0.002)	.	.	.	38 mm Ø x ~7 or 19+ mm
12X 12750U	.	.	.	.	0.111	.	.	.	.	0.159	0.100	.	.	-40 mm Ø x ~15 mm
12X 32550A	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x ~15 mm
BS 6418	.	.	.	.	.	0.0012	.	.	.	0.003	.	.	.	57 mm Ø x ~7 or 19+ mm
IARM 380B	.	.	.	.	(0.0016)	.	.	.	.	0.0011	(0.003)	.	.	31 mm Ø x 2 or 18 mm
HRT FE2018-N	(0.0003)	.	.	.	.	.	.	.	.	.	.	.	.	36 mm Ø x 20 mm
IMZ 113	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
12X 722M24A	.	.	.	.	.	.	.	.	.	.	.	0.0028	.	-38 mm Ø x ~15 mm
VS UG6/5	.	.	.	.	(0.01)	.	.	.	.	(0.01)	0.16	.	.	-45 mm Ø x ~28 mm
12X 356D	(0.002)	Ca:0.0063	.	Se:0.010	0.019	.	0.034	0.0203	.	0.016	0.086	0.011	.	40 mm Ø x ~15 mm
DSZU C043A	(0.001)	0.0004	.	.	0.006	.	.	.	.	0.041	0.092	.	.	40 mm Ø x 25 mm
IARM 229B	(0.0006)	(0.0003)	.	.	(0.0019)	(0.0017)	(0.0005)	(0.0006)	(0.003)	0.0019	(0.003)	.	(0.0008)	31 mm Ø x 2 mm
ECRM 197-1D	.	.	.	.	.	.	.	.	.	0.0005	.	.	.	38 mm Ø x 25 mm
BS 3961	.	.	.	.	.	.	.	.	.	(<0.003)	.	.	.	44 mm Ø x ~7 or 19+ mm
TL 1668	(0.00024)	0.0019	.	(0.0003)	(0.0002)	.	(0.0007)	(0.0003)	.	0.0032	.	0.0008	(0.0003)	37 mm Ø x 20 mm
<b>BS 8620F</b>	(0.0003)	0.0020	97.1	(0.0002)	0.0025	0.0026	(0.002)	(0.002)	<b>17025</b>	0.0016	0.0016	.	(0.0008)	38 mm Ø x ~7 or 19+ mm
DSZU C048	.	(0.0017)	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 25 mm
TL 1001	.	.	.	.	.	.	.	.	.	(0.0134)	.	.	.	40 mm Ø x 20 mm
IPT 502	.	.	.	.	.	.	.	.	.	0.0016	.	.	.	36 mm Ø x 20 mm
VS UG4/11	.	.	.	.	0.071	.	.	.	.	0.034	0.0092	.	.	-45 mm Ø x ~28 mm
IARM 33D	0.0002	(0.0003)	.	.	0.002	0.0013	<0.001	(0.002)	.	0.003	<0.005	.	<0.002	31 mm Ø x 2 or 18 mm
BS 3952	.	.	.	.	.	.	.	.	.	.	.	.	.	39 mm Ø x ~7 or 19+ mm
ECRM 187-2D	0.00048	.	.	.	.	.	.	.	.	.	.	.	.	39 mm Ø x 28 mm
Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units
<b>BS 9325A</b>	(0.0001)	0.0039	92.8	(0.0002)	0.0017	.	(0.0003)	.	(0.010)	0.0030	0.024	<b>17025</b>	(0.001)	-40 mm Ø x ~30 mm
<b>BS 4820A</b>	0.0002	0.0003	.	0.0003	(0.002)	0.0011	(0.0002)	0.0024	.	0.0012	(0.002)	<b>17025</b>	.	38 mm Ø x ~7 or 19+ mm
12X 12747V	.	.	.	.	.	.	.	.	.	0.099	0.0276	.	.	-40 mm Ø x ~15 mm
VS RG31/1	.	.	.	.	.	.	.	.	.	0.21	0.39	.	.	-45 mm Ø x ~28 mm
KUT B3	.	.	.	.	.	.	.	.	.	1.19	.	.	.	30-35mm Ø x 39 mm
VS UG5/5	.	.	.	.	(0.01)	.	.	.	.	(0.003)	0.38	.	.	-45 mm Ø x ~28 mm
IARM 155F	.	.	.	.	0.0016	(0.003)	.	.	.	0.0020	(0.004)	.	.	31 mm Ø x 2 or 18 mm
IMZ 112B ## BACKORDERED	.	.	.	.	0.013	.	.	.	.	0.010	.	.	.	40 mm Ø x 40 mm
VS UG8/10	.	.	.	.	(0.003)	.	.	.	.	0.0034	.	.	.	-45 mm Ø x ~28 mm
VS UG114	.	.	.	.	.	.	.	.	.	0.006	.	.	0.065	-45 mm Ø x ~25 mm
IMZ 162	.	.	.	.	.	.	.	.	.	0.12	.	.	.	40 mm Ø x 40 mm
VS UG113	.	.	.	.	.	.	.	.	.	0.006	0.007	.	0.169	-45 mm Ø x ~25 mm
BS 4620	0.00006	0.0001	.	0.0001	0.0001	0.0009	0.0002	0.0024	.	0.0026	0.0009	0.0002	.	38 mm Ø x ~7 or 19+ mm
<b>BS 51F</b>	(0.0002)	(0.0005)	[96.7]	(0.0001)	(0.0007)	(0.002)	(0.0008)	(0.003)	(0.005)	0.0012	(0.0024)	<b>17025</b>	(0.0009)	38 mm Ø x ~7 or 19+ mm
ECRM 192-1D	.	.	.	.	.	.	.	.	.	.	.	.	.	-35 mm Ø x ~30 mm
VS UG112	.	.	.	.	.	.	.	.	.	0.0028	0.005	.	0.0047	-45 mm Ø x ~25 mm
BS LF3	0.0001	(0.0001)	.	.	.	0.004	.	.	.	.	.	.	.	38 mm Ø x ~7 or 19+ mm
HRT FE2012-N	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 20 mm
IMZ 74A	(0.002)	(0.0004)	.	.	0.041	.	.	.	.	0.022	.	.	.	43 mm Ø x 20 mm
12X 19MNV56A	.	.	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x ~15 mm
ECRM 087-1D	.	.	.	.	.	.	.	0.0046	.	.	.	.	.	38 mm Ø x 25 or 30 mm
12X 15180A	.	.	.	.	.	.	.	.	.	.	.	0.0016	.	-40 mm Ø x ~20 mm
ECRM 194-2D	0.00155	.	.	.	0.0290	.	.	.	.	0.00322	.	.	.	39 mm Ø x 28 mm
BS 3962	.	.	.	.	.	.	.	.	.	.	.	.	.	37 mm Ø x ~7 or 19+ mm
VS UG7/11	.	.	.	.	.	.	.	.	.	0.20	0.385	.	.	-45 mm Ø x ~28 mm
HRT FE1999-N	0.0002	.	.	.	0.002	.	.	.	.	0.001	.	.	.	40 mm Ø x 20 mm last
BS XCCT	.	.	.	.	(0.001)	(0.005)	(<0.001)	(0.0004)	.	(0.002)	.	.	(<0.002)	36 mm Ø x ~7 or 19+ mm
IMZ 176A	.	.	.	.	.	.	.	.	.	.	(0.015)	.	.	40 mm Ø x 40 mm
BS 15A	(0.0002)	(0.0005)	.	.	0.041	.	(0.0003)	(0.003)	.	0.008	(0.004)	.	0.022	32 mm Ø x 17 mm last
ECRM 193-1D	.	.	.	.	0.0232	.	.	.	.	(0.0013)	.	.	.	36-41 mm Ø x 28-35 mm
BS 47A	.	.	.	.	0.002	(0.003)	.	.	.	0.003	.	.	.	38 mm Ø x ~7 or 19+ mm
Number	B	Ca	Fe	Mg	Nb	O	Pb	Sb	Ta	Ti	W	Zn	Zr	Units







**LOW ALLOY STEEL XRF SET**

Part Number: BS LAS-24 Set of 24 samples, each 35 - 45 mm ø x 7 mm discs **CRM, 17025** others are RM

Alloy	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	As	Ca	Co	N	Sn	V
300M	BS 4340M	0.414	0.74	0.004	<0.001	1.65	0.134	1.78	0.78	0.35	0.076	0.007	.	0.013	0.0020	0.009	0.056
1345	BS XCCV	0.44	1.75	0.012	0.024	0.28	0.015	0.019	0.041	0.007	0.033	0.0023	.	0.006	0.0056	(0.0004)	<0.003
3115	BS XCCT	0.158	0.52	0.005	0.011	0.28	0.027	1.27	0.65	0.020	0.006	0.004	.	0.017	0.0076	(0.002)	0.031
4130	BS 3932	0.321	0.54	0.016	0.018	0.33	0.200	0.19	1.00	0.229	0.020	0.004	0.0043	0.011	0.0070	0.012	0.005
4140	BS 1962	0.41	0.94	0.007	0.011	0.242	0.224	0.16	1.05	0.229	0.018	0.007	.	0.008	0.0095	0.010	0.004
4150 + S	<b>BS 42</b>	0.516	1.24	0.021	0.073	0.235	0.252	0.183	0.67	0.190	0.020	(0.004)	.	0.012	0.0080	0.012	0.003
4330	<b>BS 4330MOD</b>	0.316	0.92	0.0052	0.0010	0.269	0.105	1.83	0.848	0.478	0.031	0.0038	(0.001)	0.034	0.0031	0.0062	0.083
4340	<b>BS 4340</b>	0.418	0.695	0.0119	0.0187	0.279	0.149	1.79	0.807	0.231	0.028	0.0043	0.0005	0.0068	0.0080	0.0063	0.0033
4615	BS 51E	0.15	0.59	0.010	0.021	0.28	0.22	1.75	0.14	0.21	0.028	.	.	0.035	0.0086	0.010	(0.0011)
4620	BS 4620	0.189	0.57	0.006	0.018	0.25	0.216	1.75	0.072	0.24	0.032	(0.0084)	(0.0001)	0.012	0.0078	0.013	(0.0008)
4820	BS 4820	0.188	0.57	0.010	0.025	0.25	0.11	3.29	0.12	0.21	0.020	0.005	0.0046	0.008	0.0079	(0.008)	(0.002)
6150	<b>BS 43A</b>	0.49	0.82	0.0074	0.025	0.252	0.18	0.24	0.92	0.059	(0.003)	(0.005)	(0.0006)	0.008	0.0072	0.011	0.145
8620	BS 1931	0.194	0.84	0.007	0.018	0.235	0.116	0.42	0.50	0.168	0.021	0.007	(0.0008)	0.012	0.0079	0.007	0.002
8822	BS 8822	0.228	0.92	0.011	0.025	0.26	0.17	0.47	0.52	0.34	0.022	0.007	(0.0004)	0.019	0.0085	0.011	0.003
8740	BS 67B	0.40	0.94	0.007	0.020	0.23	0.19	0.53	0.51	0.22	0.024	.	.	0.011	0.0078	0.009	(0.002)
9310	BS 58D	0.127	0.45	0.010	0.005	0.32	0.156	3.02	1.35	0.14	0.042	.	.	0.009	0.0147	0.012	0.005
9325	BS 9325	0.25	0.91	0.008	0.007	0.32	0.13	3.29	1.48	0.31	0.030	(0.004)	0.0049	0.010	0.0089	0.009	0.004
P-20	BS 55E	0.307	0.72	0.014	0.024	0.60	0.032	0.053	1.66	0.40	(0.004)	.	.	(0.005)	0.0096	0.002	0.019
AMS 6418	BS 69B	0.2258	1.28	0.008	0.013	1.27	0.086	1.71	0.28	0.39	0.024	.	.	0.035	0.0057	0.006	(0.002)
A193	BS 4942	0.414	0.56	0.015	0.021	0.22	0.165	0.16	0.97	0.54	(0.004)	0.005	0.0006	0.010	0.0080	0.014	0.28
A485-1	BS A485-1	0.98	1.10	0.019	0.004	0.62	0.16	0.13	1.07	0.029	0.017	0.006	.	0.010	0.0060	0.011	0.003
E52100	BS 53E	1.08	0.37	0.007	0.012	0.24	0.11	0.26	1.45	0.10	0.003	.	.	0.011	0.0086	0.005	0.004
Nitriding	BS 68C	0.38	0.60	0.018	0.008	0.305	0.178	0.166	1.77	0.36	1.06	(0.004)	(0.0002)	0.011	0.0045	0.008	0.007
LF 3	BS LF 3	0.183	0.52	0.006	0.018	0.206	0.080	3.36	0.098	0.056	0.017	0.006	(0.0001)	0.056	0.0054	0.006	(0.002)

Alloy Number C Mn P S Si Cu Ni Cr Mo Al As Ca Co N Sn V  
 ## this item sold out, most BS are available as XRF

**CRM SOLUBLE ELEMENTS IN LOW ALLOY STEEL SET**

available in set/7 only -S = Soluble, -T = Total 38 mm ø x 30 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al-S	Al-T	B-S	B-T	Mo
NCS HS11717a-1	0.0023	0.018	0.012	0.0027	0.0054	0.0036	0.011	0.023	0.0069	0.0078	0.0002	0.0004	0.0053
NCS HS11717a-2	0.0028	0.104	0.014	0.011	0.077	0.049	0.045	0.042	0.024	0.026	0.0011	0.0012	0.304
NCS HS11717a-3	0.032	0.303	0.018	0.067	1.55	0.403	0.563	0.236	0.295	0.298	0.0018	0.0020	0.034
NCS HS11717a-4	0.096	0.669	0.012	(0.050)	1.09	0.316	0.400	0.102	0.214	0.216	0.0085	0.0096	0.144
NCS HS11717a-5	0.243	1.04	0.030	0.042	0.769	0.248	0.393	0.106	0.101	0.104	0.0071	0.0074	0.105
NCS HS11717a-6	0.387	1.47	0.038	0.030	0.436	0.167	0.206	0.409	0.050	0.051	0.0047	0.0049	0.071
NCS HS11717a-7	0.498	2.10	0.050	0.022	0.176	0.075	0.107	0.612	0.022	0.024	0.0031	0.0033	0.196

Number	As	Bi	Co	N	Nb	Pb	Sb	Sn	Ti	V
NCS HS11717a-1	0.0034	<0.00001	0.0015	0.0016	<0.0005	<0.0001	0.00041	0.00020	0.0002	(0.0001)
NCS HS11717a-2	0.011	<0.00001	0.058	0.0017	0.031	<0.0001	0.00031	0.00073	0.020	0.011
NCS HS11717a-3	0.019	<0.00001	0.099	0.0032	0.079	<0.0001	0.00041	0.016	0.049	0.052
NCS HS11717a-4	0.073	(0.00001)	0.146	0.0031	0.223	<0.0001	0.00044	0.049	0.202	0.098
NCS HS11717a-5	0.071	(0.00001)	0.296	0.0048	0.318	<0.0001	0.00052	0.099	0.178	0.257
NCS HS11717a-6	0.045	(0.00001)	0.248	0.0049	0.106	<0.0001	0.00048	0.151	0.124	0.201
NCS HS11717a-7	0.034	(0.00001)	0.198	0.0063	0.153	<0.0001	0.00050	0.197	0.088	0.147

**RM TOOL STEEL XRF SET**

Part Number: BS TS-18 AVAILABLE INDIVIDUALLY **17025** ~7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	N
A-2	BS 36C	0.96	0.46	0.023	0.027	0.31	0.18	0.19	5.01	0.99	.	(0.04)	0.11	0.03	.
A-10	BS A-10	1.41	1.75	0.016	0.022	1.15	0.16	1.82	0.24	1.53	0.006	<0.005	(0.004)	(0.010)	.
D-2	BS 37D	1.54	0.28	0.021	0.015	0.29	0.063	0.21	11.07	1.09	.	0.16	0.80	0.07	0.016
H-10	BS 49	0.36	0.33	0.014	0.015	0.92	0.072	0.20	3.51	2.41	0.004	0.31	0.62	2.00	0.0186
H-11	BS TH11	0.423	0.31	0.016	0.005	0.88	0.041	0.11	5.04	1.27	.	(0.01)	0.46	(0.008)	.
H-12	BS TH12	0.372	0.40	0.020	0.005	0.92	0.064	0.16	5.02	1.41	.	1.06	0.62	0.07	.
H-13	BS 34D	0.395	0.38	0.017	0.005	1.06	0.049	0.10	5.15	1.24	.	0.10	0.94	0.031	.
L-6	<b>BS 39B</b>	0.67	0.62	0.009	0.019	0.214	0.163	1.45	0.79	0.17	(0.011)	.	(0.01)	(0.02)	.
M-1	BS TM1	0.86	0.23	0.007	0.012	0.46	0.054	0.057	3.72	8.4	.	1.7	1.05	0.45	.
M-2	BS 32C	0.84	0.29	(0.018)	0.0010	0.29	0.13	0.35	3.98	4.85	(0.02)	6.3	2.03	0.31	.
O-1	<b>BS 35D</b>	0.879	1.13	0.021	0.024	0.22	0.141	0.132	0.495	0.035	(0.005)	0.46	0.181	0.012	.
O-6	<b>BS 41</b>	1.41	0.89	0.013	0.011	1.02	0.038	0.15	0.22	0.23	(0.007)	0.035	0.046	.	.
S-1	BS 33E	0.49	0.29	0.022	0.005	0.20	0.038	0.08	1.25	0.045	.	2.75	0.19	0.006	.
S-5	BS 38C	0.60	0.81	0.011	0.012	2.08	0.26	0.24	0.28	0.41	0.015	0.004	0.214	0.036	0.0081
S-7	BS TS7	0.529	0.70	0.016	0.010	0.27	0.05	0.10	3.18	1.34	.	0.19	0.35	0.043	.
T-1	<b>BS 30D</b>	0.745	0.348	0.029	0.0010	0.301	0.116	0.191	3.93	0.342	0.0123	17.73	1.077	0.101	0.0168
	BS 10V	2.46	0.52	0.019	0.079	0.89	0.076	0.08	5.41	1.30	<0.002	0.013	9.50	0.009	0.064
HP9-4-30	BS 9-4-30	0.30	0.22	0.008	<0.001	0.06	0.09	7.25	1.00	1.00	0.004	0.01	0.085	4.40	0.0015

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	W	V	Co	N
-------	--------	---	----	---	---	----	----	----	----	----	----	---	---	----	---

## TOOL STEEL

## CONTINUED ON THE NEXT PAGE

# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	W	Al
1	BS PM15	3.54	0.416	0.0198	0.0127	0.912	0.142	0.203	5.33	0.0330	1.22	0.111	0.0029	14.79	0.109	0.0025
2	BS 107	2.46	0.52	0.019	0.079	0.89	0.076	0.08	5.41	0.009	1.30	0.064	.	9.50	0.013	<0.002
1	DSZU C070	2.43	0.38	0.021	0.054	0.79	0.130	0.153	5.57	0.053	1.28	.	.	9.39	0.29	.
1	BS A-11	2.32	0.507	0.023	0.123	0.98	0.092	0.25	5.21	0.044	1.25	0.110	0.0019	9.24	(0.080)	0.0054
1	DSZU C082	2.32	0.33	0.029	0.014	0.36	0.118	0.239	12.24	0.035	1.11	.	.	4.02	0.17	.
1	ECRM 288-1D	2.08	0.292	0.024	(0.0012)	0.260	0.060	0.298	12.00	0.018	0.103	0.0151	.	0.055	(0.68)	0.012
1	DSZU C080	1.68	0.31	0.025	0.020	1.89	0.120	0.162	5.06	0.028	0.39	.	.	5.12	3.40	.
1	BS 37G	1.663	0.326	0.021	0.0007	0.352	0.044	0.152	11.77	0.0166	0.78	0.0310	0.0025	0.70	0.034	0.0060
1	BS TS15	1.64	0.27	(0.017)	0.067	0.357	0.065	(0.18)	4.12	4.87	0.48	0.045	0.0016	4.81	11.6	0.0032
1	ECRM 274-1D	1.563	0.397	0.0148	0.0096	1.057	0.0281	0.077	8.036	(0.0230)	1.4551	0.0769	(0.0011)	4.010	0.0087	(0.0025T)
2	CT D2	1.53	0.48	0.013	0.005	0.40	0.04	0.10	11.46	0.02	0.75	.	.	0.89	<0.01	.
1	IARM 41D	1.519	0.256	0.021	0.012	0.256	0.047	0.114	11.5	(0.020)	0.74	0.0152	(0.003)	0.77	0.034	0.014
2	BS 41A	1.50	0.93	0.004	0.001	0.97	0.034	0.17	0.20	0.006	0.19	0.0077	0.004	(0.003)	<(0.003)	0.010
1	IARM 45B	1.42	0.90	0.010	0.008	0.92	0.018	0.024	0.061	0.004	0.24	0.0080	0.002	(0.003)	<(0.004)	0.010
2	BS 41	1.41	0.89	0.013	0.011	1.02	0.038	0.15	0.22	.	0.23	.	.	0.046	0.0035	(0.007)
2	BS A-10	1.41	1.75	0.016	0.022	1.15	0.016	0.82	0.24	(0.010)	1.53	.	.	(0.004)	<0.005	0.006
1	IARM 251A	1.398	0.33	0.014	0.058	0.58	0.13	0.131	4.1	0.129	5.16	0.044	0.003	3.9	5.5	0.01
2	IARM 45A	1.39	0.88	0.014	0.012	1.02	0.049	0.11	0.13	0.004	0.25	0.0079	0.003	0.005	.	0.011
1	DSZU C073	1.32	0.23	0.019	0.013	0.27	0.112	0.198	3.97	8.31	4.97	.	.	2.82	6.40	.
2	CT X27081	1.32	0.20	0.004	0.001	0.24	0.026	0.031	0.052	.	0.008	.	.	3.39	.	.
1	DSZU C072	1.10	0.29	0.024	0.019	0.55	0.106	0.192	4.25	0.011	5.39	.	.	3.59	6.33	.
3	CZ HS-2A	1.24	0.27	0.024	0.017	0.24	0.08	0.21	4.15	9.9	3.75	.	0.003	3.4	9.3	0.035
1	DSZU C077	1.16	0.19	0.030	0.024	0.40	0.142	0.271	4.07	7.73	3.05	.	.	2.04	12.17	.
1	DSZU C075	1.16	0.16	0.021	0.015	0.47	0.120	0.202	3.10	8.03	4.06	.	.	2.10	9.27	.
1	BS M-47	1.14	0.20	0.020	0.002	0.464	0.080	0.17	3.72	4.99	9.24	0.0219	(0.004)	1.23	1.36	(0.002)
1	IMZ 102/3	1.11	0.15	0.014	(0.0045)	1.06	0.13	0.021	1.59	.	0.43	.	.	(0.012)	.	0.017
1	DSZU C074	1.10	0.16	0.023	0.020	1.16	0.141	0.158	3.93	5.08	5.21	.	.	1.94	6.47	.
1	DSZU C071	1.06	0.20	0.020	0.028	0.38	0.162	0.149	3.77	8.10	9.67	.	.	1.07	1.74	.
1	SS 487/1	1.02	0.26	0.022	0.029	0.18	.	(0.14)	3.91	7.95	9.41	.	.	1.14	1.80	0.006
1	DSZU C081	1.01	0.32	0.017	0.011	1.10	0.124	0.207	7.78	0.029	2.13	.	.	0.25	0.05	.
2	CT M7	1.00	0.29	0.012	0.003	0.34	0.066	0.10	3.60	0.015	8.49	.	.	2.02	1.78	.
1	IARM 39B	0.99	0.54	0.017	0.003	0.35	0.10	0.14	4.79	0.014	1.01	0.0096	0.003	0.22	(0.026)	0.006
1	IARM 39C	0.99	0.45	0.019	0.007	0.28	0.077	0.144	4.99	0.013	0.97	0.011	0.0029	0.21	0.011	0.017
2	BS 36D	0.97	0.68	0.021	0.007	0.27	0.060	0.089	5.25	0.010	0.96	0.0108	.	0.29	0.028	0.010
2	CT A2	0.95	0.72	0.010	0.004	0.40	0.06	0.10	5.13	.	1.05	.	.	0.22	.	.
1	SS 485/1	0.94	0.41	0.043	0.039	0.30	.	(0.14)	4.02	4.97	0.66	.	.	1.02	17.8	(0.006)
1	IARM 320A	0.93	0.33	0.021	(0.0015)	0.36	0.091	0.204	4.22	4.90	4.79	(0.014)	0.0032	1.76	6.01	0.023
2	CT O1	0.91	1.27	0.009	0.004	0.36	0.05	0.06	0.49	.	0.07	.	.	0.25	0.51	.
1	ECRM 290-1D	0.91	0.24	0.016	0.016	0.08	0.081	0.33	4.18	5.12	4.81	0.0325	.	1.92	6.24	.
2	CT M10	0.88	0.27	0.016	0.004	0.30	0.061	0.14	3.97	0.012	7.89	.	.	1.99	0.008	.
2	BS 35D	0.879	1.13	0.021	0.024	0.22	0.141	0.132	0.495	0.012	0.035	.	(0.003)	0.181	0.46	(0.005)
1	IARM 304A	0.857	0.260	0.019	0.0016	0.36	0.14	0.133	3.55	0.278	8.04	0.034	0.002	1.23	1.65	0.009
2	14X 14946D	0.85	0.53	0.051	0.048	0.46	0.25	1.06	5.06	0.44	0.21	.	.	1.03	16.9	.
2	BS 32D	0.85	0.30	0.027	0.0022	0.25	0.039	0.053	4.14	0.010	4.92	0.018	.	1.82	6.15	0.018
1	IARM 306B	0.84	0.24	0.006	(0.001)	0.21	0.058	0.095	4.12	0.010	4.2	0.0049	(0.002)	0.98	(0.01)	0.08
1	SRM 1157	0.836	0.34	0.011	0.004	0.18	0.08	0.228	4.36	0.028	4.86	.	.	1.82	6.28	.
1	BS M-50	0.834	0.244	0.0066	0.0009	(0.205)	0.064	0.074	4.28	0.0151	4.29	0.0057	(0.0018)	0.99	0.0052	0.073
2	14X 14948C	0.83	0.65	0.011	0.017	0.26	0.04	0.29	4.04	0.16	0.14	.	.	0.65	18.8	.
2	CT M2	0.82	0.33	0.012	0.004	0.27	0.06	0.25	4.03	0.05	4.96	.	.	1.81	6.47	.
1	IARM 44C	0.82	0.301	0.027	0.004	0.31	0.12	0.132	4.04	0.247	5.02	0.033	0.004	1.91	6.0	0.05
2	CT M1	0.80	0.30	0.012	0.005	0.22	0.087	0.12	3.91	.	8.22	.	.	1.05	1.58	.
1	IARM FeTi-18	0.80	0.295	0.026	<(0.0010)	0.30	0.034	0.14	3.98	0.096	0.124	0.0195	0.026	1.05	18.0	0.054
1	BS 30D	0.745	0.348	0.029	0.010	0.301	0.116	0.191	3.93	0.101	0.342	0.0168	0.0189	1.077	17.73	0.0123
1	IARM 281A	0.74	0.30	0.015	0.019	0.29	0.096	0.15	3.89	4.8	0.49	0.0064	0.004	0.90	17.6	0.007
1	SS 486/1	0.74	0.21	0.029	0.021	0.27	.	(0.06)	4.54	0.08	5.20	.	.	1.82	5.80	(0.005)
1	IARM 40C	0.72	1.91	0.014	0.012	0.32	0.142	0.255	0.99	0.010	1.27	0.0083	0.008	0.010	0.009	0.019
1	14X HS1C	0.72	0.29	0.018	0.020	0.23	0.07	0.28	4.00	0.25	0.36	0.023	.	1.04	17.2	.
3	CZ HS-1A	0.72	0.28	0.023	0.011	0.28	0.08	0.14	4.15	4.7	0.06	.	0.003	1.33	17.5	0.03
1	IARM 43B	0.711	0.56	0.008	0.013	0.251	0.180	1.39	0.651	0.012	0.206	0.0093	0.0047	0.0035	<0.005	0.021
2	BS 40B	0.71	2.28	0.020	0.006	0.35	0.076	0.089	1.18	0.020	1.07	0.0076	0.002	0.10	0.11	0.002
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	W	Al
1	DSZU C076	0.69	0.18	0.024	0.022	0.58	0.120	0.213	5.75	13.88	4.29	.	.	2.03	9.81	.
1	BS 481/1	0.68	0.25	0.023	0.022	0.15	0.15	(0.09)	3.40	0.31	0.28	.	.	0.56	14.0	.
1	IARM 40B	0.68	1.98	0.012	0.003	0.39	0.050	0.096	1.04	0.015	1.22	0.0107	0.003	0.014	0.013	(0.006)
2	BS 39B	0.67	0.62	0.009	0.019	0.214	0.163	1.45	0.79	(0.02)	0.17	.	.	(0.01)	.	(0.011)
1	SS 482/1	0.67	0.26	0.027	0.027	0.14	.	(0.16)	3.95	0.29	0.40	.	.	1.04	17.8	.
1	DSZU C078	0.67	0.22	0.022	0.019	0.117	0.116	0.121	3.98	0.022	0.14	.	.	1.04	18.30	.
1	SS 483/1	0.65	0.22	0.023	0.023	0.16	.	(0.08)	2.90	2.06	0.18	.	.	0.22	9.28	.
2	BS 38C	0.60	0.81	0.011	0.012	2.08	0.26	0.24	0.28	0.036	0.41	0.0081	0.007	0.214	0.004	0.015
1	ECRM 179-2D	0.598	0.539													

## TOOL STEEL CONTINUED FROM THE PREVIOUS PAGE

Number	Als	As	B	Ca	Nb	O	Pb	Sb	Sn	Ta	Zr	Units
<b>BS PM15</b>	.	0.0040	(0.0002)	(0.0001)	0.014	0.0129	(0.00001)	(0.0010)	0.0034	(0.0003)	(0.0005)	38 mm Ø x 19+ mm <b>17025</b>
BS 10V	.	.	.	.	.	.	.	.	.	.	.	41 mm Ø x -7 or 19+ mm last
DSZU C070	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
<b>BS A-11</b> Fe:79.5	.	0.0057	0.0008	(0.0002)	(0.0070)	0.028	(0.00006)	(0.001)	0.0055	.	(0.001)	38 mm Ø x -7 or 19+ mm <b>17025</b>
DSZU C082	.	.	.	.	.	.	.	.	.	.	.	~35 mm Ø x 25 mm
ECRM 288-1D	.	(0.0065)	.	.	.	.	.	.	.	.	.	~36-41 mm Ø x 28-35 mm
DSZU C080	.	.	.	.	.	.	.	.	.	.	.	~35 mm Ø x 25 mm
BS 37G	.	0.0026	0.0003	0.0014	0.0026	.	0.0005	0.0009	0.0010	.	.	34 mm Ø x -7 or 19+ mm
<b>BS TS15</b>	.	(0.006)	(0.0005)	(0.001)	0.009	(0.018)	.	Fe:71.4	0.0074	.	(0.003)	38 mm Ø x -7 or 19+ mm <b>17025</b>
ECRM 274-1D	.	(0.0013)	(0.0005)	.	.	(0.0026)	(0.000064)	(0.0002)	(0.0010)	.	.	38 mm Ø x 25 mm
CT D2	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
IARM 41D	.	(0.01)	(0.0006)	(0.0008)	(0.004)	(0.003)	(0.0008)	.	(0.005)	.	(0.002)	31 mm Ø x 2 or 18 mm
<b>BS 41A</b>	.	0.002	.	0.0006	.	0.002	.	.	0.002	.	.	38 mm Ø x -7 or 19+ mm <b>25(pre-17025)</b>
IARM 45B	.	(0.002)	(0.0001)	(0.001)	(0.002)	(0.0005)	(0.001)	0.008	.	.	(0.001)	31 mm Ø x 2 or 18 mm
<b>BS 41</b>	.	.	.	.	.	.	.	.	(0.008)	.	.	last <b>17025</b>
BS A-10	.	.	.	.	.	.	.	.	.	.	.	42 mm Ø x -7 or 19+ mm
IARM 251A	.	0.016	(0.002)	(0.0005)	0.016	(0.01)	(0.002)	.	0.011	.	(0.002)	40 mm Ø x -7 or 19+ mm
IARM 45A	.	(0.003)	(0.0001)	.	0.002	(0.0017)	(<0.005)	.	0.005	.	.	31 mm Ø x 2 mm
DSZU C073	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
CT X27081	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm last
DSZU C072	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
CZ HS-2A	.	.	.	.	.	.	.	.	0.01	.	.	~39 mm Ø x 25 mm
DSZU C077	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
DSZU C075	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
<b>BS M-47</b>	.	0.006	.	(0.002)	(0.004)	0.0037	.	.	0.006	.	.	38 mm Ø x -7 or 19+ mm <b>17025</b>
IMZ 102/3	.	.	(0.0007)	.	.	.	.	.	.	.	(0.007)	40 mm Ø x 40 mm
DSZU C074	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
DSZU C071	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
SS 487/1	.	(0.012)	.	.	.	.	.	.	(0.006)	.	.	38 mm Ø x 19 mm
DSZU C081	.	.	.	.	.	.	.	.	.	.	.	~35 mm Ø x 25 mm
CT M7	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
IARM 39B	.	.	.	.	0.006	.	.	.	0.004	.	.	31 mm Ø x 2 or 18 mm
IARM 39C	.	(0.005)	0.001	(0.001)	0.0040	0.001	(0.0001)	(0.002)	0.005	.	(0.002)	31 mm Ø x 2 or 18 mm
BS 36D	.	0.002	.	.	.	.	.	.	0.016	.	.	38 mm Ø x -7 or 19+ mm
CT A2	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
SS 485/1	.	(0.022)	.	.	.	.	.	.	0.019	.	.	38 mm Ø x 19 mm
IARM 320A	.	0.013	0.0011	.	(0.015)	(0.0021)	.	.	0.008	.	(0.003)	31 mm Ø x 2 or 18 mm
CT 01	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -19 mm
ECRM 290-1D	.	.	.	.	.	.	.	.	.	.	.	~36-41 mm Ø x 28-35 mm
CT M10	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
<b>BS 35D</b>	.	.	.	.	(0.001)	.	.	.	0.006	.	.	38 mm Ø x -7 or 19+ mm <b>17025</b>
IARM 304A	.	(0.01)	0.002	(0.002)	0.021	0.002	.	(0.001)	0.006	(0.002)	(0.002)	31 mm Ø x 2 or 18 mm
14X 14946	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
BS 32D	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x -7 or 19+ mm
IARM 306B	.	(0.003)	(0.001)	.	0.007	(0.001)	(0.001)	0.0025	0.004	.	(0.002)	31 mm Ø x 2 or 18 mm
SRM 1157	.	.	.	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
<b>BS M-50</b>	.	0.0035	(0.0001)	(0.001)	0.0008	0.0010	(0.0001)	(0.0006)	0.0045	Fe:88.8	(0.0006)	38 mm Ø x -7 or 19+ mm <b>17025</b>
14X 14948C	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm last of stock
CT M2	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
IARM 44C	.	(0.01)	(0.002)	.	0.012	(0.003)	(0.002)	(0.004)	0.010	(0.004)	.	31 mm Ø x 2 mm
CT M1	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
IARM FeT1-18	.	.	.	.	(0.004)	(0.0027)	.	.	(0.010)	.	.	31 mm Ø x -2 or 18+ mm
<b>BS 30D</b>	.	0.0128	(0.0002)	0.0004	0.0071	0.0019	(0.0002)	0.0032	0.0246	(0.02)	(0.0001)	38 mm Ø x -7 or 19+ mm <b>17025</b>
IARM 281A	.	(0.02)	(0.003)	.	0.094	(0.003)	.	.	0.02	.	(0.002)	31 mm Ø x 2 or 18 mm
SS 486/1	.	(0.016)	.	.	.	.	.	.	0.014	.	.	38 mm Ø x 19 mm
IARM 40C	.	0.008	0.0009	(0.001)	0.003	0.0013	.	.	0.008	.	(0.002)	31 mm Ø x 2 or 18 mm
14X HS1C	.	.	.	.	.	.	.	.	(0.035)	.	.	40 mm Ø x 15 mm
CZ HS-1A	.	.	.	.	.	.	.	.	0.02	.	.	~39 mm Ø x 25 mm
IARM 43B	.	0.005	0.0002	.	0.004	0.0016	<0.0005	.	0.013	.	.	31 mm Ø x 2 or 18 mm
BS 40B	.	0.004	0.0006	.	.	.	.	.	0.005	.	.	41 mm Ø x -7 or 19+ mm
Number	Als	As	B	Ca	Nb	O	Pb	Sb	Sn	Ta	Zr	Units
DSZU C076	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
SS 481/1	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm last of stock
IARM 40B	.	.	(0.0010)	.	0.005	(0.0014)	.	.	0.004	.	.	31 mm Ø x 2 or 18 mm
<b>BS 39B</b>	.	.	.	.	.	.	.	.	(0.011)	.	.	41 mm Ø x -7 or 19+ mm <b>17025</b>
SS 482/1	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
DSZU C078	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x -15 mm
SS 483/1	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
BS 38C	.	0.011	.	.	(0.002)	.	0.022	.	0.022	.	.	38 mm Ø x -7 or 19+ mm
ECRM 179-2D	.	.	.	.	0.00144	.	.	0.00175	.	.	.	30 to 35 mm Ø x 20 mm
IARM 47B	.	.	(<0.001)	.	(0.002)	(0.0014)	(0.0003)	.	0.008	.	.	31 mm Ø x 2 (LAST) or 18 (OK) mm
DSZU C079	.	.	.	.	.	.	.	.	.	.	.	~35 mm Ø x 25 mm
BS 33D	.	.	.	.	.	.	.	.	0.005	.	.	41 mm Ø x 12 mm
BS 33E	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 12 mm
CT X67975	.	.	.	.	.	.	<0.001	.	0.003	.	.	30-35 mm Ø x -16 mm
IARM 259A	.	0.006	0.0003	.	0.003	0.0014	<0.0005	.	0.004	.	0.001	31 mm Ø x 2 mm
<b>BS D-6</b>	.	0.011	(0.0003)	0.0011	(0.002)	(0.0008)	(0.0003)	0.0012	0.0104	Mg: 0.0002	.	38 mm Ø x -7 or 19 mm <b>17025</b>
IMZ 57/1	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
IARM 46B	.	(0.01)	0.0003	.	0.003	0.002	<0.002	.	0.016	.	.	31 mm Ø x 2 or 18 mm
IMZ 53/1	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
IMZ 56/1	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
<b>BS H-19</b>	.	0.0056	.	.	0.008	0.0071	.	.	0.0056	.	.	38 mm Ø x -7 or 19+ mm <b>17025</b>
IARM 255A	.	(0.002)	0.0004	(0.0004)	0.004	0.0011	<0.001	.	0.006	.	<0.005	31 mm Ø x 2 or 18 mm
IMZ 58/1	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
IMZ 51/1	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
ECRM 276-2D	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 25 or 30 mm
<b>BS H-13A</b> Fe:90.2	.	0.0050	(0.0007)	(0.0006)	0.0052	(0.016)	(0.0004)	(0.002)	(0.005)	.	(0.002)	38 mm Ø x -7 or 19+ mm <b>17025</b>
CT H13	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
IARM 255B	.	.	.	.	(0.006)	.	.	.	(0.006)	.	.	31 mm Ø x 2 or 18 mm
IARM 42C	.	(0.01)	0.0011	(0.0005)	(0.004)	0.003	0.0007	(0.004)	(0.006)	(0.004)	(0.002)	31 mm Ø x 2 or 18 mm
ECRM 271-1D	.	0.0057	.	0.0009	.	0.0020	.	.	0.0084	.	.	35 mm Ø x 25 mm
BS 49	.	.	.	.	.	.	.	.	(0.004)	.	.	49 mm Ø x -7 or 19+ mm
BS 9-4-30	.	.	.	.	.	.	.	.	.	.	.	35 mm Ø x -7 or 19+ mm
IARM 341A	.	(0.003)	0.0005	0.0011	(0.005)	0.0008	(0.001)	(0.001)	(0.005)	.	(0.003)	31 mm Ø x 2 or 18 mm
IMZ 196	.	.	0.065	.	0.073	.	.	.	.	.	.	37 mm Ø x 30 mm
IMZ 170	.	.	.	.	0.087	.	.	(0.002)	0.007	.	.	40 mm Ø x 40 mm
CZ CM-17A	0.0105	0.0060	.	.	.	.	0.0177	.	0.0109	.	.	~37 mm Ø x -25 mm
VS LG43/1	.	.	.	.	.	.	.	.	.	.	.	~45 mm Ø x -28 mm
IMZ 197	.	.	(0.007)	.	(0.011)	.	.	.	0.015	.	.	37 mm Ø x 30 mm
NCS HS20741	.	.	.	.	.	.	.	.	.	.	.	35 mm Ø x 40 mm
VS LG42/1	.	.	.	.	.	.	.	.	.	.	.	~45 mm Ø x -28 mm
VS LG37/1	.	.	.	.	.	.	.	.	.	.	.	~45 mm Ø x -28 mm
IMZ 179	.	(0.007)	.	.	(0.004)	.	.	.	0.010	.	.	40 mm Ø x 40 mm
IMZ 157	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
NCS HS20742	.	.	.	.	.	.	.	.	.	.	.	35 mm Ø x 40 mm
IMZ 177	.	.	.	.	.	.	.	.	0.008	.	.	40 mm Ø x 40 mm
13X 14713A	.	.	.	Mg:0.0016	.	.	.	.	0.0034	.	.	~40 mm Ø x -15 mm
SS 422	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
IMZ 101/2	.	.	(0.0005)	.	.	.	.	.	.	.	(0.002)	40 mm Ø x 40 mm
SS 423	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
SS 424	.	.	.	.	.							

## ALUMINUM IN STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM and 2 = RM

#	Number	Al	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	Ti	V
1	ECRM 299-1D	5.33	0.172	22.32	0.0154	0.2678	0.0152	0.00022	0.299	0.0382	0.0187	0.0186	0.0198	.	0.1289	0.0329
1	IMZ 158	1.56	0.24	25.51	0.091	1.34	0.015	0.007	2.23	0.097	.	0.025	.	.	0.12	0.078
1	13X PH17700A	1.172	6.98	16.88	0.0732	0.496	0.0181	0.0008	0.551	0.146	0.0464	0.340	0.0192	0.0201	0.051	0.0390
1	<b>BS 192</b>	1.17	7.11	16.44	0.074	0.835	0.025	0.0005	0.387	0.412	0.104	0.430	0.0290	0.168	0.076	0.124
2	CT X92834	1.14	8.32	12.57	0.035	0.044	0.003	0.003	0.019	0.030	0.030	2.20	.	0.001	0.019	<0.004
1	IARMPe177PH-18	1.09	7.11	17.08	0.080	0.730	0.020	(0.0005)	0.51	0.36	0.048	0.350	0.0153	0.009	0.083	0.062
1	13X PH13800A	1.075	8.04	12.53	0.0386	0.0332	0.0064	0.0030	0.081	0.0449	0.0220	2.10	0.0041	.	0.0122	0.0188
1	IARM 21D	1.03	8.29	12.69	0.032	0.052	0.008	(0.0014)	0.039	0.017	0.078	2.23	0.0037	(0.005)	0.016	0.017
2	BS 184A	1.00	8.34	12.66	0.035	0.06	0.007	0.001	0.080	0.041	0.036	2.20	0.0045	(0.006)	0.051	0.014
1	<b>BS 192A</b>	0.98	7.01	16.44	0.066	0.768	0.021	<0.002	0.300	0.334	0.114	0.28	0.029	0.208	0.083	0.077
1	IARM 152C	0.94	7.30	16.99	0.072	0.74	0.024	0.0006	0.263	0.316	0.113	0.36	0.0172	0.012	0.098	0.072

Number	As	B	Ca	O	Sn	Ta	W	Zr	Units
ECRM 299-1D	0.0054	0.0002	.	.	.	.	.	0.1775	40 mm Ø x 25 mm
IMZ 158	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
13X PH17700A	.	0.0033	.	.	0.0055	.	0.009	.	~38 mm Ø x ~15 mm
<b>BS 192</b>	(0.005)	(0.0003)	0.0007	0.0014	0.008	(0.001)	0.05	.	38 mm Ø x ~7 or 19+ mm
CT X92834	.	0.0009	.	.	0.002	.	.	<0.001	30-35 mm Ø x x ~19 mm
IARMPe177PH-18	.	(0.0017)	.	.	(0.006)	.	(0.011)	.	31 mm Ø x 2 or 18 mm
13X PH13800A	.	.	.	.	0.0051	.	.	.	~38 mm Ø x ~15 mm
IARM 21D	.	.	.	.	.	.	(0.012)	.	31 mm Ø x 2 or 18 mm
BS 184A	.	(0.0004)	(0.0003)	(0.0003)	(0.002)	.	0.032	.	38 mm Ø x ~7 or 19+ mm
<b>BS 192A</b>	(0.0035)	(0.0003)	(0.0006)	(0.0006)	0.008	.	0.048	.	38 mm Ø x ~7 or 19+ mm
IARM 152C	(0.004)	0.0029	(0.0005)	(0.001)	0.007	(0.005)	0.026	.	31 mm Ø x 2 mm

## CALCIUM IN STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM and 2 = RM

#	Number	Ca	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	V	W
1	<b>BS Ca304-4</b>	0.0075	8.77	18.26	0.096	0.783	0.0205	0.0070	0.887	0.143	(0.007)	0.0041	0.061	0.063	0.0686	0.0056
1	13X 14923A	0.0044	0.452	11.26	0.205	0.501	0.0197	0.0031	0.330	0.0563	0.0207	0.819	0.0321	0.005	0.295	.
1	ECRM 379-1D	0.0033	30.83	26.79	0.0121	1.804	0.0166	0.0006	0.393	0.984	0.0390	3.290	0.0550	(0.0028)	0.0663	(0.0091)
2	BS 193	0.0020	1.82	18.48	0.104	12.11	0.018	0.002	0.66	0.088	0.028	0.21	0.37	0.014	0.107	(0.007)
2	BS SS4952	0.0019	0.23	13.15	0.347	0.41	0.016	0.003	0.66	0.045	0.030	0.049	0.027	0.004	0.089	(0.007)
2	BS 82E	0.0014	12.49	22.38	0.062	1.61	0.027	0.001	0.58	0.26	0.12	0.31	0.072	0.062	0.064	0.041
1	<b>BS 9942</b>	0.0014	13.55	18.21	0.021	1.84	0.025	0.006	0.49	0.305	0.086	3.30	0.071	0.005	0.072	0.032
1	<b>BS 9842</b>	0.0010	20.02	24.19	0.059	1.50	0.025	0.0016	0.99	0.147	0.237	0.111	0.037	0.026	0.075	0.011
1	ECRM 272-1D	0.00090	0.2445	11.927	0.2815	0.600	0.0156	0.0196	0.420	0.0192	0.0145	0.0030	0.0508	0.0028	0.0167	.
2	BS 94C	0.0008	0.43	25.90	0.057	0.45	0.024	0.002	0.62	0.056	0.042	0.20	0.065	0.032	0.12	(0.03)
2	BS 87F	0.0007	10.12	17.30	0.055	1.64	0.024	0.025	0.67	0.28	0.17	0.29	0.037	0.57	0.13	0.050

Number	Al	As	B	O	Pb	Sb	Sn	Ti	Zn	Units
<b>BS Ca304-4</b>	0.017	0.0063	0.0031	0.013	0.0008	(0.0002)	0.0024	0.0046	Zr:0.0036	~38 mm Ø x ~38mm Fe: 70.7 <b>17025</b>
13X 14923A	0.003	.	.	.	.	.	0.004	.	.	~40 mm Ø x ~15 mm
ECRM 379-1D	(0.00246)	(0.0018)	0.00190	(0.0027)	(0.000038)	0.00057	0.0021	(0.0014)	.	38 or 45 mm Ø x 25 mm
BS 193	(0.003)	.	0.0007	(0.004)	.	.	0.004	0.003	.	32 mm Ø x ~7 or 19+ mm
BS SS4952	0.003	0.002	(0.0004)	0.005	.	.	0.004	0.002	.	38 mm Ø x ~7 or 19+ mm
BS 82E	0.006	.	0.0024	.	.	.	0.006	0.003	.	38 mm Ø x ~7 to 19 mm last
<b>BS 9942</b>	0.004	(0.004)	0.0014	(0.0023)	.	.	0.006	(0.002)	.	44 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
<b>BS 9842</b>	0.014	(0.002)	0.0025	(0.0044)	.	.	0.005	0.003	.	38 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
ECRM 272-1D	0.0046	0.0116	0.0018	.	.	0.0007	.	0.00096	0.0031	38 mm Ø x 25 or 30 mm
BS 94C	0.004	.	(0.0005)	0.0061	.	.	0.006	.	.	44 mm Ø x ~7 or 19+ mm
BS 87F	0.004	0.005	(0.0006)	0.005	.	.	0.004	0.004	.	41 mm Ø x ~7 or 19+ mm

## COPPER IN STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM and 2 = RM

\* Provisional Analysis

#	Number	Cu	Ni	Cr	C	Mn	P	S	Si	Co	Mo	N	Nb	Ti	V	W
1	13X PH 3N	5.83	3.03	16.0	0.110	0.39	0.0136	0.019	1.25	0.306	0.74	0.111	0.45	0.0193	0.246	.
1	13X PH 4P	5.53	4.07	15.5	0.033	0.69	0.021	0.019	0.64	0.50	0.255	0.082	0.355	0.075	0.55	.
1	13X PH 2M	4.03	3.56	16.80	0.0598	1.184	0.0201	0.0419	0.502	0.0927	1.009	0.052	0.143	0.049	0.1028	.
2	BS 9621	3.42	4.61	14.93	0.035	0.31	0.017	0.0011	0.468	0.029	0.063	0.013	0.27	(0.001)	0.096	(0.01)
2	BS 185A	3.41	4.43	14.46	0.033	0.49	0.022	0.002	0.38	0.026	0.30	0.027	0.32	(0.001)	0.048	(0.014)
1	<b>BS 17-4PHB</b>	3.35	4.52	15.60	0.042	0.559	0.022	0.023	0.43	0.040	0.110	0.047	0.315	0.0045	0.061	(0.02)
2	BS 9622	3.34	4.34	14.34	0.032	0.63	0.019	0.004	0.42	0.040	0.27	0.028	0.33	(0.001)	0.074	(0.020)
2	BS 17-4PHA	3.30	4.69	15.40	0.018	0.85	0.023	0.022	0.40	0.072	0.34	0.022	0.204	.	0.043	.
2	CT 20 Cb-3	3.28	33.55	19.63	0.034	0.19	0.017	0.003	0.38	0.035	2.25	.	0.86	.	0.053	.
1	IARM 22C	3.24	4.63	14.28	0.042	0.63	0.027	0.0004	0.39	0.086	0.48	0.030	0.29	0.002	0.068	0.031
2	CT 630	3.25	4.20	15.94	0.036	0.39	0.018	0.013	0.63	0.11	0.11	0.028	0.36	.	0.022	.
1	<b>BS 17-4PHC</b>	3.23	4.24	15.40	0.033	0.81	0.022	0.027	0.399	0.077	0.45	0.027	0.258	(0.001)	0.090	0.121
2	BS 187A	3.10	33.06	19.75	0.022	0.52	0.017	0.0025	0.26	0.32	2.06	0.0157	0.57	(0.002)	0.10	(0.02)
1	ECRM 273-1D	3.046	4.85	14.747	0.0336	0.785	0.0131	0.0004	0.378	0.0391	0.2462	0.0444	0.221	.	0.0512	.
1	VS LG64	2.88	28.3	24.7	0.049	0.75	0.017	0.0032	0.76	.	2.89	.	0.048	0.64	0.094	0.013
1	SRM C2400	2.63	4.07	17.06	0.036	0.71	0.013	0.003	0.61	0.10	0.23	.	0.15	.	0.092	.
2	CT 455	2.32	8.22	11.37	0.012	0.074	0.010	0.005	0.13	0.027	0.002	0.002	1.18	.	.	.
2	BS S51962	2.22	8.32	11.42	0.008	0.06	0.006	0.0025	0.06	(0.015)	0.008	0.0025	0.27	1.11	0.071	(<0.02)
1	13X 45500A	2.20	8.36	11.39	0.0041	0.0263	0.0049	0.0020	0.059	0.0152	0.0185	0.0030	0.250	1.187	0.0689	.
1	IARM 16C	2.08	8.23	11.34	0.003	0.024	0.007	0.0046	0.03	0.017	0.009	0.0030	0.248	1.16	0.070	0.008
1	SS 475	1.94	5.66	14.14	0.050	0.89	0.037	0.008	0.21	0.22	1.59	.	0.22	.	.	.
1	<b>BS 9812</b>	1.65	6.61	14.82	0.031	0.485	0.018	0.004	0.43	0.110	0.76	0.0195	0.645	(0.005)	0.088	0.025
1	<b>BS 9811</b>	1.63	6.55	14.87	0.027	0.380	0.016	0.0010	0.36	0.055	0.744	0.0196	0.62	(0.003)	0.086	0.013
1	IARM 318B	1.63	5.71	15.9	0.050	1.02	0.022	0.0006	0.41	0.100	1.57	0.032	0.086	0.014	0.115	0.087
1	13X PH2S143A	1.61	5.20	13.45	0.044	0.544	0.0205	0.0022	0.478	0.0475	1.325	0.024	0.222	.	0.087	0.019
1	<b>BS 179B</b>	1.56	6.17	25.9	0.0161	0.890	0.0243	0.0002	0.371	0.0394	3.34	0.239	0.008	(0.0008)	0.079	0.053
1	IARM 15C	1.54	6.35	14.39	0.032	0.760	0.019	0.0018	0.26	0.024	0.722	0.0148	0.63	(0.002)	0.041	(0.020)
1	13X NSA 7B	1.53	6.37	25.69	0.013	0.864	0.0160	0.0005	0.278	0.047	3.28	0.232	(0.009)	.	0.080	0.133
1	<b>BS 179C</b>	1.53	6.10	25.9	0.0164	0.878	0.0236	0.0003	0.373	0.0386	3.34	0.236	0.009	(0.0005)	0.080	0.056
1	<b>BS 450</b>	1.51	6.24	14.4	0.029	0.596	0.016	0.0013	0.323	0.028	0.671	0.022	0.59	<0.008	0.051	0.016
2	CT 450	1.49	6.36	15.20	0.036	0.39	0.014	0.006	0.29	0.16	0.80	0.028	0.67	.	0.043	.
1	ECRM 295-1D	1.481	24.40	19.51	0.0166	1.758	0.0167	0.0004	0.418	0.0450	3.996	0.0615	.	.	0.0453	.
1	IARM 239B	1.48	5.78	25.9	0.013	0.86	0.025	0.0005	0.39	0.048	3.42	0.25	0.024	0.002	0.099	0.106
1	13X NSA 7A	1.42	5.67	25.91	0.0209	0.951	0.022	0.0009	0.359	.	3.25	0.247	0.015	.	.	.
2	HRT FE2004-H	1.33	24.25	19.08	0.021	1.83	0.021	0.004	0.47	0.046	4.17	.	0.046	0.005	0.042	.
1	13X PH 7F	0.77	5.41	13.16	0.118	1.487	0.028	0.0057	1.402	0.049	2.52	0.044	0.241	0.0196	0.043	.

Number	Al	Ag	As	B	Ca	Cd	Fe	Mg	O	Pb	Sb	Sn	Ta	Units
13X PH 3N	0.050	.	.	0.0042	.	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm
13X PH 4P	0.029	.	.	0.0031	.	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm
13X PH 2M	0.0419	.	.	0.0047	.	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm
BS 9621	0.003	.	.	0.0004	(0.0001)	.	.	.	.	.	.	0.003	(0.002)	38 mm Ø x ~7 or 19+ mm
BS 185A	0.002	.	.	0.0017	(0.0002)	.	.	.	(0.0021)	.	.	0.007	(0.002)	38 mm Ø x ~7 or 19+ mm
<b>BS 17-4PHB</b>	0.034	.	(0.003)	0.0036	(0.0004)	<b>17025</b>	[74.8]	(0.0002)	(0.002)	(0.001)	(0.002)	0.012	(0.002)	41 mm Ø x ~7 or 19+ mm
BS 9622	0.002	.	.	0.0004	.	.	.	.	.	.	.	0.006	.	38 mm Ø x ~7 or 19+ mm
BS 17-4PHA	.	.	.	0.0016	.	.	.	.	.	.	.	.	last	38 mm Ø x ~7 or 19+ mm
CT 20 Cb-3	.	0.0019	.	0.0023	.	.	.	.	.	0.002	.	0.003	.	30-35 mm Ø x ~19 mm
IARM 22C	0.006	.	(0.004)	0.0006	(0.0002)	.	.	.	0.0021	(0.00003)	.	0.013	(0.004)	31 mm Ø x 2 18 mm
CT 630	.	0.0004	.	0.0018	.	.	.	.	.	0.001	.	0.007	.	30-35 mm Ø x ~16 mm
<b>BS 17-4PHC</b>	0.0023	.	0.0043	0.0026	0.0007	<b>17025</b>	74.8	.	0.010	(0.0001)	.	0.0100	.	44 mm Ø x ~7 or 19+ mm
BS 187A	(0.009)	.	.	0.0022	.	.	.	.	0.0029	last of stock	.	0.003	<0.002	41 mm Ø x ~7 mm
ECRM 273-1D	.	.	0.0030	.	.	.	.	.	.	.	.	0.0021	.	40 mm Ø x 20 mm
VS LG64	0.189	.	.	.	.	.	.	.	.	.	.	.	.	~47 mm Ø x ~30 mm
SRM C2400	.	.	.	.	.	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
CT 455	.	0.0002	.	0.0024	.	.	.	.	.	<0.001	.	0.004	.	30-35 mm Ø x ~19 mm
BS S51962	0.067	.	0.002	0.0018	.	.	.	.	(0.001)	.	.	0.004	.	38 mm Ø x ~7 or 19+ mm
13X 45500A	0.073	.	.	.	.	.	.	.	.	.	.	0.0048	(0.0050)	~38 mm Ø x ~15 mm
IARM 16C	0.072	.	(0.003)	0.0011	.	.	.	.	0.0014	.	.	(0.003)	.	31 mm Ø x 2 or 18 mm
SS 475	0.013	.	.	.	.	.	.	.	.	.	.	0.015	.	38 mm Ø x 19 mm
<b>BS 9812</b>	(0.002)	.	(0.005)	(0.0003)	0.0012	.	.	.	(0.007)	<b>25(pre-17025)</b>	.	0.004	.	50 mm Ø x ~7 or 19+ mm
<b>BS 9811</b>	(0.003)	.	(0.003)	(0.0003)	0.0014	.	.	.	(0.0060)	<b>25(pre-17025)</b>	.	0.004	.	38 mm Ø x ~7 or 19+ mm
IARM 318B	(0.004)	.	(0.004)	0.0003	.	.	.	.	0.009	.	.	0.004	(0.004)	31 mm Ø x 2 or 18 mm
13X PH2S143A	.	.	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm
<b>BS 179B</b>	0.0070	.	0.0036	0.0015	(0.0004)	<b>17025</b>	[61.5]	(0.0004)	0.0037	(0.00002)	0.0005	0.0019	(0.0006)	38 mm Ø x 19+ mm
IARM 15C	(0.005)	.	0.0044	(0.0006)	(0.0004)	.	.	.	(0.003)	(0.003)	(0.003)	0.009	(0.004)	31 mm Ø x 2 or 18 mm
13X NSA 7B	0.0142	.	.	0.0018	.	.	.	.	.	0.0009	0.0020	.	.	~41 mm Ø x ~15 mm
<b>BS 179C</b>	0.0078	.	0.0034	0.0015	(0.0003)	<b>17025</b>	[61.6]	(0.0004)	0.0038	(0.00002)	0.0005	0.0018	(0.0006)	38 mm Ø x ~7 or 19+ mm
<b>BS 450</b>	(0.003)	.	0.0033	(0.0003)	<0.005	<b>17025</b>	75.5	.	0.0027	<0.005	0.0010	0.0046	.	44 mm Ø x ~7 or 19+ mm
CT 450	.	0.0013	.	.	.	.	.	.	.	0.001	.	0.008	.	30-35 mm Ø x ~15-19 mm
ECRM 295-1D	0.0203	.	0.0041	0.0018	.	.	48.36	(0.0003)	.	.	0.0007	0.0025	.	38 mm Ø x 25 or 30 mm
IARM 239B	0.008	.	0.0008	.	.	.	.	.	(0.004)	.	.	(0.003)	.	31 mm Ø x 2 mm
13X NSA 7A	(0.009)	.	.	.	.	.	.	.	.	.	.	.	.	42 mm Ø x 15 mm last
HRT FE2004-H	0.005	.	.	0.0021	.	.	.	.	.	.	.	.	.	32 mm Ø x 20 mm
13X PH 7F	0.012	.	.	.	.	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm

## MARAGING STEEL AND COBALT IN STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM, 2 = RM

#	Number	Co	Mo	Ni	Cr	C	Mn	P	S	Si	Cu	Al	B	N	Nb	Ti
1	IARM 326A	48.4	(0.002)	0.037	(0.002)	(0.002)	0.003	0.0013	0.0011	0.029	(0.002)	(0.003)	(0.001)	0.0004	0.038	(0.002)
1	IMZ 521	20.25	4.84	8.63	0.040	0.015	0.039	0.0031	0.0058	0.072	0.027	.	.	0.0113	.	.
1	IMZ 522	18.72	6.45	11.47	0.022	0.0088	0.032	(0.003)	0.0043	0.048	0.019	.	.	0.0045	(0.008)	0.54
1	IMZ 520	17.66	4.92	10.10	0.242	0.011	0.070	0.0043	0.019	0.094	0.080	.	(0.001)	0.0105	(0.008)	(0.007)
1	IARM 98B	17.0	0.010	29.4	0.012	0.007	0.18	0.002	0.0007	0.17	0.028	0.07	0.001	0.0024	0.002	0.03
1	IMZ 523	14.44	6.67	15.94	0.048	0.0098	0.051	(0.004)	0.0039	0.043	0.059	.	.	0.0037	(0.008)	0.70
1	IARM 242A	13.5	1.21	11.1	3.00	0.24	0.018	0.002	0.0004	0.02	0.007	0.004	(0.0005)	0.0003	0.004	0.009
2	CT ISO045A	13.39	1.18	11.38	3.12	0.228	0.002	0.001	0.0004	<0.010	0.006	0.004	.	.	.	0.005
1	IARM 309A	12.3	4.71	18.4	0.053	0.0059	0.018	0.004	0.0006	0.020	0.023	0.11	0.0032	0.0010	0.004	1.47
1	IMZ 524	12.25	4.95	13.75	0.085	0.012	0.68	(0.004)	0.004	0.13	0.024	.	.	0.0038	(0.007)	0.85
1	DSZU C093	12.08	3.79	15.80	0.42	0.013	0.32	(0.006)	(0.007)	(0.10)	(0.12)	0.17	.	.	.	1.56
1	BS 161A	9.22	4.82	18.40	0.12	0.004	0.031	0.004	0.0007	0.032	0.22	0.14	0.0023	(0.002)	(0.004)	0.65
2	CT 300	9.07	4.97	18.51	0.034	0.005	0.032	0.005	0.004	0.030	0.047	0.12	0.0020	.	.	0.69
1	DSZU C091	8.07	4.98	18.20	0.12	0.035	0.092	(0.006)	(0.011)	(0.09)	(0.12)	0.05	.	.	.	0.81
1	IARM 308A	7.80	4.78	18.53	0.023	0.003	0.019	0.004	0.0005	0.014	0.018	0.097	0.0029	0.0013	0.003	0.46
1	ECRM 285-2D	7.76	4.99	18.07	0.0236	0.0018	0.0168	0.0053	0.0025	0.0117	0.0094	0.1067	0.0009	0.0007	.	0.520
2	CT 250	7.54	4.88	18.44	0.008	0.002	0.006	0.003	0.002	0.008	0.008	0.058	0.0024	.	.	0.41
2	DSZU C55	5.75	1.32	2.24	14.9	(0.19)	0.73	(0.042)	.	0.68	.	.	.	.	0.27	.
1	DSZU C092	5.21	5.50	20.12	0.23	0.015	0.27	(0.006)	(0.009)	(0.10)	(0.16)	(0.006)	.	(0.11)	.	(0.008)
2	DSZU C53	5.20	1.71	1.47	14.8	(0.26)	0.82	(0.036)	.	0.29	.	.	.	.	0.13	.
2	DSZU C54	5.19	1.47	1.88	18.5	(0.06)	0.60	(0.036)	.	0.56	.	.	.	(0.13)	0.40	.
2	DSZU C51	4.07	0.68	1.67	10.8	(0.16)	0.40	(0.019)	.	0.25	.	.	.	(0.09)	0.10	.
2	DSZU C52	3.35	1.08	1.68	11.0	(0.17)	0.24	(0.018)	.	0.12	.	.	.	.	0.15	.
1	BS 85D	0.97	0.59	9.98	17.09	0.048	1.69	0.024	0.024	0.54	0.45	0.13	(0.001)	(0.02)	0.062	0.48

Number	As	Ca	Fe	Mg	O	Sb	Sn	Ta	V	W	Zr	Units
IARM 326A	<0.005	.	49.6	(0.001)	0.0082	.	<0.001	(0.01)	1.94	(0.001)	0.002	31 mm Ø x 2 mm Fe: 49.6
IMZ 521	.	.	.	.	.	.	(0.002)	.	3.97	5.23	.	38 mm Ø x 20 mm
IMZ 522	.	.	.	.	.	.	(0.001)	.	2.21	2.25	.	38 mm Ø x 20 mm
IMZ 520	.	.	.	.	.	.	(0.002)	.	4.03	4.90	.	38 mm Ø x 20 mm
IARM 98B	<0.002	<0.0005	52.9	0.0040	0.0021	.	0.002	<0.05	(0.003)	(0.02)	<0.01	31 mm Ø x 2 mm
IMZ 523	.	.	.	.	.	.	(0.001)	.	2.01	1.87	.	38 mm Ø x 20 mm
IARM 242A	.	.	.	.	0.0006	.	(0.001)	0.008	0.01	<0.01	.	31 mm Ø x 2 mm
CT ISO045A	.	.	70.70	.	.	.	.	.	.	.	.	30-35 mm Ø x -19 mm
IARM 309A	.	.	.	.	0.0005	.	(0.001)	(0.006)	0.01	0.01	0.008	31 mm Ø x 2 or 18 mm
IMZ 524	(0.003)	.	.	.	.	.	.	.	3.02	1.84	.	38 mm Ø x 20 mm
DSZU C093	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x 17 mm
BS 161A	(0.002)	(0.0008)	25(pre-17025)	(0.0004)	.	(0.0015)	(0.03)	0.031	(0.008)	(0.002)	.	38 mm Ø x -12 or 19 mm last
CT 300	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -16 mm
DSZU C091	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x 17 mm
IARM 308A	.	.	.	.	0.0005	.	0.001	<0.01	0.01	0.01	0.01	31 mm Ø x 2 or 18 (last) mm
ECRM 285-2D	.	.	.	.	.	.	.	.	.	.	0.0050	38 mm Ø x 25 or 30 mm
CT 250	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x -19 mm
DSZU C55	.	.	.	.	.	.	.	.	0.29	(1.17)	.	42 mm Ø x 25 mm
DSZU C092	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x 17 mm
DSZU C53	.	.	.	.	.	.	.	.	0.33	(0.59)	.	42 mm Ø x 25 mm
DSZU C54	.	.	.	.	.	.	.	.	0.47	(0.71)	.	42 mm Ø x 25 mm
DSZU C51	.	.	.	.	.	.	.	.	0.15	(0.32)	.	42 mm Ø x 25 mm
DSZU C52	.	.	.	.	.	.	.	.	0.10	(0.91)	.	42 mm Ø x 25 mm
BS 85D	(0.01)	0.0004	[67.8]	.	(0.002)	(0.001)	0.0062	(0.001)	0.132	(0.07)	(0.004)	38 mm Ø x -7 or 19+ mm 17025

## TUNGSTEN IN STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM and 2 = RM

#	Number	W	Ni	Cr	C	Mn	P	S	Si	Cu	Co	Mo	N	Nb	Ti	V
1	VS LG57	4.24	25.2	13.70	0.016	0.52	0.011	0.0023	0.56	0.080	.	0.401	.	.	1.81	0.65
1	13X 14219K	4.17	12.66	21.46	0.0997	0.482	0.0401	0.0456	1.504	0.138	0.0475	0.169	.	0.140	.	0.0188
1	13X 14212S	3.68	8.81	21.64	0.119	0.166	0.032	0.0386	2.47	0.611	0.1090	0.520	0.0055	0.550	.	0.1175
1	VS LG59	3.08	35.1	15.81	0.073	1.15	0.011	0.0083	0.63	0.083	.	0.094	.	0.106	1.12	0.273
1	113X 14215L	3.02	15.86	22.89	0.136	1.110	0.0050	0.0068	0.596	0.0110	0.0057	0.0048	.	0.0196	.	0.0480
2	BS 183A	2.60	1.85	12.14	0.172	0.35	0.016	0.0040	0.37	0.093	0.036	0.12	0.0256	0.006	0.002	0.090
1	IARM 20C	2.59	1.93	12.15	0.18	0.30	0.018	0.0047	0.35	0.060	0.031	0.12	0.0222	0.010	(0.003)	0.086
1	IMZ 161	1.05	0.55	12.90	0.074	0.29	0.023	0.023	0.65	0.56	.	1.10	.	.	.	0.33

Number	Al	As	B	Ca	O	Sb	Sn	Units
VS LG57	0.151	.	.	.	.	.	.	-47 mm Ø x -30 mm
13X 14219K	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
13X 14212S	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
VS LG59	0.079	.	.	.	.	.	.	-47 mm Ø x -30 mm
13X 14215L	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
BS 183A	0.002	(0.002)	(<0.0005)	0.0020	0.0065	(0.001)	0.003	38 mm Ø x -7 or 19+ mm
IARM 20C	(0.004)	.	.	.	0.0068	.	0.004	31 mm Ø x 2 mm
IMZ 161	.	.	.	.	.	.	.	40 mm Ø x 40 mm



## MANGANESE STAINLESS STEEL

# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	Mn	Ni	Cr	C	P	S	Si	Cu	Mo	Al	Co	N	Nb	V	W
1	IARM 294A	21.6	2.9	19.7	0.017	0.026	0.0028	0.43	0.34	1.8	(0.01)	0.021	0.78	(0.03)	0.046	(0.01)
1	IARM 295A	19.7	1.84	18.0	0.021	0.028	0.0041	0.36	0.113	0.97	(0.01)	0.021	0.62	0.018	0.046	0.016
1	ECRM 294-1D	18.68	0.429	17.98	0.0657	0.0271	0.00031	0.283	0.0242	0.0861	(0.0095)	0.0288	0.566	(0.00117)	0.0694	(0.00114)
1	IARM 214A	18.3	2.33	12.36	0.018	0.033	0.002	1.00	0.36	0.44	(0.002)	0.021	0.27	0.23	0.04	0.02
1	VS RG20/1	15.77	0.673	14.35	0.064	(0.02)	(0.01)	0.81	0.265	0.089	.	.	.	0.175	0.166	0.007
1	VS RG22/1	13.41	3.94	13.25	0.054	(0.02)	(0.008)	0.63	0.358	0.121	.	.	.	0.38	0.125	0.137
2	BS 193	12.11	1.82	18.48	0.104	0.018	0.002	0.66	0.088	0.21	(0.003)	0.028	0.37	0.014	0.107	(0.007)
2	CT ISO035A	12.04	1.81	18.48	0.102	0.023	0.002	0.59	0.17	0.28	<0.004	0.037	0.33	0.004	0.058	0.002
1	IARM 296A	10.6	1.71	11.2	0.074	0.027	0.002	0.38	0.12	0.60	(0.005)	0.018	0.23	0.043	0.056	(0.01)
2	BS 190	9.72	6.74	19.57	0.022	0.015	0.001	0.46	0.072	0.15	(0.004)	0.044	0.255	(0.004)	0.11	0.015
2	CT ISO129A	9.31	6.86	19.62	0.030	0.002	<0.001	0.40	0.152	0.25	0.014	0.102	0.264	0.025	0.144	0.03
1	13X NSC6A	8.85	6.52	20.47	0.0266	0.0049	0.0055	0.523	0.0064	(0.002)	(0.009)	.	0.235	.	0.0052	.
1	VS RG23/1	8.74	1.98	18.5	0.045	(0.02)	(0.004)	0.49	0.099	0.401	.	.	.	0.24	0.69	0.3
2	BS 181A	8.16	8.15	16.52	0.071	0.019	0.001	4.03	0.18	0.21	0.022	0.072	0.148	0.017	0.094	0.04
1	<b>BS 181B</b>	8.07	8.18	16.17	0.070	0.021	0.0009	3.94	0.206	0.173	0.0119	0.044	0.158	0.026	0.044	0.016
1	13X NSC2Q	8.02	3.63	20.95	0.574	.	0.014	1.02	1.01	0.339	0.37	.	0.299	2.03	0.293	0.063
1	13X 21800A	8.00	8.32	16.81	0.0765	0.032	0.0011	4.03	0.431	0.325	0.012	0.0943	0.125	0.007	0.0619	.
1	13X NSC4G	7.78	7.52	31.7	0.470	.	0.0065	1.53	0.208	1.31	0.26	0.238	0.90	2.37	0.224	0.208
1	NM 303	7.21	1.59	12.68	0.16	0.035	0.050	0.40	0.68	0.17	.	0.063	.	.	0.071	.
1	SRM 1297	7.11	5.34	16.69	0.066	0.038	0.0033	0.397	0.442	0.331	.	0.127	.	.	0.080	.
1	VS RG21/1	6.39	7.52	15.53	0.169	(0.02)	(0.008)	1.95	0.17	0.88	.	.	.	0.48	1.71	(0.2)
3	CZ SL-5A	5.8	4.94	11.7	0.37	0.021	0.014	0.36	2.90	4.12	0.035	0.26	.	0.20	0.21	0.78
2	BS 191	5.71	5.34	16.33	0.098	0.024	0.023	3.73	0.33	0.36	(0.002)	0.11	0.117	0.024	0.083	0.033
1	VS RG19/1	5.63	17.73	24.5	0.064	(0.02)	(0.009)	0.90	(0.2)	0.166	.	.	0.108	0.407	0.206	.
1	13X NSA4B	5.55	17.62	23.85	0.115	0.0302	0.0095	0.519	0.595	4.32	0.0048	.	0.446	0.154	.	.
1	IARM FeN50-18	5.27	11.90	21.0	0.030	0.026	(0.0013)	0.24	0.28	2.01	(0.006)	0.081	0.26	0.18	0.121	0.023
1	13X NSA10A	5.23	12.98	20.67	0.0180	0.0206	0.0007	0.375	0.170	2.636	.	0.060	0.342	0.143	0.151	(0.061)
2	BS 180A	5.05	13.19	21.09	0.018	0.012	0.001	0.32	0.067	2.04	0.012	0.039	0.334	0.20	0.20	0.02
1	IARM 292A	5.0	1.47	21.35	0.030	0.018	0.001	0.75	0.29	0.097	0.010	0.031	0.245	0.009	0.084	0.01
1	<b>BS 180B</b>	4.65	11.9	21.5	0.022	0.017	0.0008	0.46	0.201	2.20	(0.007)	0.111	0.315	0.131	0.149	0.050
2	HRT FE2017-H	4.43	15.45	20.15	0.015	0.022	0.002	0.34	0.21	3.17	.	.	0.311	0.131	.	.
1	IARM 17D	4.15	11.83	21.06	0.041	0.026	0.0018	0.416	0.412	1.52	0.0032	0.23	0.311	0.14	0.118	0.056
1	13X NSC7B	3.55	7.50	23.9	0.397	0.019	0.0098	0.88	0.220	0.435	0.204	0.297	0.429	0.82	0.167	0.041
1	13X NSC5C	2.06	4.42	21.6	0.524	.	0.024	1.18	0.84	0.472	0.24	0.093	0.265	2.31	0.102	0.050

Number	As	B	Ca	O	Pb	Sb	Sn	Ta	Te	Ti	Zr	Units
IARM 294A	.	(0.003)	.	(0.003)	.	.	(0.006)	(0.003)	.	(0.002)	(0.002)	31 mm Ø x 2 or 18 mm
IARM 295A	.	0.002	.	(0.003)	.	.	0.004	.	.	0.0019	(0.001)	31 mm Ø x 2 or 18 mm
ECRM 294-1D	0.0037	(<0.00005)	(0.00026)	.	(0.000128)	(0.00053)	(0.0014)	.	(<0.00008)	(0.0008)	(0.0001)	40 mm Ø x 20 mm
IARM 214A	.	(0.001)	.	0.0026	.	.	0.008	.	.	0.02	.	31 mm Ø x 2 or 18 mm
VS RG20/1	.	.	.	.	.	.	.	.	.	0.093	.	-45 mm Ø x -30 mm
VS RG22/1	.	.	.	.	.	.	.	.	.	0.33	.	-45 mm Ø x -30 mm
BS 193	.	0.0007	0.0020	(0.004)	.	.	0.004	.	.	0.003	.	32 mm Ø x ~7 or 19+ mm
CT ISO035A	.	.	Fe: 65.91	.	(<0.0001)	.	0.003	.	.	0.001	<0.001	30-35 mm Ø x ~19 mm
IARM 296A	.	(0.001)	.	(0.003)	.	.	0.007	.	.	(0.002)	.	31 mm Ø x 2 mm
BS 190	.	0.0005	.	0.0045	.	.	0.003	.	.	0.002	.	38 mm Ø x ~7 or 19+ mm
CT ISO129A	.	.	Fe: 62.62	.	.	.	.	.	.	.	.	30-35 mm Ø x ~16 mm
13X NSC6A	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 13 mm HIP
VS RG23/1	.	.	.	.	.	.	.	.	.	0.21	.	-45 mm Ø x -30 mm
BS 181A	.	0.0009	.	0.0010	.	.	0.005	.	.	0.007	last	38 mm Ø x ~7 mm
<b>BS 181B</b>	(0.002)	(0.0008)	(0.001)	0.0010	(0.0005)	(0.0007)	(0.004)	Fe:62.9	<b>17025</b>	0.0051	(0.0004)	38 mm Ø x ~7 or 19+ mm
13X NSC2Q	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x ~15 mm
13X 21800A	.	(0.001)	.	.	.	.	.	.	.	.	.	-38 mm Ø x ~15 mm
13X NSC4G	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x ~15 mm
NM 303	.	.	.	.	.	.	.	.	.	.	.	35 mm Ø x 20 mm
SRM 1297	.	.	.	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
VS RG21/1	.	.	.	.	.	.	.	.	.	0.18	.	-45 mm Ø x ~30 mm
CZ SL-5A	0.005	.	.	.	.	.	0.004	0.07	.	0.004	.	-39 mm Ø x 25 mm
BS 191	.	(0.0006)	.	0.002	.	.	(0.006)	0.002	.	0.012	.	38 mm Ø x ~7 or 19+ mm
VS RG19/1	.	.	.	.	.	.	.	.	.	0.14	.	-45 mm Ø x ~30 mm
13X NSA4B	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x ~15 mm
IARM FeN50-18	.	.	.	(0.006)	.	.	(0.007)	.	.	(0.002)	.	31 mm Ø x 2 or 18 mm
13X NSA10A	.	0.0031	.	.	.	.	.	.	.	.	.	-38 mm Ø x ~15 mm
BS 180A	.	(0.0023)	.	0.003	.	.	(0.002)	.	last	(0.002)	.	37 mm Ø x ~7 or ~19+ mm
IARM 292A	.	0.0011	.	0.0024	.	.	0.004	(0.006)	.	0.005	.	31 mm Ø x 2 mm
<b>BS 180B</b>	(0.004)	0.0011	0.0009	0.0043	<b>17025</b>	(0.0007)	0.0040	(0.003)	Fe:58.5	(0.005)	(0.0009)	38 mm Ø x ~7 or 19+ mm
HRT FE2017-H	.	.	.	.	.	.	.	.	.	.	.	30 mm x 30 mm x 10 mm
IARM 17D	0.005	0.001	(0.002)	0.003	(0.0002)	(0.001)	0.0044	(0.003)	.	0.010	(0.002)	31 mm Ø x 2 or 18 mm
13X NSC7B	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x ~15 mm
13X NSC5C	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x ~15 mm

## CRM

## NICKEL BINARIES

analysis listed in mass %

-40 mm Ø x ~15 mm

Number	Ni	C	Mn	P	S	Si	Cu	Cr	Al	Co	N	Mg	Mo	Nb	Ti	W
14X FeNi50C	51.5	0.0245	0.057	0.0168	0.16	0.151	0.089	0.066	0.319	0.416	.	.	.	.	.	.
14X FeNi45C	45.88	0.0082	0.0222	0.026	0.0015	0.77	0.089	0.076	0.98	0.572	.	.	.	.	.	.
14X FeNi40C	40.1	0.012	0.031	0.0148	1.03	0.050	0.081	0.64	2.00	1.057	.	.	.	.	.	.
14X 94100A	41.00	0.0055	0.443	0.0051	0.0027	0.103	0.0628	0.0265	.	0.0208	0.0016	0.0021	0.0053	(0.01)	0.0011	0.0017
14X FeNi10A	10.12	0.095	0.272	0.015	0.027	0.061	0.029	0.070	0.025	.	0.0055	.	.	.	.	.
14X FeNi8A	8.10	0.097	0.330	0.015	0.029	0.097	0.030	0.250	0.029	.	0.0061	.	.	.	.	.
14X FeNi6A	6.08	0.100	0.330	0.0155	0.028	0.075	0.028	0.073	0.025	.	0.0055	.	.	.	.	.



## SULFUR AND PHOSPHORUS IN STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	S	P	Ni	Cr	C	Mn	Si	Cu	Al	Co	Mo	N	Nb	Ti	V
2	CT 416	0.36	0.018	0.24	13.15	0.088	0.52	0.63	0.004	.	0.019	0.065	0.020	.	.	0.025
1	IARM 10D	0.334	0.0178	0.291	12.42	0.110	1.11	0.475	0.192	(0.0027)	0.0187	0.148	0.0241	0.0027	0.0015	0.051
2	BS 150	0.33	0.020	0.19	18.61	0.048	1.71	0.43	0.042	0.002	0.024	1.97	0.029	0.003	.	0.054
1	SRM 1223	0.329	0.018	0.232	12.64	0.127	1.08	0.327	0.081	.	.	0.053	.	.	.	0.068
2	BS 90F	0.328	0.023	0.30	13.01	0.085	0.53	0.58	0.12	(0.006)	0.021	0.14	0.037	0.011	.	0.076
1	<b>BS 303</b>	0.326	0.028	8.17	17.23	0.044	1.80	0.415	0.627	0.0019	0.071	0.410	0.023	0.008	0.017	0.056
1	13X 30300A	0.312	0.0205	8.60	17.62	0.041	1.83	0.422	0.025	.	0.0255	0.334	0.034	.	.	0.091
2	CT 303	0.31	0.029	9.08	17.78	0.070	1.64	0.58	0.49	.	0.16	0.41	.	.	.	0.044
1	IARM 355A	0.31	0.0186	0.427	17.81	0.0274	0.47	0.435	0.083	0.0016	0.047	0.337	0.0439	0.0095	0.0020	0.038
2	BS 154	0.302	0.027	0.25	17.58	0.030	0.40	1.26	0.063	(0.002)	0.019	0.31	0.039	0.005	.	0.046
2	13X 12549K	0.29	0.092	1.26	11.70	0.16	0.34	0.43	0.10	.	0.52	1.49	.	0.23	.	.
2	BS 153	0.280	0.018	0.140	17.38	0.026	0.41	0.53	0.052	0.002	0.017	0.30	0.021	0.002	(0.004)	0.045
2	BS 152	0.275	0.022	0.14	13.41	0.320	0.36	0.44	0.050	(0.002)	0.015	0.061	0.020	0.006	.	0.051
3	CZ SP-1A	0.26	0.024	8.6	17.7	0.047	1.87	0.33	0.52	0.004	0.095	0.42	.	0.012	0.02	0.058
1	IARM 352A	0.21	0.0182	0.269	13.11	0.341	1.13	0.357	0.148	(0.0025)	(0.016)	0.38	0.029	(0.012)	0.0015	0.028
1	13X 43020A	0.189	0.0246	0.517	16.07	0.147	1.439	0.415	0.0687	0.0047	0.0191	0.226	0.0212	0.0102	.	0.0542
1	IMZ 154	0.16	0.040	9.86	17.71	0.076	2.18	0.89	0.33	(0.16)	0.105	2.58	.	.	1.00	0.073
1	NCS HS41751A	0.16	0.035	8.07	17.41	0.075	1.70	0.71	0.26	.	0.13	0.33	0.077	.	.	0.068
2	BS 155	0.145	0.014	0.13	16.64	1.00	0.35	0.40	0.035	(0.001)	0.019	0.46	0.032	0.002	.	0.10
1	13X 12536T	0.090	0.0449	12.12	16.09	0.146	0.374	0.546	0.0793	0.108	0.280	2.48	0.0084	0.060	0.444	0.0513
1	13X 12535BE	0.0591	0.0400	14.79	16.95	0.229	0.342	1.407	0.130	0.194	0.146	4.09	0.029	.	0.625	0.252
1	SRM C1154a	0.051	0.06	13.08	19.31	0.100	1.44	0.53	0.44	.	0.38	0.068	.	.	0.039	0.135
1	VS LG58	0.0280	0.0135	4.26	23.4	0.48	0.99	0.292	0.388	.	.	2.41	.	0.214	.	0.264
2	13X 19004B	0.014	0.069	17.9	22.8	0.066	1.96	0.36	0.022	.	.	3.62	.	0.18	.	.
1	13X 19004C	0.0135	0.074	17.90	22.77	0.075	2.01	0.35	0.0112	0.030	0.0501	3.43	.	0.152	.	0.041

Number	Ag	As	B	O	Pb	Sn	Ta	W	Units
CT 416	0.0002	.	.	.	<0.001	0.005	.	.	30-35 mm Ø x ~16 mm
IARM 10D	.	(0.007)	(0.002)	(0.005)	.	0.010	.	(0.005)	31 mm Ø x 2 or 18 mm
BS 150	.	.	.	0.012	.	(0.003)	.	0.01	35 mm Ø x ~7 or 19+ mm
SRM 1223	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
BS 90F	.	.	.	0.011	.	0.005	.	0.032	38 mm Ø x ~7 or 19+ mm
<b>BS 303</b>	.	.	0.0013	0.0058	.	0.0091	.	0.023	44 mm Ø x ~7 or 19+ mm <b>17025</b>
13X 30300A	.	.	0.0035	.	.	.	.	.	~40 mm Ø x ~15 mm
CT 303	0.0003	.	.	.	0.001	0.007	.	.	30-35 mm Ø x ~16 mm
IARM 355A	.	(0.004)	(0.0011)	(0.010)	(0.0002)	(0.005)	.	(0.018)	31 mm Ø x 2 or 18 mm
BS 154	.	.	.	0.008	.	(0.005)	.	(0.01)	38 mm Ø x ~7 or 19+ mm
13X 12549K	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm
BS 153	.	(0.004)	.	.	(0.001)	0.002	.	(0.002)	35 mm Ø x ~7 or 19+ mm
BS 152	.	.	.	.	.	0.003	.	<0.01	41 mm Ø x ~7 or 19+ mm
CZ SP-1A	.	0.006	0.0007	.	.	0.01	.	0.03	~39 mm Ø x 25 mm
IARM 352A	.	(0.005)	(0.0007)	(0.005)	.	0.0046	.	(0.005)	31 mm Ø x 2 or 18 mm
13X 43020A	.	.	(0.0032)	.	.	.	.	0.0108	~40 mm Ø x ~15 mm
IMZ 154	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
NCS HS41751A	.	.	.	.	.	.	.	.	38 mm Ø x 38 mm
BS 155	.	.	.	0.0048	.	(0.003)	.	.	36 mm Ø x ~7 or 19+ mm
13X 12536T	.	.	0.0214	.	.	0.0068	0.104	.	~40 mm Ø x ~15 mm
13X 12535BE	.	.	0.0051	.	.	0.0194	(0.020)	.	~40 mm Ø x ~15 mm
SRM C1154a	.	.	.	.	0.017	.	.	.	32 mm Ø x 19 mm
VS LG58	.	.	.	.	.	.	0.21	.	~47 mm Ø x ~30 mm
13X 19004B	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm
13X 19004C	.	.	(0.001)	.	.	(0.001)	0.011	.	~40 mm Ø x ~15 mm

## SELENIUM IN STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM and 2 = RM

#	Number	Se	Ni	Cr	C	Mn	P	S	Si	Cu	Al	Co	Mo	N	Nb	Ti
2	BS 151	0.328	0.24	13.19	0.090	0.41	0.021	0.018	0.65	0.11	(0.002)	0.018	0.088	0.022	0.005	(<0.003)
2	BS 186A	0.229	35.86	0.16	0.040	0.72	0.008	0.0053	0.19	0.016	(0.001)	0.028	0.0032	0.0026	(<0.002)	(<0.003)
1	IARM 253A	0.21	9.17	17.90	0.041	1.50	0.140	0.0089	0.50	0.223	0.003	0.088	0.348	0.0373	0.016	0.002
1	IARM 24B	0.19	35.86	0.121	0.053	0.82	0.009	0.0010	0.28	0.052	0.002	0.036	0.011	0.0017	<0.01	0.002
1	IARM 353A	0.17	0.265	17.01	0.98	0.95	0.019	0.025	0.49	0.13	0.0018	0.032	0.50	0.027	(0.011)	0.0015
2	CT ISO124A	0.167	48.07	0.079	0.011	0.73	0.007	0.006	0.40	0.015	.	0.012	0.009	.	.	.
2	BS 156	0.142	0.35	16.87	1.06	1.15	0.022	0.007	0.47	0.09	(<0.002)	0.047	0.50	0.041	0.005	0.001
1	IARM 253B	0.13	9.11	17.64	0.051	1.61	0.13	0.011	0.46	0.44	(0.004)	0.145	0.59	0.031	0.021	0.0027

Number	B	Fe	O	Sn	Ta	V	W	Zr	Units
BS 151	.	.	0.009	0.005	.	0.046	0.010	.	50 mm Ø x ~7 or 19+ mm
BS 186A	.	.	.	(0.002)	.	0.0012	(0.01)	.	38 mm Ø x ~7, ~12 or 19 mm
IARM 253A	0.0003	.	0.009	0.01	.	0.106	0.10	.	31 mm Ø x 2 or 18 mm
IARM 24B	(0.001)	62.6	0.003	0.0018	<0.005	<0.005	<0.04	<0.005	31 mm Ø x 2 or 18 mm
IARM 353A	(0.0006)	.	(0.005)	0.0056	(0.004)	0.116	0.041	(0.002)	31 mm Ø x 2 mm
CT ISO124A	.	50.65	.	.	.	.	.	.	44-47 mm Ø x ~11 or ~19 mm
BS 156	.	.	0.0045	(0.004)	.	0.13	0.11	.	41 mm Ø x ~7 or 19+ mm
IARM 253B	0.0007	.	0.007	(0.012)	(0.003)	0.092	(0.05)	.	31 mm Ø x 2 or 18 mm

## STAINLESS STEEL WITH NI &lt; 5.0 %

## CONTINUED ON THE NEXT PAGE

# = Class, 1=CRM, 2=RM, and 3=RM with no uncertainties \*\* Provisional Analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
3	CZ SL-4A	1.38	2.85	0.038	0.017	2.28	0.75	2.04	26.3	0.11	0.92	.	1.11	0.8	0.54	0.35
2	BS 156	1.06	1.15	0.022	0.007	0.47	0.09	0.35	16.87	0.047	0.50	0.041	0.005	0.001	0.13	0.11
1	BS 938	1.047	0.59	0.0266	<0.0025	0.49	0.02	0.187	16.72	0.021	0.46	0.051	0.0029	0.0012	0.057	0.0016
1	IARM T3d	1.040	0.697	0.0195	0.0012	0.614	0.184	0.256	16.36	0.0212	0.488	0.0492	0.0074	0.0035	0.058	0.046
1	13X 44004B	1.012	0.378	0.0232	0.0018	0.440	0.0587	0.197	16.50	0.0167	0.468	0.0308	0.008	(0.004)	0.0484	0.0156
2	BS 155	1.00	0.35	0.014	0.005	0.40	0.035	0.13	16.64	0.019	0.46	0.032	0.002	.	0.10	.
1	NCS HS41752	0.97	0.46	0.023	0.0016	0.48	0.082	0.192	17.61	.	0.057	.	.	.	0.088	.
1	ECRM 291-1D	0.90	0.81	0.017	0.0088	0.91	0.071	0.56	17.15	0.0233	2.10	0.1142	.	.	0.39	.
1	VS LG40/1	0.66	0.318	(0.02)	(0.006)	0.289	(0.15)	0.271	13.67	.	0.039	.	.	.	0.038	.
1	VS LG39/1	0.406	0.64	(0.02)	(0.007)	0.94	(0.12)	0.42	13.11	.	0.136	.	.	.	0.135	.
2	HRT FE2018-H	0.37	0.73	0.026	(0.003)	0.33	0.29	0.56	16.34	.	1.04	0.0134	.	.	0.064	.
1	13X 14122A	0.356	0.480	0.0177	0.0021	0.449	0.066	0.632	15.91	0.0224	0.855	0.0290	0.006	.	0.101	0.004
1	13X 40900A	0.035	0.716	0.0032	0.0059	0.616	0.134	0.231	10.98	0.053	0.102	0.007	0.032	0.530	0.099	.
2	BS SS4952	0.347	0.41	0.016	0.003	0.66	0.045	0.23	13.15	0.030	0.049	0.027	0.004	0.002	0.089	(0.007)
1	IARM 154C	0.339	0.423	0.0174	0.0043	0.37	0.120	0.215	12.41	0.016	0.036	0.054	0.014	0.0015	0.043	(0.005)
2	BS SS4951	0.333	0.58	0.016	0.0012	0.62	0.033	0.15	13.55	0.013	0.009	0.0127	0.006	0.002	0.032	.
2	BS 152	0.320	0.36	0.022	0.275	0.44	0.050	0.14	13.41	0.015	0.061	0.020	0.006	.	0.051	<0.01
1	IRSID 1825	0.305	0.650	0.019	0.022	0.336	0.100	0.308	12.90	0.026	0.052	.	.	.	0.052	.
1	13X 42027A	0.294	0.356	0.0139	0.0005	0.544	0.035	0.163	15.25	0.0191	0.990	0.402	0.004	(0.002)	0.048	0.019
1	ECRM 272-1D	0.2815	0.600	0.0156	0.0196	0.420	0.0192	0.2445	11.927	0.0145	0.0030	0.0508	0.0028	0.00096	0.167	.
1	SS 469	0.279	0.598	0.015	0.020	0.421	(0.02)	0.246	11.93	(0.01)	.	.	.	.	(0.02)	.
1	VS LG38/1	0.255	0.73	(0.02)	(0.01)	0.81	(0.16)	0.551	11.75	.	0.344	.	.	.	0.190	.
1	IMZ 168	0.24	1.36	0.019	0.012	1.12	0.093	0.17	13.91	(0.019)	0.026	(0.057)	.	(0.003)	0.053	.
1	IARM 205D	0.232	0.736	0.0209	0.0028	0.257	0.122	0.841	12.18	0.043	1.002	0.0484	0.013	0.0022	0.319	1.07
1	BS 422	0.232	0.640	0.0169	0.0013	0.404	0.080	0.676	11.25	0.0293	0.896	0.050	0.045	0.0011	0.274	0.95
1	SS 472	0.227	1.02	0.032	0.029	1.05	(0.02)	1.95	15.82	(0.02)	0.661	.	.	.	(0.02)	.
1	13X 42200A	0.220	0.651	0.0182	0.0012	0.314	0.136	0.738	11.41	0.0114	1.042	0.0585	0.0203	.	0.246	1.177
1	NCS HS41749	0.21	0.39	0.023	0.012	0.56	1.15	1.52	12.27	.	0.158	.	.	.	0.074	.
1	13X 42000A	0.208	0.679	0.0241	0.0253	0.496	0.202	0.295	12.56	0.0161	0.0398	0.0273	.	.	0.046	.
1	13X 14923A	0.205	0.501	0.0197	0.0031	0.330	0.0563	0.452	11.26	0.0207	0.819	0.0321	0.005	.	0.295	.
1	VS LG41/1	0.200	0.91	(0.02)	(0.008)	0.64	(0.12)	1.53	15.90	.	0.277	.	.	.	0.303	.
1	IMZ 171	0.195	0.42	0.020	0.014	0.21	0.116	0.59	11.44	0.024	1.23	0.057	.	(0.001)	0.26	.
1	NCS HS41748	0.194	0.62	0.016	0.011	0.54	0.008	0.077	12.70	.	0.010	.	.	.	0.048	.
2	HRT FE2015-H	0.19	0.52	0.021	0.002	0.37	0.07	0.25	12.87	.	0.07	0.045	.	.	0.055	.
1	13X 12548M	0.188	0.577	0.027	0.219	0.425	0.230	1.075	12.96	0.353	1.318	0.0500	0.586	.	.	0.031
2	HRT FE2010-H	0.18	0.60	0.024	0.004	0.39	0.08	1.94	15.95	0.023	0.13	.	.	.	0.044	0.024
1	SS 70	0.18	0.38	0.024	0.020	0.35	(0.06)	0.40	16.35	.	.	.	.	.	.	.
1	IARM 20B	0.18	0.35	0.019	0.004	0.40	0.069	1.94	12.42	0.030	0.32	0.0434	0.010	0.004	0.17	3.52
1	IARM 20C	0.18	0.30	0.018	0.007	0.35	0.060	1.93	12.15	0.031	0.12	0.0222	0.010	(0.003)	0.086	2.59
1	IMZ 167	0.175	1.16	0.016	0.0025	0.755	0.106	0.16	13.07	(0.021)	0.024	0.053	.	(0.002)	0.054	.
1	SS 473	0.172	0.494	0.019	0.030	0.604	(0.02)	(0.06)	9.06	(0.01)	0.95	.	.	.	(0.02)	.
1	13X 41800A	0.172	0.328	0.0176	0.0006	0.316	0.104	2.05	12.30	0.0357	0.068	0.028	(0.006)	.	0.020	2.75
2	BS 183A	0.172	0.35	0.016	0.0040	0.37	0.093	1.85	12.14	0.036	0.12	0.0256	0.006	0.002	0.090	2.60
1	IARM Fe418-18	0.168	0.429	0.016	(0.0005)	0.32	0.22	2.00	12.4	0.029	0.104	0.031	(0.019)	.	0.046	2.63
1	13X 15024X	0.166	0.610	0.0284	0.0294	0.750	0.332	2.99	14.65	0.1059	0.299	0.0156	0.039	.	0.150	0.039
1	13X 43100A	0.166	0.378	0.0199	0.0050	0.535	0.134	2.10	16.39	0.0239	0.0768	0.075	0.006	.	0.0577	0.004
2	13X 12549K	0.166	0.34	0.092	0.29	0.43	0.10	1.26	11.70	0.52	1.49	.	.	.	0.03	.
1	IARM 12C	0.155	0.55	0.022	0.0032	0.34	0.33	2.23	15.78	0.048	0.125	0.056	0.020	(0.002)	0.040	0.015
1	SS 470	0.153	0.235	0.024	0.035	0.335	(0.02)	0.369	17.68	(0.02)	.	.	.	.	(0.02)	.
2	BS 92B	0.150	0.42	0.021	0.003	0.42	0.13	2.12	15.92	0.04	0.17	0.073	(0.006)	.	0.07	0.02
1	SRM 1219	0.149	0.42	0.026	0.001	0.545	0.162	2.16	15.64	.	0.164	0.078	.	.	0.056	.
1	BS 431	0.146	0.579	0.0232	0.0047	0.393	0.282	2.25	15.8	0.050	0.092	0.049	0.034	0.0007	0.062	0.012
1	IARM 335A	0.138	0.85	0.016	0.0005	0.39	0.086	4.27	15.30	0.063	2.72	0.085	0.015	(0.002)	0.094	0.008
1	BS 355	0.136	0.862	0.0171	0.0003	0.374	0.173	4.18	15.43	0.053	2.73	0.081	0.0103	0.0007	0.106	0.0069
1	13X 41001A	0.136	0.464	0.0142	0.0037	0.298	0.056	0.0939	12.06	0.0143	0.0102	0.0316	.	.	0.079	.
1	IARM Fe410-18	0.136	0.417	0.014	0.0014	0.29	0.046	0.280	12.2	0.012	0.046	0.032	0.046	.	0.065	(0.008)
1	NCS HS28747	0.132	0.453	0.027	0.0068	0.502	0.126	1.79	16.44	0.051	0.153	0.030	.	(0.002)	0.075	.
1	BS 410C	0.131	0.381	0.0206	0.0051	0.366	0.084	0.352	12.78	0.0185	0.055	0.039	0.056	0.0006	0.042	0.0131
1	BS 002I	0.128	0.420	0.021	0.008	0.354	0.040	0.100	12.00	0.015	0.016	0.029	(0.001)	(0.003)	0.029	0.005
1	IARM 10C	0.128	0.35	0.026	0.29	0.37	0.155	0.24	12.25	0.022	0.08	0.015	0.003	0.002	0.024	0.011
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	SRM 1223	0.127	1.08	0.018	0.329	0.327	0.081	0.232	12.64	.	0.053	.	.	.	0.068	.
1	ECRM 296-1D	0.1166	0.676	0.0178	0.0026	0.242	0.1498	2.790	11.82	0.0218	1.700	0.0214	.	.	0.363	.
1	BS 416	0.116	0.64	0.0237	0.35	0.232	0.154	0.371	13.41	0.0241	0.030	0.043	(0.006)	0.0012	0.100	0.0034
1	13X T5035U	0.115	0.674	0.0415	0.0456	0.636	0.204	2.38	14.00	0.199	0.399	0.0584	0.500	.	0.160	0.048
1	13X 64152A	0.114	0.666	0.0123	0.0020	0.224	0.0622	2.50	11.34	0.0185	1.567	0.0339	.	.	0.275	.
1	13X 41600A	0.111	0.627	0.0253	0.302	0.442	0.160	0.331	13.23	0.0216	0.0499	0.0245	0.0053	.	0.0888	(0.003)
1	IARM 291A	0.11	0.71	0.016	0.009	0.23										



## STAINLESS STEEL WITH C &gt; 0.05 %

CONTINUED ON THE NEXT PAGE

# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	VS LG76	0.445	0.342	0.021	0.0076	0.455	0.098	13.39	13.77	.	0.263	0.031	.	0.020	0.041	2.38
1	VS LG74	0.373	0.962	0.024	0.0049	2.49	0.093	23.66	18.30	0.031	0.104	0.030	.	0.030	.	0.052
1	KUT S21	0.37	0.19	0.017	0.021	1.26	0.11	22.3	3.99	.	4.12	.	.	0.50	.	.
2	CZ CM-19A	0.361	0.783	0.0440	0.0182	1.588	0.986	15.27	13.12	0.222	1.023	(0.021)	0.091	0.254	1.235	0.311
1	VS LG79	0.313	1.28	0.017	0.0036	0.703	0.065	8.72	19.23	.	1.18	.	0.47	0.049	0.049	1.16
2	CZ SP-3C	0.30	0.43	0.026	0.011	0.84	0.185	5.31	16.42	0.041	0.26	.	(0.04)	(0.17)	0.19	0.12
1	DSZU C016	0.281	3.26	0.0192	0.0174	1.16	0.054	7.47	21.9	.	0.52	0.010	.	0.72	0.036	0.014
3	CZ SP-3B	0.27	0.29	0.023	0.008	0.72	0.62	5.65	15.1	0.02	0.24	.	.	0.13	0.10	0.12
1	KUT S19	0.26	0.32	0.012	0.021	2.32	0.19	12.8	7.00	.	0.11	.	0.81	0.048	.	.
1	SRM C1153a	0.225	0.544	0.030	0.019	1.00	0.226	8.76	16.70	0.127	0.24	.	.	.	0.176	.
1	13X 18001B	0.207	0.463	0.0090	0.0786	0.203	0.149	6.13	15.92	0.0231	0.816	0.0347	0.612	.	0.0996	.
1	KUT H6/1	0.20	0.49	0.021	0.024	0.67	0.10	0.15	18.9	.	.	.	.	0.10	.	(0.12)
2	CZ SP-3D	0.171	0.34	0.021	0.015	0.71	0.73	5.36	16.44	0.033	0.25	.	(0.04)	0.088	0.11	0.12
2	13X NSB1D	0.17	0.44	.	0.015	0.58	.	10.0	19.1	.	0.11	0.04	.	.	.	.
1	IARM 339A	0.16	1.71	0.004	0.009	0.64	0.021	12.9	17.0	0.007	2.79	0.0060	(0.005)	(0.002)	0.007	(0.0119)
1	13X 18002D	0.159	0.722	0.0245	0.0487	0.352	0.116	7.92	17.77	0.0514	0.209	0.072	1.531	.	0.0542	.
2	CZ CM-18A	0.143	1.792	0.0182	0.0119	0.903	2.393	20.44	20.59	0.097	2.282	0.0848	.	.	0.113	0.097
1	SS 468/1	0.143	1.70	0.014	0.020	1.41	.	8.90	17.96	0.018	.	.	.	.	.	.
1	SRM C1152a	0.142	0.95	0.023	0.0064	0.64	0.097	10.86	17.76	0.22	0.44	.	.	.	0.033	.
1	VS LG32/5	0.138	0.54	0.0057	0.039	0.185	0.019	7.10	19.75	.	0.110	.	.	0.92	0.317	0.205
1	13X NSA2J	0.132	1.03	0.0252	0.0275	0.739	0.259	10.08	17.82	.	2.013	0.131	0.155	.	0.139	.
1	IARM 289A	0.126	1.67	0.006	0.0019	0.58	0.016	7.12	17.0	0.054	(0.005)	0.0032	0.008	0.028	0.01	0.01
1	IARM 241D	0.125	1.94	(0.003)	0.0023	1.00	0.242	8.98	18.12	0.022	(0.02)	(0.008)	0.028	0.018	0.031	(0.012)
1	DSZU C018	0.125	1.09	0.0268	0.0099	0.53	0.163	9.33	17.54	.	0.189	0.009	.	0.54	0.048	0.066
1	13X NSB3G	0.121	0.632	.	.	0.471	.	9.26	15.22	.	0.630	0.198	.	.	.	.
1	KUT H5	0.12	0.48	0.017	(0.003)	0.70	0.22	0.20	21.8	.	.	.	.	0.03	.	0.10
1	13X 18003C	0.113	1.000	0.0545	0.0245	0.805	0.0433	10.08	19.56	0.100	0.401	0.090	1.042	.	0.0750	.
1	IRSID 1819	0.112	0.903	0.023	0.0112	0.616	0.064	7.10	17.31	0.117	0.110	0.0288	.	.	.	.
1	13X 17002E	0.112	0.801	0.0409	0.0250	0.486	0.1012	7.87	17.45	0.0702	0.204	0.061	0.487	.	0.0587	.
1	NCS HS28743	0.110	0.841	0.024	0.0082	0.780	0.089	18.02	23.71	0.102	0.115	0.057	0.016	(0.003)	0.077	.
1	IMZ 166A	0.108	1.99	0.019	0.005	2.51	0.025	21.93	25.53	0.030	(0.025)	0.077	.	0.003	0.038	.
1	13X 12855N	0.107	0.918	0.0020	0.0063	0.863	0.340	11.79	16.29	0.155	2.96	0.0078	0.098	0.083	.	0.199
1	13X 14828A	0.104	1.52	0.0268	0.0067	2.19	0.409	11.25	19.3	0.143	0.301	0.037	0.016	.	0.080	0.0167
1	VS LG81	0.104	0.29	0.0121	0.0014	0.231	0.088	22.5	11.51	.	1.22	.	0.004	2.93	0.040	0.012
1	VS LG77	0.101	0.34	0.0149	0.0021	0.44	0.116	4.32	15.67	.	0.020	0.054	0.109	.	0.022	0.006
1	IMZ 164	0.100	1.77	0.019	0.002	0.82	0.26	6.75	20.96	0.035	3.48	0.249	0.049	(0.003)	0.053	(0.025)
2	13X 17003A	0.10	0.85	0.037	0.035	0.78	0.08	11.9	11.89	0.07	0.27	.	0.34	.	.	.
1	VS LG73	0.098	1.26	0.019	0.0073	0.570	0.140	17.74	22.60	0.247	0.061	0.0319	.	0.0022	.	0.102
1	KUT S20	0.097	1.50	0.011	0.025	1.80	0.44	18.2	2.06	.	3.15	.	1.22	(0.01)	.	.
1	VS LG80	0.097	0.709	0.025	0.0029	2.15	0.166	19.38	24.7	.	0.086	0.064	.	0.015	0.032	0.029
2	BS 253	0.094	0.58	0.018	<0.001	1.81	0.14	10.89	20.68	0.15	0.21	0.146	0.017	0.005	0.050	0.03
1	IARM 234C	0.092	1.93	0.0090	(0.0027)	0.88	3.41	9.00	18.15	0.034	0.012	(0.01)	0.053	0.026	0.055	(0.006)
1	SS 462	0.092	0.74	0.010	0.018	0.46	.	12.53	12.37	.	.	.	.	.	.	.
1	DSZU C015	0.087	0.420	0.0118	0.059	0.214	0.070	12.15	15.36	.	0.89	0.020	.	0.177	0.021	0.023
1	SS 464/1	0.086	0.791	0.020	0.028	0.57	.	20.05	25.39	0.054	.	.	.	.	.	.
1	13X 17004B	0.084	0.497	0.018	0.039	1.23	0.0449	16.04	21.37	0.055	0.455	0.0086	0.179	0.034	.	.
1	IMZ 165	0.082	0.98	0.017	0.007	1.42	0.040	19.01	23.28	0.029	0.025	0.105	.	(0.002)	0.042	.
1	SS 467/1	0.082	0.788	0.018	0.019	0.52	.	9.21	18.09	.	.	.	0.99	.	.	.
1	13X 12854M	0.081	1.84	0.038	0.028	0.89	0.205	11.38	15.64	0.344	2.00	0.0097	0.33	0.052	.	0.141
1	VS LG35/5	0.078	0.81	0.042	0.0094	1.01	0.066	8.23	18.44	.	0.39	.	.	0.73	0.041	0.107
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	13X 17001C	0.0769	1.543	0.055	0.0134	0.215	0.0161	6.31	14.83	0.0979	0.0967	.	0.546	.	.	.
1	KUT S26	0.076	0.99	0.027	0.026	0.67	0.14	3.31	18.9	.	2.59	.	0.07	0.11	.	.
1	NCS HS41750	0.075	1.43	0.031	0.012	0.33	0.276	6.35	16.31	.	0.107	0.058	.	(0.001)	0.064	.
1	ECRM 270-1D	0.0742	0.540	0.0196	0.0007	1.517	0.1076	10.86	20.88	0.0685	0.2099	0.1417	.	(0.0019)	0.0256	(0.0244)
1	VS LG78	0.074	1.60	0.017	0.0017	0.58	0.053	35.4	14.71	.	0.061	0.0062	0.004	1.31	0.020	3.16
1	BS 192	0.074	0.835	0.025	0.0005	0.387	0.412	7.11	16.44	0.104	0.430	0.0290	0.168	0.076	0.124	0.05
2	BS 83G	0.073	1.66	0.024	0.004	0.56	0.114	19.15	24.50	0.153	0.085	0.026	0.061	(0.003)	0.077	0.007
1	NM 301	0.073	1.38	0.037	0.021	0.39	0.41	7.89	18.0	0.17	0.36	.	.	.	0.07	.
1	VS LG72	0.072	1.32	.	0.0050	0.334	0.306	12.4	16.36	0.090	2.07	0.0073	.	0.57	.	0.077
1	NM 302	0.072	1.06	0.031	0.018	0.49	0.40	10.12	16.92	0.19	2.03	.	.	.	0.066	.
1	13X 12534X	0.0716	0.589	0.0192	0.0086	0.811	0.0586	8.50	17.71	0.0602	2.04	.	0.201	0.348	0.110	0.010
1	IARM 316A	0.070	0.61	0.023	0.0011	1.50	0.19	10.81	21.07	0.118	0.250	0.16	(0.003)	(0.002)	0.042	0.022
1	IARM 18D	0.069	8.1	0.032	0.0025	3.68	0.421	8.39	16.7	0.086	0.325	0.170	(0.031)	0.012	0.064	(0.026)
1	13X 12853L	0.069	1.156	0.0053	0.0062	0.994	0.092	12.31	17.13	0.0415	2.718	0.0086	0.180	0.0455	.	0.089
1	VS LG63	0.068	0.356	0.010	0.0050	0.285	0.024	22.15	10.13	.	1.65	.	0.113	2.98	0.086	0.43
1	KUT S25	0.067	1.90	0.045	0.015	1.49	0.07	13.8	15.6	.	1.77	.	0.07	0.46	.	.
1	SRM 1171	0.067	1.81	(0.019)	(0.013)	0.536	0.1205	11.18	17.50	(0.097)	0.167	.	.	0.346	.	(0.012)
1	BS 9841	0.067	1.69	0.024	0.024	0.54	0.356	19.55	24.30	0.116	0.57	0.064	0.070	(0.002)	0.070	0.06
1	SS 465/1	0.066	1.380	0.021	0.012	0.405	0.098	9.24	17.31	0.053	0.092	.	.	0.40	0.102	.
1	BS 192A	0.066	0.768	0.021	<0.002	0.300	0.334	7.01	16.44	0.114	0.28	0.029	0.208	0.083	0.077	0.048
1	IMZ 152	0.065	1.42	0.010	0.0025	0.52	0.061	9.48	18.04	.	0.017	.	.	.	.	0.030
1	IMZ 152A	0.065	1.38	0.0115	0.0072	0.55	0.065	8.47	17.10	(0.006)	0.010	0.083	(0.003)	(0.003)	0.013	(0.004)
1	VS LG71	0.064	1.33	0.032	0.0072	0.602	0.204	10.40	17.63	0.188	0.161	.	.	0.473	.	0.048
2	CT 304	0.063	0.78	0.026	0.023	0.56	0.34	9.60	18.57	0.20	0.33	.	0.043	.	0.037	.
2	BS 82E	0.062	1.61	0.027	0.001	0.58	0.26	12.49	22.38	0.12	0.31	0.072	0.062	0.003	0.064	0.041
1	13X 31008A	0.062	1.232	0.030	0.0040	0.510	0.157	19.35	24.45	0.078	0.337	0.063	0.012	.	0.079	0.166
1	KUT H7/1	0.062	0.35	0.018	0.022	0.42	0.085	0.10	9.07	.	.					

## STAINLESS STEEL WITH C &gt; 0.05 %

## CONTINUED FROM THE PREVIOUS PAGE

Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units
VS LG76	0.034	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
VS LG74	0.035	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
KUT S21	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
CZ CM-19A	0.0788	.	(0.091)	.	(0.0036)	.	.	.	.	0.0283	.	.	-37 mm Ø x -25 mm
VS LG79	0.059	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
CZ SP-3C	0.095	(0.03)	1.67	.	.	.	.	.	.	(0.02)	.	.	-39 mm Ø x 25 mm
DSZU C016	0.007	.	.	.	0.0004	.	.	.	.	.	.	.	40 mm Ø x 25 mm
CZ SP-3B	0.08	.	0.88	.	.	.	.	.	.	0.01	.	.	-39 mm Ø x 25 mm
KUT S19	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
SRM C1153a	.	.	.	.	.	.	.	0.006	.	.	.	.	32 mm Ø x 19 mm
13X 18001B	0.0157	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
KUT H6/1	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
CZ SP-3D	0.037	(0.03)	2.45	.	.	.	.	.	.	(0.04)	.	.	-39 mm Ø x 25 mm
13X NSB1D	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm
IARM 339A	0.004	(0.001)	0.0006	.	0.0014	.	0.016	.	.	(0.002)	(0.005)	(0.003)	31 mm Ø x 2 or 18 mm
13X 18002D	0.0617	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
CZ CM-18A	0.0344	.	.	.	.	.	.	.	.	.	.	.	-37 mm Ø x -25 mm
SS 468/1	.	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm
SRM C1152a	.	.	.	.	.	.	.	0.0047	.	.	.	.	32 mm Ø x 19 mm
VS LG32/5	0.156	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -25 mm
13X NSA2J	.	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
IARM 289A	0.01	.	0.0003	.	.	.	0.0104	.	.	(0.002)	<0.005	.	31 mm Ø x 2 mm
IARM 241D	0.022	(0.001)	0.0016	.	(0.0012)	.	(0.005)	(0.0003)	.	(0.0022)	(0.007)	(0.005)	31 mm Ø x 2 or 18 mm
DSZU C018	0.086	.	.	.	0.0003	.	.	.	.	.	.	.	40 mm Ø x 25 mm
13X NSB3G	.	.	.	.	.	.	.	0.006	.	.	.	.	42 mm Ø x 15 mm
KUT H5	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
13X 18003C	0.0292	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
IRSID 1819	.	.	(0.0004)	.	.	.	.	.	.	.	.	.	47 mm x 47 mm x 30 mm
13X 17002E	(0.030)	.	0.0012	.	.	.	.	.	.	.	(0.012)	.	-40 mm Ø x -15 mm
NCS HS28743	0.0056	0.0042	.	.	.	.	.	0.0004	.	0.0025	.	.	38 mm Ø x 35 mm
IMZ 166A	0.036	(0.0026)	.	.	.	.	.	.	.	(0.0035)	.	.	40 mm Ø x 40 mm
13X 12855N	0.048	.	0.0098	.	.	.	.	.	0.093	.	0.122	.	-40 mm Ø x -15 mm
13X 14828A	0.008	.	.	.	.	.	.	.	.	0.0128	.	.	-40 mm Ø x -15 mm
VS LG81	0.409	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
VS LG77	.	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
IMZ 164	0.040	(0.005)	.	.	.	.	.	(0.002)	.	(0.003)	.	.	40 mm Ø x 40 mm
13X 17003A	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm
VS LG73	.	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
KUT S20	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
VS LG80	0.025	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
<b>BS 253</b>	0.016	0.005	.	.	.	0.044	.	.	.	0.006	<b>25(pre-17025)</b>	.	38 mm Ø x -7 or 19+ mm
IARM 234C	0.035	(0.001)	0.0023	.	(0.0017)	.	(0.005)	(0.001)	.	0.0017	(0.003)	(0.006)	31 mm Ø x 2 or 18 mm
SS 462	.	0.007	.	.	.	.	.	0.0005	.	.	.	.	38 mm Ø x 19 mm
DSZU C015	(0.008)	.	.	.	0.0017	.	.	.	.	.	.	.	40 mm Ø x 25 mm
SS 464/1	.	(0.003)	.	.	.	.	.	0.0004	.	.	.	.	38 mm Ø x 19 mm
13X 17004B	0.043	.	0.0066	.	.	.	.	.	.	.	0.057	.	-40 mm Ø x -15 mm
IMZ 165	0.038	(0.003)	.	.	.	.	.	(0.001)	.	0.003	.	.	40 mm Ø x 40 mm
SS 467/1	.	0.004	.	.	.	.	.	0.004	.	.	0.0017	.	38 mm Ø x 19 mm
13X 12854M	.	.	0.0101	0.0052	.	.	.	.	0.068	.	0.020	0.0146	-40 mm Ø x -15 mm
VS LG35/5	0.087	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -25 mm
Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units
13X 17001C	0.0312	.	0.0085	.	.	.	.	.	.	.	0.0124	.	-40 mm Ø x -15 mm
KUT S26	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
NCS HS41750	0.009	.	.	.	.	.	.	.	.	.	.	.	38 mm Ø x 35 mm
ECRM 270-1D	(0.0023)	(0.0034)	Ce: 0.0487	La: 0.0154	.	.	.	.	(0.0007)	(0.0035)	.	(0.002)	38 mm Ø x 25 mm
VS LG78	0.15	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
<b>BS 192</b>	1.17	(0.005)	(0.0003)	.	0.0007	.	0.0014	<b>25(pre-17025)</b>	.	0.008	(0.001)	.	38 mm Ø x -7 or 19+ mm
BS 83G	(0.004)	.	(0.001)	.	.	.	0.0064	.	.	0.003	.	.	38 mm Ø x -7 or 19+ mm
NM 301	.	.	.	.	.	.	.	.	.	.	.	.	35 mm Ø x 20 mm
VS LG72	0.089	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x 28 mm
NM 302	.	.	.	.	.	.	.	.	.	.	.	.	35 mm Ø x 20 mm
13X 12534X	0.0485	.	.	.	.	.	.	.	.	.	0.031	.	-40 mm Ø x -15 mm
IARM 316A	0.006	0.007	(0.0003)	.	0.0017	0.064	0.0052	(0.0001)	.	0.006	(0.003)	.	31 mm Ø x 2 or 18 mm
IARM 18D	(0.006)	.	(0.0011)	.	.	.	.	.	.	(0.007)	.	.	31 mm Ø x 18 mm
13X 12853L	0.18	.	0.0018	.	.	.	.	.	.	.	0.034	.	-40 mm Ø x -15 mm
VS LG63	0.45	.	.	.	.	.	.	.	.	.	.	.	-47 mm Ø x -30 mm
KUT S25	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
SRM 1171	.	.	.	.	.	.	.	.	.	.	.	.	31 mm Ø x 19 mm
<b>BS 9841</b>	<(0.006)	(0.003)	0.0026	<b>25(pre-17025)</b>	.	.	(0.011)	(0.001)	(0.006)	0.006	.	(0.002)	44 mm Ø x -7 or 19+ mm
SS 465/1	0.026	.	0.0006	.	.	.	.	<(0.001)	.	.	.	.	38 mm Ø x 19 mm
<b>BS 192A</b>	0.98	(0.0035)	(0.0003)	.	(0.0006)	.	(0.0006)	.	.	0.008	<b>25(pre-17025)</b>	.	38 mm Ø x -7 or 19+ mm
IMZ 152	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm
IMZ 152A	(0.004)	(0.002)	0.0022	.	.	.	.	.	.	(0.001)	.	.	38 mm Ø x 20 mm
VS LG71	0.072	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
CT 304	.	.	.	.	.	.	.	<0.001	.	0.017	.	.	30-35 mm Ø x -16 mm Ag: 7ppm
BS 82E	0.006	.	0.0024	.	0.0014	.	.	.	.	0.006	.	.	38 mm Ø x -7 to 19 mm last
13X 31008A	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -15 mm
KUT H7/1	.	.	.	.	.	.	.	.	.	.	.	.	30-35 mm Ø x 18 mm
CT 316	.	.	.	.	.	.	.	0.001	.	0.006	.	.	30-35 mm Ø x -19 mm Ag: 5ppm
VS LG36/5	0.080	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -25 mm
<b>BS 321D</b>	0.103	0.0040	0.0012	.	(0.0003)	.	0.0009	(0.0003)	(0.001)	0.0091	<b>17025</b>	(0.001)	44 mm Ø x -7 or 19+ mm Fe,Mg
13X NSB2D	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 15 mm
<b>BS 9842</b>	0.014	(0.002)	0.0025	.	0.0010	.	(0.0044)	.	.	0.005	<b>25(pre-17025)</b>	.	38 mm Ø x -7 or 19+ mm
BS 82D	(0.002)	.	0.0040	.	0.0007	.	0.007	.	.	0.004	.	last	38 mm Ø x -7 mm
SRM 1172	.	.	.	.	.	.	.	.	.	.	<0.001	.	32 mm Ø x 19 mm
VS LG82	0.076	.	.	.	.	.	.	.	.	.	.	.	-45 mm Ø x -28 mm
BS 87F	0.004	0.005	(0.0006)	.	0.0007	.	0.005	.	.	0.004	.	.	41 mm Ø x -7 or 19+ mm
BS 86F	(0.007)	(0.003)	0.0026	.	(0.001)	.	.	(0.001)	.	0.004	.	.	44 mm Ø x -7 or 19+ mm
DSZU C017	0.28	.	.	.	0.0031	.	.	.	.	.	.	.	40 mm Ø x 25 mm
IARM Fe304H-18	(0.005)	0.0076	.	.	.	.	(0.008)	.	.	(0.014)	.	.	31 mm Ø x 2 or 18 mm
BS 347B	0.002	(0.003)	0.0036	.	(0.0005)	.	0.005	.	.	0.006	<(0.004)	.	38 mm Ø x -7 or 19+ mm
BS 347A	(0.002)	(0.003)	(0.0004)	.	(0.0002)	.	0.0047	.	.	0.007	<(0.004)	.	38 mm Ø x 19+ mm
Number	Al	As	B	Bi	Ca	Ce	O	Pb	Sb	Sn	Ta	Zr	Units

## STAINLESS STEEL WITH C &lt; 0.05 %

CONTINUED ON THE NEXT PAGE

# = Class, where 1 = CRM, 2 = RM, and 3 = RM with no uncertainties

analysis listed in mass %

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	ECRM 269-1D	0.0499	1.262	0.0313	0.0010	0.441	0.366	8.044	18.150	0.1116	0.397	0.0460	0.0242	0.0006	0.0991	0.0306
1	IARM 8H *	0.049	1.81	0.0250	(0.002)	0.40	0.192	9.08	17.14	0.083	0.237	0.027	0.48	0.0027	0.049	(0.016)
1	IARM 6i	0.049	1.76	0.0208	(0.023)	0.31	0.202	9.20	17.76	0.052	0.133	(0.013)	(0.018)	0.60	0.048	(0.023)
1	ECRM 289-1D	0.0489	1.016	0.0114	0.0027	0.531		24.68	14.63	0.065	1.102			2.01	0.260	
1	IMZ 150A	0.048	1.35	0.0064	0.0095	0.59	0.090	12.75	18.89	0.125	0.12		0.0026	0.021	(0.027)	0.11
1	IARM 4F	0.047	1.17	0.0195	0.0015	0.494	0.146	20.1	24.5	0.067	0.142	0.056	0.007	0.0031	0.146	0.012
1	13X 14211R	0.047	0.787	0.0093	0.008	1.73	0.336	12.64	24.48	0.034	0.395		0.150	0.206	0.039	2.99
1	13X 32100A	0.0463	1.52	0.0298	0.0011	0.498	0.415	9.32	17.39	0.105	0.282	0.0115	0.0191	0.376	0.106	0.021
1	IARM Fe303-18	0.046	1.55	0.033	0.35	0.47	0.61	8.12	17.2	0.140	0.42	0.069	0.015		0.072	0.029
1	<b>BS 188B</b>	0.046	0.247	0.016	(0.0007)	0.266	0.120	24.81	14.32	0.274	1.30	0.0021	0.099	2.20	0.264	0.043
1	IARM 4G	0.0454	1.36	0.027	0.0008	0.630	0.320	19.2	24.9	0.085	0.580	0.058	0.008	0.029	0.092	0.017
1	IARM 6J	0.045	1.52	0.028	(0.002)	0.62	0.383	9.00	17.74	0.191	0.387	0.0109	0.010	0.34	0.081	0.026
1	<b>BS 303</b>	0.044	1.80	0.028	0.326	0.415	0.627	8.17	17.23	0.071	0.410	0.023	0.008	0.017	0.056	0.023
1	IARM 4E	0.044	1.07	0.0224	0.0006	0.514	0.234	20.18	24.25	0.066	0.32	0.038	0.024	(0.003)	0.052	0.046
3	CZ SL-3A	0.043	1.73	0.024	0.002	0.53	0.22	19.6	24.6	0.06	0.38	0.065	0.013	0.003	0.066	0.03
1	KUT S15	0.043	0.38	(0.02)	0.013	0.26	1.54	3.90	16.7		2.46		0.64			
1	IARM 8i	0.0424	1.395	0.0352	0.0118	0.38	0.441	9.01	17.08	0.301	0.416	0.052	0.60	(0.008)	0.057	0.060
1	13X 14216P	0.0424	0.663	0.0048	0.0070	1.566	0.231	12.06	23.44	0.248	0.209	0.0152	0.248		0.0722	2.25
1	IARM 8G	0.042	1.468	0.0327	0.0126	0.36	0.390	9.02	17.20	0.162	0.359	0.046	0.53	0.0024	0.062	0.032
1	VS LG70	0.042	0.834	0.042	0.0020	0.382	0.062	9.17	17.10	0.209	0.096	0.0134		0.305		0.0053
1	NILAB 500HA D	0.041	1.541	0.024	0.012	0.720	0.182	11.00	16.93	0.139	2.73	0.1154	0.023		0.074	
1	13X 12538J	0.04	0.78			0.64		6.07	23.72		1.53					
1	NCS HS28741	0.039	1.07	0.037	0.016	0.425	0.399	8.19	18.31	0.208	0.027	0.069		(0.002)	0.106	
1	13X 14207L	0.0388	0.597	0.0061	0.0060	1.448	0.186	12.43	19.63	0.0089	0.573	0.0099	0.258	0.0119	0.0043	2.99
1	IRSID 1821	0.037	1.72	(0.025)	(0.004)	0.542	0.058	10.42	17.04	0.266	2.04	0.0125		0.297		
1	IMZ 153A	0.037	1.49	0.021	0.0073	0.73	0.102	13.57	16.45	0.015	2.61	0.107	0.034	0.036	0.020	
1	ECRM 292-1D	0.0367	1.744	0.0175	0.0055	0.402	0.0391	10.09	18.00	0.0255	0.0464	0.0640	0.571			
1	13X 6E286A	0.036	1.172	0.0173	(0.0006)	0.216	0.195	25.21	15.00	0.083	1.190	0.0040		1.92	0.264	0.098
2	BS 184A	0.035	0.06	0.007	0.001	0.080	0.041	8.34	12.66	0.036	2.20	0.0045	(0.006)	0.051	0.014	0.032
1	SS 462/1	0.0345	0.722	0.0053	0.0041	0.463	0.0112	12.85	11.888		0.0304					
1	SRM C1151a	0.034	2.37	0.017	0.038	0.29	0.385	7.25	22.59	0.033	0.79				0.040	
1	13X 31400A	0.033	1.60	0.026	0.0006	2.23	0.210	18.76	24.38	0.129	0.240	0.0288	0.018		0.092	0.015
1	<b>BS 9812</b>	0.031	0.485	0.018	0.004	0.43	1.65	6.61	14.82	0.110	0.76	0.0195	0.645	(0.005)	0.088	0.025
1	13X NSA9B	0.030	1.52	0.0237	0.0009	0.290	0.154	5.75	22.39	0.033	3.27	0.184	0.021		0.060	0.033
1	13X 30403B	0.0277	1.820	0.0321	0.0266	0.288	0.497	8.13	18.30	0.178	0.313	0.083	0.0201	0.0013	0.0700	0.035
2	HRT FE2014-H	0.027	1.91	0.023	(0.002)	0.39	0.25	9.92	17.16		0.41	(0.018)		0.31		
1	VS LG75	0.027	0.728	0.0046	0.0026	0.298	0.029	24.5	14.80	0.190	0.052	0.0044		1.76		4.14
1	<b>BS 9811</b>	0.027	0.380	0.016	0.0010	0.36	1.63	6.55	14.87	0.055	0.744	0.0196	0.62	(0.003)	0.086	0.013
1	SRM 1155a	0.0260	1.593	0.0271	(0.0020)	0.521	0.2431	12.471	17.803	0.225	2.188	(0.0428)	0.0082	0.0039	0.0725	0.0809
1	13X 32900A	0.0251	1.478	0.0276	0.0269	0.556	0.354	5.57	24.91	0.0724	1.310	0.097		0.0139	0.0938	0.017
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	Ti	V	W
1	<b>BS 317L</b>	0.025	1.17	0.029	0.0017	0.67	0.23	13.51	18.2	0.14	3.07	0.055	0.031	0.0034	0.091	0.017
1	IARM 162D	0.0240	1.82	0.0296	0.0271	0.570	0.52	8.15	18.31	0.074	0.573	0.097	0.0090	0.013	0.063	0.028
1	IARM Fe304L-18	0.024	1.39	0.034	0.029	0.43	0.54	8.17	18.34	0.056	0.462	0.081	0.013	0.0056	0.076	0.056
1	IARM 153C	0.0225	1.60	0.0289	0.0288	0.349	0.442	11.10	18.22	0.251	3.00	0.086	0.015	0.004	0.058	0.043
1	ECRM 297-1D	0.0223	0.897	0.0137	0.0101	0.344	0.204	12.33	18.37	0.0413	0.290	0.0152	(0.0089)	0.0072	0.0535	(0.0057)
1	NCS HS28746	0.021	1.87	0.031	0.0009	0.510	0.340	8.24	17.19	0.191	0.069	0.011		0.184	0.096	
1	<b>BS 9942</b>	0.021	1.84	0.025	0.006	0.49	0.305	13.55	18.21	0.086	3.30	0.071	0.005	(0.002)	0.072	0.032
1	<b>BS 9941</b>	0.021	1.78	0.027	0.024	0.33	0.424	13.68	18.48	0.178	3.24	0.036	0.015	(0.002)	0.062	0.068
1	IARM Fe316L-18	0.021	1.70	0.033	0.029	0.438	0.550	10.12	16.7	0.209	2.02	0.067	(0.027)	(0.003)	(0.067)	(0.06)
1	IRSID 1820	0.021	1.61	(0.021)	0.0079	0.428	0.045	9.07	19.51	0.151	0.115	0.064				
1	<b>BS 2205A</b>	0.021	1.48	0.029	0.0006	0.53	0.300	5.26	22.73	0.071	3.17	0.157	0.010	(0.002)	0.083	(0.02)
1	NCS HS28742	0.021	0.940	0.034	0.0028	0.414	0.043	8.11	18.2	0.216	0.025	0.059		0.006	0.089	
1	IARM 301B	0.0206	0.807	0.0251	0.0010	0.419	0.192	7.01	25.06	0.055	3.75	0.297	0.020	(0.003)	0.070	0.050
1	13X NSA8B	0.0206	0.596	0.0248	0.0007	0.285	0.589	7.48	25.49	0.0448	3.49	0.232	0.026		0.0583	0.599
1	13X NSA13A	0.020	0.761	0.0249	0.0005	0.257	0.156	6.73	25.27	0.032	3.73	0.269	0.028		0.0712	0.035
1	SS 463/1	0.019	1.400	0.025	0.019	0.270	0.276	10.20	18.46	0.116	0.265	0.063				
1	<b>BS 2205</b>	0.0199	1.029	0.0227	0.0005	0.564	0.196	5.27	22.92	0.041	3.26	0.169	0.0052	0.0019	0.0560	0.0309
1	13X NSA12A	0.0192	1.272	0.0267	0.0007	0.492	1.485	24.84	19.63	0.090	4.20	0.0662	0.0088		0.0660	0.047
1	IARM 212D	0.019	1.21	0.024	0.0007	0.34	1.125	5.53	22.60	0.049	3.27	0.182	(0.009)	(0.002)	0.063	0.014
1	13X FV520BA	0.0181	0.655	0.0221	0.0016	0.342	1.462	5.29	13.73	0.030	1.334	0.0197	0.301		0.080	0.020
2	HRT FE2000-H	0.018	2.02	0.022	(0.003)	0.36	0.15	5.98	22.15	0.048	3.27	0.20	0.010	0.005	0.042	0.063
1	IARM FE2205-18	0.018	1.18	0.023	(0.0013)	0.46	0.208	5.57	22.6	0.104	3.20	0.17	0.011	(0.003)	0.063	0.024
1	NCS HS28745	0.018	1.17	0.042	0.0057	0.317	0.334	10.34	16.61	0.185	2.05	0.070		(0.002)	0.070	
1	SS 476	0.0171	1.755	0.0302	0.0234	0.323	0.302	10.17	16.88	0.162	2.04	0.0794	0.0107		0.066	0.041



## STAINLESS STEEL WITH C &lt; 0.05 %

## CONTINUED FROM THE PREVIOUS PAGE

analysis listed in mass %

Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units
ECRM 269-1D		0.0061						0.0099		35 mm Ø x 25 mm
IARM 8H	(0.005)		(0.0002)					(0.008)	(0.01)	31 mm Ø x 2 or 18 mm
IARM 61	0.084	(0.005)	0.0034	(0.0004)	0.0012			(0.0060)		31 mm Ø x 2 or 18 mm
ECRM 289-1D	0.199		0.0044					0.111		38 mm Ø x 30 mm
IMZ 150A	0.022									40 mm Ø x 40 mm
IARM 4F	0.015	(0.003)	(0.0012)	(0.002)	(0.004)		(0.001)	(0.005)	(0.007)	31 mm Ø x 2 or 18 mm
13X 14211R	0.089								0.0152	~40 mm Ø x ~15 mm
13X 32100A	0.0247		0.0025					0.0115		~38 mm Ø x ~15 mm
IARM Fe303-18		0.007	(0.0012)		(0.006)			(0.015)		31 mm Ø x 2 or 18 mm
<b>BS 188B</b>	0.168	0.0045	0.0047	(0.00003)	0.0006	(0.0001)	(0.0006)	0.0051		38 mm Ø x ~7 or 19+ mm Fe: 55.8 <b>17025</b>
IARM 4G	0.008	(0.005)	0.0032	(0.001)	(0.003)	(0.0005)	(0.001)	0.008	(0.008)	31 mm Ø x 2 or 18 mm
IARM 6J	0.0195		0.0024		(0.001)			(0.009)	(0.01)	31 mm Ø x 2 or 18 mm
<b>BS 303</b>	0.0019		0.0013	(0.0015)	0.0058			0.0091		44 mm Ø x ~7 or 19+ mm <b>17025</b> Fe:[70.7]
IARM 4E	0.004	(0.005)	0.0011		0.0021			0.0060	0.005	31 mm Ø x 2 or 18 mm
CZ SL-3A	0.007		0.002					0.006		~39 mm Ø x 25 mm
KUT S15										30-35 mm Ø x 18 last
IARM 81	(0.0030)		(0.0005)		(0.004)			(0.012)		31 mm Ø x 2 or 18 mm
13X 14216P										~40 mm Ø x ~15 mm
IARM 8G	0.0030	(0.007)	(0.0005)	(0.0005)	(0.003)			0.0107	(0.004)	31 mm Ø x 2 or 18 mm
VS LG70	0.029									~45 mm Ø x ~28 mm
NILAB 500HA D										38 mm Ø x 20 mm
13X 12538J										40 mm Ø x 15 mm
NCS HS28741		0.0035				0.0001		0.0051		38 mm Ø x 35 mm
13X 14207L	0.0226								0.082	~40 mm Ø x ~15 mm
IRSD 1821										47 mm x 47 mm x 30 mm
IMZ 153A	0.036									38 mm Ø x 20 mm
ECRM 292-1D	(0.002)	(0.008)		(0.0006)					(0.001)	38 mm Ø x 25 or 30 mm
13X 66286A	0.193		0.0044							~40 mm Ø x ~15 mm
BS 184A	1.00		(0.0004)	(0.0003)	(0.0003)			(0.002)	(0.002)	38 mm Ø x ~7 or 19+ mm
SS 462/1										38 mm Ø x 19 mm
SRM C1151a						0.0039				32 mm Ø x 19 mm
13X 31400A	0.022			0.0024						~40 mm Ø x ~15 mm
<b>BS 9812</b>	(0.002)	(0.005)	(0.0003)	0.0012	(0.007)			0.004		50 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
13X NSA9B			0.0018							~40 mm Ø x ~15 mm
13X 30403B	0.0056			0.0027				0.0139		~40 mm Ø x ~15 mm
HRT FE2014-H										35mm Ø x 20 mm
VS LG75	0.113									~45 mm Ø x ~28 mm
<b>BS 9811</b>	(0.003)	(0.003)	(0.0003)	0.0014	(0.0060)			0.004		38 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
SRM 1155a	<0.01	(0.007)	(0.002)		(0.003)	<0.005		(0.0069)		32 mm Ø x 19 mm
13X 32900A	0.007		0.0028	0.0033						~40 mm Ø x ~15 mm
Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units
<b>BS 317L</b>	0.0044	(0.003)	0.0012	0.0017	(0.006)	(0.0002)	(0.002)	0.0049	(0.002)	37 mm Ø x ~7 or 19+ mm <b>17025</b>
IARM 162D	(0.0026)	0.0072	0.0027	(0.003)	0.005		(0.0019)	0.0102	(0.005)	31 mm Ø x 2 mm
IARM Fe304L-18	(0.003)	0.007	(0.0012)		(0.006)			(0.013)		31 mm Ø x 2 or 18 mm
IARM 153C	(0.003)	0.0061	0.0009	(0.0026)	0.006	(0.001)	(0.002)	0.010	(0.006)	31 mm Ø x 2 or 18 mm
ECRM 297-1D	0.0195	0.0040	1.146	(0.0002)						40 mm Ø x 30 mm
NCS HS28746	0.086	0.0032				0.0002		0.0065		38 mm Ø x 35 mm
<b>BS 9942</b>	0.004	(0.004)	0.0014	0.0014	(0.0023)			0.006		44 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
<b>BS 9941</b>	0.004	(0.010)	0.0025	(0.0003)	(0.0058)			0.007		38 mm Ø x ~7 or 19+ mm <b>25(pre-17025)</b>
IARM Fe316L-18	(0.006)				(0.005)			(0.013)		31 mm Ø x 18 mm
IRSD 1820			(0.0013)							47 mm x 47 mm x 30 mm
<b>BS 2205A</b>	(0.004)	0.0072	0.0022	0.0007	0.0046			0.0058		38 mm Ø x ~7 or 19+ mm <b>17025</b> Fe: 66.2
NCS HS28742		0.0025				0.0001		(0.0001)		38 mm Ø x 35 mm
IARM 301B	0.005	(0.004)	0.0024	(0.0009)	0.0069	(0.0003)	(0.0006)	0.0051	(0.003)	31 mm Ø x 2 mm
13X NSA8B			0.0017							~38 mm Ø x ~15 mm
13X NSA13A	(0.007)		0.0030			(0.0008)		0.0046		~40 mm Ø x ~15 mm
SS 463/1			0.0022							38 mm Ø x 19 mm
<b>BS 2205</b>	0.0080	0.0059	0.0016	0.0014	0.0034	(0.0001)	0.0010	0.0050	<b>17025</b>	38 mm Ø x 13 mm Fe:[67.0] Mg:(0.0004) last
13X NSA12A	0.0169		0.0020							~40 mm Ø x ~15 mm
IARM 212D	(0.005)	(0.01)	0.001	(0.001)	0.0034	(0.001)		(0.003)	(0.003)	31 mm Ø x 2 mm last of stock
13X FV520BA										~40 mm Ø x ~15 mm
HRT FE2000-H			0.0013							40 mm Ø x 20 mm
IARM Fe2205-18	(0.007)				(0.004)			(0.006)		31 mm Ø x 2 or 18 mm
NCS HS28745		0.0055				0.0001		0.0073		38 mm Ø x 35 mm
SS 476		0.0053		0.0028				0.0059		38 mm Ø x 19 mm
<b>BS 304B</b>	0.0036	0.0051	(0.0004)	0.0009	0.0038	(0.0008)		0.0057		38 mm Ø x ~7 or 19+ mm <b>17025</b> Fe: 69.6
IARM 239C	0.007	(0.004)	0.0014					(0.003)	(0.004)	31 mm Ø x 2 or 18 mm
IARM FeZ100-18	(0.017)		0.002		(0.003)			(0.006)		31 mm Ø x 2 or 18 mm
<b>BS 179C</b>	0.0078	0.0034	0.0015	(0.0003)	0.0038	(0.00002)	0.0005	0.0018	(0.0006)	38 mm Ø x ~7 or 19+ mm <b>17025</b> Fe:[61.6]
<b>BS 179B</b>	0.0070	0.0036	0.0015	(0.0004)	0.0037	(0.00002)	0.0005	0.0019	(0.0006)	38 mm Ø x 19+ mm <b>17025</b> Fe:[61.5]
ECRM 287-1D			0.924							38 mm Ø x 25 or 30 mm
13X 34700A	0.023		0.0008							~38 mm Ø x ~15 mm
13X NSA11A	(0.021)									~38 mm Ø x ~15 mm
CZ SL-2A	0.005	0.008	0.002					0.01		~39 mm Ø x 25 mm
<b>BS 316F</b>	(0.002)	0.0067	0.0019	0.0018	0.0055	(0.0002)		0.0092	Fe:68.1	38 mm Ø x ~7 or 19+ mm <b>17025</b>
IARM 319A	(0.010)	(0.004)	0.0020		0.0025			0.0055	(0.002)	31 mm Ø x 2 mm
ECRM 298-1D	0.0285		0.0021			0.00008				38 mm Ø x 25 mm Fe: 63.38 last of stock
SS 466/2	0.0018	0.0020	0.0039							38 mm Ø x 19 mm
IARM 163E *	0.0039	(0.008)	0.0019	(0.002)	0.007		(0.002)	0.012		31 mm Ø x 2 mm * Provisional Analysis, last
HRT FE2016-H										30 mm Ø x 20 mm
SS 461/1	0.069									38 mm Ø x 19 mm
13X 30600A	0.020				Mg:0.0016					~32 mm Ø x ~20 mm
BS SS1961	0.067	0.004	0.0022		(0.002)			0.004		38 mm Ø x 12 mm last
JK 27B			0.00072	0.0022				0.0068		~37 mm Ø x 25 mm
BS SS1962	0.062	0.002	0.0018		(0.001)			0.004		38 mm Ø x ~7 or 19+ mm
IARM 354A	(0.05)	(0.002)	0.0023	(0.0003)	(0.0012)	(0.004)	(0.0002)	(0.002)		31 mm Ø x 2 or 18 mm
CT ISO123A	0.027		0.0021							44-47 mm Ø x ~16 mm Fe: 74.72
13X 46500A	0.069		0.0016					0.0030		~32 mm Ø x ~20 mm
ECRM 284-3D		0.00131	0.00020					0.00074		39 mm Ø x 28 mm
Number	Al	As	B	Ca	O	Pb	Sb	Sn	Ta	Units



## RM TRACE ELEMENTS IN STAINLESS STEEL

certified analysis							informational analysis											40 mm Ø x 20 mm		
Number	As	Pb	Sb	Sn	Zn		C	Mn	P	Si	Cu	Ni	Cr	Mo	N	B	Ca	Ti	V	
DSZU C25	0.093	0.038	0.094	0.095	0.034		0.3	0.1	0.02	0.3	0.7	1.6	13	0.1	0.10	0.03	0.004	.	0.03	
DSZU C22	0.051	0.023	0.050	0.051	0.019		0.4	0.1	0.02	0.2	0.5	1.5	13	0.1	0.04	0.03	0.002	.	0.03	
DSZU C33	0.021	0.0046	0.015	0.020	0.019		0.1	1.1	0.03	1.0	0.3	16	17	1.2	0.14	0.02	0.0004	0.05	.	
DSZU C24	0.014	0.0017	0.010	0.011	0.0035		0.4	0.1	0.02	0.2	0.3	1.5	13	0.1	0.12	0.007	0.003	.	0.03	
DSZU C31	0.012	0.0017	0.007	0.010	0.028		0.1	1.4	0.03	0.8	0.2	10	17	0.8	0.04	0.02	0.008	0.05	.	
DSZU C23	0.008	0.0008	0.006	0.010	0.0028		0.4	0.1	0.02	0.3	0.2	1.4	13	0.1	0.10	0.004	0.002	.	0.03	
DSZU C21	0.005	0.0002	0.0011	0.003	0.0026		0.4	0.1	0.02	0.3	0.2	1.2	13	0.1	0.03	0.002	0.001	.	0.03	

## STAINLESS STEEL XRF SETS

AVAILABLE IN SETS OR INDIVIDUALLY

~7 mm discs

Grade	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Nb	V	W
<b>SET BS SS-17</b>															
15-5PH	BS 185A	0.033	0.49	0.022	0.002	0.38	3.41	4.43	14.46	0.026	0.30	0.027	0.32	0.048	(0.014)
17-4PH	BS 17-4PHA	0.018	0.85	0.023	0.022	0.40	3.30	4.69	15.40	0.072	0.34	0.022	0.204	0.043	.
17-7PH	BS 192	0.075	0.84	0.025	0.001	0.38	0.41	7.10	16.42	0.104	0.42	0.029	0.17	0.13	0.04
253 MA	BS 253	0.094	0.58	0.018	<0.001	1.81	0.14	10.89	20.68	0.15	0.21	0.146	0.017	0.050	0.03
255	<b>BS 179C</b>	0.0164	0.878	0.0236	0.0003	0.373	1.53	6.10	25.9	0.0386	3.34	0.236	0.009	0.080	0.056
2205 (318)	<b>BS 2205</b>	0.0199	1.029	0.0227	0.0005	0.564	0.196	5.27	22.92	0.041	3.26	0.169	0.0052	0.0560	0.0309
303	<b>BS 303</b>	0.044	1.80	0.028	0.326	0.415	0.627	8.17	17.23	0.071	0.410	0.023	0.008	0.056	0.023
304 L	BS 81P	0.026	1.35	0.023	0.012	0.36	0.19	10.06	18.15	0.21	0.41	0.069	.	0.078	0.037
309	BS 82E	0.062	1.61	0.027	0.001	0.58	0.26	12.49	22.38	0.12	0.31	0.072	0.062	0.064	0.041
310	BS 83G	0.073	1.66	0.024	0.004	0.56	0.114	19.15	24.50	0.153	0.085	0.026	0.061	0.077	0.007
316	<b>BS 316F</b>	0.015	1.46	0.029	0.026	0.55	0.437	10.09	16.79	0.126	2.10	0.061	0.011	0.062	0.045
317 L	<b>BS 317L</b>	0.025	1.17	0.029	0.0017	0.67	0.23	13.51	18.2	0.14	3.07	0.055	0.031	0.091	0.017
321	<b>BS 85D</b>	0.048	1.69	0.024	0.024	0.54	0.45	9.98	17.09	0.97	0.59	(0.02)	0.062	0.132	(0.07)
330	BS 86F	0.054	1.30	0.021	0.021	1.22	0.23	34.99	18.74	0.098	0.24	0.035	0.19	0.061	(0.03)
347	BS 347B	0.051	1.57	0.028	0.026	0.51	0.15	9.16	17.24	0.05	0.38	0.056	0.71	0.04	(0.005)
355	BS 355	0.136	0.862	0.0171	0.0003	0.374	0.173	4.18	15.43	0.053	2.73	0.081	0.0103	0.106	0.0069
PH13-8 Mo	BS 184A	0.035	0.06	0.007	0.001	0.080	0.041	8.34	12.66	0.036	2.20	0.0045	(0.006)	0.014	0.032
<b>SET BS 400-SS-16</b>															
182PM	BS 150	0.048	1.71	0.020	0.33	0.43	0.042	0.19	18.61	0.024	1.97	0.029	0.003	0.054	0.01
410	BS 410C	0.131	0.381	0.0206	0.0051	0.366	0.084	0.352	12.78	0.0185	0.055	0.039	0.0056	0.0006	0.0131
416	BS 90F	0.085	0.53	0.023	0.328	0.58	0.12	0.30	13.01	0.021	0.14	0.037	0.011	0.076	0.032
416 Se	BS 151	0.090	0.41	0.021	0.018	0.65	0.11	0.24	13.19	0.018	0.088	0.022	0.005	0.046	0.010
420	BS 98	0.309	0.48	0.019	0.0014	0.72	0.098	0.21	13.35	0.020	0.034	0.0181	0.003	0.075	0.009
420F	BS 152	0.32	0.36	0.022	0.275	0.44	0.050	0.14	13.41	0.015	0.061	0.020	0.006	0.051	<0.01
422	BS 97	0.216	0.71	0.021	0.0004	0.39	0.066	0.76	11.82	0.041	1.05	0.030	0.007	0.21	0.95
430	BS 91E	0.066	0.42	0.017	0.002	0.52	0.05	0.17	16.58	0.02	0.035	0.032	(0.004)	0.09	0.01
430F	BS 153	0.026	0.41	0.018	0.280	0.53	0.052	0.140	17.38	0.017	0.30	0.021	0.002	0.045	(0.002)
431	BS 92B	0.150	0.42	0.021	0.003	0.42	0.13	2.12	15.92	0.04	0.17	0.073	(0.006)	0.07	0.02
440C	BS 93E	1.02	0.52	0.022	0.0010	0.90	0.12	0.35	17.33	0.048	0.50	0.0359	0.005	0.24	0.11
440F	BS 155	1.00	0.35	0.014	0.145	0.40	0.035	0.13	16.64	0.019	0.46	0.032	0.002	0.10	.
440F Se	BS 156	1.06	1.15	0.022	0.007	0.47	0.09	0.35	16.87	0.047	0.50	0.041	0.005	0.13	0.11
446	BS 94C	0.057	0.45	0.024	0.002	0.62	0.056	0.43	25.90	0.042	0.20	0.065	0.032	0.12	(0.03)
450	BS 95A	0.035	0.58	0.026	0.004	0.46	1.50	6.42	14.72	0.081	0.73	0.0255	0.55	0.052	0.02
455	BS 96A	0.009	0.04	0.007	0.004	0.06	2.07	8.38	11.62	0.03	0.021	.	0.26	0.07	.

Number	Al	B	Ca	Se	Sn	Ti
--------	----	---	----	----	----	----

**SET BS SS-17**

BS 185A	0.002	0.0017	(0.0002)	.	0.007	(0.001)
BS 17-4PHA	.	0.0016	.	.	.	Ta: (0.002)
BS 192	1.15	(0.0004)	0.0007	.	0.009	0.078
BS 253	0.016	.	.	.	0.006	0.005
<b>BS 179C</b>	0.0078	0.0015	(0.0003)	.	0.0018	(0.0005)
					As: 0.0034	O: 0.0038
					Sb: 0.0005	<b>17025</b>
<b>BS 2205</b>	0.0080	0.0016	0.0014	.	0.0050	0.0019
<b>BS 303</b>	0.0019	0.0013	(0.0015)	.	0.0091	0.017
BS 81P	(0.003)	0.0026	(0.0004)	.	0.007	0.003
BS 82E	0.006	0.0024	0.0014	.	0.006	0.003
BS 83G	(0.004)	(0.001)	O: 0.0064	.	0.003	(0.003)
<b>BS 316F</b>	(0.002)	0.0019	0.0018	.	0.0092	0.011
<b>BS 317L</b>	0.0044	0.0012	0.0017	.	0.0049	0.0034
<b>BS 85D</b>	0.13	(0.001)	0.0004	.	0.0062	0.48
BS 86F	(0.007)	0.0026	(0.001)	.	0.004	(0.006)
BS 347B	0.002	0.0036	(0.0005)	.	0.006	(0.002)
BS 355	0.0192	0.0039	(0.0002)	.	0.0038	0.0007
BS 184A	1.00	(0.0004)	(0.0003)	.	(0.002)	0.051
					O: 0.0020	
<b>SET BS 400-SS-16</b>						
BS 150	0.002	.	.	.	(0.003)	(0.002)
BS 410C	0.0079	(0.0001)	0.0022	.	0.0023	0.0006
BS 90F	(0.006)	.	.	.	0.005	(0.002)
BS 151	(0.002)	.	.	0.328	0.005	(0.003)
BS 98	0.003	.	(0.0005)	.	0.006	0.002
BS 152	(0.002)	.	.	.	0.003	(0.002)
BS 97	0.018	.	.	.	(0.003)	(0.002)
BS 91E	(0.002)	.	0.0008	.	0.004	(0.002)
BS 153	(0.004)	.	.	.	0.002	(0.004)
BS 92B	(0.002)	.	(0.0009)	.	0.006	(0.002)
BS 93E	0.009	.	.	.	0.003	0.007
BS 155	(0.001)	.	.	.	(0.003)	(0.002)
BS 156	(0.002)	.	.	0.142	(0.004)	0.001
BS 94C	0.004	.	0.0008	.	0.006	.
BS 95A	0.002	0.0010	0.0008	.	0.008	(0.003)
BS 96A	0.08	(0.0017)	.	.	.	1.18



## HIGH ALLOY STEEL XRF SET

Part Number:	BS HAS-12	RM except CRM as noted, available as set or individually										* Provisional Analysis					~7 mm Ø discs		
Number Grade	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al	B	Co	N	Nb	Sn	Ti	V	W	O
<b>BS 189A</b> AL6XN CRM	0.0147	0.639	0.019	(0.001)	0.30	0.184	23.8	20.4	6.04	0.0129	(0.0002)	0.100	0.198	(0.13)	0.0035	0.0065	0.054	0.037	0.0024
		<b>17025</b>																	
BS 179A Alloy 255	0.017	1.04	0.021	0.001	0.44	1.94	5.84	25.45	3.24	(0.009)	(0.001)	0.58	0.184	0.030	0.005	0.006	0.070	(0.2)	.
<b>BS 183B</b> Greek Ascology CRM	0.181	0.344	0.018	0.0042	0.41	0.074	1.96	12.45	0.33	0.0009	(0.0007)	0.032	0.044	(0.0075)	0.0046	(0.0016)	0.165	3.5	(0.0054)
		<b>17025</b>																	
BS 186A Invar 36	0.040	0.72	0.008	0.0053	0.19	0.016	35.86	0.16	0.0032	(0.001)	.	0.028	0.0026	(<0.002)	(0.002)	(<0.003)	0.0012	(0.01)	.
BS 187A Carp. 20Cb3	0.022	0.52	0.017	0.0025	0.26	3.10	33.06	19.75	2.06	(0.009)	0.0022	0.32	0.0157	0.57	0.003	(0.002)	0.10	(0.02)	.
<b>BS 188B</b> A-286 CRM	0.046	0.247	0.016	(0.0007)	0.266	0.120	24.81	14.32	1.30	0.168	0.0047	0.274	0.0021	0.099	0.0051	2.20	0.264	0.043	0.0006
		<b>17025</b>																	
BS 190 Nitronic® 40	0.022	9.72	0.015	0.001	0.46	0.072	6.74	19.57	0.15	(0.004)	0.0005	0.044	0.255	(0.004)	0.003	0.002	0.11	0.015	0.0045
BS 180A Nitronic® 50	0.018	5.05	0.012	0.001	0.32	0.067	13.19	21.09	2.04	0.012	(0.0024)	0.039	0.334	0.20	(0.002)	(0.002)	0.20	0.02	0.003
BS 181A Nitronic® 60	0.071	8.16	0.019	0.001	4.03	0.18	8.15	16.52	0.21	0.022	0.0009	0.072	0.148	0.017	0.005	0.007	0.094	0.04	0.0010
BS 193 18Cr-12Mn	0.104	12.11	0.018	0.002	0.66	0.088	1.82	18.48	0.21	(0.003)	0.0007	0.028	0.37	0.014	0.004	0.003	0.107	(0.007)	.
BS 182 17Cr-15Mn	0.037	15.09	0.022	(0.003)	0.46	0.56	1.11	16.67	0.99	.	.	0.032	(0.40)	(0.005)	(0.003)	(0.003)	0.059	(0.01)	.
BS 191 16Cr-6Mn-4Si	0.098	5.71	0.024	0.023	3.66	0.33	5.34	16.33	0.36	(0.002)	(0.0006)	0.11	0.117	0.024	(0.006)	0.012	0.083	0.033	.

## CRM CAST IRON SETS AVAILABLE IN SETS ONLY, as grouped

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Sn	Ti	V	Ce	La	Mg	N
30 mm Ø x 28 mm																	
NCS HS11712a-6	4.02	1.41	0.021	0.026	0.163	1.83	1.89	0.112	0.019	0.726	0.057	0.238	0.509	<0.0001	<0.0001	0.104	0.013
NCS HS11712a-7	3.94	1.38	0.085	0.0048	0.918	1.10	1.37	1.05	0.214	0.168	0.134	0.114	0.390	<0.0001	<0.0001	0.056	0.0063
NCS HS11712a-5	3.52	0.311	0.420	0.019	1.17	0.389	1.03	0.766	.	0.629	0.013	0.161	0.324	<0.0001	<0.0001	0.021	0.0047
NCS HS11712a-4	3.16	0.462	0.396	0.017	1.96	0.921	0.778	1.40	0.0073	0.428	0.024	0.065	0.166	<0.0001	<0.0001	0.025	0.0073
NCS HS11712a-2	2.22	0.301	0.043	0.058	2.44	0.458	0.341	2.13	0.060	0.087	0.044	0.065	0.055	0.0010	0.010	0.0085	0.024
NCS HS11712a-3	2.55	0.878	0.071	0.045	1.50	0.641	0.519	0.417	0.034	0.354	0.021	0.027	0.085	0.027	0.0061	0.024	0.024
NCS HS11712a-1	1.75	0.080	0.580	0.119	3.40	0.025	0.030	2.48	0.248	0.031	0.0031	0.038	0.021	<0.0001	<0.0001	0.0006	0.015
30 mm Ø x 30 mm																	
NCS HS19701-7	4.13	2.06	0.306	0.111	1.85	.	0.026	0.157	.	.	0.043	0.399	0.821	.	.	.	.
NCS HS19701-6	3.93	1.46	0.168	0.124	0.99	.	0.094	0.387	.	(0.112)	0.0018	0.105	0.506	.	.	.	.
NCS HS19701-5	3.67	0.596	0.072	0.117	0.183	.	0.502	0.171	.	(0.68)	0.0022	0.066	0.335	.	.	.	.
NCS HS19701-4	3.70	0.857	0.087	0.076	0.451	.	0.032	0.117	.	(0.031)	0.0017	0.030	0.158	.	.	.	.
NCS HS19701-3	3.29	1.22	0.045	0.056	0.689	.	0.046	0.030	.	.	0.009	0.043	0.071	.	.	.	.
NCS HS19701-2	2.99	0.329	0.033	0.038	0.937	.	0.194	0.080	.	.	0.024	0.216	0.044	.	.	.	.
NCS HS19701-1	2.46	0.072	0.011	0.019	0.099	.	0.183	0.511	.	.	0.005	0.0059	0.0090	.	.	.	.

**RM GRAY IRON** as cast (not chill cast) CONTAINS FREE GRAPHITE **OBS regularly requires extension of preburn time to analyze correctly**

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	As	Co	Mo	Sb	Sn	Ti	V	mm Ø x mm H
BS 20G	3.33	0.58	0.028	0.029	3.02	0.54	0.38	0.086	0.008	0.004	0.022	0.19	<(0.001)	0.12	0.012	0.018	47 x 19+
BS 20W	3.27	0.62	0.045	0.036	2.64	0.29	0.082	0.092	0.004	0.004	0.005	0.054	<(0.001)	0.086	0.015	0.007	47 x 13
BS 20R	3.25	0.62	0.047	0.034	2.72	0.35	0.096	0.094	0.005	0.004	0.006	0.053	<(0.001)	0.104	0.015	0.007	47 x 19+
BS 20E	3.24	0.80	0.042	0.044	2.29	0.23	0.156	0.088	0.006	(0.003)	0.006	0.042	<(0.002)	0.093	0.017	0.007	47 x 19+
BS 20P	3.22	0.63	0.032	0.044	2.62	0.067	0.143	0.079	0.008	(0.004)	0.018	0.033	<(0.001)	0.099	0.018	0.017	44 x 19+

**DUCTILE / NODULAR IRON**

# = Class, where 1 = CRM and 2 = RM

\* Provisional Analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Ce	Co	Mg	Mo	Ti	V
1	SCRM 666/12	3.599	0.106	.	.	1.763	0.0581	1.709	0.102	.	.	.	<b>0.083</b>	0.0979	0.1069	0.0486
1	SCRM 667/13	3.04	0.222	.	.	2.866	0.497	1.303	0.294	.	0.110	.	<b>0.070</b>	.	.	0.103
1	<b>BS 285BH</b>	3.43	0.732	0.0470	0.0128	1.93	0.321	1.38	1.05	0.0168	.	0.0034	<b>0.052</b>	0.238	0.0429	0.122
1	<b>BS 286CI</b>	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.052</b>	0.258	0.052	0.150
1	<b>BS 285BG</b>	3.44	0.731	0.0469	0.0126	1.93	0.321	1.39	1.05	0.0165	.	0.0038	<b>0.051</b>	0.238	0.0427	0.122
1	<b>BS 286CH</b>	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.051</b>	0.258	0.052	0.150
1	<b>BS 285BF</b>	3.43	0.732	0.0472	0.0127	1.93	0.320	1.386	1.047	0.0164	.	0.0033	<b>0.050</b>	0.238	0.0424	0.122
1	<b>BS 286CG</b>	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.050</b>	0.258	0.052	0.150
1	<b>BS 285BE</b>	3.45	0.732	0.0474	0.0128	1.93	0.321	1.38	1.047	0.0162	.	(0.003)	<b>0.049</b>	0.238	0.0428	0.122
1	<b>BS 286CF</b>	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.049</b>	0.258	0.052	0.150
1	<b>BS 285BD</b>	3.45	0.730	0.0471	0.0126	1.93	0.322	1.39	1.047	0.0160	.	0.0036	<b>0.048</b>	0.238	0.0427	0.121
1	<b>BS 286CE</b>	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.048</b>	0.258	0.052	0.150
1	<b>BS 286CD</b>	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.047</b>	0.258	0.052	0.150
1	<b>BS 286CC</b>	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.046</b>	0.258	0.052	0.150
1	BS 291GK *	3.34	0.50	0.034	0.014	2.31	0.23	0.098	0.069	0.044	.	0.004	<b>0.046</b>	0.030	0.027	0.033
1	BS 291GJ *	3.34	0.50	0.034	0.014	2.31	0.23	0.098	0.069	0.043	.	0.004	<b>0.045</b>	0.030	0.027	0.033
1	SCRM 670/22	3.55	0.300	0.040	0.009	2.25	0.96	0.87	0.49	.	0.013	.	<b>0.044</b>	0.014	0.104	0.019
1	BS 291GI *	3.34	0.50	0.034	0.014	2.31	0.23	0.098	0.069	0.043	.	0.004	<b>0.044</b>	0.030	0.027	0.033
1	<b>BS 286CB</b>	3.27	0.714	0.20	(0.012)	2.00	0.363	1.43	0.349	0.012	(0.03)	0.027	<b>0.043</b>	0.258	0.052	0.150
1	BS 291GH *	3.34	0.50	0.034	0.014	2.31	0.23	0.098	0.069	0.042	.	0.004	<b>0.043</b>	0.030	0.027	0.033
1	BS 291GG *	3.34	0.50	0.034	0.014	2.31	0.23	0.098	0.069	0.041	.	0.004	<b>0.042</b>	0.030	0.027	0.033
1	BS 291GF *	3.34	0.50	0.034	0.014	2.31	0.23	0.098	0.069	0.040	.	0.004	<b>0.041</b>	0.030	0.027	0.033
1	BS 291GE *	3.34	0.50	0.034	0.014	2.31	0.23	0.098	0.069	0.039	.	0.004	<b>0.040</b>	0.030	0.027	0.033
1	<b>BS 291FE</b>	3.35	0.500	0.023	0.017	2.33	0.208	0.097	0.020	0.040	.	0.0035	<b>0.039</b>	0.035	0.025	0.017
1	BS 291GD *	3.34	0.50	0.034	0.014	2.31	0.23	0.098	0.069	0.039	.	0.004	<b>0.039</b>	0.030	0.027	0.033
1	<b>BS 291FD</b>	3.35	0.500	0.023	0.017	2.33	0.208	0.097	0.020	0.040	.	0.0035	<b>0.038</b>	0.035	0.025	0.017
1	BS 291GC *	3.34	0.50	0.034	0.014	2.31	0.23	0.098	0.069	0.038	.	0.004	<b>0.038</b>	0.030	0.027	0.033
1	BS 291GB *	3.34	0.50	0.034	0.014	2.31	0.23	0.098	0.069	0.037	.	0.004	<b>0.037</b>	0.030	0.027	0.033
1	BS 291GA *	3.34	0.50	0.034	0.014	2.31	0.23	0.098	0.069	0.036	.	0.004	<b>0.036</b>	0.030	0.027	0.033
2	BAS SIMO 1/5	2.72	0.330	0.031	0.014	3.94	0.005	0.035	0.889	0.029	.	0.004	<b>0.034</b>	0.738	0.008	0.004
1	SRM C1137a	2.86	0.52	0.087	0.017	1.15	0.192	2.17	0.643	(0.007)	0.016	.	<b>0.032</b>	0.86	(0.04)	0.019
1	BAS SIMO 2/2	2.14	0.434	0.025	0.007	4.75	0.010	0.0189	0.856	0.013	0.006	0.0029	<b>0.026</b>	0.484	0.005	0.009
1	SCRM 669/15	3.09	0.52	0.041	0.0108	2.41	0.217	0.48	0.260	.	0.040	.	<b>0.023</b>	0.057	0.058	0.50
1	SCRM 668/14	3.77	0.702	0.045	0.0220	1.72	0.65	0.096	0.99	.	0.023	.	<b>0.009</b>	0.0179	0.086	0.195
1	SRM C2424	2.68	0.268	0.041	0.024	3.37	0.125	0.061	0.13	<(0.01)	0.0046	(0.05)	<b>0.006</b>	0.019	0.050	0.083

Number	As	B	Ca	Fe	La	Nb	Pb	Sn	W	Zr	Units
SCRM 666/12	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
SCRM 667/13	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
<b>BS 285BH</b>	0.0007	0.0084	0.0010	90.54	Sb:(0.2)	0.0040	0.0009	0.0017	0.0612	0.0055	~35 mm Ø x ~30 mm <b>17025</b>
<b>BS 286CI</b>	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm <b>17025</b>
<b>BS 285BG</b>	0.0008	0.0084	0.0010	90.54	Sb:(0.2)	0.0039	0.0009	0.0017	0.0611	0.0055	~35 mm Ø x ~30 mm <b>17025</b>
<b>BS 286CH</b>	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm <b>17025</b>
<b>BS 285BF</b>	0.0009	0.0084	0.0010	90.54	Sb:(0.2)	0.0039	0.0008	0.0018	0.0608	0.0054	~35 mm Ø x ~30 mm <b>17025</b>
<b>BS 286CG</b>	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm <b>17025</b>
<b>BS 285BE</b>	0.0010	0.0084	0.0009	90.53	Sb:(0.2)	0.0038	0.0007	0.0016	0.0607	0.0054	~35 mm Ø x ~30 mm <b>17025</b>
<b>BS 286CF</b>	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm <b>17025</b>
<b>BS 285BD</b>	0.0010	0.0084	0.0009	90.54	Sb:(0.2)	0.0039	0.0007	0.0017	0.0608	0.0055	~35 mm Ø x ~30 mm <b>17025</b>
<b>BS 286CE</b>	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm <b>17025</b>
<b>BS 286CD</b>	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm <b>17025</b>
<b>BS 286CC</b>	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm <b>17025</b>
BS 291GK *	0.005	0.016	0.001	[93.1]	Sb:0.003	0.004	<0.005	0.048	0.004	0.002	~33-35 mm Ø x ~28-32 mm
BS 291GJ *	0.005	0.016	0.001	[93.1]	Sb:0.003	0.004	<0.005	0.048	0.004	0.002	~33-35 mm Ø x ~28-32 mm
SCRM 670/22	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
BS 291GI *	0.005	0.016	0.001	[93.1]	Sb:0.003	0.004	<0.005	0.048	0.004	0.002	~33-35 mm Ø x ~28-32 mm
<b>BS 286CB</b>	(0.002)	0.0086	0.0012	91.1	(0.005)	(0.005)	(0.0007)	(0.01)	0.0025	(0.003)	~35 mm Ø x ~30 mm <b>17025</b>
BS 291GH *	0.005	0.016	0.001	[93.1]	Sb:0.003	0.004	<0.005	0.048	0.004	0.002	~33-35 mm Ø x ~28-32 mm
BS 291GG *	0.005	0.016	0.001	[93.1]	Sb:0.003	0.004	<0.005	0.048	0.004	0.002	~33-35 mm Ø x ~28-32 mm
BS 291GF *	0.005	0.016	0.001	[93.1]	Sb:0.003	0.004	<0.005	0.048	0.004	0.002	~33-35 mm Ø x ~28-32 mm
BS 291GE *	0.005	0.016	0.001	[93.1]	Sb:0.003	0.004	<0.005	0.048	0.004	0.002	~33-35 mm Ø x ~28-32 mm
<b>BS 291FE</b>	(0.002)	0.014	0.0008	93.1	.	(0.002)	(0.001)	(0.06)	(0.002)	(0.001)	~35 mm Ø x ~25 mm <b>17025</b>
BS 291GD *	0.005	0.016	0.001	[93.1]	Sb:0.003	0.004	<0.005	0.048	0.004	0.002	~33-35 mm Ø x ~28-32 mm
<b>BS 291FD</b>	(0.002)	0.014	0.0008	93.1	.	(0.002)	(0.001)	(0.06)	(0.002)	(0.001)	~35 mm Ø x ~25 mm <b>17025</b>
BS 291GC *	0.005	0.016	0.001</								

## CAST IRON WITH MAGNESIUM - continued on the next page

# = Class, where 1 = CRM and 2 = RM

\* Provisional Analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V
1	CZ 20034 17b	4.38	0.501	0.089	0.0040	0.178	0.111	2.34	0.200	0.009	.	(0.002)	(0.003)	0.043	0.030	0.016	0.086
1	CZ 20034 17a	4.30	0.494	0.115	0.0034	0.170	0.082	2.38	0.200	0.007	.	(0.002)	(0.003)	0.043	0.030	0.016	0.086
1	CZ 20034 17c	4.08	0.503	0.104	0.0033	0.150	0.037	2.32	0.178	0.007	.	(0.002)	(0.003)	0.043	0.030	0.015	0.076
1	Y 2863-11	4.03	0.61	0.613	0.026	0.79	0.96	0.46	1.65	0.0075	.	.	.	.	0.94	0.29	0.079
2	CZ SPL17 43A	3.98	1.322	0.190	0.008	1.63	0.385	0.411	0.032	(0.04)	.	0.024	0.017	0.045	0.152	0.065	0.152
2	CZ SPL17 42A	3.94	0.764	0.294	0.0040	1.94	0.199	0.492	0.145	(0.06)	.	0.087	0.039	0.010	0.021	0.126	0.093
1	Y 451045	3.90	0.12	0.023	0.0027	2.29	0.022	0.45	0.028	0.033	.	.	.	.	0.0030	0.016	0.0014
1	CZ 02033 2g	3.78	0.096	0.125	0.009	1.10	0.88	0.650	0.027	0.036	(0.004)	0.019	0.013	0.012	(0.002)	0.029	0.017
1	SCRM 668/14	3.77	0.702	0.045	0.0220	1.72	0.65	0.096	0.99	0.009	.	.	0.023	.	0.0179	0.086	0.195
1	Y 2863-12	3.77	0.158	0.053	0.057	0.150	0.55	0.192	2.31	0.0024	.	.	.	.	0.44	0.030	0.229
1	CZ 02033 2f	3.77	0.091	0.159	0.009	1.23	0.89	0.658	0.022	0.053	.	0.024	0.018	(0.003)	(0.002)	0.021	0.010
1	Y 4510251B-16	3.75	0.39	0.034	0.012	1.69	0.423	0.60	0.52	0.053	.	0.061	0.034	.	0.203	0.036	0.198
1	CZ 02033 3c	3.68	0.333	0.026	0.007	2.15	0.421	0.040	0.100	0.006	(0.005)	0.024	0.013	0.026	0.490	0.021	0.016
1	SCRM 666/12	3.599	0.106	.	.	1.763	0.0581	1.709	0.102	0.0838	.	.	.	.	0.0979	0.1069	0.0486
2	Y 4510058B-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.042	.	.	0.022	.	0.180	0.044	0.174
2	Y 4510058C-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.039	.	.	0.022	.	0.180	0.044	0.174
2	Y 4510058D-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.036	.	.	0.022	.	0.180	0.044	0.174
2	Y 4510058E-18	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	0.032	.	.	0.022	.	0.180	0.044	0.174
1	SCRM 670/22	3.55	0.300	0.040	0.009	2.25	0.96	0.87	0.49	0.044	.	.	0.013	.	0.014	0.104	0.019
2	CZ SPL17 31A	3.54	0.041	0.025	0.006	2.10	0.005	0.538	0.019	0.070	.	0.005	(0.004)	0.022	0.004	0.007	0.008
1	CZ 20034 15b	3.52	0.048	0.054	0.0031	1.66	1.322	0.681	0.067	0.037	.	0.029	0.021	0.027	0.004	0.025	0.013
2	CZ SPL17 34A	3.48	0.980	0.105	0.008	2.29	0.230	0.493	0.102	0.026	.	0.010	0.008	0.025	0.072	0.044	0.073
1	CZ 20034 15c	3.47	0.060	0.054	0.0028	1.68	1.123	0.728	0.078	0.040	.	0.010	0.030	0.026	(0.002)	0.036	0.019
2	CZ SPL17 32A	3.39	0.288	0.037	0.007	2.74	0.306	0.015	0.060	0.024	.	0.029	(0.004)	(0.002)	0.116	0.044	0.005
1	CZ 02033 3b	3.38	0.260	0.012	0.012	1.74	0.400	0.049	0.235	0.012	.	0.026	0.006	0.012	0.456	0.023	0.009

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Te	Al	Ce	Co	Mo	Ti	V
2	CZ SPL17 40A	3.38	0.042	0.021	0.0035	1.98	0.010	0.045	0.031	0.007	.	0.096	0.012	0.027	0.005	0.015	0.014
1	VS ChG 28	3.29	0.414	0.025	0.015	2.22	1.29	0.166	0.127	0.010	.	0.015	.	.	0.0024	0.0041	0.0020
1	CZ 20034 14b	3.26	0.240	0.0115	0.0096	2.34	0.640	0.020	0.042	0.015	.	0.012	0.012	0.005	0.635	0.021	0.012
1	CZ 02033 3d	3.24	0.317	0.008	0.006	2.12	0.396	0.025	0.236	0.016	.	0.055	0.006	0.014	0.453	0.016	0.072
1	CZ 02033 1f	3.23	0.693	0.043	0.005	2.68	0.018	0.373	0.035	0.070	(0.007)	0.073	0.036	0.024	0.182	0.041	0.014
1	CZ 20034 13c	3.15	0.704	0.0261	0.0044	2.23	0.089	1.299	0.124	0.064	.	0.022	0.011	0.024	0.360	0.015	0.043
1	CZ 20034 14c	3.14	0.275	0.0162	0.0081	2.49	0.585	0.030	0.045	0.017	.	0.007	0.019	0.009	0.646	0.018	0.013
1	CZ 20034 13a	3.13	0.691	0.0244	0.0046	2.19	0.021	1.266	0.122	0.053	.	0.017	0.011	0.024	0.364	0.014	0.048
1	CZ 20034 13b	3.12	0.692	0.0243	0.0041	2.12	0.021	1.313	0.125	0.054	.	0.019	0.011	0.024	0.364	0.012	0.048
1	VS ChG 24	3.05	0.245	0.260	0.0048	2.50	0.100	0.87	0.031	0.015	.	0.007	.	.	0.031	0.060	0.0067
1	Y 2863-9	3.04	1.43	0.049	0.015	1.53	0.269	1.59	0.72	0.043	.	.	.	.	1.38	0.212	0.41
1	VS ChM5/1	3.04	0.311	0.056	0.016	1.37	.	.	0.72	0.045	.	0.013	.	.	.	.	.
1	SCRM 667/13	3.04	0.222	.	.	2.866	0.497	1.303	0.294	0.070	.	.	0.110	.	.	.	0.103
1	BS CC-11A	3.07	1.23	0.020	0.011	1.90	0.007	0.046	0.048	0.014	0.026	0.0055	0.018	(0.007)	0.0063	0.0091	0.0066
1	BS CC-11B	2.97	1.17	0.020	0.008	1.94	0.0210	0.173	0.189	0.025	0.019	0.028	0.045	(0.022)	0.018	0.031	0.0179
1	VS ChM6/1	3.03	0.54	0.055	0.0074	2.75	.	.	0.072	0.105	.	0.022	.	.	.	.	.
1	VS ChM8/1	3.02	0.83	0.055	0.0034	3.39	.	.	0.105	0.105	.	0.041	.	.	.	.	.
2	CZ SPL17 36A	3.02	0.057	0.026	0.010	2.13	0.007	0.011	0.014	0.012	.	(0.003)	0.0007	(0.004)	0.004	0.021	0.021
1	VS ChM13	2.96	1.05	0.043	0.009	2.98	0.062	1.65	0.273	0.09	.	0.065	.	.	.	0.018	0.0096
1	SCRM 669/14	2.955	0.526	.	.	2.201	0.194	0.473	0.214	0.0224	.	.	0.0415	.	0.0550	0.0499	0.532
1	VS ChG 26	(2.9)	0.126	0.123	0.0041	2.98	0.014	1.52	0.050	0.044	.	0.038	.	.	0.075	0.0026	0.040
1	VS ChM10	2.89	0.43	0.067	0.017	1.13	0.082	0.85	0.067	0.024	.	0.005	.	.	.	0.028	0.079
1	SRM C1137a	2.86	0.52	0.087	0.017	1.15	0.192	2.17	0.643	0.032	.	(0.007)	0.016	.	0.86	(0.04)	0.019
2	CZ SPL17 33A	2.75	0.710	0.060	0.007	3.10	0.730	0.389	0.239	0.021	.	0.054	0.026	0.015	0.220	0.130	0.356
1	SRM C2424	2.68	0.268	0.041	0.024	3.37	0.125	0.061	0.13	0.006	.	(<0.01)	0.0046	(0.05)	0.019	0.050	0.083
1	VS ChM9	2.61	1.28	0.075	0.021	1.59	0.095	0.38	0.083	0.011	.	0.016	.	.	.	0.027	0.068
1	VS ChM11	2.26	0.77	0.032	0.011	2.32	0.067	1.75	0.122	0.066	.	0.035	.	.	.	0.014	0.0044
1	Y 2863-7	1.98	3.42	0.067	0.0061	3.10	0.089	4.47	0.150	0.050	.	.	0.019	.	0.052	0.060	0.87

BS: 28-34 mm Ø x 17-35 mm

CKD 24x: 37 mm x 37 mm x ~15-20 mm  
CZ: 40 mm Ø x 18 mmSCRM: 48 mm x 42 mm x 12 mm  
SRM: 32 mm Ø x 19 mmVS: ~40 mm Ø x ~40 mm  
Y: 30 mm Ø x 30 mm

## CAST IRON WITH MAGNESIUM - continued from the previous page

sizes shown below

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
CZ 20034 17b	0.008	(0.0002)	(0.001)	.	.	.	.	(0.002)	.	.	(0.002)	0.004	.	.
CZ 20034 17a	0.007	(0.0002)	(0.001)	.	.	.	.	(0.002)	.	.	(0.002)	0.004	.	.
CZ 20034 17c	0.0005	(0.0006)	(0.002)	.	.	.	.	(0.002)	.	.	(0.002)	0.004	.	.
Y 2863-11	(0.022)	0.053	.	.	.	.	0.33	(0.0057)	(0.174)	.	(0.108)	0.010	.	.
CZ SPL17 43A	.	0.0014	(0.002)	.	.	.	0.008	0.014	(0.004)	.	0.067	0.038	Zn:0.013	.
CZ SPL17 42A	.	0.0036	(0.002)	.	.	.	0.045	0.020	0.015	.	0.027	0.020	Zn:0.013	.
Y 451045	.	.	.	.	.	.	.	.	.	.	.	.	.	.
CZ 02033 2g	.	0.0023	0.006	.	.	.	.	0.008	0.029	.	0.015	(0.004)	.	Zn: 0.020
SCRM 668/14	.	.	.	.	.	.	.	.	.	.	.	.	.	.
Y 2863-12	(0.0097)	0.0078	.	.	.	.	0.21	(0.056)	(0.471)	.	(0.307)	0.13	.	.
CZ 02033 2f	.	0.0020	(0.002)	.	.	.	.	0.005	0.028	.	0.014	(0.003)	(0.005)	Zn: 0.018
Y 4510251B-16	.	0.0044	.	.	.	0.016	.	.	.	.	0.030	.	.	last
CZ 02033 3c	(0.007)	0.0044	(0.002)	.	.	.	.	0.005	.	.	0.009	(0.003)	.	.
SCRM 666/12	.	.	.	.	.	.	.	.	.	.	.	.	.	.
Y 4510058B-18	0.0021	0.024	.	.	.	.	.	.	.	.	.	.	.	.
Y 4510058C-18	0.0021	0.024	.	.	.	.	.	.	.	.	.	.	.	.
Y 4510058D-18	0.0021	0.024	.	.	.	.	.	.	.	.	.	.	.	.
Y 4510058E-18	0.0021	0.024	.	.	.	.	.	.	.	.	.	.	.	last
SCRM 670/22	.	.	.	.	.	.	.	.	.	.	.	.	.	.
CZ SPL17 31A	.	(0.0004)	.	.	.	.	.	.	.	.	(0.003)	(0.005)	.	.
CZ 20034 15b	(0.003)	0.0033	0.010	.	.	.	.	.	0.058	.	0.005	0.007	.	.
CZ SPL17 34A	.	0.0076	(0.005)	.	.	.	0.014	(0.006)	0.007	.	0.051	0.016	Zn:0.007	.
CZ 20034 15c	(0.003)	0.0057	0.008	.	.	.	.	.	0.056	.	0.006	0.004	.	.
CZ SPL17 32A	.	(0.0005)	(0.007)	.	.	.	.	0.022	0.023	.	(0.012)	(0.008)	Zn:0.011	.
CZ 02033 3b	.	0.0042	0.001	.	.	.	.	0.009	.	.	0.019	.	.	.

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
CZ SPL17 40A	.	0.0008	.	.	.	.	.	.	.	.	(0.004)	.	Zn:(0.002)	.
VS ChG 28	.	.	.	.	.	.	.	.	0.015	.	0.0017	.	.	.
CZ 20034 14b	0.034	0.0100	0.007	.	.	.	.	(0.005)	0.016	.	0.028	(0.005)	0.014	Zn: 0.009
CZ 02033 3d	(0.018)	0.0071	(0.002)	.	.	.	.	0.005	0.007	.	0.009	.	.	.
CZ 02033 1f	.	0.0043	(0.001)	.	.	.	.	0.009	.	.	0.030	0.022	(0.008)	.
CZ 20034 13c	(0.002)	.	.	.	.	.	.	.	(0.002)	.	0.014	(0.003)	(0.02)	.
CZ 20034 14c	0.035	0.0123	.	.	.	.	.	.	0.020	.	0.025	(0.003)	0.013	Zn: 0.010
CZ 20034 13a	(0.002)	.	.	.	.	.	.	.	(0.002)	.	0.014	(0.003)	0.029	.
CZ 20034 13b	(0.002)	.	.	.	.	.	.	.	(0.002)	.	0.014	(0.003)	0.023	.
VS ChG 24	.	.	.	.	.	.	.	.	0.009	.	0.077	.	.	.
Y 2863-9	(0.041)	0.153	.	.	.	.	0.11	(0.093)	(0.116)	.	(0.124)	.	.	.
VS ChM5/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.
SCRM 667/13	.	.	.	.	.	.	.	.	.	.	.	.	.	.
<b>BS CC-11A</b>	0.0018	0.0008	(0.005)	(0.0009)	93.6	(0.004)	(0.007)	(0.002)	(0.01)	Zn:0.0032	(0.004)	(0.017)	(0.0025)	<b>17025</b>
<b>BS CC-11B</b>	0.0074	0.0033	(0.016)	(0.002)	93.2	(0.008)	0.043	0.014	0.026	Zn:0.008	0.021	0.028	0.0165	<b>17025</b>
VS ChM6/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.
VS ChM8/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.
CZ SPL17 36A	.	0.022	(0.007)	.	.	.	.	0.016	.	.	(0.002)	.	Zn:(0.002)	.
VS ChM13	.	.	.	.	.	.	.	.	.	.	.	.	.	.
SCRM 669/14	.	.	.	.	.	.	.	.	.	.	.	.	.	.
VS ChG 26	.	.	.	.	.	.	.	.	.	.	0.031	.	.	.
VS ChM10	.	.	.	.	.	.	.	.	.	.	.	.	.	.
SRM C1137a	.	.	.	.	.	.	.	.	.	.	.	.	.	.
CZ SPL17 33A	.	0.0064	(0.002)	.	.	.	0.032	0.010	0.019	.	0.039	0.079	Zn:0.009	.
SRM C2424	.	(0.002)	.	.	.	0.0011	.	.	.	.	.	.	.	.
VS ChM9	.	.	.	.	.	.	.	.	.	.	.	.	.	.
VS ChM11	.	.	.	.	.	.	.	.	.	.	.	.	.	.
Y 2863-7	(0.021)	0.100	.	.	.	.	0.041	(0.0025)	(0.010)	.	(0.0073)	.	.	.

Number	As	B	Bi	Ca	Fe	La	Nb	Pb	Sb	Se	Sn	W	Zr	Other
--------	----	---	----	----	----	----	----	----	----	----	----	---	----	-------

BS: 28-35 mm Ø x 17-35 mm

CZ: 40 mm Ø x 18 mm  
SCRM: 48 mm x 42 mm x 12 mmSRM: 32 mm Ø x 19 mm  
Y: 30-35 mm Ø x 18-30 mmVS ChM: ~39 mm Ø x ~39 mm  
VS ChG: ~34 mm x ~35 mm X ~22 mm

**RM CAST IRON WITH YOUR CHOICE OF MAGNESIUM LEVELS** each unit: 2 pcs mushroom 43 mm Ø x 5 mm

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mg	Al	Ce	Co	Sn	Ti	V	Zn	Other
CTIF 6134	3.70	0.25	0.030	<0.01	1.60	0.020	2.00	0.040	*	.	<0.03	.	.	.	.	.	.
CTIF 8532	3.7	0.288	0.05	.	2.6	0.0443	0.888	0.04	*	.	<0.025	.	0.0303	0.02	0.07	.	.
CTIF 6135	3.6	0.38	0.0130	(0.003)	0.9	0.0219	1.98	0.04	*	(0.006)	.	0.037	.	0.007	0.0155	.	.
CTIF 4500	3.38	0.60	0.059	(0.002)	1.97	.	1.45	0.014	*	0.033	0.023	0.065	.	.	.	.	.
CTIF 5781	3.35	0.26	0.030	(0.0025)	2.50	0.0061	0.83	0.040	*	.	.	(0.004)	.	0.0208	0.0150	.	.
CTIF 4497	3.12	0.605	0.043	(-0.002)	2.66	0.048	1.90	0.040	*	.	.	.	0.094	0.031	0.44	.	.
CTIF 7160	3.1	0.57	0.05	(0.001)	2.4	0.08	1.0	(0.1)	*	(0.02)	0.02	0.09	.	0.013	0.018	.	As: 0.009
CTIF 5037	3.04	0.76	0.043	(0.0025)	3.40	.	0.64	0.014	*	.	.	.	.	0.029	.	.	.
CTIF 3601B	3.0	0.35	0.037	(0.005)	2.1	0.019	1.08	0.029	*	.	<0.01	.	.	0.016	(0.005)	<0.05	Pb:(<0.002)
CTIF 8018	3.0	0.7	0.07	(0.0015)	3.0	0.08	0.127	0.09	*	0.02	(<0.02)	.	0.07	0.06	0.39	.	Sb:(0.01)
CTIF 6736	2.8	0.65	0.012	(0.002)	1.6	0.0258	1.7	0.03	*	.	.	.	.	0.008	(0.03)	.	.
CTIF 5783	2.55	0.2	0.0266	(0.003)	2.3	0.110	1.23	0.05	*	.	.	0.0074	.	0.015	0.0127	.	As: 0.0016

Magnesium level available in the below samples. X = available

For Mg Range	Order Suffix	3601B	4497	4500	5037	5781	5783	6134	6135	6736	7160	8018	8532
<0.005	<0.005	X	.	.	.	X	X	.	.	.	.	X	X
0.005 - 0.009	0.005	X	.	.	X	X	X	.	.	X	.	X	X
0.010 - 0.014	0.01	.	.	.	X	X	X	.	.	X	X	X	X
0.015 - 0.024	0.02	X	.	.	X	X	X	.	X	X	X	X	X
0.025 - 0.034	0.03	.	.	.	X	.	X	.	X	X	X	X	X
0.035 - 0.044	0.04	.	.	.	X	.	X	.	X	X	X	X	X
0.045 - 0.054	0.05	.	.	.	X	.	X	.	X	X	X	X	X
0.055 - 0.064	0.06	.	X	X	.	.	X	.	X	X	X	X	X
0.065 - 0.074	0.07	.	X	X	.	.	X	.	X	X	X	X	X
0.075 - 0.084	0.08	.	X	X	.	.	X	X	X	X	X	X	X
0.085 - 0.094	0.09	.	X	X	.	.	X	X	X	X	X	X	X
0.095 - 0.104	0.10	.	.	.	.	.	X	X	X	X	X	X	X
0.105 - 0.114	0.11	.	.	.	.	.	X	X	X	X	X	X	X
0.115 - 0.124	0.12	.	.	.	.	.	X	X	X	X	X	X	X
0.125 - 0.134	0.13	.	.	.	.	.	X	X	X	X	X	X	X
0.135 - 0.144	0.14	.	.	.	.	.	X	X	X	X	X	X	X
0.145 - 0.154	0.15	.	.	.	.	.	.	.	.	.	X	.	.
0.155 - 0.164	0.16	.	.	.	.	.	.	.	.	.	X	.	.
0.165 - 0.174	0.17	.	.	.	.	.	.	.	.	.	X	.	.
0.175 - 0.184	0.18	.	.	.	.	.	.	.	.	.	X	.	.

The above cast iron samples can be ordered with your choice of Magnesium. Examples:  
 to order CTIF 6736 with Mg 0.035 - 0.044 then order as part number CTIF 6736 0.04  
 to order CTIF 8018 with 0.08 % Mg, order as part number CTIF 8018 0.08

**CRM WHITE IRON** analysis listed in mass %

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	Nb	Ti	V
<b>BS WI-2</b>	3.61	0.80	0.22	0.056	0.52	0.0124	0.254	0.229	0.0118	0.219	0.128	0.089	0.215
SRM CII45	2.92	0.187	0.215	0.191	0.271	0.46	0.62	0.63	0.058	0.48	.	0.012	0.112
VS ChG 8/6	(2.7)	1.51	0.040	0.013	3.93	.	.	(0.2)	.	.	.	.	(0.3)
VS ChG 10/6	(2.7)	0.86	0.103	0.0072	2.86	.	.	(0.2)	.	.	.	.	(0.3)
VS ChG 11/6	(2.7)	0.312	0.23	0.039	1.79	.	.	(0.2)	.	.	.	.	(0.3)
VS ChG 9/6	(2.7)	0.155	0.38	0.071	0.80	.	.	(0.2)	.	.	.	.	(0.3)
<b>BS WI-1</b>	1.75	0.24	0.051	0.114	1.90	0.027	0.053	0.048	0.0074	0.0103	0.027	0.020	0.008

Number	Al	As	B	Bi	Ca	Fe	Mg	Pb	Sb	Sn	W	Zr	Units
<b>BS WI-2</b>	0.0192	0.0016	0.0008	.	(0.00013)	[93.6]	(0.0002)	0.013	0.023	0.0042	0.023	0.0045	~35 mm Ø x ~30 mm
SRM CII45	(0.04)	(0.03)	(0.02)	(<0.01)	.	.	.	0.0012	(0.04)	(0.10)	.	(0.002)	32 mm Ø x 19 mm
VS ChG 8/6	.	(0.003-0.006)	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~40 mm
VS ChG 10/6	.	(0.003-0.006)	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~40 mm
VS ChG 11/6	.	(0.003-0.006)	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~40 mm
VS ChG 9/6	.	(0.003-0.006)	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~40 mm
<b>BS WI-1</b>	0.075	0.0067	0.0032	.	0.0005	[95.5]	0.0009	0.115	.	0.0081	0.185	0.0034	~35 mm Ø x ~30 mm



## CAST IRON WITH C &gt; 2.75%

## CONTINUED ON THE NEXT PAGE

# = Class, 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
2	CZ SPL17 35A	4.55	0.096	0.024	0.011	0.078	0.004	0.024	0.022	(0.002)	0.023	0.003	.	(0.002)	(0.002)	0.009	.
1	CZ 02033 4e	4.45	0.034	0.023	0.006	0.090	0.005	0.049	0.030	(0.003)	0.033	0.002	.	(0.001)	0.011	0.015	.
1	SCRMM 672/1	4.322	0.474	0.198	0.036	0.143	0.100	0.083	0.0186	(0.0102)	0.139	0.117	.	0.0047	0.0373	0.0988	.
1	CZ 02033 4d	4.19	0.112	0.050	0.041	0.259	0.084	0.063	0.056	0.007	(0.003)	0.024	.	(0.001)	0.009	0.012	0.009
1	SCRMM 659/9	4.174	1.010	0.0215	0.0372	1.361	.	.	.	.	.	.	.	.	.	.	.
1	Y 2582-7	4.13	2.06	0.306	0.111	1.85	.	0.026	0.157	.	.	.	.	.	0.399	0.821	.
1	DSZU CH04	4.01	1.77	0.074	0.018	0.73	0.55	0.273	0.100	0.014	(0.05)	(0.004)	(0.005)	(0.002)	0.025	(0.004)	.
1	DSZU CH05	3.99	2.23	0.119	0.039	0.46	0.61	0.85	1.63	(0.002)	(0.07)	0.109	(0.3)	(0.01)	0.070	0.200	.
1	CZ 02033 4b	3.95	0.145	0.041	0.046	0.252	0.062	0.023	0.049	0.003	0.005	0.005	.	0.001	0.006	0.004	0.008
1	VS ChG 2/9	3.93	0.456	0.513	0.078	0.387	0.082	.	0.060	.	.	.	.	.	0.080	0.049	.
1	DSZU CH06	3.88	0.85	0.050	0.050	0.28	1.03	1.23	(2.8)	0.025	(0.07)	0.29	(0.05)	(0.03)	0.33	0.205	.
1	CZ 20034 16c	3.87	1.311	0.173	0.0243	0.95	0.345	0.376	0.332	0.004	0.006	0.195	.	0.125	0.057	0.027	0.017
1	CZ 20034 16a	3.80	1.292	0.171	0.0266	1.00	0.332	0.390	0.374	0.007	0.010	0.203	.	0.125	0.0763	0.021	0.019
1	11X C6W	3.80	0.967	0.088	0.064	0.81	0.952	0.072	0.396	0.021	0.046	1.32	0.010	0.030	0.195	0.045	0.0045
1	CZ 20034 16b	3.78	1.327	0.170	0.0236	1.00	0.332	0.388	0.378	0.007	0.010	0.202	.	0.121	0.070	0.029	0.020
1	VS ChG 32	3.74	1.90	0.061	0.018	0.60	0.171	.	0.031	.	.	0.113	.	0.060	0.040	0.294	.
1	SCRMM 674/1	3.71	1.437	0.0180	0.078	0.484	.	0.161	0.0296	0.0061	0.0066	0.0497	.	0.0164	0.0131	0.0125	.
1	Y 2582-4	3.70	0.857	0.087	0.076	0.451	.	0.032	0.117	.	.	(0.031)	.	0.030	0.158	.	.
2	CZ SPL17 39A	3.70	0.812	0.160	0.045	1.90	0.298	0.032	0.488	0.008	(0.002)	0.203	.	(0.003)	(0.074)	0.232	0.035
1	Y 2582-5	3.67	0.596	0.072	0.117	0.183	.	0.502	0.171	.	.	(0.68)	.	0.066	0.335	.	.
1	VS ChG 1/9	3.61	1.12	0.184	0.038	1.13	0.041	.	0.017	.	.	.	.	.	0.014	0.006	.
1	CZ 02033 7b	3.61	0.304	0.021	0.020	1.82	0.036	1.28	0.536	0.022	0.050	0.96	.	.	0.015	0.007	.
1	CZ 02033 7c	3.55	0.389	0.028	0.026	1.73	0.016	1.26	0.542	0.040	0.048	0.966	.	(0.004)	0.026	0.067	.
1	DSZU CH03	3.54	0.40	0.023	0.034	0.57	0.194	0.187	0.612	0.035	(0.05)	(0.019)	(0.010)	(0.004)	0.059	0.009	.
1	VS ChG 3/9	3.54	0.387	0.037	0.053	0.516	0.123	.	0.100	.	.	.	.	.	0.125	0.096	.
1	VS ChG 27	3.53	1.21	0.044	0.029	1.82	0.348	0.022	0.162	0.008	.	0.147	.	0.115	0.056	0.160	.
1	SCRMM 660/10	3.522	0.398	0.143	0.1089	1.719	.	.	.	.	.	.	.	.	.	.	.
1	VS ChG 5/9	3.51	0.60	0.104	0.036	0.84	0.037	.	0.307	.	.	.	.	.	(0.1)	0.441	.
1	11X HPC4Q	3.48	1.19	1.63	0.102	1.70	0.078	2.03	0.788	.	.	0.101	.	.	.	0.029	.
1	Y 2863-5	3.47	0.78	0.564	0.070	0.89	0.365	0.62	1.53	.	.	0.67	.	.	0.133	0.129	.
1	11X C3AD	3.45	0.896	0.539	0.180	1.06	0.351	4.34	1.669	0.0104	0.240	0.235	0.021	0.166	0.127	0.605	0.007
2	CZ SPL17 41A	3.41	0.512	0.199	0.068	1.92	0.151	0.104	0.125	(0.003)	0.031	0.041	.	0.066	0.048	0.011	(0.001)
1	VS CHL1/1	3.39	0.53	0.048	0.029	1.32	0.344	0.410	0.264	.	0.017	0.036	.	.	0.061	0.073	.
2	CZ SPL17 38A	3.39	0.401	0.067	0.036	2.37	0.510	0.306	0.141	0.034	0.021	0.101	0.008	0.032	0.012	0.061	0.028
1	11X C10D	3.38	0.754	0.104	0.086	1.89	0.643	0.873	0.429	0.024	0.059	0.288	.	0.035	0.0474	0.1048	.
1	VS ChG 35	3.34	1.23	0.102	0.021	0.617	0.090	2.15	0.233	.	.	0.027	.	.	0.022	0.043	.
1	KUT 120	3.34	0.59	0.059	0.18	1.84	.	.	.	.	.	.	.	.	.	.	.
1	Y 2863-3	3.32	1.27	0.115	0.049	2.27	0.62	2.01	0.49	.	.	0.313	.	.	0.176	0.45	.
1	KUT 121	3.32	0.61	0.135	0.17	(1.86)	.	.	.	.	.	.	.	.	.	.	.
1	KUT 205	3.32	0.80	0.025	(0.010)	1.88	0.81	0.61	0.64	.	.	1.79	.	(0.035)	.	.	.
1	KUT 206	3.32	0.75	0.027	(0.010)	1.84	1.01	0.21	0.12	.	.	2.14	.	(0.107)	.	.	.
1	KUT 122	3.31	0.61	0.22	0.20	1.72	.	.	.	.	.	.	.	.	.	.	.
1	KUT 123	3.30	0.69	0.31	0.074	(1.87)	.	.	.	.	.	.	.	.	.	.	.
1	NCS HS11784	3.30	0.528	0.78	0.031	2.68	0.015	0.024	0.812	(0.0012)	.	0.142	(0.0012)	0.0005	0.084	0.020	.
1	Y 2582-3	3.29	1.22	0.045	0.056	0.689	.	0.046	0.030	.	.	.	.	.	0.043	0.071	.
1	11X HPC1H	3.29	0.620	0.808	0.0035	3.27	.	.	1.056	.	.	0.060	.	.	.	.	.
1	VS ChG 4/9	3.24	1.42	0.030	0.024	0.455	0.199	.	0.155	.	.	.	.	.	0.10	0.169	.
1	11X HPC3K	3.24	1.00	2.52	0.078	1.37	0.132	1.52	1.19	.	.	0.172	.	.	.	0.042	.
2	BAS NCRM3	3.24	0.67	0.125	0.090	0.29	1.21	3.64	3.95	.	.	0.78	.	.	.	0.02	.
1	NCS HS11782	3.21	1.09	0.088	0.035	1.64	0.042	0.014	0.061	.	.	0.0048	.	.	0.027	0.0079	.
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
1	KUT 125	3.20	0.73	0.70	0.019	(1.87)	.	.	.	.	.	.	.	.	.	.	.
1	VS ChG 31	3.19	0.97	0.047	0.043	1.60	0.281	.	0.156	.	.	0.0069	.	0.013	0.0063	0.0035	.
1	NCS HS11785	3.19	0.482	0.79	0.030	2.52	0.021	0.031	0.817	(0.0030)	.	0.139	(0.0009)	0.0010	0.076	0.018	.
1	DSZU CH02	3.18	1.09	0.007	0.0116	1.35	0.038	0.658	0.59	0.026	(0.06)	0.224	(0.4)	(0.014)	0.161	(0.005)	.
1	11X C2V	3.17	1.23	0.256	0.077	1.180	0.191	1.803	1.126	0.104	0.116	0.116	0.0160	0.0627	0.0870	0.328	0.0115
1	VS ChM 12	3.17	1.00	0.030	0.007	3.10	0.062	1.65	0.039	0.050	.	.	.	.	0.013	0.0027	.
1	SCRMM 671/1	3.165	0.811	0.108	0.0503	0.868	.	0.0627	0.0609	0.030	0.098	0.0259	.	0.0103	0.0407	0.0122	.
1	KUT 126	3.16	0.81	1.41	0.016	1.90	.	.	.	.	.	.	.	.	.	.	.
1	KUT 202	3.16	0.81	0.024	(0.010)	1.77	0.24	2.07	2.36	.	.	0.44	.	(0.21)	.	.	.
1	SCRMM 657/9	3.157	0.112	0.101	0.0401	3.209	.	.	.	.	.	.	.	.	.	.	.
1	KUT 204	3.15	0.80	0.023	(0.009)	1.79	0.64	1.09	1.22	.	.	1.38	.	(0.215)	.	.	.
1	KUT 127	3.14	0.79	1.55	0.014	1.81	.	.	.	.	.	.	.	.	.	.	.
1	CZ 02033 6c	3.11	1.25	0.097	0.019	3.25	0.273	0.021	1.33	0.024	0.005	0.006	.	0.131	0.107	0.192	.
2	CZ SPL17 37A	3.07	0.211	0.025	0.023	3.30	0.149	0.106	0.328	0.039	0.031	0.325	.	0.073	0.008	0.122	(0.001)
1	VS ChG 30	3.06	2.10	0.090	0.035	1.97	0.576	.	0.24	.	.	0.0061	.	0.015	0.012	0.0074	.
2	BAS NCRM1	3.05	1.22	0.300	0.156	0.95	2.17	0.57	0.55	.	.	1.02	.	.	.	0.03	.
1	VS ChL3/1	3.04	0.250	0.067	0.024	2.39	0.60	1.08	0.533	.	0.016	0.262	.	.	0.043	0.103	.
1	DSZU CH08	3.02	0.79	0.056	0.058	2.05	1.60	2.52	2.13	0.29	(0.07)	0.96	(0.3)	(0.008)	0.315	0.34	.
1	VS ChG 39	3.01	0.82	0.304	0.088	1.45	0.414	1.09	1.08	.	.	0.113	.	.	0.168	0.274	.
2	BS CC-11																

## CAST IRON WITH C &gt; 2.75%

## CONTINUED FROM THE PREVIOUS PAGE

analysis in mass % except \* = mg/kg

Number	As	B	Bi	Ca*	Ce	La	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
CZ SPL17 35A	.	(0.0002)	.	.	.	.	.	.	(0.002)	.	.	.	(0.005)	.	40 mm Ø x 18 mm
CZ 02033 4e	.	.	(0.002)	.	.	.	.	.	.	(0.002)	.	.	.	.	40 mm Ø x 18 mm
SCRM 672/1	0.0079	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
CZ 02033 4d	(0.012)	(0.0001)	(0.002)	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 18 mm
SCRM 659/9	.	.	.	.	.	.	.	.	.	0.007	.	.	.	.	48 mm x 42 mm x 12 mm
Y 2582-7	0.043	.	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
DSZU CH04	.	(0.0007)	.	(7)	.	.	(0.0001)	.	(0.007)	.	.	.	(<0.0002)	.	-30 mm x -35 mm x -19mm
DSZU CH05	.	(0.03)	.	(20)	.	.	(0.001)	.	.	.	.	.	.	.	-30 mm x -35 mm x -19mm
CZ 02033 4b	.	.	.	.	.	.	.	.	0.004	(0.001)	.	.	.	.	40 mm Ø x 18 mm
VS ChG 2/9	(0.003)	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -40 mm
DSZU CH06	.	(0.02)	.	(10)	.	.	.	.	.	.	.	.	0.1	.	-35 mm x -35 mm x -19mm
CZ 20034 16c	(0.003)	0.020	.	.	.	.	.	.	0.015	0.010	.	.	0.015	(0.002)	40 mm Ø x 18 mm
CZ 20034 16a	.	0.005	0.018	.	.	.	.	.	0.006	0.011	.	.	0.019	(0.002)	40 mm Ø x 18 mm
11X C5W	0.0544	0.0043	0.007	Cd:(0.0003)	Ag:0.0042	.	.	0.0070	0.007	0.058	0.006	0.013	0.0242	.	-40 mm Ø x -15 mm
CZ 20034 16b	0.005	0.018	.	.	.	.	.	.	0.007	0.011	.	.	0.019	(0.002)	40 mm Ø x 18 mm
VS ChG 32	.	.	0.361	.	.	.	.	.	.	.	.	.	.	.	-37 mm x -37 mm x -24 mm
SCRM 674/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
Y 2582-4	0.0017	.	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
CZ SPL17 39A	.	0.0195	0.008	.	.	.	.	.	0.017	0.037	.	.	.	.	40 mm Ø x 18 mm
Y 2582-5	0.0022	.	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
VS ChG 1/9	(0.003)	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -40 mm
CZ 02033 7b	.	.	.	.	.	.	.	.	.	.	.	.	0.045	.	40 mm Ø x 18 mm
CZ 02033 7c	.	0.0008	(0.002)	.	.	.	.	.	.	.	.	(0.006)	0.037	.	40 mm Ø x 18 mm
DSZU CH03	(0.004)	(0.001)	.	(20)	.	.	(0.0001)	.	(0.01)	.	.	.	(0.006)	.	-30 mm x -35 mm x -16mm
VS ChG 3/9	(0.003)	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -40 mm
VS ChG 27	.	.	.	.	.	.	.	.	.	0.029	.	.	.	.	-35 mm x -35 mm x -22 mm
SCRM 660/10	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
VS ChG 5/9	(0.003)	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -40 mm
11X HPC4Q	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
Y 2863-5	.	0.060	.	.	.	.	.	.	.	.	.	.	0.158	.	30 mm Ø x 18-30 mm
11X C3AD	0.086	0.0253	0.0124	.	.	.	.	0.0075	0.0170	0.243	0.028	.	0.040	.	-40 mm Ø x -15 mm
CZ SPL17 41A	.	(0.0004)	(0.007)	.	.	.	.	.	0.010	0.016	.	.	0.012	.	40 mm Ø x 18 mm
VS ChL1/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -38 mm
CZ SPL17 38A	.	0.0027	(0.002)	.	.	.	.	.	(0.003)	0.018	.	.	(0.005)	.	40 mm Ø x 18 mm
11X C10D	0.019	0.0030	.	Cd:(0.0004)	.	.	.	0.0057	0.006	0.040	.	.	0.308	.	-40 mm Ø x -15 mm
VS ChG 35	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-34 mm Ø x -37 mm
KUT 120	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
Y 2863-3	.	0.056	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
KUT 121	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
KUT 205	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
KUT 206	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
KUT 122	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
KUT 123	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
NCS HS11784	0.0041	.	0.0083	.	.	.	.	.	0.0002	0.0007	.	.	.	.	31 mm Ø x 28 mm
Y 2582-3	0.009	.	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
11X HPC1H	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
VS ChG 4/9	(0.003)	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -40 mm
11X HPC3K	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-40 mm Ø x -15 mm
BAS NCRM3	.	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
NCS HS11782	0.0065	.	.	.	.	.	.	.	.	.	.	.	.	.	31 mm Ø x 28 mm
Number	As	B	Bi	Ca*	Ce	La	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
KUT 125	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
VS ChG 31	.	.	0.068	.	.	.	.	.	.	.	.	.	.	.	-37 mm x -37 mm x -24 mm
NCS HS11785	0.0049	.	0.013	.	.	.	.	.	0.0002	0.0005	.	.	.	.	31 mm Ø x 28 mm
DSZU CH02	.	(0.016)	.	(10)	.	.	(0.002)	.	.	.	.	.	.	.	-35 mm Ø x -18 mm
11X C2V	0.0541	0.0098	0.0084	.	.	.	.	0.0096	0.0133	0.115	0.0157	.	0.0228	.	-40 mm Ø x -15 mm
VS ChM 12	.	.	.	.	.	.	(0.08)	.	.	.	.	.	.	.	-38 mm Ø x -38 mm
SCRM 671/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 12 mm
KUT 126	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
KUT 202	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
SCRM 657/9	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
KUT 204	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
KUT 127	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
CZ 02033 6c	.	0.0024	.	.	.	.	.	.	.	(0.003)	0.044	.	0.007	.	40 mm Ø x 18 mm
CZ SPL17 37A	.	0.0124	(0.002)	.	.	.	.	.	(0.002)	.	.	.	0.026	.	40 mm Ø x 18 mm
VS ChG 30	.	.	0.082	.	.	.	.	.	.	.	.	.	.	.	-37 mm x -37 mm x -24 mm
BAS NCRM1	.	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
VS ChL3/1	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-38 mm Ø x -38 mm
DSZU CH08	.	(0.08)	.	(10)	.	.	.	.	.	.	.	.	.	.	-35 mm x -35 mm x -19mm
VS ChG 39	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-34 mm Ø x -37 mm
BS CC-11	0.006	0.0012	(<0.0005)	2	(0.001)	(0.001)	(0.013)	.	0.0007	0.14	.	(0.002)	(0.002)	(0.002)	32 mm Ø x 17 mm last
BAS LARM2	0.044	.	.	.	0.008	.	.	.	0.007	.	.	.	.	.	40 mm x 37 mm x 10 mm
BAS LARM4	.	.	.	.	0.008	.	.	.	0.018	.	.	.	.	.	40 mm x 37 mm x 10 mm
BAS LARM1	.	0.006	0.011	.	0.005	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
BAS LARM5	0.018	0.0012	0.0010	.	.	.	.	.	0.0005	.	.	.	.	.	40 mm x 37 mm x 10 mm
BAS LARM3	0.092	0.003	0.022	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
Y 2863-4	.	0.041	.	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
BAS LARM5/1	.	0.0016	0.0012	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
BAS NCRM2	.	.	.	.	.	.	.	.	<0.001	.	.	.	.	.	40 mm x 37 mm x 10 mm
KUT 124	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
CZ 02033 6b	.	.	.	.	.	.	.	.	.	0.049	.	.	.	.	40 mm Ø x 18 mm
SCRM 662/4	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
VS ChG 36	.	.	.	.	.	.	.	.	.	.	.	.	.	.	-34 mm Ø x -37 mm
CZ 20034 12b	0.024	0.047	0.006	.	.	.	.	.	0.009	0.046	.	.	0.007	(0.002)	40 mm Ø x 18 mm
SRM C1145a	(0.03)	(0.02)	.	.	.	.	.	.	0.0012	(0.04)	.	.	.	(0.002)	32 mm Ø x 19 mm
11X C1R	0.0141	0.0357	0.011	.	.	.	.	0.0091	0.005	0.046	0.0050	.	0.100	0.0030	-40 mm Ø x -15 mm
VS ChG 34	.	.	0.223	.	.	.	.	.	.	.	.	.	.	.	-37 mm x -37 mm x -24 mm
CZ 20034 12a	0.022	0.036	0.005	.	.	.	.	.	0.007	0.046	.	.	0.011	(0.002)	40 mm Ø x 18 mm
NCS HS11786	0.0075	.	0.015	.	.	.	.	.	0.0003	0.0008	.	.	.	.	31 mm Ø x 28 mm
11X C5Y	0.0203	0.0058	0.005	.	.	.	.	0.0094	0.0108	0.030	0.0072	(0.0022)	0.0072	(0.0024)	-40 mm Ø x -15 mm
KUT 201	.	.	.	.	.	.	.	.	.	.	.	.	.	.	30 x 30 x 13 mm
Number	As	B	Bi	Ca*	Ce	La	Mg	N	Pb	Sb	Se	Te	W	Zr	Units

CAST IRON WITH C < 2.75%

# = Class, 1 = CRM and 2 = RM

analysis in mass % except \* = mg/kg

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
1	VS ChL4/1	2.69	1.37	0.054	0.027	1.99	0.161	0.725	0.92	.	0.017	0.116	.	.	0.11	0.258	.
1	SRM C1291	2.67	1.14	0.028	0.032	1.34	0.26	4.34	2.78	.	.	0.32	.	.	.	0.031	.
1	VS ChG 6/9	2.65	0.83	0.54	0.027	0.53	0.34	.	0.241	.	.	.	.	.	0.028	0.130	.
1	DSZU CH01	2.61	0.258	0.012	0.0045	1.95	0.097	0.072	0.88	0.079	(0.06)	0.070	(0.010)	(0.05)	0.132	0.134	.
1	VS ChG 40	2.59	1.56	0.059	0.019	1.60	0.98	1.61	1.47	.	.	0.229	.	.	0.18	0.325	.
1	11X C8V	2.60	0.394	1.00	0.204	1.643	0.310	0.275	0.148	0.086	0.126	0.148	0.0217	0.1063	0.235	0.064	0.0068
1	SCRM 661/4	2.56	0.30	0.84	0.068	2.96	.	.	(1)	.	.	.	.	.	.	.	.
1	SCRM 656/9	2.537	0.820	0.060	0.108	2.504	.	.	.	.	.	.	.	.	.	.	.
1	Y 2863-2	2.50	1.83	0.069	0.026	3.14	0.020	3.73	0.136	.	.	0.096	.	.	0.066	0.61	.
1	VS ChG 37	2.49	0.92	0.038	0.046	2.03	0.512	0.90	0.82	.	.	0.55	.	.	0.092	0.227	.
1	SCRM 673/1	2.455	0.123	0.317	0.0112	1.702	.	0.103	0.0423	0.0287	0.053	0.0092	.	0.0206	0.0718	0.052	.
1	CZ 20034 11b	2.44	0.382	0.271	0.140	3.67	0.130	0.082	1.178	0.067	0.005	1.144	.	0.074	0.041	0.182	.
1	VS ChG 38	2.43	0.302	0.386	0.084	2.30	1.20	0.162	1.98	.	.	0.046	.	.	0.105	0.119	.
1	CZ 02033 5b	2.42	0.812	0.033	0.073	1.32	0.031	0.188	0.061	0.062	.	0.089	.	.	0.007	0.005	.
1	VS ChL2/1	2.38	1.03	0.054	0.023	0.55	0.97	0.114	0.077	.	0.013	0.012	.	.	0.009	0.050	.
1	CZ 20034 11a	2.37	0.343	0.271	0.163	3.31	0.086	0.084	1.219	0.046	0.005	1.130	.	0.070	0.028	0.184	.
1	SCRM 652/4	2.34	1.19	0.071	0.129	0.878	.	.	(1)	.	.	.	.	.	.	.	.
1	DSZU CH07	2.33	1.36	0.090	0.064	3.01	0.35	0.403	0.34	0.036	.	0.66	(0.08)	(0.07)	0.150	0.52	.
1	CZ 02033 5a	2.30	0.804	0.035	0.100	1.26	0.014	0.096	0.054	0.060	.	0.100	.	.	0.008	0.005	.
1	CZ 02033 5c	2.30	0.704	0.027	0.091	1.40	0.013	0.188	0.085	0.103	0.013	0.104	.	(0.002)	0.008	0.054	.
1	11X C4S	1.954	0.565	0.1014	0.096	2.98	0.095	3.21	1.382	0.006	0.0210	0.177	0.0233	0.0140	0.080	0.0165	0.0037
1	SCRM 675	1.92	1.81	0.045	0.072	1.29	0.012	0.210	0.080	0.007	0.023	0.034	.	0.0062	0.007	0.178	0.0006
1	SCRM 655/4	1.90	0.44	0.180	0.076	2.110	.	.	(1)	.	.	.	.	.	.	.	.
1	Y 2863-1	1.78	2.41	0.021	0.009	3.62	0.022	4.77	0.031	.	.	0.038	0.0052	.	0.068	1.13	.

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Sn	Ti	V	Zn
---	--------	---	----	---	---	----	----	----	----	----	----	----	----	----	----	---	----

Number	As	B	Bi	Ca*	Ce	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
--------	----	---	----	-----	----	----	---	----	----	----	----	---	----	-------

VS ChL4/1	.	.	.	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~38 mm
SRM C1291	.	.	.	.	.	.	.	.	.	.	.	.	.	32 mm Ø x 19 mm
VS ChG 6/9	(0.003)	.	.	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~40 mm
DSZU CH01	.	(0.03)	.	(10)	.	(0.0005)	.	.	.	.	.	(0.02)	.	~30 mm x ~35 mm
VS ChG 40	.	.	.	.	.	.	.	.	.	.	.	.	.	~34 mm Ø x ~37 mm
11X C8V	0.0812	0.0366	0.014	.	.	.	0.0065	0.0052	0.069	0.0210	0.0049	0.0258	0.0064	~40 mm Ø x ~15 mm
SCRM 661/4	.	.	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
SCRM 656/9	.	.	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
Y 2863-2	.	0.0025	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm
VS ChG 37	.	.	.	.	.	.	.	.	.	.	.	.	.	~34 mm Ø x ~37 mm
SCRM 673/1	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
CZ 20034 11b	0.005	0.0032	0.007	.	.	.	.	0.007	0.011	.	.	(0.005)	0.007	40 mm Ø x 18 mm
VS ChG 38	.	.	.	.	.	.	.	.	.	.	.	.	.	~34 mm Ø x ~37 mm
CZ 02033 5b	.	0.014	0.020	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 18 mm
VS ChL2/1	.	.	.	.	.	.	.	.	.	.	.	.	.	~38 mm Ø x ~38 mm
CZ 20034 11a	0.005	0.0018	0.011	.	.	.	.	0.017	0.013	.	.	(0.005)	0.007	40 mm Ø x 18 mm
SCRM 652/4	1.92	1.81	0.045	0.072	1.29	0.012	0.210	0.080	0.007	0.023	0.034	.	0.0062	48 mm x 42 mm x 12 mm
DSZU CH07	.	(0.13)	.	(10)	.	(0.01)	.	.	.	.	.	.	.	~35 mm x ~35 mm x ~19mm
CZ 02033 5a	.	.	.	.	.	.	.	.	.	.	.	.	.	40 mm Ø x 18 mm
CZ 02033 5c	.	0.0078	0.007	.	.	.	.	.	.	(0.002)	(0.010)	.	(0.009)	40 mm Ø x 18 mm
11X C4S	0.0235	0.0351	0.0070	.	.	.	0.0126	0.034	0.0055	0.009	.	0.099	.	~40 mm Ø x ~15 mm
SCRM 675	0.035	.	.	.	.	.	.	.	.	.	.	.	.	40 mm x 37 mm x 10 mm
SCRM 655/4	.	.	.	.	.	.	.	.	.	.	.	.	.	48 mm x 42 mm x 12 mm
Y 2863-1	.	0.0024	.	.	.	.	.	.	.	.	.	.	.	30 mm Ø x 18-30 mm

Number	As	B	Bi	Ca*	Ce	Mg	N	Pb	Sb	Se	Te	W	Zr	Units
--------	----	---	----	-----	----	----	---	----	----	----	----	---	----	-------

ALLOYED CAST IRON, CHART 1 of 2

# = Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
2	DSZU CH021	3.93	3.66	0.064	0.009	0.52	0.369	5.86	9.07	0.168	4.42	.	.	0.093	0.61	.	.
1	VS CHG41/1	3.88	1.23	0.037	0.090	1.77	0.56	5.84	8.7	.	0.50	.	.	0.21	0.25	.	.
2	BAS NCRM5	3.70	0.27	0.025	0.015	1.15	0.204	6.74	10.44	.	0.10	.	.	.	0.06	.	.
1	SRM C1292	3.47	0.55	0.049	0.016	0.59	0.36	5.04	11.4	.	0.25	.	.	.	0.041	.	.
2	BAS CRRM5/2	3.43	0.30	0.029	0.018	0.20	0.22	0.36	30.35	0.15	0.63	.	.	0.009	0.11	.	.
1	Y 451052-1	3.31	1.54	0.369	0.0047	0.098	0.449	2.57	1.17	.	1.47	.	.	.	0.952	.	.
1	<b>BS PML5</b>	3.54	0.416	0.0198	0.0127	0.912	0.142	0.203	5.33	0.0025	1.22	(0.00001)	0.0034	0.0029	14.79	(0.0002)	0.111
1	VS CHG 48	3.44	0.100	0.0070	0.0039	0.923	0.90	0.280	22.79	0.049	0.591	.	0.0018	0.0022	0.0016	0.072	.
1	VS CHG44/1	3.25	1.91	0.018	0.029	1.28	2.46	0.210	25.4	.	0.028	.	.	0.43	0.106	.	.
1	Y 451052-7	3.13	0.201	0.024	0.116	2.48	0.154	0.129	31.26	.	0.086	.	.	0.033	0.087	.	.
2	58A SC01141	3.08	0.62	0.045	0.036	0.56	0.77	1.21	15.32	.	2.70	.	.	0.020	0.28	.	.
1	SRM C1290	3.04	0.66	0.030	0.013	0.971	0.065	0.917	30.5	.	(0.041)	.	.	.	0.442	.	.
1	Y TSK205	3.03	0.16	0.041	0.088	1.65	0.35	0.37	30.35	.	0.22	.	.	.	0.077	.	0.108
1	Y 451054-2	3.00	1.42	0.133	0.016	0.56	0.324	1.43	7.23	.	2.48	.	.	0.015	0.88	.	.
1	NCS HS11788	2.97	1.62	0.191	0.010	3.29	0.51	17.77	2.56	(0.0023)	0.0013	.	0.0003	0.043	0.017	.	.
1	Y 451052-2	2.96	1.24	0.211	0.0077	0.491	1.57	1.99	9.75	.	2.17	.	.	0.300	0.669	.	.
2	BAS NIRM5/1	2.95	1.01	0.103	0.005	1.50	0.21	21.7	0.51	.	.	.	.	.	0.055	.	.
2	58A ZS01036	2.95	0.719	0.077	0.024	0.970	0.448	0.806	13.89	.	0.683	.	0.048	0.035	0.135	.	.
2	BAS NIRM2/2	2.94	2.01	0.096	0.007	1.43	5.93	13.69	1.48	.	.	.	.	.	0.044	.	.
2	BAS CRRM4/2	2.93	0.58	0.049	0.042	0.45	0.53	0.58	21.93	<0.005	1.15	.	.	0.008	0.11	.	.
2	11X 20003K	2.91	1.53	0.174	0.007	3.03	0.52	17.8	2.53	.	.	.	.	.	.	.	.
1	11X S/1 Cr3J	2.91	0.861	0.072	0.023	1.07	9.01	14.53	1.61	.	.	.	.	.	.	.	.
2	DSZU CH022	2.90	1.76	0.033	0.018	0.43	2.53	2.19	14.85	0.053	2.65	.	.	0.078	0.45	.	.
2	11X 20001J	2.90	0.58	0.005	0.143	1.01	0.01	21.4	1.50	.	.	.	.	.	.	.	.
2	11X S/2 Cr1E	2.83	1.68	0.31	0.011	2.85	0.02	16.5	2.48	.	.	.	.	.	.	.	.
1	11X 15294W	2.76	0.451	0.082	0.029	0.36	0.103	0.309	29.3	(0.147)	0.091	0.012	0.036	.	0.132	.	.
1	Y 451054-3	2.73	1.09	0.105	0.036	0.99	0.451	1.20	12.97	.	2.08	.	.	0.045	0.66	.	.
1	VS CHG45	(2.7)	1.01	0.096	0.047	2.96	0.040	0.60	32.65	.	0.198	.	.	0.011	0.111	.	.
1	VS CHG42/1	2.69	2.78	0.068	0.034	0.411	1.37	0.26	14.8	.	1.87	.	.	0.131	0.48	.	.
2	BAS NCRM4	2.66	0.40	0.203	0.012	2.13	0.68	5.34	7.94	.	0.57	.	.	.	0.11	.	.
1	NCS HS11787	2.65	1.08	0.067	0.037	2.07	0.306	19.84	1.98	(0.085)	0.0014	.	0.0054	0.022	0.0096	.	.
1	11X 15310B	2.63	0.97	0.070	0.029	0.99	2.37	4.59	20.7	0.018	0.92	.	.	0.034	0.096	.	.
1	Y TSK201	2.56	1.07	0.253	0.023	0.66	1.53	2.44	10.14	.	2.56	.	.	.	0.42	.	0.029
2	BAS NIRM6/1	2.53	4.07	0.225	0.049	2.68	0.11	26.9	1.02	.	0.51	.	.	.	.	.	.
2	BAS NIRM3	2.51	0.51	0.208	0.096	2.21	1.00	17.8	2.43	.	.	.	.	.	.	.	.
1	VS ChG 47	2.43	0.949	0.099	0.083	2.73	0.0104	0.149	14.45	0.0056	0.0019	.	0.093	0.041	0.129	.	.
1	VS CHG45/1	1.96	0.59	0.021	0.0091	3.08	0.056	0.95	33.8	.	0.209	.	.	.	0.21	.	.
1	VS CHG43/1	0.87	1.02	0.063	0.076	4.44	0.171	0.439	23.7	.	0.107	.	.	0.033	0.040	.	.

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
---	--------	---	----	---	---	----	----	----	----	----	----	----	----	----	---	----	---

Number	B	Ce	Co	Nb	W	Zr	Units	Other
DSZU CH021	.	.	.	.	.	.	35 mm x 35 mm x 16 mm	
VS CHG41/1	.	.	.	.	.	.	-37 mm Ø x -22 mm	
BAS NCRM5	.	.	.	.	.	.	40 mm x 37 mm x 10 mm	
SRM C1292	.	.	.	.	.	.	32 mm Ø x 19 mm	
BAS CRRM5/2	.	.	.	.	.	.	48 mm x 42 mm x 12 mm	
Y 451052-1	0.177	.	.	0.018	0.015	.	30 mm Ø x 18-30 mm	
<b>BS PML5</b>	.	.	0.0330	0.014	0.109	(0.0005)	38 mm Ø x 19+ mm	17025 Fe:[73.0] As:0.0040 N:0.111 O:0.0129
VS CHG 48	As:0.0021	.	0.044	.	.	Sb:0.0017	-35 mm Ø x -17 mm	
VS CHG44/1	.	.	.	.	.	.	-37 mm Ø x -22 mm	
Y 451052-7	0.015	.	.	0.010	0.175	.	30 mm Ø x 18-30 mm	
58A SC01141	.	.	.	.	.	.	-35 mm Ø x -30 mm	
SRM C1290	.	.	.	.	.	.	32 mm Ø x 19 mm	
Y TSK205	.	.	.	.	.	.	35 mm Ø x 18-30 mm	
Y 451054-2	.	.	.	.	.	.	30 mm Ø x 18-30 mm	
NCS HS11788	0.0008	.	(0.0063)	.	(0.0002)	.	31 mm Ø x 28 mm	As: 0.014
Y 451052-2	0.142	.	.	0.182	1.99	.	30 mm Ø x 18-30 mm	
BAS NIRM5/1	.	0.016	.	0.15	.	.	48 mm x 42 mm x 12 mm	
58A ZS01036	.	.	0.024	0.025	0.172	.	-32 mm Ø x -30 mm	As: (0.003)
BAS NIRM2/2	.	0.018	.	.	.	.	48 mm x 42 mm x 12 mm	
BAS CRRM4/2	.	.	.	.	.	.	48 mm x 42 mm x 12 mm	
11X 20003K	.	.	.	.	.	.	40 mm Ø x 15 mm	
11X S/1 Cr3J	.	.	.	.	.	.	-40 mm Ø x -15 mm	
11X 20001K	.	.	.	.	.	.	40 mm Ø x 15 mm	
11X S/2 Cr1E	.	.	.	.	.	.	40 mm Ø x 15 mm	
11X 15294W	.	.	0.128	.	0.265	.	-40 mm Ø x -15 mm	
Y 451054-3	.	.	.	.	.	.	30 mm Ø x 18-30 mm	
VS ChG45	.	.	.	.	.	.	-36 mm x -36 mm Ø x -18 mm	last
VS CHG42/1	.	.	.	.	.	.	-37 mm Ø x -22 mm	
DSZU CH022	.	.	.	.	.	.	35 mm x 35 mm x 16 mm	
BAS NCRM4	.	.	.	.	.	.	40 mm x 37 mm x 10 mm	
NCS HS11787	0.0007	.	(0.0054)	.	(0.0002)	.	31 mm Ø x 28 mm	As: 0.0075
11X 15310B	.	.	0.157	.	0.188	.	-40 mm Ø x -15 mm	
Y TSK201	.	.	.	.	.	.	35 mm Ø x 18-30 mm	
BAS NIRM6/1	.	0.006	.	.	.	.	48 mm x 42 mm x 12 mm	
BAS NIRM3	.	0.007	.	0.09	.	.	40 mm x 37 mm x 10 mm	
VS ChG 47	As:0.014	.	0.0042	.	.	Sb:0.040	-35 mm Ø x -17 mm	
VS CHG45/1	.	.	.	.	.	.	-37 mm Ø x -22 mm	
VS CHG43/1	.	.	.	.	.	.	-37 mm Ø x -22 mm	

Number	B	Ce	Co	Nb	W	Zr	Units	Other
--------	---	----	----	----	---	----	-------	-------

## ALLOYED CAST IRON, CHART 2 of 2

# = Class, where 1 = CRM and 2 = RM

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
1	Y 451052-3	2.40	1.06	0.115	0.015	0.821	0.953	1.55	13.30	.	0.869	.	.	0.171	0.482	.	.
2	BAS CRRM3/2	2.37	0.92	0.073	0.087	1.21	1.09	1.35	18.78	0.102	1.58	.	.	0.015	0.042	.	.
2	DSZU CH023	2.33	0.43	0.023	0.073	0.98	0.054	0.715	23.45	0.255	1.46	.	.	0.38	0.288	.	.
1	Y 451054-4	2.31	0.725	0.071	0.046	1.40	0.739	0.914	17.60	.	1.44	.	.	0.084	0.46	.	.
1	Y TSK200	2.11	0.82	0.319	0.022	0.17	1.86	3.22	4.97	.	3.50	.	.	.	0.60	.	0.021
2	BAS NIRM1	2.05	6.72	0.055	0.005	3.15	0.20	11.80	0.246	.	.	.	.	.	.	0.021	.
2	DSZU CH024	2.01	1.22	0.102	0.037	2.18	0.88	0.222	27.84	0.096	3.86	.	.	0.099	0.164	.	.
1	Y 451052-4	2.00	0.803	0.090	0.025	1.16	0.738	1.07	18.28	.	0.598	.	.	0.087	0.380	.	.
2	BAS NIRM4	1.97	2.37	0.051	0.008	3.03	0.52	20.2	3.56	.	.	.	.	.	.	0.014	.
1	NCS HS11789	1.97	1.08	0.048	0.076	2.58	6.39	17.80	2.51	0.061	0.062	0.015	0.014	0.011	0.0093	.	.
2	BAS CRRM2/1	1.92	1.11	0.097	0.079	1.18	1.59	1.61	14.13	0.054	2.44	.	.	0.070	0.063	.	.
1	VS ChG 46	1.87	0.067	0.0106	0.108	3.24	0.0109	5.44	8.58	.	0.63	.	.	.	0.109	.	.
2	BAS CRRM1/1	1.83	1.45	0.132	0.099	1.53	2.01	2.03	11.18	0.117	3.05	.	.	0.096	0.040	.	.
1	Y 451054-5	1.83	0.466	0.043	0.091	1.80	0.904	0.517	23.40	.	0.739	.	.	0.068	0.26	.	.
1	Y TSK202	1.81	1.16	0.201	0.057	2.00	1.10	1.91	15.42	.	2.20	.	.	.	0.33	.	0.075
2	DSZU CH025	1.80	0.387	0.030	0.026	2.70	1.23	1.77	35.14	0.351	0.302	.	.	0.117	0.044	.	.
2	BAS CRRM1/2	1.70	1.43	0.16	0.099	1.84	1.97	2.03	11.28	0.140	3.06	.	.	0.054	0.063	.	.
2	DSZU CH026	1.62	0.305	0.050	0.032	1.14	0.288	3.63	35.87	0.059	0.96	.	.	0.013	0.067	.	.
1	Y 451052-5	1.48	0.579	0.041	0.058	1.37	0.583	0.708	22.55	.	0.359	.	.	0.056	0.314	.	.
2	BAS NIRM8/2	1.45	1.58	0.105	0.014	5.61	0.23	35.3	2.47	.	0.77	.	.	.	.	0.033	.
1	Y 451054-6	1.45	0.254	0.024	0.123	2.38	1.15	0.216	28.96	.	0.213	.	.	0.084	0.13	.	.
1	VS ChG44	1.24	0.87	(1.2)	0.076	1.50	2.27	0.175	25.44	.	0.035	.	.	0.104	0.079	.	.
1	Y TSK203	1.23	0.68	0.117	0.044	0.46	0.75	1.55	19.93	.	1.58	.	.	.	0.22	.	0.094
1	Y 451052-6	1.16	0.302	0.033	0.086	1.44	0.845	0.289	25.76	.	0.150	.	.	0.019	0.146	.	.
1	Y TSK204	0.91	0.34	0.078	0.063	1.00	0.53	0.97	25.37	.	0.95	.	.	.	0.14	.	0.114

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	Pb	Sn	Ti	V	Mg	N
	Number	B	Ce	Co	Nb	W	Units		Other								
	Y 451052-3	0.102	.	.	0.149	1.57	30 mm Ø x 18-30 mm										
	BAS CRRM3/2	.	.	.	.	.	40 mm x 37 mm x 10 mm										
	DSZU CH023	.	.	.	.	.	35 mm x 35 mm x 16 mm										
	Y 451054-4	.	.	.	.	.	30 mm Ø x 18-30 mm										
	Y TSK200	.	.	.	.	.	35 mm Ø x 18-30 mm										
	BAS NIRM1	.	0.018	.	.	.	40 mm x 37 mm x 10 mm										
	DSZU CH024	.	.	.	.	.	35 mm x 35 mm x 16 mm										
	Y 451052-4	0.086	.	.	0.071	1.05	30 mm Ø x 18-30 mm										
	BAS NIRM4	.	0.011	.	0.37	.	40 mm x 37 mm x 10 mm										
	NCS HS11789	0.0008	.	(0.0075)	.	(0.0002)	31 mm Ø x 28 mm		As: 0.0076	Bi: 0.067							
	BAS CRRM2/1	.	.	.	.	.	40 mm x 37 mm x 10 mm										
	VS ChG 46	.	.	.	.	Sb:0.140	~35 mm Ø x ~17 mm										
	BAS CRRM1/1	.	.	.	.	.	40 mm x 37 mm x 10 mm		last								
	Y 451054-5	.	.	.	.	.	30 mm Ø x 18-30 mm										
	Y TSK202	.	.	.	.	.	35 mm Ø x 18-30 mm										
	DSZU CH025	.	.	.	.	.	35 mm x 35 mm x 16 mm										
	BAS CRRM1/2	.	.	.	.	.	40 mm x 37 mm x 10 mm										
	DSZU CH026	.	.	.	.	.	35 mm x 35 mm x 16 mm										
	Y 451052-5	0.076	.	.	0.022	0.694	30 mm Ø x 18-30 mm										
	BAS NIRM8/2	.	0.013	.	.	.	48 mm x 42 mm x 12 mm										
	Y 451054-6	.	.	.	.	.	30 mm Ø x 18-30 mm										
	VS ChG44	.	.	.	.	.	~36 mm x ~36 mm Ø x ~18 mm		last								
	Y TSK203	.	.	.	.	.	35 mm Ø x 18-30 mm										
	Y 451052-6	0.055	.	.	0.014	0.370	30 mm Ø x 18-30 mm										
	Y TSK204	.	.	.	.	.	35 mm Ø x 18-30 mm										
	Number	B	Ce	Co	Nb	W	Units		Other								

## RM CAST IRON MUSHROOMS

## CONTINUED ON THE NEXT PAGE

typical analysis

each unit is one pair of 43 mm Ø x 5 mm mushroom discs

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF FO19	4.04	1.05	1.05	0.032	0.057	.	.	.	.	.	.	.	.	.	.
CTIF FO12	3.71	1.86	0.44	0.038	0.004	0.77	.	.	0.008	.	.	0.011	.	.	.
CTIF FO8	3.6	1.04	0.37	0.107	0.021	0.215	0.30	0.30	.	.	0.005	0.05	0.055	0.014	.
CTIF FCR7	3.59	1.07	0.365	0.099	0.0427	0.704	0.947	33.65	.	.	2.62	.	.	.	.
CTIF FO6	3.49	0.55	0.715	0.87	0.106	0.120	0.128	0.45	.	.	0.202	0.039	0.080	0.110	.
CTIF FO10	3.5	0.67	1.05	0.20	0.101	0.114	0.118	0.38	.	.	0.20	.	0.1	0.08	.
CTIF NH3	3.47	0.85	0.175	0.36	0.024	0.031	2.53	1.76	.	.	0.73	.	.	.	.
CTIF FO11	3.45	1.57	0.685	0.052	0.103	0.211	0.235	0.34	.	(0.013)	0.225	0.066	0.078	0.113	.
CTIF FO18	3.43	1.24	0.590	1.34	0.136	0.049	0.140	0.170	.	.	0.179	0.046	0.057	0.102	.
CTIF NH7-1	3.43	0.95	0.63	0.035	0.022	0.105	5.53	9.02	.	.	.	.	.	.	.
CTIF FCR5	3.43	0.35	0.62	0.052	0.0175	1.02	2.69	28.5	.	.	3.27	.	.	.	.
CTIF FT2-1	3.39	1.415	0.78	0.045	0.095	0.01	0.070	0.030	.	.	.	.	0.100	0.405	.
CTIF NiMo1	3.22	2.585	0.200	0.0590	(0.0030)	0.376	2.165	0.0353	.	0.0205	0.457	0.0020	0.0190	0.0169	.
CTIF FL7	3.22	2.550	0.100	1.34	0.048	0.351	0.232	0.043	.	.	0.335	0.0291	0.0525	0.0796	.
CTIF FT3	3.2	1.55	0.345	0.063	0.051	0.015	0.092	0.685	.	.	.	.	0.2	0.016	.
CTIF NH7-2	3.2	1.20	0.91	0.034	0.0120	0.108	5.53	8.87	.	.	.	.	.	.	.
CTIF FO5	3.2	0.7	0.2	1.30	0.027	0.12	0.172	0.3	.	.	0.41	0.109	0.04	0.14	.
CTIF NH9	3.13	1.24	0.65	0.087	0.029	0.203	4.11	11.70	.	.	0.059	.	.	.	.
CTIF NR Cu1	3.12	1.465	0.172	0.090	0.99	4.95	18.02	0.994	(0.095)	.	.	.	.	.	.
CTIF FL6	3.1	1.4	0.6	0.012	0.18	0.079	1.03	0.167	.	0.028	0.50	0.005	0.15	0.033	.
CTIF FL10	3.1	1.3	0.85	0.323	0.066	0.104	0.10	(0.07)	(0.03)	.	0.0335	0.028	0.045	0.048	(0.02)
CTIF FFA 1	3.090	0.0300	0.100	0.0022	0.0009	0.0622	0.0450	0.0710	.	0.0097	0.0109	.	0.0010	0.0010	.
CTIF NR 8S	3.05	1.41	4.39	0.124	.	0.071	14.20	0.191	.	.	.	.	.	.	.
CTIF FO17	3.01	2.48	0.475	0.470	0.168	(0.006)	0.021	(0.016)	.	0.032	.	0.024	0.032	0.018	.
CTIF FAL 1	3.0	1.0	0.2	0.04	<0.001	0.2	0.06	0.04	2.1	.	0.015	.	0.01	.	.
CTIF NR 3L	2.99	3.05	0.72	0.088	0.052	0.26	21.58	2.97	.	.	.	.	.	.	.
CTIF NH1	2.98	1.35	0.90	0.060	0.105	1.99	1.38	0.83	.	.	1.45	.	.	.	.
CTIF NH8	2.98	0.80	0.57	0.052	0.076	0.065	8.16	5.03	.	.	0.125	.	.	.	.
CTIF NR 3S	2.92	2.91	0.77	0.024	.	0.33	24.63	3.05	.	.	.	.	.	.	.
CTIF FT1	2.9	2.12	0.71	0.12	0.025	0.012	0.11	0.057	.	.	.	0.067	0.19	0.525	.

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
CTIF NR 8L	2.89	1.70	5.19	0.054	0.030	0.075	13.33	0.165	.	.	.	.	.	.	.
CTIF NH4	2.84	0.49	0.28	0.12	0.022	0.09	3.60	2.46	.	.	0.30	.	.	.	.
CTIF FO4	2.81	1.51	0.64	0.58	0.009	0.31	0.32	0.17	.	.	0.095	0.013	0.075	0.049	.
CTIF FCR2	2.86	1.07	0.740	0.137	0.055	0.135	1.87	11.8	.	.	3.88	.	.	.	.
CTIF FL5	2.8	2.3	0.4	0.02	(0.005)	0.5	0.05	0.35	.	0.010	0.01	0.07	0.01	0.01	.
CTIF FCR Ni3	2.74	0.69	0.47	0.036	0.011	.	11.05	31.65	.	.	.	.	.	.	.
CTIF NH6	2.70	2.28	0.355	0.066	0.036	0.115	7.06	6.60	.	.	0.11	.	.	.	.
CTIF FO9	2.7	1.5	0.7	0.02	0.015	0.31	0.355	0.18	.	.	0.13	0.144	0.017	0.022	.
CTIF FL4	2.6	2.91	0.5	0.288	0.137	0.0168	0.061	0.45	.	.	0.090	0.011	0.0296	0.116	.
CTIF NR 1S	2.58	3.02	1.54	0.19	0.0015	0.11	20.60	2.00	.	.	.	.	.	.	.
CTIF NR 1L	2.50	3.00	1.34	0.125	0.10	0.49	25.87	1.74	.	.	.	.	.	.	.
CTIF NH2	2.50	1.81	1.04	0.047	0.058	1.02	1.78	1.26	.	.	1.01	.	.	.	.
CTIF NR Cu2	2.48	2.07	1.078	0.113	0.049	6.50	15.85	2.05	.	.	.	.	.	.	.
CTIF NR 4S	2.47	4.87	1.71	0.145	.	0.63	18.30	1.50	.	.	.	.	.	.	.
CTIF FCR4	2.47	1.40	2.05	0.097	0.066	1.32	0.571	24.2	.	.	2.16	.	.	.	.
CTIF FCR1	2.46	0.48	0.63	0.019	0.007	0.031	1.30	18.71	.	.	1.41	.	.	.	.
CTIF FO7	2.45	0.675	0.70	0.84	0.085	0.125	0.15	0.455	.	.	0.26	.	0.065	0.13	.
CTIF NR 4L	2.41	5.89	1.495	0.155	0.010	0.758	15.90	1.403	.	.	.	.	.	.	.
CTIF NR 2S	2.32	1.43	0.530	0.062	.	0.210	36.3	0.51	.	.	.	.	.	.	.
CTIF NH5	2.31	0.31	0.24	0.115	0.04	0.035	4.90	2.85	.	.	0.017	.	.	.	.
CTIF FL3	2.3	2.1	0.27	0.729	(0.013)	0.102	0.553	0.107	.	.	0.106	0.111	0.05	0.049	.
CTIF NR 4G	2.24	5.60	1.72	0.11	(0.002)	0.64	21.30	1.40	.	.	.	.	.	.	.
CTIF NR 2G	2.25	1.47	0.380	0.0476	(0.003)	0.232	36.34	0.395	.	.	.	.	.	.	.
CTIF FL2	2.18	3.61	0.0400	0.049	0.082	0.0497	0.0238	0.440	(0.006)	0.0263	(0.004)	0.140	0.0750	0.201	.
CTIF FL1	2.1	3.2	0.80	0.118	0.0765	0.0195	0.245	0.06	.	(0.022)	0.038	0.305	0.020	0.015	.
CTIF FCR Ni2	2.02	1.50	0.61	0.185	0.024	.	13.05	29.00	.	.	.	.	.	.	.
CTIF NR Cu3	1.94	3.12	0.60	0.046	0.016	8.05	13.3	3.50	.	.	.	.	.	.	.
CTIF NR 6S	1.82	2.44	0.99	0.019	.	0.03	30.75	1.06	.	.	.	.	.	.	.
CTIF NR 5L	1.77	2.99	1.207	0.037	0.083	0.48	33.89	0.27	.	.	.	.	.	.	.
CTIF NR 6L	1.76	2.07	0.70	0.031	0.063	0.020	30.37	3.49	.	.	.	.	.	.	.
CTIF NR 5S	1.67	1.97	1.23	0.035	.	0.50	27.05	0.24	.	.	.	.	.	.	.
CTIF FCR6	1.44	0.76	1.47	0.201	0.086	0.480	0.188	30.84	.	.	0.455	.	.	.	.
CTIF FCR Ni1	1.27	1.63	0.71	0.41	0.06	0.02	16.50	26.20	.	.	.	.	.	.	.

Number	C	Si	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	Sn	Ti	V	W
--------	---	----	----	---	---	----	----	----	----	----	----	----	----	---	---



## CAST IRON MUSHROOMS

## CONTINUED FROM THE PREVIOUS PAGE

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF F019	.	.	.	.	.	.	.	.	.	0.0005	.
CTIF F012	.	.	.	.	.	.	.	.	.	.	.
CTIF F08	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR7	.	.	.	.	.	.	.	.	.	.	.
CTIF F06	.	.	.	.	.	.	.	.	.	.	.
CTIF F010	.	.	.	.	.	.	.	.	.	.	.
CTIF NH3	.	.	.	.	.	.	.	.	.	.	.
CTIF F011	.	.	.	.	.	.	.	.	.	.	.
CTIF F018	.	.	.	.	.	0.0040	.	.	.	.	.
CTIF NH7-1	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR5	.	.	.	.	.	.	.	.	.	.	.
CTIF FT2-1	.	.	.	.	.	.	.	.	.	.	.
CTIF NiMo1	.	.	.	.	.	.	.	.	.	.	.
CTIF FL7	(0.0266)	(0.010)	.	(0.010)	.	0.0035	.	.	.	.	.
CTIF FT3	.	.	.	.	.	.	.	.	.	.	.
CTIF NH7-2	.	.	.	.	.	.	.	.	.	.	.
CTIF F05	.	.	.	.	.	.	.	.	.	.	.
CTIF NH9	.	.	.	.	.	.	.	.	.	.	.
CTIF NR Cu1	.	.	.	.	.	.	.	.	.	.	.
CTIF FL6	.	0.008	.	.	.	.	.	.	.	.	.
CTIF FL10	(0.022)	.	(0.012)	(0.004)	.	.	(0.018)	(0.002)	(0.032)	(0.001)	(0.029)
CTIF FFA 1	0.0109	.	.	.	.	0.0125	.	.	.	.	.
CTIF NR 8S	.	.	.	.	.	.	.	.	.	.	.
CTIF F017	.	.	.	.	.	.	.	.	.	.	.
CTIF FAL 1	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 3L	.	.	.	.	.	.	.	.	.	.	.
CTIF NH1	.	.	.	.	.	.	.	.	.	.	.
CTIF NH8	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 3S	.	.	.	.	.	.	.	.	.	.	.
CTIF FT1	.	.	.	.	.	.	.	.	.	.	.

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
CTIF NR 8L	.	.	.	.	.	.	.	.	.	.	.
CTIF NH4	.	.	.	.	.	.	.	.	.	.	.
CTIF F04	.	.	.	.	.	.	.	.	.	.	last of stock
CTIF FCR2	.	.	.	.	.	.	.	.	.	.	.
CTIF FL5	.	(0.002)	.	(0.0005)	.	.	.	.	.	.	.
CTIF FCR Ni3	.	.	.	.	.	.	.	.	.	.	.
CTIF NH6	.	.	.	.	.	.	.	.	.	.	.
CTIF F09	.	.	.	.	.	.	.	.	.	.	.
CTIF FL4	(0.05)	.	.	(0.003)	.	0.007	.	.	.	.	.
CTIF NR 1S	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 1L	.	.	.	.	.	.	.	.	.	.	.
CTIF NH2	.	.	.	.	.	.	.	.	.	.	.
CTIF NR Cu2	.	.	.	.	.	(0.0079)	.	.	.	.	.
CTIF NR 4S	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR4	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR1	.	.	.	.	.	.	.	.	.	.	.
CTIF F07	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 4L	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 2S	.	.	.	.	.	.	.	.	.	.	.
CTIF NH5	.	.	.	.	.	.	.	.	.	.	.
CTIF FL3	.	.	.	.	.	0.008	.	.	.	.	.
CTIF NR 4G	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 2G	.	.	.	.	.	.	0.27	.	.	.	.
CTIF FL2	.	.	.	(0.0135)	.	.	.	.	.	.	.
CTIF FL1	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR Ni2	.	.	.	.	.	.	.	.	.	.	.
CTIF NR Cu3	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 6S	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 5L	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 6L	.	.	.	.	.	.	.	.	.	.	.
CTIF NR 5S	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR6	.	.	.	.	.	.	.	.	.	.	.
CTIF FCR Nil	.	.	.	.	.	.	.	.	.	.	.

Number	As	B	Bs	Bi	Ce	N	Nb	Pb	Sb	Te	Zn
--------	----	---	----	----	----	---	----	----	----	----	----

**CARBON STEEL**

# = Class, where 1 = CRM and 2 = RM

\* Provisional Analysis

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
1 VS UG128	0.816	0.405	0.014	0.0139	0.324	0.0235	0.032	0.038	0.0078	.	.	0.0088	0.0046	.
1 <b>BS 54J</b>	0.78	0.77	0.0090	0.0108	0.552	0.080	0.037	0.177	0.0021	0.0042	0.0138	0.0060	0.0014	0.0024
1 VS UG129	0.728	.	.	0.013	.	.	.	.	0.0014	.	.	.	.	.
1 NM 309	0.57	0.80	0.037	0.046	0.20	.	0.034	0.081	.	.	.	.	.	.
1 IARM Fe1050-18	0.499	0.79	0.0045	0.027	0.223	0.179	0.068	0.100	(0.003)	0.0056	0.018	0.0097	0.0270	.
1 NM 306A	0.46	0.71	0.085	0.043	0.28	.	0.023	0.13	.	.	.	.	.	.
1 VS UG131	0.39	0.56	0.0100	0.0031	0.207	0.030	0.026	0.853	.	.	.	0.0070	.	.
1 BS 1030A *	0.34	0.75	0.006	0.015	0.26	0.19	0.14	0.11	0.002	0.006	0.029	<0.05	0.026	<0.005
1 SS 452/1	0.323	1.30	0.035	0.017	0.055	0.22	0.19	0.067	.	.	0.054	.	.	0.054
1 VS UG121	(0.3)	0.55	0.014	0.027	0.244	0.180	0.078	0.126	0.023	.	.	0.0068	0.0018	.
1 BS 1026A *	0.27	0.76	0.007	0.021	0.18	0.095	0.081	0.12	0.009	0.005	0.05	<0.05	0.026	0.001
1 IARM Fe1020-18	0.226	0.547	0.006	0.024	0.235	0.198	0.078	0.125	(0.003)	0.0065	0.0252	0.0098	0.036	.
1 IMZ 112A	0.212	0.471	0.0055	0.0188	0.257	0.068	0.055	0.099	0.017	0.080	0.054	0.0058	0.043	0.072
2 BS 57F	0.196	0.554	0.009	0.027	0.202	0.197	0.070	0.120	(0.002)	0.007	0.018	0.0077	0.063	.
2 BS 2971	0.187	1.01	0.015	0.024	0.237	0.065	0.111	0.152	0.022	.	0.040	0.0084	(0.002)	.
1 VS UG132	0.180	0.466	0.0075	0.0030	0.201	0.039	0.024	0.035	.	.	.	0.0054	.	.
1 12X 10180D	0.179	0.807	0.014	0.025	0.286	0.066	0.053	0.0251	(0.003)	0.007	0.0026	0.007	.	.
1 IMZ 71A	0.126	0.493	0.0126	0.0075	0.494	0.90	0.036	0.505	0.019	0.025	0.018	0.0065	0.055	0.023
1 NM 308	0.11	0.47	0.013	0.008	0.067	.	0.009	0.032	.	.	.	0.0038	0.0040	.
1 VS UG122	(0.1)	0.433	(0.02)	(0.02)	0.396	0.288	0.378	0.72	.	.	.	.	.	.
1 VS UG120	0.096	0.685	0.027	(0.02)	0.96	0.447	0.634	0.75	0.011	.	.	(0.008)	0.0078	.
1 DSZU C041a	0.085	1.35	0.021	0.0092	0.59	0.046	0.032	0.035	0.029	0.010	0.0038	(0.008)	0.0033	(0.003)
1 IARM Fe1215-18	0.043	0.96	0.059	0.29	(0.006)	0.164	0.055	0.051	.	0.0055	0.016	0.0109	0.0020	.
1 <b>BS XCAS</b>	0.024	0.471	0.008	0.0064	0.339	0.020	0.031	0.035	(0.027)	0.0086	0.0069	0.0055	0.020	(0.006)
1 <b>BS XCAS-2</b>	0.021	0.58	0.0055	0.0059	0.40	0.047	0.099	0.039	0.073	0.016	0.013	0.0139	0.018	0.020
1 DSZU C040A	0.013	0.012	0.0023	0.0029	0.060	0.007	0.005	0.007	0.039	(0.002)	(0.001)	0.0068	(0.001)	(0.002)

Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units	Others
VS UG128	.	.	.	.	.	.	.	.	.	-38 mm Ø x ~20 mm	.
<b>BS 54J</b>	0.0025	<0.0005	97.6	(0.002)	(0.0011)	(0.0006)	(0.005)	0.0020	1080	38 mm Ø x ~7 or 19+ mm	<b>17025</b>
VS UG129	.	.	.	.	.	.	.	.	.	-38 mm Ø x ~20 mm	.
NM 309	.	.	.	.	.	.	.	.	1060 + P	40 mm Ø x 20 mm	.
IARM Fe1050-18	(0.0030)	(0.0005)	98.0	(0.0013)	0.0026	0.0015	0.0103	0.0008	1050	31 mm Ø x 2 or 18 mm	.
NM 306A	.	.	.	.	.	.	.	.	1045 + P	40 mm Ø x 20 mm	.
VS UG131	.	.	.	.	.	.	.	.	.	-39 mm Ø x ~25 mm	.
BS 1030A *	0.006	<0.005	[98.0]	0.001	<0.05	0.001	0.016	0.001	1030	38 mm Ø x ~7 or 19+ mm	.
SS 452/1	0.015	.	.	.	.	.	0.094	0.031	.	38 mm Ø x 19 mm	.
VS UG121	.	.	.	.	.	.	.	.	.	-45 mm Ø x ~25 mm	.
BS 1026A *	<0.05	<0.005	[98.3]	0.001	<0.05	<0.05	0.008	<0.005	1026	38 mm Ø x ~7 or 19+ mm	.
IARM Fe1020-18	0.0044	.	98.5	(0.0012)	(0.007)	0.0018	0.0080	.	1020	31 mm Ø x 2 or 18 mm	.
IMZ 112A	0.023	0.0010	.	0.0123	Pb:0.008	0.021	0.162	0.0138	1023	38 mm Ø x 20 mm	Zn: 0.0020
BS 57F	(0.006)	.	Ca:(0.0003)	.	(0.006)	.	0.008	.	1020	44 mm Ø x 17 or 19+ mm	last
BS 2971	0.003	.	.	.	.	(0.005)	.	.	LF-2	44 mm Ø x ~7 or 19+ mm	last
VS UG132	.	.	.	.	.	.	.	.	.	-39 mm Ø x ~25 mm	.
12X 10180D	0.0068	.	.	.	.	.	0.0033	.	1018	-40 mm Ø x ~15 mm	.
IMZ 71A	0.016	0.0009	.	0.0100	.	0.013	0.015	0.0041	1010 - 1013	35 mm Ø x 20 mm	Zr: 0.0065
NM 308	.	.	.	.	.	.	.	.	1010	40 mm Ø x 20 mm	.
VS UG122	.	.	.	.	.	.	.	.	.	-45 mm Ø x ~25 mm	.
VS UG120	.	.	.	.	.	.	.	.	.	-45 mm Ø x ~25 mm	.
DSZU C041a	(0.004)	(0.0005)	.	(0.002)	.	.	(0.004)	0.0049	.	40 mm Ø x 25 mm	.
IARM Fe1215-18	0.0043	.	.	0.0012	.	0.0018	0.0083	0.0007	1215	-38 mm Ø x ~3 or ~19 mm	.
<b>BS XCAS</b>	0.0016	(0.0002)	99.0	(0.0015)	0.008	0.0006	0.0017	0.0010	1008	38 mm Ø x 30 mm	<b>17025</b>
<b>BS XCAS-2</b>	(0.004)	0.021	98.6	(0.003)	0.0066	(0.0016)	(0.0015)	0.011	1009 + Al	-37 mm D x ~30 mm	<b>17025</b> Ca: 0.0032
DSZU C040A	(0.0002)	0.00032	.	(0.0003)	Ca:0.0021	(0.0002)	0.0010	.	1005	40 mm Ø x 25 mm	.

**RESULFURIZED STEEL**

# = Class, where 1 = CRM and 2 = RM

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
1 IARM 307B	0.162	1.45	(0.012)	0.094	(0.30)	0.191	0.195	0.105	0.034	0.0101	0.045	(0.011)	(0.003)	.
2 CZ CM-22A	0.154	1.443	0.086	0.084	0.248	0.419	3.10	0.167	(0.004)	0.130	0.132	0.0065	0.653	0.59

Number	As	Nb	Sn	Ti	Alloy	Units
IARM 307B	.	(0.0013)	0.010	(0.003)	1118	31 mm Ø x 2 or 18 mm
CZ CM-22A	0.057	0.019	0.069	0.0038	.	-39 mm Ø x ~25 mm

## LOW ALLOY AND TOOL STEEL, CHART 1 of 2

# = Class, where 1 = CRM and 2 = RM

\* Provisional Analysis

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
2 BS 37D	1.54	0.28	0.021	0.015	0.29	0.063	0.21	11.07	.	0.07	1.09	0.016	0.80	0.16
1 IARM FeM4-18	1.42	0.298	0.013	0.062	0.60	0.104	0.127	4.16	.	0.080	5.07	0.042	3.97	5.55
1 IARM FeM62-18	1.32	0.27	0.016	0.015	0.37	0.115	0.129	3.86	(0.006)	0.105	10.2	0.045	2.02	6.31
1 BS E52100 *	1.00	0.37	0.012	0.005	0.27	0.090	0.065	1.54	0.019	0.007	0.021	0.007	0.005	0.002
2 BS 36C	0.96	0.46	0.023	0.027	0.31	0.18	0.19	5.01	.	0.03	0.99	.	0.11	(0.04)
2 BS TM1	0.86	0.23	0.007	0.012	0.46	0.054	0.057	3.72	.	0.45	8.4	.	1.05	1.7
1 IARM FeM2-18	0.853	0.337	0.025	(0.0010)	0.26	0.098	0.182	4.23	(0.014)	0.28	4.92	0.0148	1.90	5.81
1 IARM FeM1-18	0.85	0.318	0.013	(0.003)	0.44	0.091	0.104	3.67	0.007	0.226	8.0	0.037	1.19	1.98
1 BS 33F	0.569	0.295	0.0134	0.0009	0.76	0.039	0.211	1.31	0.019	0.017	0.202	0.0124	0.25	2.28
2 BS TS7	0.529	0.70	0.016	0.010	0.27	0.05	0.10	3.18	.	0.043	1.34	.	0.35	0.19
1 BS TS-7A	0.527	0.74	0.013	0.016	0.84	0.127	(0.031)	3.35	0.061	(0.005)	1.62	0.0124	0.265	(0.0014)
1 IARM FeS7-18	0.51	0.271	0.021	0.0032	0.47	0.128	0.170	3.28	(0.015)	0.0106	1.39	0.0102	0.233	(0.016)
1 BS D-6A	0.47	0.78	0.0076	0.0010	0.232	0.136	0.60	0.99	0.038	0.013	1.00	0.0031	0.123	0.0019
1 12X 41400B	0.452	0.764	0.0095	0.041	0.32	0.161	0.156	0.999	0.0137	.	0.177	0.0124	.	.
1 BS 4140C	0.43	0.922	0.010	0.026	0.29	0.260	0.131	0.94	0.0215	0.0078	0.169	0.0064	0.0026	(0.003)
2 PV 101/1	0.424	0.798	0.014	0.027	0.177	0.108	0.091	1.013	.	.	0.099	.	.	.
2 BS TH11	0.423	0.31	0.016	0.005	0.88	0.041	0.11	5.04	.	(0.008)	1.27	.	0.46	(0.01)
1 BS 300A **	0.416	0.716	0.0049	0.0008	1.71	0.118	1.87	0.798	0.098	0.0087	0.38	0.0023	0.070	<0.01
1 IARM I70B	0.400	0.821	(0.005)	(0.004)	0.21	(0.005)	0.197	0.009	0.230	(0.005)	(0.003)	.	0.94	(0.02)
2 BS 34D	0.395	0.38	0.017	0.005	1.06	0.049	0.10	5.15	.	0.031	1.24	.	0.94	0.10
1 BS 8740	0.39	0.86	0.011	0.023	0.25	0.16	0.55	0.49	0.037	0.0086	0.27	0.0073	0.0024	0.0023
2 BS 68C	0.38	0.60	0.018	0.008	0.305	0.178	0.166	1.77	1.06	0.011	0.36	0.0045	0.007	.
1 IARM Fe5140H-18	0.37	0.93	0.014	0.022	0.187	0.253	0.266	0.67	0.13	0.0081	0.031	0.007	(0.0024)	(0.003)
2 BS TH12	0.372	0.40	0.020	0.005	0.92	0.064	0.16	5.02	.	0.07	1.41	.	0.62	1.06
1 BS 4330MOD	0.316	0.92	0.0052	0.0010	0.269	0.105	1.83	0.848	0.031	0.034	0.478	0.0031	0.083	(0.001)
1 IARM 378A	0.274	1.38	0.018	0.037	0.307	0.299	0.142	0.187	(0.0029)	0.013	0.031	(0.02)	0.0844	(0.006)
2 BS 9325	0.25	0.91	0.008	0.007	0.32	0.13	3.29	1.48	0.030	0.010	0.31	0.0089	0.004	(0.016)
1 IARM 169B	0.232	0.75	(0.004)	(0.004)	(0.32)	(0.005)	(0.010)	0.010	0.36	(0.003)	(0.004)	.	0.002	(0.003)
2 BS 8822	0.228	0.92	0.011	0.025	0.26	0.17	0.47	0.52	0.022	0.019	0.34	0.0085	0.003	(0.003)
1 IARM Fe8620-18	0.211	0.857	0.012	0.026	0.23	0.197	0.446	0.536	0.0246	0.0085	0.197	0.007	0.0061	(0.004)
1 BS 8822A *	0.21	0.85	0.021	0.033	0.28	0.032	0.57	0.56	0.011	0.005	0.38	0.008	0.003	<0.05
1 BS 4820B	0.199	0.67	0.0081	0.0113	0.269	0.221	3.32	0.116	0.038	0.012	0.251	0.0075	0.0016	(0.003)
2 BS 1931	0.194	0.84	0.007	0.018	0.235	0.116	0.42	0.50	0.021	0.012	0.168	0.0079	0.002	.
1 IARM Fe4820-18	0.192	0.541	(0.011)	0.0018	0.26	0.167	3.51	0.144	0.022	0.0107	0.287	0.007	0.0015	(0.004)
2 PV 102/1	0.186	1.226	0.024	0.018	0.184	0.109	0.140	0.995	.	.	0.030	.	.	.
2 BS 8620A	0.184	0.80	0.008	0.079	0.21	0.15	0.44	0.48	0.016	0.010	0.16	0.0107	0.004	.
1 BS 1982	0.128	0.441	0.012	0.026	0.255	0.177	0.197	2.09	0.021	0.010	0.89	0.0097	0.003	.
2 BS 58D	0.127	0.45	0.010	0.005	0.32	0.156	3.02	1.35	0.042	0.009	0.14	0.0147	0.005	.
1 IARM Fe9310-18	0.121	0.62	0.009	0.0128	0.256	0.158	3.07	1.09	0.036	0.009	0.086	0.0070	0.0030	.
1 IARM FeDP1080-18	0.110	1.88	0.014	(0.006)	0.11	0.042	0.554	0.554	(0.002)	0.069	0.445	(0.009)	(0.0043)	(0.030)
1 BS 3310	0.104	0.54	0.0092	0.0144	0.257	0.199	3.49	1.55	0.035	0.0096	(0.052)	0.0075	0.0029	(0.003)
2 HRT FE2003-H	0.104	0.46	0.013	0.002	0.43	0.05	0.26	8.66	(0.004)	0.013	0.93	.	0.217	.
1 IARM FeF9-18	0.104	0.459	(0.011)	0.0036	0.345	0.093	0.148	8.72	.	0.013	0.94	0.0323	0.214	0.0030
1 IARM Fe91-18	0.099	0.453	0.015	(0.002)	0.27	0.041	0.187	8.24	(0.006)	0.013	0.94	0.046	0.198	(0.003)
1 IARM FeP92-18	0.092	0.737	(0.005)	(0.005)	0.20	0.074	0.82	9.4	(0.005)	0.036	0.52	(0.0036)	0.188	1.97
2 BS 74B	0.08	0.91	0.087	0.316	0.002	0.006	0.012	0.019	(0.002)	.	0.008	.	.	.
1 IARM FeT23-18	0.068	0.82	0.012	0.006	0.18	0.046	0.53	2.47	.	0.085	0.261	(0.003)	0.238	1.60

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
BS 37D	.	.	.	.	0.0031	.	0.004	.	.	D-2	37 mm Ø x -7 or 19+ mm	.	.	.
IARM FeM4-18	0.0058	.	79.0	.	(0.017)	(0.003)	0.0050	0.0018	.	M-4	-38 mm Ø x -3 or -19 mm	.	.	.
IARM FeM62-18	.	(0.003)	.	(0.017)	(0.003)	.	.	(0.003)	.	M-62	31 mm Ø x 2 or 18 mm	.	.	.
BS E52100 *	0.003	.	[96.6]	0.001	<0.005	<0.005	0.005	0.001	.	E52100	38 mm Ø x 19 mm	.	.	.
BS 36C	.	.	.	.	.	.	.	.	.	A-2	38 mm Ø x -7 or 19+ mm	.	.	last
BS TM1	.	.	.	.	.	.	.	.	.	M-1	41 mm Ø x -7 or 19+ mm	.	.	last
IARM FeM2-18	(0.008)	.	81.4	(0.021)	(0.0016)	.	(0.007)	(0.0016)	.	M-2	31 mm Ø x 2 or 18 mm	.	.	.
IARM FeM1-18	.	.	.	.	.	.	0.0041	0.0044	.	M-1	-38 mm Ø x -3 or -19 mm	.	.	Zr: 0.0013
BS 33F	(0.003)	(0.0007)	94.0	(0.002)	0.0024	(0.01)	(0.004)	(0.002)	.	S-1 MOD	38 mm Ø x -7 to 19+ mm	.	.	17025
BS TS7	.	.	.	.	.	.	.	.	.	S-7	38 mm Ø x -7 or 19+ mm	.	.	last
BS TS-7A	(0.005)	0.0021	92.3	<0.01	(0.005)	<0.01	(0.004)	(0.003)	.	S-7	36 mm Ø x 25 mm	17025	.	Ca: 0.0004
IARM FeS7-18	(0.005)	.	(93.6)	(0.005)	0.0023	(0.0016)	(0.006)	0.0014	.	S-7	31 mm Ø x 2 or 18 mm	.	.	Pb: 0.0003
BS D-6A	0.0101	0.0004	95.6	<0.01	0.0009	0.0014	(0.009)	0.0024	.	D-6	31 mm Ø x -7 or 19+ mm	.	.	17025 Ca: 0.0011
12X 41400B	0.015	.	.	.	.	.	0.0099	.	.	4140	-38 mm Ø x -20 mm	.	.	Zn: 0.0012
BS 4140C	0.0052	(0.0007)	96.8	0.0019	0.0011	0.0021	0.0095	0.0009	.	4140	38 mm Ø x -7 or 19+ mm	.	.	Ca: 0.0010 17025
PV 101/1	.	.	.	.	.	.	.	.	.	42CrMo4	40 mm Ø x 25 mm	.	.	.
BS TH11	.	.	.	.	.	.	.	.	.	H-11	38 mm Ø x -7 or 19+ mm	.	.	last
BS 300A **	0.0029	(0.00032)	93.8	(0.002)	<0.01	0.0011	0.0065	0.0095	.	300M	38 mm Ø x -7 or 19+ mm	.	.	17025
IARM I70B	.	(0.0004)	.	(0.004)	.	.	(0.002)	(0.19)	.	CLA7	31 mm Ø x 2 or 18 mm	.	.	.
BS 34D	.	.	.	.	.	.	.	.	.	H-13	41 mm Ø x -7 or 19+ mm	.	.	last
BS 8740	0.0051	0.0003	96.91	(0.0007)	(0.001)	0.0017	0.008	0.0012	.	8740	38 mm Ø x -7 or 19+ mm	.	.	17025
BS 68C	(0.004)	.	.	.	.	.	0.008	.	.	P-20 + Al	37 mm Ø x -7 or 19+ mm	.	.	last
IARM Fe5140H-18	(0.011)	.	.	(0.002)	.	.	0.0089	0.0015	.	5140H	31 mm Ø x 2 or 18 mm	.	.	.
BS TH12	.	.	.	.	.	.	.	.	.	H-12	38 mm Ø x -7 or 19+ mm	.	.	last
BS 4330MOD	0.0038	(0.0009)	95.1	0.007	(0.001)	(0.0007)	0.0062	0.0027	.	4330MOD	44 mm Ø x -7 or 19+ mm	.	.	Zr: 0.0016 17025
IARM 378A	.	(0.0006)	.	(0.003)	.	.	0.0236	(0.003)	.	A615-75	31 mm Ø x 2 or 18 mm	.	.	.
BS 9325	0.004	Ca: 0.0049	.	.	0.0010	.	0.009	.	.	9325	38 mm Ø x -7 or 19+ mm	.	.	last
IARM 169B	.	0.0003	.	(0.004)	.	.	(0.002)	0.23	.	CLA6	31 mm Ø x 2 or 18 mm	.	.	.
BS 8822	0.007	.	.	.	0.0022	.	0.011	.	.	8822	47 mm Ø x -7 or 19+ mm	.	.	last
IARM Fe8620-18	0.009	.	.	.	.	.	0.0072	0.0015	.	8620	31 mm Ø x 2 or 18 mm	.	.	.
BS 8822A *	<0.05	0.0005	[97]	0.002	<0.05	0.002	0.004	0.002	.	8822	37 mm Ø x 25 mm	Ta: 0.007	.	.
BS 4820B	0.0055	Ca: 0.0004	94.8	0.0022	(0.0015)	0.0028	0.0098	0.0013	.	4820	38 mm Ø x -7 to 19+ mm	.	.	17025
BS 1931	0.007	.	.	.	(0.0052)	.	0.007	.	.	8620	41 mm Ø x -7 or 19+ mm	.	.	last
IARM Fe4820-18	(0.006)	.	.	(0.003)	(0.003)	.	.	.	.	4820	31 mm Ø x 2 or 18 mm	.	.	.
PV 102/1	.	.	.	.	.	.	.	.	.	16MnCr5	40 mm Ø x 25 mm	.	.	.
BS 8620A	0.007	Bi: 0.073	.	.	(0.004)	.	0.009	(0.002)	.	8620 + Bi	38 mm Ø x -7 or 19+ mm	.	.	last
BS 1982	0.007	.	.	(0.003)	0.0017	0.002	0.013	(0.001)	.	F-22	39 mm Ø x -7 or 19+ mm	.	.	last
BS 58D	.	.	.	.	.	.	0.012	.	.	9310	41 mm Ø x -7 or 19+ mm	.	.	last
IARM Fe9310-18	.	.	94.6	0.285	(0.0017)	.	0.008	.	.	9310	31 mm Ø x 2 or 18 mm	.	.	.
IARM FeDP1080-18	.	.	0.014	(0.0055)	(0.0055)	.	(0.0064)	(0.0013)	.	DP1080	31 mm Ø x 2 or 18 mm	.	.	.
BS 3310	0.0058	(0.0008)	93.7	(0.0009)	(0.									

## LOW ALLOY AND TOOL STEEL, CHART 2 of 2

# = Class, where 1 = CRM and 2 = RM

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
2 HRT FE2019-H	1.54	0.39	0.025	(0.003)	0.51	0.08	0.14	11.89	0.015	.	0.86	.	0.80	.
2 CZ LA-4D	1.143	1.266	0.028	0.0091	0.181	0.066	0.367	1.83	0.067	0.037	0.136	0.0064	0.103	0.025
1 ECRM 268-1D	1.134	0.293	0.0209	0.0154	0.373	0.123	0.143	4.57	.	0.0290	3.20	2.03	8.47	3.70
1 VS UG127	0.962	0.93	0.020	0.029	0.427	0.145	0.151	0.188	0.0051	.	.	0.0155	0.141	.
1 VS UG126	0.856	0.78	0.0128	0.0077	0.348	0.030	0.029	0.591	0.0015	.	.	0.0123	0.075	.
1 VS UG130	0.80	0.228	0.0078	0.0071	0.226	0.252	0.104	0.258	.	.	.	.	.	.
2 CZ CM-1D	0.735	1.80	0.0218	0.026	0.341	0.186	0.547	0.456	0.024	0.029	0.100	0.0124	0.089	0.063
1 12X LA4C	0.657	0.374	0.050	0.0258	0.482	0.265	0.485	0.526	0.183	0.099	0.405	0.0116	0.372	0.091
1 NCS HSL3752	0.51	0.99	0.027	0.011	0.21	.	.	0.67	.	.	0.27	.	0.09	.
1 DSZU C051	0.443	0.795	0.0162	0.029	0.293	0.140	0.041	0.048	(0.010)	(0.003)	.	.	(0.002)	.
2 CZ LA-5C	0.439	1.87	0.017	0.0088	0.394	0.138	2.59	3.815	0.081	0.088	0.86	0.024	0.536	0.631
2 HRT FE2021-N	0.33	0.31	0.0178	0.0014	0.28	0.070	0.193	2.81	0.014	0.011	2.7	0.007	0.52	0.027
1 IMZ 54/1	0.43	0.14	(0.009)	0.010	0.17	(0.034)	4.01	0.12	.	.	(0.007)	.	0.19	.
1 SS 214/2	0.39	1.61	0.032	0.043	0.18	0.21	0.15	0.09	.	.	0.26	.	.	.
1 SS 408/1	0.285	0.51	0.037	0.028	0.23	0.66	4.45	0.102	.	.	0.09	.	0.031	.
2 CZ CM-8B	0.185	1.95	0.015	0.014	0.112	0.081	0.032	1.22	0.0028	0.007	0.011	0.0075	0.0078	(0.009)
1 IRSID 1658	0.180	0.618	0.014	0.032	0.160	0.345	0.241	0.147	0.029	.	0.046	.	(0.002)	.
2 HRT FE2019-N	0.17	1.27	0.015	(0.001)	0.30	0.03	0.33	0.75	0.068	(0.003)	0.40	0.0040	(0.003)	.
1 VS RG31	0.169	0.291	0.0048	0.006	0.39	0.46	2.08	1.31	.	0.28	0.306	.	0.207	0.39
1 DSZU C042a	0.132	0.488	0.0091	0.0062	0.286	0.137	0.195	0.995	0.018	0.009	0.31	(0.01)	0.189	(0.006)
1 12X 12746V	0.048	1.19	0.034	0.064	0.156	0.646	0.226	0.374	0.459	0.142	0.658	0.0208	0.105	.
1 VS UG102	0.045	1.78	0.0082	.	0.222	0.172	0.277	0.0143	0.036	.	0.209	.	.	.
1 12X LA6D	0.009	0.086	0.0041	0.0057	0.075	0.0250	0.033	0.099	0.174	0.0051	0.0110	0.0070	0.0033	.

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Units	Others				
HRT FE2019-H	.	.	.	0.071	.	.	.	0.012	40 mm Ø x 20 mm					
CZ LA-4D	0.010	.	.	0.0046	.	.	0.014	0.0154	~39 mm Ø x ~25 mm	Pb:0.040				
ECRM 268-1D	0.0062	0.0009	.	.	.	0.0017	0.0078	.	38 mm Ø x 25 mm					
VS UG127	.	.	.	.	.	.	.	0.0094	~38 mm Ø x ~20 mm	Bi:0.011	Pb:0.0049			
VS UG126	.	.	.	.	.	.	.	.	~38 mm Ø x ~20 mm	Bi:0.0055	Pb:0.009			
VS UG130	0.0093	.	.	.	.	.	.	.	~39 mm Ø x ~25 mm					
CZ CM-1D	.	0.0017	.	0.050	.	0.0112	0.0144	0.054	~39 mm Ø x ~25 mm					
12X LA4C	0.018	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm	Zn:0.006				
NCS HSL3752	.	.	.	.	.	.	.	0.006	38 mm Ø x 38 mm					
DSZU C051	(0.002)	.	.	(0.001)	.	.	(0.004)	(0.001)	40 mm Ø x 25 mm					
CZ LA-5C	0.026	.	.	0.057	Pb:0.015	0.018	0.031	0.048	~37 mm Ø x 25 mm					
HRT FE2021-N	0.004	0.0006	Ce:0.0011	0.007	.	0.001	0.004	0.001	36 mm Ø x 20 mm	Zn:0.002	Zr:0.0012			
IMZ 54/1	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm					
SS 214/2	.	.	.	.	.	.	.	.	42 mm Ø x 19 mm					
SS 408/1	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm					
CZ CM-8B	0.0035	0.0023	.	(0.002)	.	(0.004)	0.0126	0.0008	~39 mm Ø x 25 mm					
IRSID 1658	0.034	.	.	.	.	.	0.022	(0.002)	40 mm Ø x 30 mm					
HRT FE2019-N	.	0.0016	.	0.029	.	.	.	0.004	40 mm x 40 mm x 20 mm			Ca:0.0014		
VS RG31	.	.	.	.	.	.	.	0.21	~45 mm Ø x ~28 mm					
DSZU C042a	0.0069	(0.0005)	.	0.0025	.	.	0.0079	0.0029	40 mm Ø x 25 mm					
12X 12746V	0.051	.	.	.	.	.	0.264	0.088	~40 mm Ø x ~15 mm					
VS UG102	.	.	.	0.071	.	.	.	.	~45 mm Ø x ~25 mm	Ca:0.0018				
12X LA6D	.	.	.	.	.	.	.	.	~40 mm Ø x ~15 mm	Zn:0.0083				

## SILICON STEEL

# = Class, where 1 = CRM and 2 = RM

Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Co	Mo	N	V	W
2 CZ CM-12C	3.7	0.038	0.275	0.0103	0.0110	0.175	0.046	0.081	0.145	0.0044	0.012	0.0056	0.027	(0.004)
1 ECRM 191-3C	3.226	0.0027	0.153	0.0097	0.0005	0.0097	0.0124	0.0242	0.81	.	0.00127	0.00105	0.00043	.
1 DSZU C047A	1.94	0.789	0.411	0.022	0.0107	0.150	0.311	4.76	0.054	0.105	0.76	0.022	1.21	2.37
2 CZ CM-20A	1.74	0.63	0.594	0.0383	0.020	0.237	1.007	0.97	0.076	0.124	0.365	0.0086	0.225	0.104
1 SS 405/1	1.71	0.032	1.28	0.018	0.069	0.013	0.22	0.15	.	.	(0.002)	.	0.28	.
1 SS 409/1	1.46	0.082	0.44	0.025	0.021	0.048	3.06	0.94	.	0.014	0.65	.	0.09	.
1 IMZ 52/1	1.38	0.41	0.25	0.012	(0.009)	0.094	2.35	0.12	.	.	(0.041)	.	.	.
2 CZ LA-3G	1.29	0.626	0.68	0.047	0.035	0.236	1.01	1.377	0.047	0.127	0.326	0.011	0.232	0.105
Number	As	B	Nb	Pb	Sb	Sn	Ti	Zr	Units	Others				
CZ CM-12C	0.0030	0.0033	0.0066	.	.	(0.005)	0.0128	.	~39 mm Ø x ~25 mm	Ca:0.0010				
ECRM 191-3C	0.0014	0.00024	.	.	.	0.0013	0.0020	.	~30 mm Ø x ~39 mm	Mg:0.0036				
DSZU C047A	(0.0095)	0.0006	0.020	.	.	0.0104	0.0096	.	40 mm Ø x 25 mm	Ca:0.0022				
CZ CM-20A	0.073	0.0071	0.074	0.015	0.025	0.033	0.175	0.083	~37 mm Ø x ~25 mm	Zn:0.007				
SS 405/1	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm					
SS 409/1	.	.	.	.	.	.	.	.	38 mm Ø x 19 mm					
IMZ 52/1	.	.	.	.	.	.	.	.	40 mm Ø x 40 mm					
CZ LA-3G	0.051	0.0039	0.071	0.0098	0.024	0.031	0.143	0.068	~39 mm Ø x ~25 mm	Ca:0.0016				

## STAINLESS AND HIGH ALLOY STEEL

# = Class, where 1 = CRM and 2 = RM

\* Provisional Analysis

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
2 BS 93E	1.02	0.52	0.022	0.0010	0.90	0.12	0.35	17.33	0.009	0.048	0.50	0.0359	0.24	0.11
2 BS 98	0.309	0.48	0.019	0.0014	0.72	0.098	0.21	13.35	0.003	0.020	0.034	0.0181	0.075	0.009
1 IARM FeAl100-18	0.222	(0.013)	(0.004)	(<0.0010)	(0.039)	(0.010)	11.2	2.98	(0.007)	13.4	1.19	(0.0010)	(0.007)	(0.006)
2 BS 97	0.216	0.71	0.021	0.0004	0.39	0.066	0.76	11.82	0.018	0.041	1.05	0.030	0.21	0.95
1 BS 183B	0.181	0.344	0.018	0.0042	0.41	0.074	1.96	12.45	0.0009	0.032	0.33	0.044	0.165	3.5
1 BS 183C	0.173	0.368	0.015	0.0040	0.427	0.060	1.87	12.72	0.0020	0.027	0.189	0.039	0.109	2.83
1 BS 431A	0.159	0.53	0.019	0.0036	0.31	0.111	2.21	15.78	(0.0012)	0.041	0.172	0.058	0.079	0.021
1 IARM Fe309-18	0.066	1.61	0.029	(0.002)	0.30	0.430	12.2	22.42		0.248	0.357		0.073	0.063
2 BS 91E	0.066	0.42	0.017	0.002	0.52	0.05	0.17	16.58	(0.002)	0.02	0.035	0.032	0.09	0.01
1 BS 309	0.062	1.61	0.028	0.0011	0.24	0.349	12.16	22.40	(0.0025)	0.200	0.193	0.073	0.075	(0.031)
1 BS 347C	0.051	1.67	0.022	0.0022	0.677	0.110	10.08	17.27	(0.003)	0.072	0.27	0.039	0.097	0.013
2 CZ SP-1B	0.050	1.67	0.039	0.30	0.505	0.47	8.32	17.42	(0.003)	0.161	0.40	0.063	0.060	0.032
2 BS 188A	0.050	0.139	0.015	0.0049	0.15	0.099	24.61	14.04	0.19	0.18	1.10	0.0029	0.24	0.055
2 PV 112/1	0.047	1.577	0.018	0.023	0.515	0.102	11.14	17.56			2.03			
2 HRT FE2021-H	0.041	1.19	0.021	0.002	0.34	0.17	12.7	15.6	0.007	0.044	1.11	0.088	0.59	(0.025)
1 IARM Fe174PH-18	0.041	0.47	0.024	(<0.0040)	0.52	3.33	4.73	15.10	0.007	0.047	0.315	0.0436	0.051	0.015
1 13X 41500A	0.038	0.596	0.021	0.0101	0.402	0.129	3.52	13.00		0.099	0.504	0.0504	0.091	
2 BS 95A	0.035	0.58	0.026	0.004	0.46	1.50	6.42	14.72	0.002	0.081	0.73	0.0255	0.052	0.02
1 13X 41008B	0.034	0.684	0.013	0.0070	0.761	0.267	0.338	12.36	0.028	0.053	0.042	0.0088	0.061	
1 BS 2507	0.026	0.79	0.023	(0.0005)	0.32	0.222	6.94	25.3	(0.004)	0.040	3.75	0.273	0.064	0.074
2 TL 2001D	0.0244	0.679	0.022	0.0006	0.27	0.612	7.5	25.58		0.046	3.49	0.279	0.079	0.57
1 IARM FeKovar-18	0.024	0.26	(0.004)	(0.0055)	(0.09)	0.077	29.0	0.068		17.3	0.062			(0.020)
2 PV 111/1	0.0226	1.538	0.019	0.026	0.485	0.105	8.57	18.49			0.173			
1 BS 186B	0.022	0.288	(0.0027)	0.0016	0.254	0.057	36.1	0.11	0.0080	0.041	0.025	0.0033	(0.002)	(0.007)
1 BS 160B *	0.021	0.26	0.003	0.003	0.11	0.060	29.1	0.07	0.007	17.2	0.05	<0.005	0.004	0.013
1 IARM FeN40-18	0.019	9.13	0.025	0.0012	0.31	0.421	6.42	19.45		0.122	0.343	0.348	0.086	0.030
1 BS 254	0.019	0.95	0.026	0.0009	0.312	0.612	18.47	20.2	<0.01	0.08	6.07	0.210	0.062	(0.02)
1 BS 179A	0.017	1.04	0.021	0.001	0.44	1.94	5.84	25.45	(0.009)	0.58	3.24	0.184	0.070	(0.2)
1 IARM Fe155PH-18	0.015	0.616	0.021	(0.0004)	0.430	3.35	4.79	15.13	0.014	0.024	0.129	0.0494	0.055	0.019
2 TL 2002D	0.0149	1.30	0.022	0.0206	0.53	0.438	11.0	16.7		0.087	2.05	0.0341	0.068	
1 ECRM 298-2D	0.0140	0.788	0.0210	0.0006	0.331	0.105	6.87	24.91	0.0148	0.0482	3.78	0.277	0.070	0.0094
2 BS 96A	0.009	0.04	0.007	0.004	0.06	2.07	8.38	11.62	0.08	0.03	0.021		0.07	
1 IARM 99D	(0.006)	(0.013)	(0.004)	0.0011	(0.03)	(0.045)	18.4	(0.12)	0.117	9.24	4.8	0.0014	(0.037)	(0.010)
1 BS 161B	0.0031	0.010	(0.004)	0.0007	0.0107	0.010	18.56	0.034	0.073	9.28	4.87	0.0011	0.0011	0.010

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	V	W
BS 93E				0.005	0.0040		0.003	0.007	440C		41 mm Ø x -7 or 19+ mm	last		
BS 98	(0.003)	(0.0002)		0.003	0.0038		0.006	0.002	420		38 mm Ø x -7 or 19+ mm	last		
IARM FeAl100-18				0.070	(0.0009)		(0.004)	(0.008)	Aermet 100		31 mm Ø x 2 or 18 mm	last		
BS 97				0.007			(0.003)	(0.002)	422		35 mm Ø x -7 or 19+ mm	last		
BS 183B	(0.005)	(0.0007)	80.4	(0.0075)	(0.0054)	0.0009	0.0046	(0.0016)	Greek Ascoloy		38 mm Ø x -7 or 19+ mm	17025		
BS 183C	0.0041	(0.0008)	81.1	0.0054	(0.005)	0.0007	0.0039	(0.002)	Greek Ascoloy		38 mm Ø x -7 or 19+ mm	17025	Ca: 0.0006	
BS 431A	0.0033	0.0002	80.5	0.0062	0.0067	0.0012	0.0047	0.0010	431		38 mm Ø x -7 or 19+ mm	17025	Zr: 0.0012	
IARM Fe309-18	0.0065			0.021		0.0018	0.012		309		-38 mm Ø x -3 or -19 mm	last		
BS 91E				0.007			0.004	(0.002)	430		41 mm Ø x -7 or 19+ mm	last		
BS 309	0.0048	(0.0004)	62.6	0.0090	0.0027	(0.0017)	0.0089	0.0020	309, 309H		38 mm Ø x -7 or 19+ mm	17025	Ca: 0.0010	
BS 347C	(0.003)	0.0018	69.1	0.58	0.0053	(0.002)	0.0034	(0.004)	347		44 mm Ø x -7 or 19+ mm	17025		
CZ SP-1B	(0.003)	0.0007		(0.012)			0.013	(0.002)			-37 mm Ø x -25 mm	last		
BS 188A		0.0065		0.050	0.0012		0.002	2.21	A-286		38 mm Ø x -7 or 19+ mm	last		
PV 112/1								0.394	316 Ti		40 mm Ø x 25 mm			
HRT FE2021-H	0.004	0.0021		0.57		0.003	0.005	0.004	X8CrNiMoVNB16-13		50 mm Ø x 20 mm			
IARM Fe174PH-18				(0.0015)	0.0035		0.0069		17-4 PH		31 mm Ø x 2 or 18 mm			
13X 41500A				0.040				0.0012	415		-40 mm Ø x -15 mm	last		
BS 95A		0.0010		0.55			0.008	(0.003)	450		38 mm Ø x -7 or 19+ mm	last		
13X 41008B				0.019			0.0081		410		-40 mm Ø x -15 mm	Zr: 0.047		
BS 2507	0.0046	0.0021	62.3	(0.011)	0.0038	0.0008	0.0050	0.0028	2507		38 mm Ø x -7 or 19+ mm	17025		
TL 2001D				0.024					Super Duplex		40 mm Ø x 20 mm			
IARM FeKovar-18			53.3				0.0021		Kovar		31 mm Ø x 2 or 18 mm			
PV 111/1									304 L		40 mm Ø x 25 mm			
BS 186B	0.0022	(0.0006)	63.0	(0.002)	0.0011	(0.0007)	0.0025	0.0028	Invar 36		43 mm Ø x -7 or 19+ mm	17025	Zr: 0.0020	
BS 160B *	<0.005	<0.005	[53.0]	0.002	<0.005	0.002	<0.05	<0.05	Kovar		38 mm Ø x -7 or 19+ mm			
IARM FeN40-18				0.032			0.0081		Nitronic 40		-38 mm Ø x -3 or -19 mm			
BS 254	(0.006)	0.0018	52.9	(0.03)	0.0038	0.0014	0.0063	0.0019	254 SMO		38 mm Ø x -7 or 19+ mm	17025	Zr: 0.0026	
BS 179A	(0.003)	(0.001)		0.030			0.005	0.006	Ferralium 255		31 mm Ø x -7 or 19+ mm	last		
IARM Fe155PH-18	(0.0026)	(0.0005)	75.03	0.273	0.0028		0.0021		15-5PH		31 mm Ø x 2 or 18 mm			
TL 2002D								0.0098	316 MOD		40 mm Ø x 20 mm			
ECRM 298-2D	0.0028	0.0024		0.0011		0.0006	0.0029	0.0023	1.4410		38 mm Ø x 25 mm			
BS 96A		(0.0017)		0.26				1.18	455		38 mm Ø x -7 or 19+ mm	last		
IARM 99D		0.0026		(0.011)				0.67	Maraging 300		31 mm Ø x 2 or 18 mm			
BS 161B		0.0027	66.6	(0.0034)	0.0005		(0.0011)	0.67	Maraging 300		41 mm Ø x -7 or 19+ mm	17025		

Number	As	B	Fe	Nb	O	Sb	Sn	Ti	Alloy	Units
--------	----	---	----	----	---	----	----	----	-------	-------

## CRM CAST IRON

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Ce	La	Mg	Se	Te
NCS AH11112	3.95	0.511	0.055	0.014	2.30	0.487	0.141	0.251	0.014	.	.	.	0.032	.	.
NCS HS11799	3.95	0.511	0.055	0.014	2.30	0.487	0.141	0.251	0.014	.	0.012	0.0064	0.032	.	.
VS ChG 56	(3.8)	(0.2)	(0.8)	(0.01)	(0.5)	(0.4)	(0.1)	(0.1)	(0.01)	(0.005)	.	.	.	.	.
VS ChG 57	(3.8)	(0.2)	1.17	(0.03)	(0.6)	(0.3)	(0.3)	(0.4)	(0.06)	(0.01)	.	.	.	.	.
NCS HS11798	3.78	0.606	0.053	0.020	2.73	0.526	0.856	0.700	0.042	.	0.0097	0.0042	(0.034)	.	.
SCRM 660/11	3.62	0.444	0.137	0.115	1.74	.	.	.	.	.	.	.	.	.	.
NCS HS92744c	3.59	0.435	0.047	0.020	1.68	0.268	0.595	0.526	.	.	0.022	.	0.042	.	.
NCS HS92746a	3.59	0.226	0.046	0.012	2.25	0.263	0.501	0.097	0.014	.	.	.	0.029	.	.
SCRM 658/12	3.33	0.55	0.243	0.076	2.03	.	.	.	.	.	.	.	.	.	.
11X C7P	3.24	2.21	0.058	0.0081	0.604	0.072	0.0273	0.61	0.029	0.006	.	.	.	.	.
NCS AH11353	3.15	0.47	0.020	0.0006	2.30	0.029	0.59	0.025	0.023	0.015	.	.	0.029	.	.
BS CC-23	2.96	0.73	0.53	0.082	0.43	0.307	0.56	0.467	0.060	0.090	(0.0006)	(0.0008)	(0.0006)	.	(0.03)
CKD 242A	1.84	0.060	0.039	0.036	3.06	0.055	0.039	0.029	0.036	0.002	(0.00)	(0.00)	0.000	(0.000)	(0.08)

continued

Number	As	B	Bi	Fe	Mo	Nb	Pb	Sb	Sn	Ti	V	W	Zn	Zr	Units in mm
NCS AH11112	.	.	.	.	0.474	.	.	.	0.055	0.117	0.312	.	.	.	31 Ø x 30
NCS HS11799	.	.	.	.	0.474	.	.	.	0.055	0.117	0.312	.	.	.	31 Ø x 30
VS ChG 56	0.18	(0.001)	.	.	(0.01)	(0.002)	.	0.014	.	(0.06)	(0.02)	(0.004)	.	.	-37 Ø x -17
VS ChG 57	0.095	(0.002)	.	.	(0.01)	(0.004)	.	(0.001)	(0.01)	(0.08)	(0.04)	(0.01)	.	.	-37 Ø x -17
NCS HS11798	.	.	.	.	0.359	.	.	0.025	0.032	0.117	0.018	.	.	.	31 Ø x 30
SCRM 660/11	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 x 42 x 12
NCS HS92744c	0.0021	0.024	.	.	0.180	.	.	.	.	0.044	0.174	.	.	.	35 Ø x 30
NCS HS92746a	(0.003)	0.0086	.	.	0.214	.	.	.	.	0.040	0.033	.	.	.	35 Ø x 30
SCRM 658/12	.	.	.	.	.	.	.	.	.	.	.	.	.	.	48 x 42 x 12
11X C7P	0.0110	0.0099	N:0.0153	.	0.040	0.0195	0.0106	0.009	0.0110	0.064	0.0079	0.053	0.0152	.	-40 Ø x -15
NCS AH11353	0.008	0.004	.	.	0.002	N:0.003	.	0.0005	0.003	0.027	0.032	0.003	.	.	30 Ø x 25
BS CC-23	0.016	0.067	.	(92.8)	0.267	(0.002)	0.008	0.17	0.052	0.091	0.195	(0.002)	17025	0.057	-32 Ø x -17
CKD 242A	0.015	0.008	(0.015)	(92.9)	1.13	0.013	(0.012)	0.007	0.010	0.19	0.37	(0.007)	(0.00)	(0.000)	37x37x ~18-20 last



ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
1.0812		ECRM 191-2D	1544		IRSID 1644	310		IARM 4G
1.2344		ECRM 271-1D	15-5PH		BS 185A	310		SS 464/1
1.2367		HRT FE2012-H	15-5PH		BS 9621	3115		BS XCCT
1.4410		ECRM 298-2D	15-5PH		BS 9622	314		IMZ 165
1.4435, 1.4436		JK 27B	15-5PH		IARM Fe155PH-18	314		IMZ 166A
1.4765		ECRM 299-1D	15-5PH		ECRM 273-1D	316 H		13X NSA2
1.5415		HRT FE2012-N	15-5PH		IARM 22C	316 H		CT 316
1.6587		HRT FE2013-N	16MnCr5		PV 102/1	316 H		IARM 339A
1.7149 20MnCrS5		ECRM 187-2D	17-4PH		13X PH2	316 H		NILAB 500HAD
1.7160		ECRM 194-1D	17-4PH		BS 17-4PHA	316 L	17025	BS 316F
1.8550		ECRM 129-3D	17-4PH	17025	BS 17-4PHB	316 L		CZ SL-2A
1.8519		HRT FE2010-N	17-4PH	17025	BS 17-4PHC	316 L		IARM Fe316L-18
1.8928		ECRM 194-2D	17-4PH		IARM Fe174PH-18	316 L		IARM 163E
1005	17025	BS 1005	17-4PH		SRM C2400	316 L		SRM 1155A
1005		DSZU C040a	17-7PH		13X PH17700	316 L		SS 466/2
1005		ECRM 064-2D	17-7PH 25(preceded 17025)		BS 192	316 MOD		TL 2002
1005		RM Fe 1/5	17-7PH 25(preceded 17025)		BS 192A	316 Ti		IRSID 1821
1005		SRM 1765	17-7PH		IARM 152C	316 Ti		PV 112/1
1005		SRM 1766	17-7PH		IARM Fe177PH-18	316 Ti		VS LG72
1005		SS 111/1	182FM		BS 150	317 L	17025	BS 317L
1008	17025	BS XCAS	18Cr2Ni12Mn		CT ISO035A	317 L	25(pre-17025)	BS 9941
1008		ECRM 057-2D	201		BS 191	317 L	25(pre-17025)	BS 9942
1009	17025	BS 1009	201		SRM 1297	317 L		IARM 153C
1009 + Al	17025	BS XCCS-2	20Cb3		BS 187A	318	17025	BS 2205
100C6		IRSID 1747	20Cb3		CT 20 Cb-3	318		BS 2205A
1010		IMZ 111	20MoCr4		ECRM 197-1D	321		13X 32100
1010		NM 308	2101		IARM 292A	321	17025	BS 85D
1011		IMZ 73	21Cr6Ni9Mn		CT ISO129A	321	17025	BS 321D
1012, 1013		IMZ 71A	2205		13x NSA9	321		IARM 6i
1016	17025	BS 1016	2205	17025	BS 2205	321		IARM 6J
1017		IMZ 112B	2205	17025	BS 2205A	321		SRM 1171
1017		IRSID 1664	2205		IARM 212D	321		SS 465/1
1018		12X 10180B	2205		HRT FE2000-H	321 - Ti		IMZ 152
1018		12X 10180C	2205		IARM Fe2205-18	32750		13X NSA13
1018	17025	BS 1018	2304		IARM 317A	3310		BS 3310
1018		ECRM 087-1D	2507	17025	BS 2507	347		13X 34700
1018		IARM 28K	2507		IARM 301B	347		BS 347A
1020	17025	BS 1020	253 MA	25(pre-17025)	BS 253	347		BS 347B
1020		BS 57F	253 MA		IARM 316A	347		BS 347C
1020		IARM Fe1020-18	254 SMO	17025	BS 254	347		IARM 8G
1023		IMZ 112A	254 SMO		NILAB 501HAD	347		IARM 8H
1026	17025	BS 1026	255, Duplex		IARM 239B	347		IARM 8i
1026		IARM 359A	255, Duplex		IARM 239C	347 H		BS 87F
1030	17025	BS 1030	300M		12X 44220	348		SRM 1172
1030		IARM 209D	300M	17025	BS 300	355	17025	BS 355
1033		IRSID 1663	300M	17025	BS 300A	355		IARM 335A
1035	17025	BS 1035	300M		IARM 340A	35MV7		IRSID 1750
1035		IARM 360A	301		IARM 289A	405		SRM 1295
1039		IRSID 1637	301		IARM 289B	409		13X 40900
1040	17025	BS 3941	301		IRSID 1819	409		13X 40930
1040		IARM 210D	302		IARM 241D	409 + Cr		NCS HS20743
1040		IRSID 1657	302 HQ		IARM 234C	410		13X 41008
1042		IRSID 1656	303		13X 30300	410	25(pre-17025)	BS 0021
1042		NM EN-8	303	17025	BS 303	410, F6NM	25(pre-17025)	BS 0022
1043		IRSID 1652	303		CT 303	410	17025	BS 410C
1045	17025	BS 1045	303		CZ SP-1A	410		CT 410
1045		BS 56E	303		IARM Fe303-18	410		IARM Fe410-18
1045		IARM 200D	303 Se		IARM 253A	410 + Mo		ECRM 296-1D
1045		IPT 503	303 Se		IARM 253B	410 + Mo		IMZ 161
1045 + P		NM 306A	304 H		13X NSB1	410 H		13X 41001
1050		IARM Fe1050-18	304 H + Ca	17025	BS CA304-4	4130	17025	BS 4130
1060		IARM 373A	304 H		CT 304	4130		IARM 143F
1060 + P		NM 309	304 H		IARM Fe304H-18	4130		SRM 1225
1069		ECRM 059-2D	304 H		SS 468/1	4130 H		IPT 501
1070	17025	BS 54H	304 L		13X 30403	4140		12X 41400
1078		ECRM 056-2D	304 L	17025	BS 304B	4140	25(pre-17025)	BS 1962
1078		SRM 1224	304 L		IARM 162D	4140	17025	BS 4140C
1080		BS 54T	304 L		IARM Fe304L-18	4140		IARM 30H
1090		SS 602/2	304 L		ECRM 287-1D	4140		IARM 30J
1095		BS 64C	304 L		ECRM 292-1D	4140 Bi		BS 4140A
1095		SRM 1227	304 L		IARM 162C	4140 Bi		BS 4140B
1117 25(preceded 17025)		BS 3993	304 L		PV 111/1	41L40MOD	17025	BS 70B
1117		BS 65C	304 L		SS 463/1	41L40MOD	17025	BS 70C
1117		IARM 29E	305		ECRM 297-1D	4150 Bi & S		BS 4150MOD
1118		IARM 307A	306		13X 30600A	4150 S	17025	BS 4150MOD-A
1118		IARM 307B	308		DSZU C017	4150 S	17025	BS 42
1140 P		BS 52D	309		BS 82E	4150 S		BS 42A
1141		BS 66B	309	17025	BS 309	415		13X 41500A
1141		IARM 348A	309		IARM Fe309-18	416		BS 90F
1144	17025	BS 1144	310		13X 31008	416	17025	BS 416
1144	17025	BS 1144A	310		BS 83G	416		CT 416
1144		IARM 199C	310	25(pre-17025)	BS 9841	416		IARM 10D
11L17	17025	BS 75F	310	25(pre-17025)	BS 9842	416		SRM 1223
11L17	17025	BS 75G	310		CZ SL-3A	416 H		13X 41600
1215		BS 66K	310		IARM 4E	416 Se		BS 151
1215	17025	BS 66L	310		IARM 4F	418		IARM Fe418-18
1215		IARM Fe1215-18				41CAD7		IRSID 1749
12L14		BS 74B				41L40	17025	BS 70B
12L14	17025	BS 74C				41L50	17025	BS 72B
12L14	17025	BS 74D				42		CT ISO138A
12L14		IARM 183C				42		CT ISO139A
12Mn18Cr		BS 193				42CrMo4		PV 101/1
1345		BS XCCV				420		BS 98
13-8PH		13X PH13800				420		BS SS4951
13-8PH		BS 184A				420		ECRM 272-1D
13-8PH		CT X92834				420		IARM 154C
13-8PH		IARM 21D				420		SS 469
1429		ECRM 058-2D				420 F		BS 152
1513		IMZ 76				420 F S		IARM 352A
1526 MOD		SRM 1269				422		13X 42200
1541		IARM 349A				422		BS 97
1541		IPT 504						
1541		IRSID 1648						

Please use the Adobe Acrobat "search" function to find the complete chemistry of these samples listed within this catalog.

ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER	ALLOY	ISO?	NUMBER
422	17025	BS 422	A-286	17025	BS 188B	Hy-Tuff		IARM 342A
422		IARM 205D	A-286		IARM 26D	Invar		14X 93603
430		BS 91E	A-286		SRM 1230	Invar-36	17025	BS 186B
430	17025	BS 430	A-36		IARM 213C	Invar-36 + Se		BS 186A
430		IARM 11D	A-36		IARM 213D	Invar-36 + Se		IARM 24B
430		NCS HS20742	A-36		SRM 1767	Invar 42		14X 94100
430 F		BS 153	A-485-1		BS A485-1	ISO 898-1		SS 457/2
430 F		BS 154	A-6		BS 40B		17025	BS 160A
430 F S		IARM 355A	A-6		IARM 40B	Kovar		BS 160B
431	17025	BS 431	A-6		IARM 40C	Kovar		IARM 98B
431		BS 92B	A615-75		IARM 378A	Kovar		IARM FeKovar-18
431		IARM 12C	A706-60		IARM 380A	L-2	17025	BS 43A
431		HRT FE2010-H	A706-60		IARM 380B	L-6	17025	BS 39B
431		SRM 1219	A706-80		IARM 381A	LDX2101		13X 32101
4320		BS 3961	Aermet 100		CT ISO045A	LF-2		BS 2971
4330 MOD		BS 4330MOD	Aermet 100		IARM 242A	LF-2	17025	BS LF2B
4330 MOD		IARM 330B	Aermet 100		IARM FeA100-18	LF-2		SS 601/2
4340	17025	BS 4340	AL6XN	17025	BS 189A	LF-3		BS LF3
4340	17025	BS 4340A	AL6XN		IARM 157D	M-1		BS TM1
4340		IARM 31G	C-.5Mo		BS 3952	M-1		CT M1
439 MOD		NCS HS11721-4	C-.5Mo		IARM 229B	M-1		IARM 304A
440 C		13X 44004	C-250		IARM 308A	M-1		IARM FeM1-18
440 C		BS 93E	C-350		IARM 309A	M-10		CT M10
440 C	17025	BS 93F	CA6NM		HRT FE2009-H	M-10		IARM 324A
440 C		IARM 13D	CA6NM		IARM 327A	M-152		13X 64152
440 F		BS 155	CD3MN		ECRM 298-1D	M-152		IARM 291A
440 F Se		BS 156	CD4MCU	17025	BS CD4MCU	M-2		BS 32D
440 F Se		IARM 353A	CD4MCU	17025	BS CD4MCU-A	M-2		CT M2
441		NCS HS11721-4	CD6MN		VS LG58	M-2		IARM 44C
446		BS 94C	CF-3		IRSID 1820	M-2		IARM FeM2-18
450		BS 95A	CLA6		IARM 169B	M-2		SRM 1157
450	17025	BS 450	CLA7		IARM 170B	M-35		IARM 320A
450	25(pre-17025)	BS 9811	CLA11		IARM 180A	M-4		IARM 251A
450	25(pre-17025)	BS 9812	CLA5		IARM 168A	M-4		IARM FeM4-18
450		IARM 15C	CLA9		IARM 172A	M-42		SS 487/1
450		CT 450	CPM15V	17025	BS PML5	M-47	17025	BS M-47
455		13X 45500	D-2		BS 37G	M-50	17025	BS M-50
455		BS 96A	D-2		CT D2	M-50		IARM 306B
455		BS SS1962	D-2		IARM 41D	M-65		IARM FeM62-18
455		CT 455	D-3, D-4		ECRM 288-1D	M-7		CT M7
455		IARM 16C	D-6	17025	BS D-6	Maraging 250		CT 250
446		IARM 14C	D-6	17025	BS D-6A	Maraging 250		ECRM 285-2
4615		BS 3962	D6-AC		IARM 299A	Maraging 300	25(pre17025)	BS 161A
4620		BS 4620	DP1080		IARM FeDP1080-18	Maraging 300	17025	BS 161B
4620	17025	BS 51F	Duplex		13X NSA9	Maraging 300		CT 300
4620		IARM 33D	Duplex	17025	BS 2205	Maraging 300		IARM 99D
465		13X 46500	Duplex		IMZ 163A	Mold Steel	17025	BS PP20
465		IARM 354A	Duplex		IMZ 164	NIT 135M		IARM 305B
465		CT ISO123A	Duplex		TL 2001	Nitriding 135G		BS 68B
4820	17025	BS 4820A	E52100		BS 53G	Nitriding 135G	17025	BS 68E
4820		BS 4820B	E52100		BS E52100	Nitronic 40		13X NSC6
4820		IARM 155F	E52100		IARM 49E	Nitronic 40		BS 190
4820		IARM Fe4820-18	E52100 Bi		BS 53M0D	Nitronic 40		IARM FeN40-18
5140H		IARM Fe5140H-18	Elect./ Magnetic		SRM 1159	Nitronic 50	17025	BS 180A
5160		IMZ 116	Electrolytic		SRM 1265a	Nitronic 50		BS 180B
6150	17025	BS 43A	F-11		BS 45A	Nitronic 50		IARM 17D
6150		BS 4941	F-11	17025	BS 45B	Nitronic 50		IARM FeN50-18
6150		IARM 34C	F-11		IARM 35L	Nitronic 60		13X 21800
630		CT 630	F-2		CT X27081	Nitronic 60		BS 181A
6418		BS 6418	F-22	17025	BS 46B	Nitronic 60	17025	BS 181B
6418		BS 69B	F-22 25(preceded 17025)		BS 1982	Nitronic 60		IARM 18D
6526		BS 9-4-30	F-22		IARM 36C	NMS 100		IARM 214A
709		CT X67975	F-22		SRM 1270	NMS 140		IARM 295A
8620		BS 1931	F-22 + Cr		HRT FE2009-N	NMS J38		IARM 294A
8620 + Bi		BS 8620A	F-5		BS 47A	O-1	17025	BS 35D
8620	17025	BS 8620F	F-5		BS 47B	O-1		CT O1
8620		IARM Fe8620-18	F-5		IARM 37C	O-6	17025	BS 41
8620		IPT 502	F-51	17025	BS 2205	O-6	25(preceded 17025)	BS 41A
86L20 25(preceded 17025)		BS 73B	F-51		BS 2205A	O-6		IARM 45A
86L20		BS 73C	F-9	17025	BS 48B	O-6		IARM 45B
86L20		IARM 182B	F-9		IARM FeF9-18	P-20	17025	BS 55G
8630	17025	BS 8630	F-91		13X 90901	P-20 + Al		BS 68C
8740		BS 67B	F-91	17025	BS 9905A	PP-20	17025	BS PP20
8740	17025	BS 8740	F-91		HRT FE2003-H	Permendur 2V		IARM 326A
8740		IARM 252C	F-91		IARM Fe91-18	RA330		BS 86F
8740		IARM 252D	Ferrallium 255		BS 179A	Railroad Steel	17025	BS 54H
8740		IARM 252E	Ferallium 255	17025	BS 179B	S-1		BS 33D
8740		IARM 252F	Ferallium 255	17025	BS 179C	S-1		BS 33E
8822		BS 8822	F6NM 25(preceded 17025)		BS 0022	S-1		IARM 46B
8822		BS 8822A	Greek Ascoloy		BS 183A	S-1 MOD	17025	BS 33F
904L		13X NSA12	Greek Ascoloy	17025	BS 183B	S-5		BS 38C
904L		ECRM 295-1D	Greek Ascoloy	17025	BS 183C	S-5		IARM 47B
9310		BS 58C	Greek Ascoloy		IARM 20C	S-7		BS TS7
9310		BS 58D	H-10		BS 49	S-7	17025	BS TS-7A
9310		BS 58E	H-11		BS TH11	S-7		IARM 259A
9310		IARM FeE9310-18	H-11		ECRM 276-2D	S-7		IARM FeS7-18
9325		BS 9325	H-11		IARM 255A	S-7		SRM 1772
9325	17025	BS 9325A	H-11		IARM 255B	S42027		13X 42027A
9-4-30		IARM 341A	H-11		IMZ 173	SA213-T22		IMZ 159
A-10		BS A-10	H-12		BS TH12	SA213-T22		IMZ 160
A-11		BS 10V	H-13		BS 34D	SA213-T22		IMZ 169
A-11	17025	BS A-11	H-13	17025	BS H-13A	SAE G2500		BS 20E
A-106 Gr B		SRM 1228	H-13		CT H13	STA 361		IARM 268B
A-193 B16		BS 4942	H-13		IARM 42C	T-1	17025	BS 30D
A-193 B16	17025	BS 4942A	H-13		IMZ 174	T-1		IARM FeT1-18
A-2		BS 36C	H-19	17025	BS H-19	T-4		IARM 281A
A-2		BS 36D	HC 250+V		SRM C1290	T-15	17025	BS TS15
A-2		CT A2	High Perm		CT ISOL24A	T23		IARM FeT23-18
A-2		IARM 39B	High Perm		CT ISOL36A	VM12		IMZ 196
A-2		IARM 39C	High Perm 49		CT ISOL41A	W-5		14X 72305
A-242		IPT 500	HSLA 100		SRM 1271	Z30C13		IRSID 1825
A-242 Mod		SRM C1285	HY 130		SRM 1226	Zeron 100, Duplex		13X NSA8
A-286		BS 188A	HY 80		SRM 1286	Zeron 100, Duplex		IARM 319A
						Zeron 100, Duplex		IARM FeZ100-18

## CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S
1005	<0.06	<0.35	<0.03	<0.05
1006	<0.08	0.25-0.40	<0.03	<0.05
1008	<0.10	0.30-0.50	<0.03	<0.05
1009	<0.15	<0.60	<0.03	<0.05
1010	0.08-0.13	0.30-0.60	<0.03	<0.05
1011	0.09-0.14	0.60-0.90	<0.03	<0.05
1012	0.10-0.15	0.30-0.60	<0.03	<0.05
1013	0.11-0.16	0.50-0.80	<0.03	<0.05
1015	0.13-0.18	0.30-0.60	<0.03	<0.05
1016	0.13-0.18	0.60-0.90	<0.03	<0.05
1017	0.15-0.20	0.30-0.60	<0.03	<0.05
1018	0.15-0.20	0.60-0.90	<0.03	<0.05
1019	0.15-0.20	0.70-1.00	<0.03	<0.05
1020	0.18-0.23	0.30-0.60	<0.03	<0.05
1021	0.18-0.23	0.60-0.90	<0.03	<0.05
1022	0.18-0.23	0.70-1.00	<0.03	<0.05
1023	0.20-0.25	0.30-0.60	<0.03	<0.05
1025	0.22-0.28	0.30-0.60	<0.03	<0.05
1026	0.22-0.28	0.60-0.90	<0.03	<0.05
1029	0.25-0.31	0.60-0.90	<0.03	<0.05
1030	0.28-0.34	0.60-0.90	<0.03	<0.05
1033	0.29-0.36	0.70-1.00	<0.03	<0.05
1034	0.32-0.38	0.50-0.80	<0.03	<0.05
1035	0.32-0.38	0.60-0.90	<0.03	<0.05
1037	0.32-0.38	0.70-1.00	<0.03	<0.05
1038	0.35-0.42	0.60-0.90	<0.03	<0.05
1039	0.37-0.44	0.70-1.00	<0.03	<0.05
1040	0.37-0.44	0.60-0.90	<0.03	<0.05
1042	0.40-0.47	0.60-0.90	<0.03	<0.05
1043	0.40-0.47	0.70-1.00	<0.03	<0.05
1044	0.43-0.50	0.30-0.60	<0.03	<0.05
1045	0.43-0.50	0.60-0.90	<0.03	<0.05
1046	0.43-0.50	0.70-1.00	<0.03	<0.05
1049	0.46-0.53	0.60-0.90	<0.03	<0.05
1050	0.48-0.55	0.60-0.90	<0.03	<0.05
1053	0.48-0.55	0.70-1.00	<0.03	<0.05
1055	0.50-0.60	0.60-0.90	<0.03	<0.05
1059	0.55-0.65	0.50-0.80	<0.03	<0.05
1060	0.55-0.65	0.60-0.90	<0.03	<0.05
1064	0.60-0.70	0.50-0.80	<0.03	<0.05
1065	0.60-0.70	0.60-0.90	<0.03	<0.05
1069	0.65-0.75	0.40-0.70	<0.03	<0.05
1070	0.65-0.75	0.60-0.90	<0.03	<0.05
1074	0.70-0.80	0.50-0.80	<0.03	<0.05
1078	0.72-0.85	0.30-0.60	<0.03	<0.05
1080	0.75-0.88	0.60-0.90	<0.03	<0.05
1084	0.83-0.93	0.60-0.90	<0.03	<0.05
1085	0.80-0.94	0.70-1.00	<0.03	<0.05
1086	0.80-0.93	0.30-0.50	<0.03	<0.05
1090	0.85-0.98	0.60-0.90	<0.03	<0.05
1095	0.90-1.03	0.30-0.50	<0.03	<0.05
Number	C	Mn	P	S

## CARBON STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si
1513	0.10-0.16	1.10-1.40	<0.03	<0.05	.
1522	0.18-0.24	1.10-1.40	<0.04	<0.05	.
1524	0.19-0.25	1.35-1.65	<0.04	<0.05	.
1526	0.22-0.29	1.10-1.40	<0.04	<0.05	.
1527	0.22-0.29	1.20-1.50	<0.04	<0.05	.
1533	0.30-0.37	1.10-1.40	<0.04	<0.05	.
1534	0.30-0.37	1.20-1.50	<0.04	<0.05	.
1541	0.36-0.44	1.35-1.65	<0.04	<0.05	.
1544	0.40-0.47	0.80-1.10	<0.04	<0.05	.
1545	0.43-0.50	0.80-1.10	<0.04	<0.05	.
1546	0.44-0.52	1.00-1.30	<0.04	<0.05	.
1548	0.44-0.52	1.10-1.40	<0.04	<0.05	.
1552	0.47-0.55	1.20-1.50	<0.04	<0.05	.
1553	0.48-0.55	0.80-1.10	<0.04	<0.05	.
1566	0.60-0.70	0.85-1.15	<0.04	<0.05	.
1570	0.65-0.75	0.80-1.10	<0.04	<0.05	.
1580	0.75-0.88	0.80-1.10	<0.04	<0.05	.
1590	0.85-0.98	0.80-1.10	<0.04	<0.05	.
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30

Number	C	Mn	P	S	Si
--------	---	----	---	---	----

## RESULFURIZED STEEL SPECIFICATIONS

Number	C	Mn	P	S
1108	0.08-0.13	0.50-0.80	<0.04	0.08-0.13
1109	0.08-0.13	0.60-0.90	<0.04	0.08-0.13
1110	0.08-0.13	0.30-0.60	<0.04	0.08-0.13
1116	0.14-0.20	1.10-1.40	<0.04	0.16-0.23
1117	0.14-0.20	1.00-1.30	<0.04	0.08-0.13
1118	0.14-0.20	1.30-1.60	<0.04	0.08-0.13
1119	0.14-0.20	1.00-1.30	<0.04	0.24-0.33
1123	0.20-0.27	1.20-1.50	<0.04	0.06-0.09
1132	0.27-0.34	1.35-1.65	<0.04	0.09-0.13
1137	0.32-0.39	1.35-1.65	<0.03	0.08-0.13
1139	0.35-0.43	1.35-1.65	<0.04	0.13-0.20
1140	0.37-0.44	0.70-1.00	<0.03	0.08-0.13
1141	0.37-0.45	1.35-1.65	<0.03	0.08-0.13
1144	0.40-0.48	1.35-1.65	<0.03	0.24-0.33
1145	0.41-0.49	0.70-1.00	<0.04	0.08-0.13
1146	0.42-0.49	0.70-1.00	<0.04	0.08-0.13
1151	0.48-0.55	0.70-1.00	<0.04	0.08-0.13
1152	0.48-0.55	0.70-1.00	<0.04	0.06-0.09
1211	<0.13	0.60-0.90	0.07-0.12	0.10-0.15
1212	<0.13	0.70-1.00	0.07-0.12	0.16-0.23
1213	<0.13	0.70-1.00	0.07-0.12	0.24-0.33
1215	<0.09	0.75-1.05	0.04-0.09	0.26-0.35

Number	C	Mn	P	S
--------	---	----	---	---

These are specifications,  
not samples for sale.

## LOW ALLOY STEEL SPECIFICATIONS

Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other
1330	0.28-0.33	1.60-1.90	<0.035	<0.04	0.15-0.35	.	.	.	.	.
1335	0.33-0.38	1.60-1.90	<0.035	<0.04	0.15-0.35	.	.	.	.	.
1340	0.38-0.43	1.60-1.90	<0.035	<0.04	0.15-0.35	.	.	.	.	.
1345	0.43-0.48	1.60-1.90	<0.035	<0.04	0.15-0.35	.	.	.	.	.
3140	0.38-0.43	0.70-0.90	<0.04	<0.04	0.15-0.35	1.10-1.40	0.55-0.75	.	.	.
4023	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4027	0.25-0.30	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4028	0.25-0.30	0.70-0.90	<0.035	0.035-0.050	0.15-0.35	.	.	0.20-0.30	.	.
4037	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4047	0.45-0.50	0.70-0.90	<0.035	<0.04	0.15-0.35	.	.	0.20-0.30	.	.
4118	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.08-0.15	.	.
4120	0.18-0.23	0.80-1.20	<0.035	<0.04	0.15-0.35	.	0.40-0.60	0.15-0.25	.	.
4121	0.18-0.23	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.45-0.65	0.15-0.25	.	.
4130	0.28-0.33	0.40-0.60	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4135	0.33-0.38	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4137	0.35-0.40	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4140	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
41L40	0.38-0.43	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	.
4142	0.40-0.45	0.45-0.65	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4145	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4147	0.45-0.50	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
4150	0.48-0.53	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	.	.
41L50	0.48-0.53	0.75-1.00	<0.035	0.02-0.04	0.15-0.35	.	0.80-1.10	0.15-0.25	0.15-0.35	.
4320	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	0.40-0.60	0.20-0.30	.	.
4340	0.38-0.43	0.60-0.80	<0.035	<0.04	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	.
4615	0.13-0.18	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4617	0.15-0.20	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4620	0.17-0.22	0.45-0.65	<0.035	<0.04	0.15-0.35	1.65-2.00	.	0.20-0.30	.	.
4715	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.70-1.00	0.45-0.65	0.45-0.65	.	.
4720	0.17-0.22	0.50-0.70	<0.035	<0.04	0.15-0.35	0.90-1.20	0.35-0.55	0.15-0.25	.	.
4815	0.13-0.18	0.40-0.60	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	.
4820	0.18-0.23	0.50-0.70	<0.035	<0.04	0.15-0.35	3.25-3.75	.	0.20-0.30	.	.
50B46	0.44-0.49	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.20-0.35	.	.	B: 0.0005-0.003
5120	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
51L20	0.17-0.22	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	0.15-0.35	.
5130	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	.
5132	0.30-0.35	0.60-0.80	<0.035	<0.04	0.15-0.35	.	0.75-1.00	.	.	.
5140	0.38-0.43	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
5150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
5160	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	.
51B60	0.56-0.64	0.75-1.00	<0.035	<0.04	0.15-0.35	.	0.70-0.90	.	.	B: >0.0005
6150	0.48-0.53	0.70-0.90	<0.035	<0.04	0.15-0.35	.	0.80-1.10	.	.	V: >0.15
8615	0.13-0.18	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8617	0.15-0.20	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8620	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
86L20	0.18-0.21	0.70-0.90	<0.035	0.02-0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	0.15-0.35	.
8622	0.20-0.25	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8630	0.28-0.33	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8637	0.35-0.40	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8640	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8645	0.43-0.48	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.15-0.25	.	.
8720	0.18-0.23	0.70-0.90	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	.
8740	0.38-0.43	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.20-0.30	.	.
8822	0.20-0.25	0.75-1.00	<0.035	<0.04	0.15-0.35	0.40-0.70	0.40-0.60	0.30-0.40	.	.
9259	0.56-0.64	0.75-1.00	<0.035	<0.04	0.70-1.10	.	0.45-0.65	.	.	.
9260	0.56-0.64	0.75-1.00	<0.035	<0.04	1.80-2.20	.	.	.	.	.
E4340	0.38-0.43	0.65-0.85	<0.025	<0.025	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30	.	.
E51100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	0.90-1.15	.	.	.
E52100	0.98-1.10	0.25-0.45	<0.025	<0.025	0.15-0.35	.	1.30-1.60	.	.	.
E9310	0.08-0.13	0.45-0.65	<0.025	<0.025	0.15-0.35	3.00-3.50	1.00-1.40	0.08-0.15	.	.
F-11	0.10-0.20	0.30-0.80	<0.04	<0.04	0.50-1.00	.	1.00-1.50	0.44-0.65	.	.
F-22	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	2.00-2.50	0.90-1.10	.	.
F-5	<0.15	0.30-0.60	<0.03	<0.03	<0.50	.	4.00-6.00	0.45-0.65	.	.
F-9	<0.15	0.30-0.60	<0.03	<0.03	0.50-1.0	.	8.00-10.00	0.90-1.10	.	.
F-91	0.08-0.12	0.30-0.60	<0.02	<0.01	0.20-0.50	<0.40	8.00-9.50	0.85-1.05	.	Al: <0.04      N: 0.03-0.07
F-91	continued									Nb: 0.06-0.10      V: 0.18-0.25
LF2	<0.30	0.60-1.35	<0.035	<0.04	0.15-0.30	.	.	.	.	.
LF3	<0.20	<0.90	<0.035	<0.04	0.20-0.35	3.25-3.75	.	.	.	.
Number	C	Mn	P	S	Si	Ni	Cr	Mo	Pb	Other

These are specifications,  
not samples for sale.

## TOOL STEEL SPECIFICATIONS

\* notes optional chemistry

Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other
A-2	0.95-1.05	<1.00	<0.03	<0.03	<0.50	.	4.75-5.50	.	0.90-1.40	0.15-0.50	.	.
A-4	0.95-1.05	1.80-2.20	<0.03	<0.03	<0.50	.	0.90-2.20	.	0.90-1.40	.	.	.
A-6	0.65-0.75	1.80-2.50	<0.03	<0.03	<0.50	.	0.90-1.20	.	0.90-1.40	.	.	.
A-7	2.00-2.85	<0.80	<0.03	<0.03	<0.50	.	5.00-5.75	.	0.90-1.40	3.90-5.15	0.50-1.50	.
A-8	0.50-0.60	<0.50	<0.03	<0.03	0.75-1.10	.	4.75-5.50	.	1.15-1.65	.	1.00-1.50	.
A-9	0.45-0.55	<0.50	<0.03	<0.03	0.95-1.15	1.25-1.75	4.75-5.50	.	1.30-1.80	0.80-1.40	.	.
A-10	1.25-1.50	1.60-2.10	<0.03	<0.03	1.00-1.50	1.55-2.05	.	.	1.25-1.75	.	.	.
A-11	2.45	0.50	.	.	0.90	.	5.25	.	1.30	9.75	.	.
D-2	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	<1.00	0.70-1.20	<1.10	.	.
D-3	2.00-2.35	<0.60	<0.03	<0.03	<0.60	.	11.00-13.50	.	.	<1.00	<1.00	.
D-4	2.05-2.40	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	.	0.70-1.20	<1.00	.	.
D-5	1.40-1.60	<0.60	<0.03	<0.03	<0.60	.	11.00-13.00	2.50-3.50	0.70-1.20	<1.00	.	.
D-7	2.15-2.50	<0.60	<0.03	<0.03	<0.60	.	11.50-13.50	.	0.70-1.20	3.80-4.40	.	.
H-10	0.35-0.45	0.25-0.70	<0.03	<0.03	0.80-1.20	.	3.00-3.75	.	2.00-3.00	0.25-0.75	.	.
H-11	0.33-0.43	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.60	0.30-0.60	.	.
H-12	0.30-0.40	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.25-1.75	<0.50	1.00-1.70	.
H-13	0.32-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	1.10-1.75	0.80-1.20	.	.
H-14	0.35-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.75-5.50	.	.	.	4.00-5.25	.
H-19	0.32-0.45	0.20-0.50	<0.03	<0.03	0.80-1.20	.	4.00-4.75	4.00-4.50	0.30-0.55	1.75-2.20	3.75-4.50	4.00-5.25
H-21	0.26-0.36	0.15-0.40	<0.03	<0.03	0.15-0.50	.	3.00-3.75	.	.	0.30-0.60	8.50-10.00	.
H-22	0.30-0.40	0.15-0.40	<0.03	<0.03	0.15-0.40	.	1.75-3.75	.	.	0.25-0.50	10.00-11.75	.
H-23	0.25-0.35	0.15-0.40	<0.03	<0.03	0.15-0.60	.	11.00-12.75	.	.	0.75-1.25	11.00-12.75	.
H-24	0.42-0.53	0.15-0.40	<0.03	<0.03	0.15-0.40	.	2.50-3.50	.	.	0.40-0.60	14.00-16.00	.
H-26	0.45-0.55	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-4.50	.	.	0.75-1.25	17.25-19.00	.
H-42	0.55-0.70	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	.
L-2	0.45-1.00	0.10-0.90	<0.03	<0.03	<0.50	.	0.70-1.20	.	<0.25	0.10-0.30	.	.
L-6	0.65-0.75	0.25-0.80	<0.03	<0.03	<0.50	1.25-2.00	0.60-1.20	.	<0.50	.	.	.
M-1	0.78-0.88	0.15-0.40	<0.03	<0.03	0.20-0.50	.	3.50-4.00	.	8.20-9.20	1.00-1.35	1.40-2.10	.
M-2	0.78-1.05	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.50-5.50	1.75-2.20	5.50-6.75	.
M-3.1	1.00-1.10	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.25-2.75	5.00-6.75	.
M-3.2	1.15-1.25	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	4.75-6.50	2.75-3.25	5.00-6.75	.
M-4	1.25-1.40	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.75	.	4.25-5.50	3.75-4.50	5.25-6.50	.
M-6	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	11.00-13.00	4.50-5.50	1.30-1.70	3.75-4.75	.
M-7	0.97-1.05	0.15-0.40	<0.03	<0.03	0.20-0.55	.	3.50-4.00	.	8.20-9.20	1.75-2.25	1.40-2.10	.
M-10	0.84-1.05	0.10-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	.	7.75-8.50	1.80-2.20	.	.
M-30	0.75-0.85	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.25	4.50-5.50	7.75-9.00	1.00-1.40	1.30-2.30	.
M-33	0.85-0.92	0.15-0.40	<0.03	<0.03	0.25-0.55	.	3.50-4.00	7.75-8.75	9.00-10.00	1.00-1.35	1.30-2.10	.
M-34	0.85-0.92	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.50-4.00	7.75-8.75	7.75-9.20	1.90-2.30	1.40-2.10	.
M-36	0.80-0.90	0.15-0.40	<0.03	<0.03	0.20-0.45	.	3.75-4.50	7.75-8.75	4.50-5.50	1.75-2.25	5.50-6.50	.
M-41	1.05-1.15	0.20-0.60	<0.03	<0.03	0.15-0.50	.	3.75-4.50	4.75-5.75	3.25-4.25	1.75-2.25	6.25-7.00	.
M-42	1.05-1.15	0.15-0.40	<0.03	<0.03	0.15-0.65	.	3.50-4.25	7.75-8.75	9.00-10.00	0.95-1.35	1.15-1.85	.
M-46	1.22-1.30	0.20-0.40	<0.03	<0.03	0.40-0.65	.	3.70-4.20	7.80-8.80	8.00-8.50	3.00-3.30	1.90-2.20	.
M-48	1.50	.	.	.	.	.	3.75	9.00	5.25	3.10	10.0	.
M-52	0.90	.	.	.	.	.	4.00	.	4.00	2.00	1.25	.
M-61	1.60	.	.	.	.	.	4.00	.	6.50	5.00	12.0	.
M-62	1.30	.	.	.	.	.	3.75	.	10.5	2.00	6.25	.
O-1	0.85-1.00	1.00-1.40	<0.03	<0.03	<0.50	.	0.40-0.60	.	.	<0.30	0.40-0.60	.
O-2	0.85-0.95	1.40-1.80	<0.03	<0.03	<0.50	.	<0.35	.	<0.30	<0.30	.	.
O-6	1.25-1.55	0.30-1.10	<0.03	<0.03	0.55-1.50	.	<0.30	.	0.20-0.30	.	.	.
O-7	1.10-1.30	<1.00	<0.03	<0.03	<0.60	.	0.35-0.85	.	<0.30	<0.40	1.00-2.00	.
P-20	0.28-0.40	0.60-1.00	<0.03	<0.03	0.20-0.80	.	1.40-2.00	.	0.30-0.55	.	.	.
P-21	0.18-0.22	0.20-0.40	<0.03	<0.03	0.20-0.40	4.00-4.25	0.20-0.30	.	.	0.15-0.25	.	Al: 1.05-1.25
P-6	0.05-0.15	0.35-0.70	<0.03	<0.03	0.10-0.40	3.25-3.75	1.25-1.75	.	.	.	.	.
S-1	0.40-0.55	0.10-0.40	<0.03	<0.03	0.15-1.20	.	1.00-1.80	.	<0.50	0.15-0.30	1.50-3.00	.
S-2	0.40-0.55	0.30-0.50	<0.03	<0.03	0.90-1.20	.	.	.	0.30-0.60	<0.50	.	.
S-4	0.50-0.65	0.60-0.95	<0.03	<0.03	1.75-2.25	.	<0.35	.	.	<0.35	.	.
S-5	0.50-0.65	0.60-1.00	<0.03	<0.03	1.75-2.25	.	<0.35	.	0.20-1.35	<0.35	.	.
S-6	0.40-0.50	1.20-1.50	<0.03	<0.03	2.00-2.50	.	1.20-1.50	.	0.30-0.50	0.20-0.40	.	.
S-7	0.45-0.55	0.20-0.80	<0.03	<0.03	0.20-1.00	.	3.00-3.50	.	1.30-1.80	0.20-0.30*	.	.
T-1	0.65-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	.	.	0.90-1.30	17.25-18.25	.
T-15	1.50-1.60	0.15-0.40	<0.03	<0.03	0.15-0.40	.	3.75-5.00	4.75-5.25	<1.00	4.50-5.25	11.75-13.00	.
T-4	0.70-0.80	0.10-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	0.80-1.20	17.50-19.00	.
T-5	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-5.00	7.00-9.50	0.50-1.25	1.80-2.40	17.50-19.00	.
T-6	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	4.00-4.75	11.00-13.00	0.40-1.00	1.50-2.10	18.50-21.00	.
T-8	0.75-0.85	0.20-0.40	<0.03	<0.03	0.20-0.40	.	3.75-4.50	4.25-5.75	0.40-1.00	1.80-2.40	13.25-14.75	.
W-1	0.70-1.50	0.10-0.40	<0.025	<0.025	0.10-0.40	<0.20	<0.15	.	<0.10	<0.10	<0.15	Cu: <0.20
W-2	0.85-1.50	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	<0.15	.	<0.10	0.15-0.35	<0.15	Cu: <0.20
W-5	1.05-1.15	0.10-0.40	<0.03	<0.03	0.10-0.40	<0.20	0.40-0.60	.	<0.10	<0.10	<0.15	Cu: <0.20

Number	C	Mn	P	S	Si	Ni	Cr	Co	Mo	V	W	Other
--------	---	----	---	---	----	----	----	----	----	---	---	-------

These are specifications,  
not samples for sale.

## STAINLESS AND HIGH ALLOY STEEL SPECIFICATIONS

\* notes optional chemistry

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	N	Nb	Other
13-8PH	<0.05	<0.20	<0.01	<0.008	<0.10	.	7.50-8.50	12.25-13.25	2.00-2.50	<0.01	.	Al: 0.90-1.35
15-5PH	<0.07	<1.00	<0.04	<0.03	<1.00	2.50-4.50	3.50-5.50	14.00-15.50	.	.	0.15-0.45	
17-4PH	<0.07	<1.00	<0.04	<0.03	<1.00	3.00-5.00	3.00-5.00	15.00-17.50	.	.	0.15-0.45	
201	<0.15	5.5-7.5	<0.060	<0.03	<1.00	.	3.50-5.50	16.00-18.00	.	<0.25	.	
202	<0.15	7.5-10.0	<0.060	<0.03	<1.00	.	4.00-6.00	17.00-19.00	.	<0.25	.	
301	<0.15	<2.00	<0.045	<0.03	<1.00	.	6.00-8.00	16.00-18.00	.	.	.	
302	<0.15	<2.00	<0.045	<0.03	<1.00	.	8.00-10.00	17.00-19.00	.	.	.	
302B	<0.15	<2.00	<0.045	<0.03	2.00-3.00	.	8.00-10.00	17.00-19.00	.	.	.	
303	<0.15	<2.00	<0.20	>0.15	<1.00	.	8.00-10.00	17.00-19.00	<0.60*	.	.	Zr: <0.60*
304	<0.08	<2.00	<0.045	<0.03	<1.00	.	8.00-10.50	18.00-20.00	.	.	.	
304L	<0.03	<2.00	<0.045	<0.03	<1.00	.	8.00-12.00	18.00-20.00	.	.	.	
305	<0.12	<2.00	<0.045	<0.03	<1.00	.	10.00-13.00	17.00-19.00	.	.	.	
308	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-12.00	19.00-21.00	.	.	.	
309	<0.20	<2.00	<0.045	<0.03	<1.00	.	12.00-15.00	22.00-24.00	.	.	.	
310	<0.25	<2.00	<0.045	<0.03	<1.50	.	19.00-22.00	24.00-26.00	.	.	.	
314	<0.25	<2.00	<0.045	<0.03	1.50-3.00	.	19.00-22.00	23.00-26.00	.	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316	<0.08	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
316L	<0.03	<2.00	<0.045	<0.03	<1.00	.	10.00-14.00	16.00-18.00	2.00-3.00	.	.	
321	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-12.00	17.00-19.00	.	.	.	Ti: >5xC
347	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	
348	<0.08	<2.00	<0.045	<0.03	<1.00	.	9.00-13.00	17.00-19.00	.	.	>10xC	Ta: <0.10
384	<0.08	<2.00	<0.045	<0.03	<1.00	.	17.00-19.00	15.00-17.00	.	.	.	
385	<0.08	<2.00	<0.045	<0.03	<1.00	.	14.00-16.00	11.50-13.50	.	.	.	
403	<0.15	<1.00	<0.04	<0.03	<0.50	.	.	11.50-13.00	.	.	.	
405	<0.08	<1.00	<0.04	<0.03	<1.00	.	.	11.50-14.50	.	.	.	Al: 0.10-0.30
409	<0.08	<1.00	<0.04	<0.01	<1.00	.	<0.50	10.50-11.75	.	.	.	Ti: 6\mtC-0.75
410	<0.15	<1.00	<0.04	<0.03	<1.00	.	.	11.50-13.50	.	.	.	
414	<0.15	<1.00	<0.04	<0.03	<1.00	.	1.25-2.50	11.50-13.50	.	.	.	
416	<0.15	<1.25	<0.06	>0.15	<1.00	.	.	12.00-14.00	<0.60*	.	.	Zr: <0.60*
420	>0.15	<1.00	<0.04	<0.03	<1.00	.	.	12.00-14.00	.	.	.	
422	0.20-0.25	<1.00	<0.04	<0.03	<0.75	<0.50	0.50-1.00	11.00-12.50	0.75-1.25	.	.	V: 0.15-0.30
422	continued											W: 0.75-1.25
430	<0.12	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	.	.	.	
430F	<0.12	<1.25	<0.06	>0.15	<1.00	.	.	16.00-18.00	<0.60*	.	.	Zr: <0.60*
431	<0.20	<1.00	<0.04	<0.03	<1.00	.	1.25-2.50	15.00-17.00	.	.	.	
440A	0.60-0.75	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440B	0.75-0.95	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
440C	0.95-1.20	<1.00	<0.04	<0.03	<1.00	.	.	16.00-18.00	<0.75	.	.	
450	<0.05	<1.00	<0.03	<0.03	<1.00	1.25-1.75	5.00-7.00	14.00-16.00	0.50-1.00	.	.	8\mtC
455	<0.05	<0.50	<0.04	<0.03	<0.50	1.50-2.50	7.50-9.50	11.00-12.50	<0.50	.	0.10-0.50	Ti: 0.80-1.40
501	>0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
502	<0.10	<1.00	<0.04	<0.03	<1.00	.	.	4.00-6.00	0.40-0.65	.	.	
Duplex	<0.05	<3.00	<0.035	<0.03	<1.50	<2.50*	4.00-7.00	18.00-25.00	0.20-5.50	<0.40	.	

These are specifications,  
not samples for sale.