

INDEX

BISMUTH 1	HARD LEAD 4	RoHS MONITOR 18
CADMIUM 1	JEWELRY SAMPLES 12	SILVER 13, 24
CHROMIUM 1	JEWELRY SET 12	
COBALT 2		TIN 14, 15, 16
	LEAD 3, 4, 5, 6	TITANIUM 16, 17
FUSIBLE ALLOY 1		
	MAGNESIUM 7, 8, 9, 10, 11	XRF 3, 4, 12, 15, 16, 19, 20
GOLD 23	MOLYBDENUM 7	
		ZAMAK 19
		ZINC 18, 19, 20, 21, 22

BISMUTH BASE and FUSIBLE SOLDER ALLOYS

= class, where 1 = CRM and 2 = RM

cast 40 mm Ø x 15 mm

Number	Bi	Cd	In	Pb	Sn	Ag	Al	As	Cu	Fe	Sb	Zn	Nominal Melting °C
1 95X BIS40 P1	57.4	0.0050	0.0164	0.043	42.3	0.035	.	0.0101	0.0670	(0.001)	0.092	0.011	.
2 95X 174	57.1	0.0089	26.08	0.082	16.70	0.0075	.	.	0.0030	.	0.086	0.037	79
2 95X 255	55.7	0.0065	0.010	43.7	0.24	0.0019	.	.	0.045	.	0.32	0.035	124
2 95X 158	50.1	9.50	0.0058	26.9	13.38	0.0021	.	.	0.049	.	0.056	0.043	70
2 95X 136	48.8	0.0092	21.49	18.0	12.05	0.0056	.	.	0.0028	.	0.022	0.031	58
2 95X 117	45.3	4.95	18.72	23.1	8.02	0.0043	.	.	0.010	.	0.010	0.0056	47
2 95X CDS50 P1	0.13	18.1	0.092	31.0	50.1	0.030	<0.002	0.027	0.26	(0.0022)	0.113	0.007	145

CRM

CADMIUM

AVAILABLE IN SETS ONLY, AS GROUPED

Number	As	Cu	Ni	Pb	Sb	Sn	Ti	Set Size
VS 18-95	.	0.0023	0.0010	0.0060	.	.	0.0011	
VS 19-95	.	0.0039	0.0018	0.011	.	.	0.0021	
VS 20-95	.	0.0068	0.00044	0.022	.	.	0.0047	40 mm x 40 mm x 25 mm
VS 21-95	.	0.013	0.0043	0.047	.	.	0.0091	
VS 22-95	.	0.024	0.011	0.12	.	.	0.023	
IMN K1	(0.00030)	.	0.0086	.	0.0064	0.0061	.	
IMN K2	0.0012	.	0.018	.	0.0038	0.0032	.	
IMN K3	0.0010	.	0.063	.	0.0010	0.00065	.	40 mm Ø x 25 mm
IMN K4	0.0056	.	0.11	.	0.0011	0.00091	.	
IMN K5	0.0014	.	0.0054	.	0.00017	.	.	

CRM

CHROMIUM ALLOY

Number	Cr	Ni	C	Co	Cu	Fe	Mn	Mo	N	P	S	Si	Units
219X 20500	51.09	45.68	0.025	(0.008)	(0.007)	1.24	0.239	0.006	0.122	(0.0026)	0.0052	1.35	43 mm Ø x 20 mm

COBALT ALLOYS

= class, where 1 = CRM and 2 = rm analysis listed in mass %

#	Number	Cr	Fe	Mn	Mo	Nb	Ni	W	Al	C	Cu	P	S	Si	Ti	Co
1	112X 14943	30.5	0.53	1.08	8.12	0.117	0.221	0.050	(0.011)	0.200	0.29	0.015	0.054	(1.0)	.	.
2	IARM 208B	30.0	1.17	0.75	6.63	0.06	0.42	0.03	0.04	0.100	0.03	0.004	0.0009	0.63	0.029	60.0
1	119X ST3	29.8	3.10	1.09	0.353	.	2.55	12.1	.	2.39	0.078	.	0.063	0.794	.	.
1	IARM 260A	29.4	0.49	0.46	0.015	0.015	10.72	7.0	0.006	0.244	0.012	0.005	0.0013	0.85	0.01	50.7
2	IARM 95C	29.0	2.47	1.55	1.37	(0.008)	2.88	3.96	0.13	1.10	0.014	0.009	0.001	0.54	0.004	57.0
2	112X 14942	28.47	1.09	0.46	6.22	.	0.29	1.67	0.18	0.090	.	.	.	1.02	.	.
1	ECRM 378-1D	28.22	0.606	0.0579	0.053	.	0.617	4.43	.	1.181	.	(0.0023)	0.0055	1.172	.	63.52
2	IARM 208A	27.7	0.78	0.68	5.3	0.020	0.80	0.07	0.07	0.28	0.021	0.030	0.001	0.77	0.012	63.4
2	IARM 208C	27.55	0.29	0.53	6.12	0.011	0.63	0.02	0.07	0.052	0.01	0.008	0.0004	0.62	0.012	64.0
2	BS 173	27.5	0.19	0.76	5.62	(0.002)	0.14	.	(0.04)	0.046	(0.008)	(0.003)	0.001	0.61	(0.004)	65.0
2	CT ISO074A	27.12	(0.93)	0.78	5.47	.	0.150	<0.01	.	0.089	0.005	0.002	0.002	0.59	.	64.87
2	112X 14941	26.85	0.76	0.14	4.16	.	1.17	0.54	0.03	0.38	.	.	.	0.45	.	.
2	113X 405	26.7	1.30	0.68	.	.	10.79	7.65	.	0.48	.	0.002	0.005	0.76	.	.
2	IARM 64C	25.4	2.99	0.79	4.72	0.016	9.47	2.39	0.138	0.064	0.019	0.0064	0.0004	0.24	0.007	53.4
2	IARM 64B	25.26	3.02	0.78	4.77	(0.018)	9.06	2.12	0.12	0.062	0.020	0.005	(0.0004)	0.27	0.011	54.2
2	113X 401	25.24	0.73	0.20	.	.	11.74	7.09	.	0.56	.	.	.	1.22	.	.
1	112X 14937	25.17	2.28	0.407	7.16	0.191	2.88	2.84	0.012	0.340	0.093	0.009	0.0242	1.18	0.017	.
2	113X 403	25.03	1.06	0.69	.	.	10.40	7.82	.	0.52	.	0.021	0.022	0.85	.	.
2	113X 402	24.86	2.15	1.26	.	.	9.41	7.96	.	0.38	.	0.045	0.036	0.32	.	.
1	119X COB1	24.71	14.7	0.398	0.401	0.346	20.74	11.64	0.022	0.064	0.087	0.026	0.0147	0.410	.	.
2	113X 404	23.7	1.28	0.69	.	.	10.76	7.71	.	0.51	.	0.002	0.006	0.75	.	.
1	IMZ 186	23.14	0.10	.	.	.	10.22	7.17	0.28	0.59	0.19	Rem
2	112X 14936	23.00	0.39	0.77	4.65	.	1.67	1.12	0.48	0.45	.	.	.	0.23	.	.
2	IARM 97C	22.2	2.37	0.82	0.36	0.023	22.8	14.6	0.19	0.130	0.027	0.011	0.0004	0.47	0.011	35.8
2	111X 12669	22.04	1.41	0.57	.	2.06	0.62	10.65	0.71	.	.
2	BS 172A	21.85	1.76	0.77	0.30	0.09	23.7	14.0	0.08	0.098	0.027	(0.011)	<0.0005	0.37	.	.
1	111X 12667	21.79	1.36	0.52	0.161	1.50	(0.70)	8.22	0.005	0.008	0.047	(0.003)	0.0068	0.749	.	.
2	IARM 97B	21.2	1.92	0.76	0.56	0.022	19.4	12.9	0.08	0.096	0.07	0.009	(0.01)	0.34	0.006	42.5
2	111X 12672	20.9	1.47	0.54	.	2.04	0.71	10.0	.	.	(0.005)	.	0.014	0.65	.	.
2	IARM 96B	20.54	2.29	1.39	1.17	0.046	10.04	14.52	0.035	0.132	0.047	0.0063	0.0005	0.16	0.007	49.4
2	BS 171B	20.5	1.82	1.90	0.65	0.046	10.68	15.1	0.08	0.087	0.035	0.008	<0.001	0.29	.	.
2	111X 12671	20.5	1.45	0.61	.	1.95	0.88	11.8	0.51	.	.
1	SRM 1242	20.0	1.80	1.58	.	(0.005)	9.78	15.1	(0.01)	0.126	0.0010	0.002	0.0007	0.016	.	51.5
2	IARM 207A	19.98	0.64	0.015	9.62	0.043	35.19	0.028	0.040	0.007	0.017	0.002	0.0027	0.053	0.91	33.46
2	IARM 96D	19.97	2.17	1.40	0.35	0.08	10.66	14.71	0.23	0.079	0.038	0.006	0.0005	0.23	0.046	49.8
2	IARM 96C	19.95	2.93	1.91	1.88	0.047	10.36	15.4	0.08	0.132	0.08	0.008	0.001	0.31	0.007	47.1
1	111X 12670	19.24	1.28	0.48	(0.057)	2.53	1.10	10.95	(0.007)	(0.007)	(0.059)	0.0052	0.026	0.589	.	.
1	IARM 256A	19.1	9.0	0.014	7.0	0.51	25.7	0.02	0.17	0.020	0.008	0.006	0.002	0.07	3.03	35.6
1	111X 12673	18.8	1.70	0.55	.	2.40	1.70	9.8	0.02	0.001	0.10	.	0.021	0.85	.	.
1	119X 81601	18.56	(5.37)	1.44	4.08	4.20	19.9	4.14	.	0.396	.	0.021	0.033	0.601	.	.

#	Number	Cr	Fe	Mn	Mo	Nb	Ni	W	Al	C	Cu	P	S	Si	Ti	Co
	Number	B	La	Mg	N	O	Pb	Sn	Ta	V	Zr	Units				
	112X 14943	0.011	.	.	0.088	43 mm	Ø x 20 mm	
	IARM 208B	0.005	.	(0.0004)	0.003	0.0015	0.0006	0.004	0.042	0.05	0.002	.	.	31 mm	Ø x 18 or 2 mm	
	119X ST3	0.148	.	.	0.040	40 mm	Ø x 15 mm	
	IARM 260A	0.008	.	<0.005	0.0323	0.006	.	.	<0.02	0.01	<0.005	.	.	31 mm	Ø x 18 or 2 mm	
	IARM 95C	(0.002)	.	(0.0004)	0.033	(0.004)	.	.	0.03	0.004	(0.005)	.	.	31 mm	Ø x 18 or 2 mm	
	112X 14942	40 mm	Ø x 15 mm	
	ECRM 378-1D	40 mm	Ø x 15 mm	
	IARM 208A	0.002	.	0.0003	0.063	(0.003)	(0.0003)	0.007	0.012	0.012	(0.001)	.	.	31 mm	Ø x 18 or 2 mm	
	IARM 208C	0.002	.	0.0002	0.169	0.0010	.	.	(0.02)	0.012	0.0014	.	.	31 mm	Ø x 18 or 2 mm	
	BS 173	(0.001)	.	.	0.190	(0.002)	.	.	.	(0.01)	.	.	.	35 mm	Ø x 12 mm	
	CT ISO074A	(0.0010)	.	.	0.17	0.005	.	.	.	30-35 mm	Ø x 20-25 mm	
	112X 14941	40 mm	Ø x 15 mm	
	113X 405	0.001	40 mm	Ø x 15 mm	
	IARM 64C	0.0010	.	0.0043	0.113	0.0012	.	<0.01	0.02	0.020	<0.01	.	.	31 mm	Ø x 18 or 2 mm	
	IARM 64B	(0.001)	.	0.005	0.12	(0.0009)	.	.	(0.028)	(0.014)	<0.01	.	.	31 mm	Ø x 18 or 2 mm	
	113X 401	0.008	40 mm	Ø x 15 mm	
	112X 14937	0.0123	.	.	0.142	50-55 mm	Ø x 15 mm	
	113X 403	0.006	40 mm	Ø x 15 mm	
	113X 402	40 mm	Ø x 15 mm	
	119X COB1	.	.	.	0.129	40 mm	Ø x 15 mm	
	113X 404	0.001	40 mm	Ø x 15 mm	
	IMZ 186	(0.007)	3.78	.	0.40	.	.	1/4 of 78 mm	Ø cylinder x 30 mm	
	112X 14936	40 mm	Ø x 15 mm	
	IARM 97C	0.0028	.	0.0010	0.075	0.0007	.	(0.001)	0.04	0.010	(0.007)	.	.	31 mm	Ø x 18 or 2 mm	
	111X 12669	40 mm	Ø x 15 mm	
	BS 172A	.	0.045	0.007	.	.	.	38 mm	Ø x 9 mm	
	111X 12667	.	.	.	0.085	.	.	.	0.145	43 mm	Ø x 20 mm	
	IARM 97B	(0.002)	0.005	<0.002	0.014	0.003	.	<0.005	0.019	0.012	(0.001)	.	.	31 mm	Ø x 18 or 2 mm	
	111X 12672	0.04	0.02	0.07	40 mm	Ø x 15 mm	
	IARM 96B	0.0021	.	(0.0005)	0.007	0.002	.	.	0.028	0.012	0.007	.	.	31 mm	Ø x 18 or 2 mm	
	BS 171B	(0.02)	.	.	.	38 mm	Ø x 9 mm	
	111X 12671	40 mm	Ø x 15 mm	
	SRM 1242	(0.0001)	.	(0.001)	0.026	.	(0.0001)	(0.001)	(0.01)	0.005	(0.01)	.	.	43 mm	Ø x 20 mm	
	IARM 207A	0.011	.	(0.0005)	0.0031	0.0011	.	.	0.007	0.011	0.003	.	.	31 mm	Ø x 18 or 2 mm	
	IARM 96D	0.003	.	(0.004)	0.0084	0.0006	.	(0.001)	0.03	0.008	(0.007)	.	.	31 mm	Ø x 18 or 2 mm	
	IARM 96C	0.002	.	(0.0002)	0.031	0.001	.	.	0.03	0.012	0.009	.	.	31 mm	Ø x 18 or 2 mm	
	111X 12670	.	.	.	0.006	.	.	0.021	0.105	40 mm	Ø x 15 mm	
	IARM 256A	0.013	.	<0.001	0.0032	0.0011	.	.	<0.005	0.03	(0.005)	.	.	31 mm	Ø x 18 or 2 mm	
	111X 12673	0.005	0.08	0.06	40 mm	Ø x 15 mm	
	119X 81601	.	.	(0.012)	0.056	.	.	.	0.104	43 mm	Ø x 20 mm	

Number	B	La	Mg	N	O	Pb	Sn	Ta	V	Zr	Units
--------	---	----	----	---	---	----	----	----	---	----	-------

LEAD

= class, where 1 = CRM and 2 = rm analysis listed in mass %

#	Number	Ag	As	Bi	Cd	Cu	Ni	Sb	Se	Sn	Te	Zn
1	83X PR1	0.123	0.0287	0.0551	0.0932	0.0039	0.0004	0.0048	(0.0010)	0.0059	0.0016	0.006
1	83X PR2	0.0537	0.0235	0.0310	0.0021	0.0346	0.0026	0.050	(0.0022)	0.104	0.0114	(0.0008)
1	83X PR4	0.0146	0.0054	0.0187	0.0083	0.0138	(0.0009)	0.0164	0.0053	0.0112	0.0198	.
1	SRM C2417	0.010	0.011	0.010	(<0.0002)	0.010	(<0.0005)	0.010	.	(<0.010)	(<0.0005)	(<0.0005)
1	IMN PL66	0.00652	0.0315	0.00488	0.0624	0.00048	0.00055	0.0310	.	0.00079	0.0010	.
2	L01.3	0.0052	0.00013	0.0006	0.00062	0.00243	0.00051	0.00027	.	(0.00007)	0.00061	0.00045
1	83X PR3	0.0033	0.0017	0.162	0.0479	0.0551	0.0142	0.095	0.0104	0.050	0.0021	(0.0011)
1	IMN PL33	0.0017	0.00026	0.0101	0.00157	0.0104	0.00397	0.0008	0.00027	0.00022	0.0235	.
1	BCR 287A	0.00152	<0.0000003	0.00673	0.000036	0.000098	0.000024	0.000040	<0.000005	<0.000005	<0.00002	<0.00001
2	83X PR5	0.0008	0.0003	0.0041	(0.0001)	0.00038	0.00046	0.00023	0.00018	0.00028	0.00023	0.0005
1	SRM C2418	0.0007	(<0.0001)	(<0.0005)	0.0003	(<0.0001)	(<0.0005)	(<0.0001)	.	(<0.0005)	(<0.0005)	(<0.0005)
1	84X BAHC	0.0005	(0.00015)	0.0130	<0.0001	0.0005	(<0.0001)	(0.0001)	<0.0001	<0.0005	(0.0001)	(0.00017)
2	L01.2	0.00013	0.000095	0.0101	0.00226	0.00180	0.0008	0.0003	.	(0.00007)	0.00074	0.0004
2	BCS 210e *	0.0001	.	0.0008	.	0.0006	<0.001	<0.002	.	<0.002	.	<0.005
1	BCR 286A	0.0000015	<0.0000002	0.00215	0.0000125	0.000149	0.0000041	0.000010	<0.000005	<0.000005	<0.00001	<0.00001

Number	Al	Au	Ca	Fe	Hg	In	Mn	Na	Pt	Ti	Tl	Units
83X PR1	.	.	.	(0.0007)	.	0.0356	.	.	(0.0016)	.	.	Disc 40 mm Ø x 15 mm
83X PR2	.	0.0008	.	.	0.0041	0.0012	.	0.0021	.	.	0.0012	Disc 40 mm Ø x 15 mm
83X PR4	.	(0.0023)	.	.	0.044	0.0030	0.0033	Disc 40 mm Ø x 15 mm
SRM C2417	(<0.0001)	.	(<0.001)	(<0.0003)	.	.	(<0.0003)	Disc 50 mm Ø x 16 mm
IMN PL66	.	.	(0.00811)	(0.0002)	.	0.0106	(0.00005)	.	.	.	0.0491	Disc 440 mm Ø x 27 mm
L01.3	Block 50 mm x 50 mm x 20 mm
83X PR3	.	0.0041	.	.	0.0103	0.0069	.	0.0026	.	.	0.0125	Disc 40 mm Ø x 15 mm
IMN PL33	.	.	(0.00034)	(0.00024)	.	0.00059	(0.00006)	.	.	.	0.00264	Disc 440 mm Ø x 27 mm
BCR 287A	0.000073	Block 60 mm x 60 mm x 12 mm
83X PR5	0.00046	0.00013	Disc 40 mm Ø x 15 mm
SRM C2418	(<0.0001)	.	(<0.0005)	(<0.0005)	.	.	(<0.0005)	Disc 50 mm Ø x 16 mm
84X BAHC	0.0305	.	0.140	(<0.0001)	.	.	(<0.0001)	Disc 55 mm Ø x 12 mm
L01.2	Block 50 mm x 50 mm x 20 mm
BCS 210e *	<0.001	.	.	0.0005	.	.	<0.001	.	.	0.001	.	Block 500 g(10.5 x 2 x 2 cms)
BCR 286A	0.00025	Block 60 mm x 60 mm x 12 mm

* BCS 210e has a certified melting point of 327.3 °C and Pb: 99.996

CRM REFINED LEAD SET

available in SET/7 ONLY

analysis listed in mg/kg

40 mm Ø x 27 mm

Number	Ag	As	Bi	Ca	Cd	Cu	Fe	In	Mn	Ni	Sb	Se	Sn	Te	Tl	Zn
IMN PL 1	193	3.6	729	.	.	7.3	4.5	(64.3)	(0.20)	136	15.4	.	3.0	145	569	6.0
IMN PL 2	97.0	2.6	460	.	218	14.9	4.4	(6.4)	(0.17)	159	7.2	33.3	2.6	349	228	(1.7)
IMN PL 3	17.0	2.5	101	(3.4)	15.7	105	(2.4)	5.9	(0.60)	39.4	8.0	2.7	2.1	235	26.4	1.8
IMN PL 4	10.3	345	59.9	.	5.1	197	.	.	.	8.5	3.4	2.7	.	23.6	21.5	.
IMN PL 5	27.3	159	296	.	.	9.1	.	287	.	6.7	572	.	13.7	13.6	135	.
IMN PL 6	64.3	318	48.3	(81.1)	623	4.7	(2.0)	104	(0.50)	5.5	310	.	7.6	8.2	494	.
IMN PL 7	151	(74.3)	61.7	.	53.2	6.8	77.7	.	26.3	270	99.2	3.5

LEAD ALLOYS CONTINUED ON THE NEXT PAGE

= class, where 1 = CRM and 2 = rm analysis listed in mass %

#	Number	Sn	Sb	Ag	As	Bi	Ca	Cd	Cu	Fe	Ni	Te	Zn
1	91X S63PR4	66.8	0.093	0.030	<0.002	0.030	.	0.021	0.021	<0.005	<0.005	0.006	<0.001
1	91X S63PR3 F	64.27	0.253	0.0222	0.0190	0.255	.	0.0015	0.133	0.0054	0.0196	(0.0002)	(0.002)
1	91X S63PR3	64.01	0.243	0.0193	0.0264	0.254	.	0.0009	0.101	0.0078	0.0085	0.0068	0.0061
1	91X S63PR2	62.38	0.539	0.054	0.0190	0.144	.	0.0130	0.0733	0.0129	0.0092	0.0032	0.004
1	91X S63Bi1	61.9	0.470	0.0592	(<0.002)	0.597	.	0.0095	0.105	0.0204	0.0131	0.0012	(0.0022)
1	91X S62AG2	61.68	0.347	2.03	0.022	0.168	.	0.0016	0.069	0.0065	(0.0016)	.	0.0011
1	91X S63PR1	61.45	0.052	0.0061	0.0064	0.0588	.	0.0045	0.214	(0.0016)	0.0060	0.0047	(0.0021)
1	91X S63PR1 F	61.30	0.075	0.0065	(0.001)	0.062	.	0.0057	0.252	0.012	0.0010	0.0008	0.0032
1	91X S63PR0	60.03	0.0182	0.0097	0.0094	0.0084	.	0.0097	0.0202	(0.0024)	0.0018	0.0034	<0.0005
1	91X S60PR4	54.6	0.098	0.045	0.044	0.097	.	0.0118	1.58	(0.0034)	0.0114	.	0.0105
2	93X S50APR3	51.5	2.3	0.02	0.02	0.25	.	0.01	0.1	0.005	0.01	.	0.01
2	91X S50PR3	51.5	0.25	0.020	0.01	0.25	.	0.001	0.10	0.005	0.015	.	0.003
2	93X S50APR2	50.0	2.8	0.05	0.03	0.15	.	0.005	0.05	0.02	0.005	.	0.025
2	93X S50APR1	48.5	3.3	0.005	0.005	0.05	.	0.001	0.2	0.015	0.001	.	0.002
2	93X S40APR3	41.5	1.7	0.02	0.02	0.25	.	0.01	0.1	0.005	0.01	.	0.01
2	91X S40PR3	41.5	0.25	0.020	0.02	0.25	.	0.009	0.10	0.005	0.010	.	0.008
2	93X S40APR2	40.0	2.2	0.05	0.03	0.15	.	0.005	0.05	0.02	0.005	.	0.025
2	91X S40PR2	40.0	0.60	0.050	0.03	0.15	.	0.005	0.05	0.020	0.005	.	0.025
1	SRM 1131	39.3	0.43	0.01	0.01	0.06	.	.	0.011	.	0.012	.	.
2	91X S40PR1	39.0	0.05	0.005	0.005	0.05	.	0.001	0.20	0.015	0.001	.	0.002
2	93X S40APR1	38.5	2.7	0.005	0.005	0.05	.	0.001	0.2	0.015	0.001	.	0.002
1	93X S30APR3	33.0	0.96	0.021	0.018	0.28	.	0.009	0.008	0.003	0.010	.	0.0053
1	91X S30PR3	30.88	0.269	0.024	0.0126	0.294	.	0.0115	0.102	0.0016	0.0269	.	(0.003)
1	93X S30APR2	30.68	1.80	0.049	0.0178	0.168	.	0.0061	0.062	0.0026	0.042	0.0102	0.028
1	91X S30PR2 B	30.2	0.60	0.044	0.028	0.15	.	0.0070	0.076	0.04	0.007	.	0.031
1	91X S30PR2	30.17	0.619	0.060	0.028	0.158	.	0.0060	0.095	0.009	0.0077	.	0.016
1	91X S30PR1	29.3	0.047	0.007	0.006	0.057	.	0.0024	0.19	(0.08)	0.0023	.	0.0013
1	93X S30APR1	28.58	2.54	0.0144	0.010	0.059	.	0.0014	0.192	(0.012)	0.0010	.	(0.0004)
2	91X S10PR3	11.5	0.25	0.020	0.02	0.25	.	0.010	0.10	0.001	0.005	.	0.008
1	86X PSS4	10.69	16.97	(0.006)	0.278	0.120	.	0.047	0.328	(0.0013)	0.0031	.	<0.002
2	91X S10PR2	10.0	0.60	0.050	0.03	0.15	.	0.005	0.05	0.001	0.001	.	0.025
1	85X SSBC	9.70	2.14	0.456	0.075	0.413	.	0.455	.	.	.	0.0037	.
1	86X PSS3	9.01	14.02	0.006	0.10	0.031	.	0.020	0.608	(0.0016)	0.0040	.	<0.001
2	91X S10PR1	9.0	0.02	0.003	0.005	0.02	.	0.002	0.02	0.001	0.010	.	0.002
1	86X PSS2	6.33	8.16	0.004	1.42	0.054	.	0.069	0.118	<0.001	0.0080	.	<0.002
1	SRM 1132	5.84	10.26	.	0.057	0.052	.	.	0.054	<0.001	0.003	.	.
1	86X PSS1	4.29	11.54	0.0049	0.554	0.195	.	0.0057	0.0249	0.0018	0.0100	.	0.0030
1	84X BA9	2.92	0.0022	0.0017	<0.0005	0.0186	0.109	0.0010	0.0026	.	(0.0003)	<0.0005	0.0020
1	85X SSCH	2.64	5.52	0.0134	0.208	0.0441	.	0.0040	0.177	(0.002)	0.010	0.0070	0.0007
1	85X PSn2	1.97	0.0269	0.0033	0.0047	0.0508	.	0.0012	0.0344	.	0.0010	0.0041	0.0005
#	Number	Sn	Sb	Ag	As	Bi	Ca	Cd	Cu	Fe	Ni	Te	Zn
1	84X BA10	1.51	0.0008	0.0015	0.0005	0.0190	0.0596	0.0002	0.0005	.	(0.0002)	(0.0002)	0.0003
1	85X ANTH	1.45	6.05	0.0071	0.217	0.0194	.	0.0046	0.0291	(0.010)	0.0062	0.0071	(0.0007)
1	BAM EB102a	1.01	(0.0004)	0.0170	(<0.0002)	0.00737	0.0635	.	0.00013	(<0.0002)	.	(<0.00011)	(<0.00005)
1	84X BA1	0.899	(0.0017)	0.0082	0.0007	0.0174	0.0960	0.0019	0.0009	.	(0.0004)	(0.0005)	0.0048
1	85X HRH	0.851	1.106	0.236	0.721	0.0996	.	0.0066	0.073	.	0.0012	0.0023	.
1	84X BACM	0.649	(0.0003)	0.0004	(0.0001)	0.0025	0.102	(<0.0001)	0.0003	<0.0005	(<0.0001)	(0.0002)	0.0002
1	83X PR8	0.603	0.259	0.505	0.155	1.186	.	0.211	0.066	.	0.0020	0.0011	(0.0015)
1	82X PAG6.5R	0.50	0.48	5.93	0.021	0.52	.	0.010	0.18	<0.001	.	.	0.007
1	84X BA2	0.490	0.0010	0.0107	0.0008	0.0319	0.0754	0.0040	0.0033	.	0.00025	.	0.0129
2	L21.04	0.43	0.001	0.0006	0.0003	0.0008	0.11	0.0007	0.001	.	0.0004	0.0003	0.002
1	85X 0494 Pb3	0.344	3.10	0.0142	0.301	0.0433	.	.	0.101	(0.0007)	.	0.0151	.
1	84X BA3	0.341	0.010	0.0082	(0.0006)	0.0411	0.0163	0.0044	0.006	.	(0.0004)	0.0004	(0.0055)
2	L21.03	0.34	0.0003	0.01	<0.0001	0.01	0.10	0.001	0.001	.	0.0001	0.0003	0.0004
1	SRM C2415	0.33	2.95	0.002	0.20	0.054	(<0.001)	0.002	0.095	<0.001	<0.001	0.0045	<0.001
1	84X BA 20	0.299	0.0030	0.0290	.	0.0194	0.334	0.0057	0.0438
1	BAM EB101a	0.294	(<0.00012)	0.00290	(<0.0002)	0.0165	0.136	(<0.0002)	0.00243	(<0.0002)	(<0.00006)	(0.0003)	0.00010
1	85X PSb12	0.270	11.50	0.0019	0.071	0.0310	.	0.00053	0.330	.	0.0033	0.0056	0.071
1	82X PAG3.5R	0.25	0.106	3.54	0.020	0.290	.	0.0027	0.073	<0.001	.	.	(0.0004)
2	L21.02	0.23	0.0007	0.007	<0.0001	0.01	0.02	0.0002	0.003	.	0.0001	0.0003	0.0007
1	83X PR7	0.189	0.795	0.290	0.051	0.479	.	0.455	0.176	(0.0008)	(0.0015)	0.0097	(0.0006)
1	BAM 103	0.183	1.64	0.0066	0.097	0.0158	.	0.000020	0.00097	.	0.00302	.	.
1	84X BA 23	0.170	0.0020	0.0039	.	0.0163	1.21	0.00014	0.00218
1	84X BA 21	0.161	0.0091	0.0122	.	0.0224	0.608	0.0057	0.0136
1	85X PSb3	0.151	2.32	0.0057	0.240	0.0234	.	0.0045	0.0406	.	0.0031	0.0049	(0.0006)
1	85X 0494 Pb2	0.147	1.93	0.0300	0.111	0.0174	.	.	0.0361	(0.0010)	.	0.0050	.
2	L21.01	0.11	0.0005	0.004	<0.0001	0.02	0.06	0.001	0.007	.	0.0001	0.0003	0.001
1	84X BA4 B	0.108	0.061	0.003	(0.0008)	0.074	(0.0014)	0.010	0.031	.	0.0007	0.030	(0.0003)
1	84X BA 22	0.108	0.00114	0.0059	.	0.0162	0.911	0.00139	0.0053
1	85X CADH	0.096	1.85	0.0076	0.201	0.0292	.	2.09	0.0260	0.0005	0.0045	0.0121	0.044
1	85X PSb5	0.094	4.68	0.0023	0.180	0.0204	.	0.0013	0.0251	.	0.0017	0.0018	(0.0019)
1	85X PSb10	0.090	10.0	0.0020	0.127	0.0410	.	0.0018	0.169	.	0.0027	0.0037	0.015
1	SRM C2416	0.09	0.79	0.0044	0.056	0.10	(<0.001)	(<0.0002)	0.065	(<0.0005)	(<0.0005)	(<0.0005)	(<0.0005)
1	82X PAG2.5R	0.082	0.25	2.21	0.010	0.13	.	0.26	0.002
1	85X 0616 Pb1	0.065	1.756	0.0048	0.077	0.0395	.	0.0029	0.0496	.	0.0009	0.0048	0.0005
1	85X 0494 Pb1	0.051	0.95	.	0.049	0.0017	.	.	0.012
1	85X PSb8	0.041	8.04	0.0049	0.0352	0.0178	.	0.0010	0.0169	.	0.0016	0.0043	<0.001
1	82X PAG1.5R	0.038	0.39	1.55	0.006	0.062	.	.	0.27	.	.	.	0.004
1	85X SASH	0.0130	1.54	0.0016	0.683	0.0602	.	0.00024	0.0245	.	0.0005	0.0006	.
#	Number	Sn	Sb	Ag	As	Bi	Ca	Cd	Cu	Fe	Ni	Te	Zn

LEAD ALLOYS CONTINUED FROM THE PREVIOUS PAGE

Number	Al	Au	Hg	In	Mg	Mn	Na	Pd	S	Se	Tl	Units
91X S63PR4	.	0.05	.	0.014	<0.005	.	Disc 40 mm Ø x 15 mm
91X S63PR3 F	.	0.175	.	0.0087	.	(0.0001)	.	.	last of stock	.	.	Disc 40 mm Ø x 15 mm
91X S63PR3	.	0.169	(0.038)	0.0097	Disc 40 mm Ø x 15 mm
91X S63PR2	(0.0014)	0.076	.	0.0154	Disc 40 mm Ø x 15 mm
91X S63Bi1	(0.0015)	0.074	.	0.0067	Disc 40 mm Ø x 15 mm
91X S62AG2	(0.0011)	0.0020	Disc 40 mm Ø x 15 mm
91X S63PR1	.	0.0348	(0.015)	0.0308	Disc 40 mm Ø x 15 mm
91X S63PR1 F	.	0.040	.	0.028	.	<0.0001	.	.	last of stock	.	.	Disc 40 mm Ø x 15 mm
91X S63PR0	.	0.0148	0.004	0.0048	Disc 40 mm Ø x 15 mm
91X S50PR4	<0.001	0.029	.	0.052	0.003	.	Disc 40 mm Ø x 15 mm
93X S50APR3	Disc 40 mm Ø x 15 mm
91X S50PR3	Disc 40 mm Ø x 15 mm
93X S50APR2	Disc 40 mm Ø x 15 mm
93X S50APR1	Disc 40 mm Ø x 15 mm
93X S40APR3	Disc 40 mm Ø x 15 mm
91X S40PR3	Disc 40 mm Ø x 15 mm
93X S40APR2	Disc 40 mm Ø x 15 mm
91X S40PR2	Disc 40 mm Ø x 15 mm
SRM 1131	Disc 32 mm Ø x 19 mm
91X S40PR1	Disc 40 mm Ø x 15 mm
93X S40APR1	Disc 40 mm Ø x 15 mm
93X S30APR3	Disc 40 mm Ø x 15 mm
91X S30PR3	.	0.0063	.	0.0085	Disc 40 mm Ø x 15 mm
93X S30APR2	.	.	.	0.0199	Disc 40 mm Ø x 15 mm
91X S30PR2 B	last of stock	.	.	Disc 40 mm Ø x 15 mm
91X S30PR2	<0.0005	0.0017	Disc 40 mm Ø x 15 mm
91X S30PR1	Disc 40 mm Ø x 15 mm
93X S30APR1	.	.	.	0.0094	Disc 40 mm Ø x 15 mm
91X S10PR3	Disc 40 mm Ø x 15 mm
86X PSS4	<0.001	.	.	0.013	.	.	.	(0.007)	.	.	.	Disc 40 mm Ø x 15 mm
91X S10PR2	Disc 40 mm Ø x 15 mm
85X SSBC	.	0.0079	.	0.209	(0.0008)	(0.0029)	0.0196	Disc 40 mm Ø x 15 mm
86X PSS3	<0.001	.	.	0.004	.	.	.	(0.003)	.	.	.	Disc 40 mm Ø x 15 mm
91X S10PR1	Disc 40 mm Ø x 15 mm
86X PSS2	<0.0005	.	.	(0.002)	<0.0005	.	.	(0.001)	.	.	.	Disc 40 mm Ø x 15 mm
SRM 1132	Disc 32 mm Ø x 19 mm
86X PSS1	.	.	.	0.0074	.	.	.	0.0023	.	.	.	Disc 40 mm Ø x 15 mm
84X BA9	0.0154	Disc 40 mm Ø x 15 mm
85X SSCH	0.0035	(0.015)	.	Disc 40 mm Ø x 15 mm
85X PSn2	(0.0008)	0.0011	.	Disc 40 mm Ø x 15 mm
Number	Al	Au	Hg	In	Mg	Mn	Na	Pd	S	Se	Tl	Units
84X BA10	0.0100	Disc 40 mm Ø x 15 mm
85X ANTH	(0.0036)	0.0149	.	Disc 40 mm Ø x 15 mm
BAM EB102a	0.0124	.	.	(<0.0002)	(<0.0001)	.	(0.0004)	.	(<0.0003)	.	0.00302	Disc 40 mm Ø x 40 mm
84X BA1	0.0240	Disc 40 mm Ø x ~15 mm
85X HRH	(0.0022)	0.0375	.	Disc 40 mm Ø x 15 mm
84X BACM	0.0124	.	.	.	(0.00008)	<0.0001	.	.	<0.0001	<0.0001	.	Disc 55 mm Ø x 12 mm
83X PR8	.	0.0082	0.089	0.224	.	.	0.0073	.	.	0.0064	.	Disc 40 mm Ø x 15 mm
82X PAG6.0R	<0.001	.	.	0.008	Disc 40 mm Ø x 15 mm
84X BA2	0.0127	.	(0.003)	Disc 40 mm Ø x 15 mm
L21.04	Block 50 mm x 50 mm x 20 mm
85X 0494 Pb3	(0.015)	0.077	.	Disc 40 mm Ø x 15 mm
84X BA3	0.0026	Disc 40 mm Ø x 15 mm
L21.03	Block 50 mm x 50 mm x 20 mm
SRM C2415	(<0.0003)	<0.001	.	.	0.0026	<0.001	.	Disc 50 mm Ø x 16 mm
84X BA 20	0.0483	Disc 40 mm Ø x 15 mm
BAM EB101a	0.0227	.	.	.	(0.0009)	.	(0.0004)	.	(<0.0003)	.	0.00102	Disc 40 mm Ø x 40 mm
85X PSb12	<0.001	0.0004	.	Disc 40 mm Ø x 15 mm
82X PAG3.5R	0.0015	.	.	0.037	Disc 40 mm Ø x 15 mm
L21.02	Block 50 mm x 50 mm x 20 mm
83X PR7	.	.	.	0.653	.	.	.	Pt:0.0047	.	0.0052	.	Disc 40 mm Ø x 15 mm
BAM 103	0.0180	0.00152	Disc 40 mm Ø x 30 mm
84X BA 23	0.0229	Disc 40 mm Ø x 15 mm
84X BA 21	0.0067	Disc 40 mm Ø x 15 mm
85X PSb3	(0.0036)	0.0187	.	Disc 40 mm Ø x 15 mm
85X 0494 Pb2	(0.0053)	0.0302	.	Disc 40 mm Ø x 15 mm
L21.01	Block 50 mm x 50 mm x 20 mm
84X BA4 B	last of stock	.	.	Disc 50 mm Ø x 10 mm
84X BA 22	0.033	Disc 40 mm Ø x 15 mm
85X CADH	<0.0005	.	.	<0.0005	0.0010	.	Disc 40 mm Ø x 15 mm
85X PSb5	0.0075	0.0024	.	Disc 40 mm Ø x 15 mm
85X PSb10	<0.001	0.0020	.	Disc 40 mm Ø x 15 mm
SRM C2416	(<0.0001)	(<0.0005)	.	.	0.0015	.	.	Disc 50 mm Ø x 16 mm
82X PAG2.5R	Disc 40 mm Ø x 15 mm
85X 0616 Pb1	.	.	(0.0003)	0.0149	.	Disc 40 mm Ø x 15 mm
85X 0494 Pb1	0.004	.	Disc 40 mm Ø x 15 mm
85X PSb8	0.005	0.0022	.	Disc 40 mm Ø x 15 mm
82X PAG1.5R	Disc 40 mm Ø x 15 mm
85X SASH	(0.0005)	.	.	Disc 40 mm Ø x ~15 mm
Number	Al	Au	Hg	In	Mg	Mn	Na	Pd	S	Se	Tl	Units

MAGNESIUM with RARE EARTHS

= class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg 66X MgD3 ##: not for Glow Discharge

#	Number	Ag	Al	Be*	Ca	Cd*	Ce	Cu	Dy	Er	Eu	Fe	Gd	Ho	K*	La	Li	Lu
2	NH AE82-04	.	8.42	14	0.0028	24	1.03	0.0045	.	.	.	0.0099	.	.	2	0.63	.	.
2	NH AE66-03	.	6.63	14	0.0001	<1	3.28	0.0020	.	.	.	0.0045	.	.	2	2.36	.	.
2	NH AE61-04	.	6.41	18	0.0024	54	0.45	0.0058	.	.	.	0.0035	.	.	3	0.36	.	.
2	NH AE63-04	.	6.10	10	0.0010	4	1.50	0.0008	.	.	.	0.0047	.	.	2	1.46	.	.
2	NH AEBH-02	.	5.07	26	.	62	0.011	0.0188	.	.	.	0.0013	.	.	.	0.013	.	.
2	NH AEAH-02	.	5.06	29	.	62	0.011	0.0189	.	.	.	0.0014	.	.	.	0.013	.	.
2	NH AE53-04	.	5.19	10	0.0002	3	1.41	0.0096	.	.	.	0.0054	.	.	1	1.00	.	.
2	NH AEH-93	.	4.96	13	.	.	2.29	0.0575	.	.	.	0.0018	.	.	.	0.90	.	.
2	NH AE-T-01	.	4.04	15	.	<1	0.15	0.0045	.	.	.	0.0058	.	.	.	0.08	.	.
2	NH AE-X-02	.	3.00	15	.	5	0.036	0.0021	.	.	.	0.0008	.	.	.	0.030	.	.
2	NH AE39-03	.	2.71	4	0.0002	<1	4.41	0.0011	.	.	.	0.0112	.	.	1	3.11	.	.
2	NH AE-S-03	.	2.05	6	.	8	0.063	0.0006	.	.	.	0.0003	.	.	.	0.040	.	.
2	NH AE-Q-02	.	1.98	13	.	4	0.087	0.0011	.	.	.	0.0017	.	.	.	0.046	.	.
2	NH AEL-93	.	1.45	5	.	.	0.79	0.0121	.	.	.	0.0058	.	.	.	0.37	.	.
2	NH AE-Y-03	.	1.38	1	.	24	0.099	0.0095	.	.	.	0.0047	.	.	.	0.064	.	.
2	NH AE-L-02	.	0.96	1	.	<1	0.35	0.0005	.	.	.	0.0145	.	.	.	0.14	.	.
1	66X MgC2	0.0048	<0.003	<1	.	.	0.0206	0.037	.	.	.	0.0009	.	.	.	0.0164	.	.
2	66X MgD3 ##	0.005	0.041	3	(0.07)	.	0.004	0.058	.	.	.	0.023	.	.	.	0.004	.	.
1	66X MgD4	(0.0017)	0.0012	<2	.	.	0.015	0.0041	.	.	.	0.0010	.	.	.	0.014	.	.
1	67X MgF1	<0.001	0.0176	.	.	.	1.88	0.0048	.	.	.	0.0024	.	.	.	1.12	.	.
1	67X MgF2	<0.001	0.0038	.	.	.	1.42	0.0033	.	.	.	(0.001)	.	.	.	0.98	.	.
1	67X MgF3	<0.001	<0.001	.	.	.	1.17	0.0010	.	.	.	<0.002	.	.	.	0.84	.	.
1	67X MgF4	<0.0005	0.079	.	.	.	0.81	0.0302	.	.	.	<0.002	.	.	.	0.47	.	.
1	67X MgF5	<0.0005	0.094	.	.	.	0.412	0.0735	.	.	.	0.0290	.	.	.	0.239	.	.
1	68X MgH1	3.21	<0.002	.	.	.	0.040	0.0046	.	.	.	<0.002	.	.	.	0.034	.	.
1	68X MgH2	2.94	<0.002	.	.	.	0.055	0.0050	.	.	.	(0.0006)	.	.	.	0.044	.	.
2	68X MgH6	1.13	0.23	0.11	.	.	.	0.03
2	68X MgL4	<0.005	0.023	.	0.006	.	.	0.049	.	.	.	0.017
1	69X MGY1	.	(0.0019)	.	.	.	0.029	(0.0015)	0.313	0.13	0.041	0.0021	0.284	0.065	.	0.166	0.119	0.007
1	69X MGY2	.	(0.0014)	.	.	.	0.047	0.0013	0.085	0.0174	<0.0005	0.0014	0.082	0.0037	.	0.0352	0.012	0.00046
1	69X MGY3	.	(0.0010)	.	.	.	0.020	0.0010	0.225	0.041	<0.0005	0.0015	0.221	0.0049	.	0.023	0.014	0.00054
1	69X MGY4	.	(0.0023)	.	.	.	0.011	0.0011	.	.	.	0.0012	1.54	.	.	0.0078	.	.
2	AA C7489	.	0.001	.	.	.	2.57	0.004
2	AA C7514	.	0.002	.	.	.	2.47	0.12
2	AA C7546	.	0.003	.	.	.	1.63	0.058
2	AA C7548	.	0.004	.	.	.	2.66	0.022
2	AA C7594	.	0.003	.	.	.	3.22	0.080
2	AA D1072
2	AA D1073
2	AA D1074
2	AA D1075
2	AA E1272	.	0	.	.	.	1.79	0.026
2	AA E1273	.	0	.	.	.	1.86	0.022

continued 66X-69X: 40-45mm Ø x 15-20mm 69X MgY4: 60mm Ø x 6mm AA: 62mm Ø x 6mm NH: 60mm Ø x 15mm R.E. = Rare Earths

Number	Mn	Na*	Nd	Ni	Pb	Pr	R.E.	Si	Sm	Sn	Tb	Th	Tm	Y	Yb	Zn	Zr	
NH AE82-04	0.106	31	0.23	0.0013	0.0031	0.085	.	0.008	.	0.0042	0.197	.	
NH AE66-03	0.29	1	0.73	0.0002	0.0170	0.28	.	0.025	.	0.0053	0.015	.	
NH AE61-04	0.064	41	0.117	0.0002	0.0163	0.04	.	0.065	.	0.0051	0.043	.	
NH AE63-04	0.19	18	0.48	0.0004	0.0022	0.14	.	0.008	.	0.0026	0.046	.	
NH AEBH-02	0.19	.	0.002	0.0108	0.0129	0.001	.	1.49	.	0.0102	0.50	.	
NH AEAH-02	0.19	.	0.002	0.0108	0.0130	0.001	.	1.47	.	0.0106	0.51	.	
NH AE53-04	0.57	3	0.73	0.0014	0.0050	0.12	.	0.012	.	0.0032	0.24	.	
NH AEH-93	0.298	.	0.61	0.0084	.	0.28	.	0.0376	0.400	.	
NH AE-T-01	0.11	.	0.03	0.0021	0.0051	0.015	.	1.13	.	0.0047	0.28	.	
NH AE-X-02	0.043	.	0.012	0.0051	0.0018	0.004	.	1.34	.	0.0009	0.0179	.	
NH AE39-03	0.29	1	1.00	0.0008	0.0066	0.40	.	0.021	.	<0.0005	0.114	.	
NH AE-S-03	0.110	.	0.016	0.0012	0.0015	0.006	.	0.56	.	0.0008	0.153	.	
NH AE-Q-02	0.09	.	0.029	0.0008	0.0012	0.009	.	1.04	.	0.0006	0.185	.	
NH AEL-93	0.161	.	0.25	0.0025	.	0.09	.	0.0172	0.053	.	
NH AE-Y-03	0.168	.	0.027	0.0004	0.0031	0.010	.	0.83	.	0.0023	0.090	.	
NH AE-L-02	0.012	.	0.098	0.0005	0.0007	0.042	.	0.004	.	0.0001	0.006	.	
66X MgC2	0.0036	.	.	0.0044	0.0074	.	.	(0.0013)	.	0.0007	4.82	0.47	
66X MgD3 ##	0.28	.	.	0.002	0.009	.	.	0.020	.	0.007	1.97	0.029	
66X MgD4	0.0053	.	.	(0.0003)	(0.0009)	.	.	<0.001	.	(0.0008)	2.77	0.69	
67X MgF1	0.0039	.	(0.05)	(0.0003)	<0.001	0.48	.	<0.005	.	<0.002	0.501	0.022	
67X MgF2	0.0047	.	0.29	0.0008	0.019	0.112	.	<0.002	.	<0.002	1.71	0.30	
67X MgF3	0.0040	.	0.212	(0.0006)	0.0140	0.106	.	(0.001)	.	<0.002	3.34	0.53	
67X MgF4	0.0023	.	0.048	(0.0003)	<0.001	0.195	.	(0.0014)	.	<0.001	5.04	0.024	
67X MgF5	0.171	.	0.011	0.0004	0.014	0.100	.	0.0026	.	<0.001	6.29	<0.001	
68X MgH1	0.0027	.	3.05	(0.0006)	<0.002	(0.014)	.	<0.005	.	<0.002	0.053	0.47	
68X MgH2	0.0038	.	2.70	(0.0006)	(0.0021)	(0.013)	.	<0.002	.	<0.005	0.123	0.46	
68X MgH6	0.17	.	.	0.01	<0.005	.	(1.0)	0.015	.	<0.002	0.21	<0.01	
68X MgL4	0.17	.	.	0.012	<0.001	.	1.33	0.01	.	0.009	.	1.32	.	.	.	0.19	<0.005	
69X MGY1	0.0109	.	2.26	(0.0005)	0.014	0.059	.	.	0.09	.	0.045	(0.013)	4.64	0.078	.	0.121	0.38	
69X MGY2	0.0026	.	2.96	0.0011	(0.002)	0.016	.	.	0.013	.	0.0046	0.0009	1.98	0.0094	.	0.354	0.41	
69X MGY3	0.0028	.	2.82	0.0012	(0.0055)	0.015	.	.	0.020	.	0.0057	.	0.0011	3.46	0.0168	0.315	0.43	
69X MGY4	0.0104	.	2.36	0.0009	(0.001)	0.0056	.	.	0.0083	0.495	0.29	
AA C7489	0.012	.	.	0.015	.	.	(5.0)	0.002	0.46	.
AA C7514	0.012	.	.	0.002	.	.	(4.7)	0.002	0.42	.
AA C7546	0.039	.	.	0.004	.	.	(3.0)	0.001	0.34	.
AA C7548	0.035	.	.	0.001	.	.	(4.8)	0.002	0.16	.
AA C7594	0.033	.	.	0.001	.	.	(6.0)	0.002	0.31	.
AA D1072	(3.4)	2.02	(0.5)	.
AA D1073	(3.7)	3.23	(0.6)	.
AA D1074	(3.4)	(2.7)	0.42	.
AA D1075	(3.7)	(2.7)	0.64	.
AA E1272	0.045	.	.	0.003	.	.	(3.3)	0.0	2.58	0.54	.
AA E1273	0.041	.	.	0.002	.	.	(3.6)	0.0	2.87	0.54	.

MAGNESIUM with ALUMINUM

= class, where 1 = CRM and 2 = RM

NH: OES only

#	Number	Al	Be	Ca	Cd	Cu	Fe	Mn	Ni	Pb	Si	Sn	Zn
1	NCS HS49722-5	11.52	(0.0023)	.	.	0.295	(0.20)	(0.68)	0.018	.	0.176	.	0.217
1	65X MgAl5	10.67	0.0062	(0.0014)	0.0034	0.0273	0.010	0.067	0.0026	0.0051	0.034	0.0021	0.348
2	AA D3738	10.38	.	.	.	0.031	.	0.21	0.004	.	0.085	.	0.32
2	NH STD1-85	9.54	0.0015	.	.	0.0130	0.0278	0.0169	0.0127	.	1.14	.	0.0009
1	65X M9A5	8.00	0.0013	(0.014)	0.0035	0.0195	0.006	0.401	0.0201	0.042	0.110	0.0124	0.411
1	NCS HS49723-3	7.33	0.00015	.	.	0.020	0.015	0.182	(0.0015)	.	0.27	.	0.171
2	NH AM60HC-99	7.06	0.0020	.	.	0.0054	0.0008	0.62	0.0052	0.0067	0.0245	0.0053	0.40
2	NH A91-L-00	6.98	0.0001	.	.	0.0004	0.0004	0.53	0.0002	0.0005	0.0021	0.0009	0.19
1	NCS HS49723-4	6.29	(0.0010)	.	.	0.020	(0.016)	0.428	(0.0068)	.	0.286	.	0.271
2	NH AM60TC-97	6.26	0.0012	.	.	0.0082	0.0055	0.442	0.0016	0.0051	0.0181	0.0060	0.18
2	NH AM60T-02	6.14	0.0019	.	.	0.0052	0.0040	0.356	0.0021	0.0040	0.0069	0.0031	0.102
2	NH K2-87	6.14	0.0012	.	.	0.0040	0.0129	0.165	0.0016	.	0.018	.	0.32
1	NCS HS49723-1	6.10	(0.0020)	.	.	0.0029	(0.039)	0.92	0.0012	.	0.034	.	0.057
2	NH AM60TC-00	6.02	0.0014	.	.	0.0052	0.0038	0.363	0.0021	0.0035	0.0063	0.0038	0.095
2	NH LT60-04	6.01	0.0012	0.0001	0.0025	0.0076	0.0044	0.34	0.0013	0.0024	0.0206	0.0024	0.15
1	NCS HS49722-1	5.96	(0.00024)	.	.	0.0035	0.0070	0.020	0.00094	.	0.097	.	0.0068
2	NH AM60TC-99	5.92	0.0018	.	.	0.0053	0.0026	0.489	0.0020	0.0031	0.0049	0.0030	0.148
1	NCS HS49724-2	5.82	0.00018	.	.	0.0016	0.0077	0.095	0.0012	.	1.54	.	0.128
2	NH AZ61-Y91	5.56	0.0006	.	.	0.0116	0.0053	0.355	0.0107	.	0.087	.	0.476
2	NH AM5002-91	4.92	0.0004	.	.	0.0121	0.0068	0.189	0.0022	.	0.0722	.	0.054
2	NH AZ61-L91	4.92	0.0004	.	.	0.0020	0.0044	0.502	0.0038	.	0.027	.	0.112
2	NH A8-L-02	4.73	0.0004	.	<0.0001	0.0010	0.0032	0.43	0.0003	0.0009	0.0040	0.0002	0.206
2	NH AM60LC-99	4.64	0.0004	.	.	0.0011	0.0158	0.115	0.0007	0.0009	0.0033	0.0011	0.0043
1	NCS HS49723-5	4.57	0.0009	.	.	0.013	0.025	(0.65)	0.0025	.	0.239	.	0.105
1	NCS HS49724-4	4.37	0.0009	.	.	0.103	0.022	0.33	0.0038	.	1.22	.	0.25
2	NH AS4100-90	4.37	0.0004	.	.	0.252	0.0117	0.144	0.0228	.	0.29	.	0.114
1	65X MgAl7	4.20	.	0.021	0.0049	0.0215	0.0069	0.203	0.0141	0.009	0.33	0.0050	0.128
2	NH A4-T-05	4.09	0.0014	0.0002	0.0018	0.0070	0.0049	0.397	0.0015	0.0023	1.18	0.0020	0.205
2	NH ALC-98	4.04	0	.	.	0.0004	0.0006	0.422	0.0002	0.0003	0.0004	0.0002	0.004
2	NH ALC-92	3.94	0	.	.	0.0005	0.0009	0.46	0.0004	0.0020	0.0054	0.0021	0.0080
1	65X M9B4	3.86	0.0033	0.0010	0.00016	0.0183	(0.009)	0.031	0.0003	0.0037	0.037	0.0050	0.333
1	NCS HS49724-1	3.69	0.00011	.	.	0.0084	0.0070	0.59	0.0012	.	0.54	.	0.102
2	NH A60-L-00	3.62	0.0003	0.0001	<0.00005	0.0044	0.0123	0.105	0.0005	0.0007	0.0054	0.0008	0.0103
2	NH K1-B-87	3.20	0.0016	.	.	0.0030	.	0.109	0.0007	.	0.014	.	0.107
2	NH K1-A-87	3.19	0.0019	.	.	0.0031	.	0.110	0.0006	.	0.014	.	0.105
2	NH A8-L98	2.62	0.0005	.	.	0.0009	0.0019	0.50	0.0012	0.0016	0.0070	0.0009	0.10
1	NCS HS49724-5	2.58	0.0012	.	.	0.039	0.033	0.23	0.014	.	1.83	.	0.152
1	NCS HS49723-2	2.55	0.0009	.	.	0.0081	0.0089	0.338	0.0008	.	0.173	.	0.237
2	AA C8209	2.55	.	.	.	0.012	(0.02)	0.15	0.001	.	0.058	.	0.18
2	NH AS2100-90	2.28	0.0008	.	.	0.045	0.0058	0.273	0.0028	.	1.08	.	0.206
2	AA C8211	2.07	.	.	.	0.033	(0.02)	0.20	0.007	.	0.090	.	0.23
2	NH AM2002-91	1.99	0.0009	.	.	0.0235	0.0036	0.440	0.0011	.	0.0831	.	0.088
2	NH AJ20-B-03	1.92	0.0029	0.0002	0.0136	0.0098	0.0096	0.108	0.0028	0.0085	0.057	0.0065	0.023
2	NH AJ20-A-03	1.91	0.0033	0.0002	0.0137	0.0099	0.0099	0.109	0.0028	0.0086	0.057	0.0065	0.023
1	NCS HS49723-6	1.36	0.0033	.	.	0.010	0.0049	0.130	0.010	.	0.065	.	0.492
2	NH A31-L91	1.19	0.0003	.	.	0.0037	0.0041	0.408	0.0007	.	0.020	.	0.202
1	NCS HS49724-3	1.09	(0.0005)	.	.	0.16	(0.004)	(0.50)	(0.0013)	.	0.68	.	0.339
1	NCS HS49725-6	(1.06)	.	.	.	0.025	0.020	0.148	0.0052	0.018	0.020	.	0.025
2	NH K0-87	1.03	0.0005	.	.	0.0022	0.0043	0.489	0.0005	0.0005	0.0076	.	0.050
2	NH AJ10-03	0.97	0.0001	0.0005	<0.00003	0.0005	0.0165	0.013	0.0002	0.0005	0.003	0.0001	0.010
1	NCS HS49725-2	(0.531)	.	.	.	0.0077	0.027	0.085	0.011	0.037	0.062	.	0.047

Number	Ag	Ce	Hg	K	La	Na	Sr	Ti	Zr	mm Ø x mm H
NCS HS49722-5	45 x 25
65X MgAl5	0.030	0.0069	0.011	.	0.0048	50x20 or 40x15
AA D3738	62 x 6
NH STD1-85	60 x 15
65X M9A5	0.0050	0.0004	(0.001)	.	50x20 or 40x15
NCS HS49723-3	45 x 25
NH AM60HC-99	60 x 15
NH A91-L-00	60 x 15
NCS HS49723-4	45 x 25
NH AM60TC-97	60 x 15
NH AM60T-02	60 x 15
NH K2-87	60 x 15
NCS HS49723-1	45 x 25
NH AM60TC-00	60 x 15
NH LT60-04	.	.	.	0.0002	.	0.0004	.	.	.	60 x 15
NCS HS49722-1	45 x 25
NH AM60TC-99	60 x 15
NCS HS49724-2	45 x 25
NH AZ61-Y91	60 x 15
NH AM5002-91	60 x 15
NH AZ61-L91	60 x 15
NH A8-L-02	60 x 15
NH AM60LC-99	60 x 15
NCS HS49723-5	45 x 25
NCS HS49724-4	45 x 25
NH AS4100-90	60 x 15
65X M9A17	0.0064	50x20 or 40x15
NH A4-T-05	.	.	.	0.0002	.	0.0006	.	.	.	60 x 15
NH ALC-98	60 x 15
NH ALC-92	60 x 15
65X M9B4	0.0046	0.0003	.	.	(0.0001)	.	.	(0.0008)	<0.001	40 x 18
NCS HS49724-1	45 x 25
NH A60-L-00	.	.	.	0.0001	.	0.0004	.	.	.	60 x 15
NH K1-B-87	60 x 15
NH K1-A-87	60 x 15
NH A8-L98	60 x 15
NCS HS49724-5	45 x 25
NCS HS49723-2	45 x 25
AA C8209	62 x 6
NH AS2100-90	60 x 15
AA C8211	62 x 6
NH AM2002-91	60 x 15
NH AJ20-B-03	.	.	.	<0.0001	.	0.017	0.17	.	.	60 x 15
NH AJ20-A-03	.	.	.	<0.0001	.	0.016	0.17	.	.	60 x 15
NCS HS49723-6	45 x 25
NH A31-L91	60 x 15
NCS HS49724-3	45 x 25
NCS HS49725-6	0.0025	.	45 x 25
NH K0-87	60 x 15
NH AJ10-03	.	.	.	<0.0001	.	0.0003	0.008	.	.	60 x 15
NCS HS49725-2	(0.00018)	.	45 x 25

RM MAGNESIUM with ALUMINUM and STRONTIUM

60 mm Ø x 15 mm

Number	Al	Mn	Sr	Zn	Ba	Be	Ca	Cd	Cu	Fe	K	Na	Ni	Pb	Si	Sn
NH AJ85-03	8.55	0.351	5.17	0.43	.	0.0019	0.148	<0.00003	0.0160	0.0012	<0.0001	0.0130	0.0121	0.0156	0.072	0.0140
NH AJ73-03	7.24	0.384	3.08	0.306	.	0.0015	0.075	0.0009	0.0071	0.0071	<0.0001	0.0163	0.0018	0.0022	0.029	0.0020
NH AJ52-A-03	4.92	0.14	1.91	0.20	0.0030	0.0006	0.0026	0.0041	0.0038	0.0056	0.0003	0.037	0.0006	0.0020	0.009	0.0013
NH AJ52-B-03	4.91	0.14	1.90	0.20	0.0030	0.0006	0.0027	0.0041	0.0038	0.0054	0.0004	0.040	0.0005	0.0019	0.009	0.0013
NH AJ52-C-03	4.90	0.14	1.92	0.20	0.0029	0.0005	0.0027	0.0041	0.0039	0.0059	0.0004	0.048	0.0006	0.0019	0.009	0.0014
NH AJ41-03	4.24	0.49	1.49	0.079	.	0.0009	0.033	0.0052	0.0009	0.0015	<0.0001	0.0009	0.0007	0.0054	0.11	0.0034
NH AJ31-03	2.80	0.20	0.84	0.034	0.0015	0.0004	0.012	0.0022	0.0320	0.0044	0.0005	0.006	0.0199	0.0050	0.006	0.0043

MAGNESIUM with MANGANESE

= class, where 1 = CRM and 2 = RM

#	Number	Mn	Al	Cu	Fe	Ni	Pb	Si	Sn	Zn
1	63X MgE3	2.36	0.015	0.012	0.004	0.0023	0.005	(0.009)	0.0055	0.022
2	NH M12-X91	2.18	0.094	0.0271	0.0015	0.0050	0.0169	0.0128	0.0457	0.251
2	AA C8096	1.88	(0.1)	(0.04)	.	(0.003)	.	(0.05)	.	(0.1)
2	AA SMD3A	1.69	0.08	0.032	.	0.002	.	0.034	.	0.058
2	AA C8095	(1.6)	0.17	0.012	.	0.005	.	0.052	.	0.029
1	63X MgE2	1.47	0.07	0.02	0.02	0.005	0.007	0.01(5)	0.01	0.02
2	AA C8016	(1.3)	0.03	0.070	.	0.011	.	0.064	.	0.11
2	AA C7857	1.07	(0.1)	(0.03)	.	(0.001)	.	(0.05)	.	(0.1)

Number	Ag	Be	Ca	Cd	Ti	Zr	mm Ø x mm H	
63X MgE3	0.0048	.	0.13	0.0009	<0.001	<0.001	50x20 or 40x15	not for Glow Discharge OES only
NH M12-X91	.	0.0003	60 x 15	
AA C8096	62 x 6	
AA SMD3A	62 x 6	
AA C8095	62 x 6	
63X MgE2	.	.	0.01	.	.	<0.002	40 x 15	
AA C8016	62 x 6	
AA C7857	62 x 6	

MAGNESIUM with ZINC

= class, where 1 = CRM and 2 = RM

#	Number	Zn	Ag	Al	Be	Ca	Cu	Fe	Mn	Ni	Pb	Si	Sn	Sr	Zr	mm Ø x mm H
1	66X MgC4	6.81	0.0074	0.039	(0.0001)	(<0.001)	0.0024	0.006	0.166	0.0009	0.0030	0.06	0.021	(0.00014)	<0.001	50x20 or 40x15
1	66X MgD5	6.25	0.044	0.040	<0.0005	(0.030)	2.88	0.008	0.307	0.0120	0.097	0.134	0.104	.	.	50x20 or 40x15
1	66X MgC3	4.97	0.001	0.011	(0.0002)	.	0.009	(0.001)	0.020	0.006	0.003	(0.003)	<0.002	.	0.13	40 x 15
2	AA C7510	3.04	.	.	0.11	.	0.019	.	.	0.001	62 x 6
2	AA SML76	(3.0)	.	0.19	.	.	(0.03)	.	(0.2)	.	.	(0.1)	.	.	.	62 x 6
2	AA SML75	(2.0)	.	0.21	.	.	(0.03)	.	(0.2)	.	.	(0.1)	.	.	.	62 x 6
2	66X MgD2	1.13	.	0.30	.	<0.005	0.08	0.014	0.74	0.008	0.012	0.07	0.011	.	<0.01	40 x 15

RM JEWELRY INDIVIDUAL XRF SAMPLES

analysis listed in mass % FLX 0740: 2mm Ø mounted in 36mm Ø x 10mm others: 3mm Ø mounted in 36mm Ø x 10mm

Number	Ag	Au	Cu	Fe	Ir	Ni	Pd	Pt	Rh	Ru	W	Zn
FLX 0720	.	99.99	0.002	.	0.002	.	0.002	0.002	0.002	.	.	.
FLX 0719	.	99.94	0.06
FLX 0701	4.59	91.76	3.65
FLX 0702	4.60	90.12	5.28
FLX 0743	.	80.07	1.12	.	.	14.35	4.46
FLX 0703	4.18	75.14	4.93	.	.	.	15.75
FLX 0708	.	75.12	17.47	.	.	5.81	1.60
FLX 0726	10.16	75.11	14.73
FLX 0728	4.79	75.1	20.11
FLX 0727	8.98	75.07	15.95
FLX 0724	15.07	75.05	9.88
FLX 0725	12.54	75.03	12.43
FLX 0704	2.75	75.03	9.74	.	.	.	12.48
FLX 0705	10.09	75.03	4.83	.	.	.	10.05
FLX 0707	2.75	75.02	15.13	.	.	5.04	2.06
FLX 0706	13.13	75.0	5.42	.	.	.	6.45
FLX 0710	30.94	59.06	3.48	.	.	.	6.52
FLX 0709	21.93	59.02	4.05	.	.	.	15.0
FLX 0903	4.32	58.69	36.99
FLX 0904	13.77	58.65	27.58
FLX 0738	19.7	58.65	19.22	2.43
FLX 0905	25.06	58.64	14.92	1.38
FLX 0715	.	58.64	26.18	.	.	6.09	9.09
FLX 0736	33.01	58.61	7.89	0.49
FLX 0712	27.36	58.59	4.05	.	.	.	10.0
FLX 0735	6.65	58.58	31.08	3.69
FLX 0739	33.39	58.53	8.08
FLX 0729	29.42	58.52	12.06
FLX 0711	10.72	58.49	26.47	4.32
FLX 0713	4.84	58.47	24.91	.	.	8.39	3.39
FLX 0714	.	58.44	41.31	0.25
FLX 0744	26.84	55.37	10.09	.	.	.	6.49	1.21
FLX 0737	6.15	38.35	46.89	8.61
FLX 0716	15.09	37.63	37.97	9.31
FLX 0731	54.31	37.52	8.17
FLX 0732	58.75	33.71	7.54
FLX 0734	6.3	33.65	50.28	9.77
FLX 0718	6.21	33.56	49.69	10.54
FLX 0717	11.92	33.52	41.04	13.52
FLX 0742	0.005	.	99.99	0.005
FLX 0740	.	.	0.005	.	0.09	.	.	.	99.90	0.005	.	.
FLX 0722	0.02	.	0.02	99.95	0.01	.	.	.
FLX 0741	.	.	4.16	95.84
FLX 0902	95.37	.	.	4.63	.
FLX 0901	95.23	.	4.77	.	.
FLX 0723	.	.	0.01	0.01	.	.	99.96	0.01	0.01	.	.	.
FLX 0721	99.97	.	0.008	.	0.005	.	0.005	0.007	0.005	.	.	.
FLX 0730	93.56	.	6.44
FLX 0733	83.75	.	16.25

Number	Ag	Au	Cu	Fe	Ir	Ni	Pd	Pt	Rh	Ru	W	Zn
--------	----	----	----	----	----	----	----	----	----	----	---	----

CRM JEWELRY XRF SET

analysis listed in mass % each sample is 0.1 mm x 8 mm x 18 mm

Number	Comment	Au	Ag	Cu	Ni	Zn
NCS HC54902	Silver	.	99.994	.	.	.
NCS HC54903	Copper	.	.	99.99	.	.
NCS HC54901	Gold	99.994
NCS HC54904	Gold	99.60	0.203	0.207	.	.
NCS HC54905	Gold	98.98	0.517	0.508	.	.
NCS HC54906	Jewelry Gold	97.99	1.02	1.02	.	.
NCS HC54907	Jewelry Gold	96.00	1.96	2.03	.	.
NCS HC54918	Jewelry Gold	91.69	3.31	3.40	0.522	1.02
NCS HC54908	Jewelry Gold	91.68	4.14	4.14	.	.
NCS HC54909	Jewelry Gold	85.00	7.45	7.51	.	.
NCS HC54919	Jewelry Gold	83.20	6.81	6.91	1.03	1.99
NCS HC54910	Jewelry Gold	78.99	5.97	15.03	.	.
NCS HC54920	Jewelry Gold	75.00	14.86	4.01	2.04	4.00
NCS HC54911	Jewelry Gold	74.99	14.95	10.02	.	.
NCS HC54912	Jewelry Gold	70.00	10.00	19.97	.	.
NCS HC54921	Jewelry Gold	66.60	3.35	19.96	4.04	6.05
NCS HC54913	Jewelry Gold	64.99	24.92	10.02	.	.
NCS HC54914	Jewelry Gold	58.50	11.50	29.99	.	.
NCS HC54922	Jewelry Gold	54.99	26.89	15.97	1.51	0.516
NCS HC54915	Jewelry Gold	49.98	9.98	39.85	.	.
NCS HC54916	Jewelry Gold	44.02	35.01	20.91	.	.
NCS HC54923	Jewelry Gold	41.59	20.50	31.84	3.00	2.98
NCS HC54917	Jewelry Gold	37.50	7.56	55.06	.	.
NCS HC54924	Jewelry Gold	35.00	9.01	40.01	8.00	7.94

CRM JEWELRY XRF SET

analysis listed in mass % thin layer on 30 mm Ø disc

Number	Ag	Au	Cu	Ni	Pd	Zn
IMN Au 1	66.59	33.32
IMN Au 2	44.67	33.36	21.98	.	.	.
IMN Au 3	10.56	37.02	20.10	.	32.49	.
IMN Au 4	19.98	37.05	10.53	32.45	.	.
IMN Au 5	25.07	37.15	23.84	8.96	.	4.92
IMN Au 6	12.54	49.97	12.53	.	24.96	.
IMN Au 7	27.71	57.89	.	.	14.44	.
IMN Au 8	7.65	59.03	11.97	14.57	.	6.78
IMN Au 9	.	57.84	15.31	16.98	.	9.74
IMN Au 10	.	74.84	9.63	12.90	.	2.60
IMN Au 11	.	74.96	.	15.06	9.99	.
IMN Au 12	.	74.99	.	24.96	.	.
IMN Au 13	2.97	91.72	5.28	.	.	.
IMN Au 14	.	96.02	4.01	.	.	.
IMN Au 15	.	98.60	1.40	.	.	.
IMN Au 16	.	99.99

RM SILVER AND SILVER ALLOYS

analysis listed in mg/kg

131X: RM, mounted in bakelite, 25 mm Ø x 3 mm

IMN: CRM, 40 mm Ø x ~15-20 mm

Number	Cu	As	Au	Bi	Cd	Fe	Ga	In	Ir	Mn	Ni	Pb	Pd	Pt	Sb	Se	Si	Sn	Te	Tl	Zn
131X PAG2	400	8	20	12	5	7	15	.	<1	10	9	12	180	10	12	10	4	14	15	.	550
131X PAG1	75	12	120	40	35	5	60	.	<1	35	25	40	180	35	50	35	30	40	120	.	50
IMN SH1	309	46.5	38.9	44.9	29.7	19.9	.	49.2	.	1.1	1.9	2.6	1.6	1.1	1.6	47.6	.	.	0.95	0.89	2.9
IMN SH2	182	27.2	23.2	28.2	23.3	13.5	.	30.3	.	82.1	12.5	26.0	8.5	9.5	25.1	27.4	.	.	8.6	9.3	22.3
IMN SH3	59.0	11.0	7.7	9.2	9.6	11.3	.	8.7	.	27.3	29.7	44.9	25.7	25.4	48.6	8.7	.	.	25.7	25.8	43.8
IMN SH4	12.3	1.8	1.7	1.4	2.2	28.5	.	(1.3)	.	45.3	51.4	81.1	42.6	42.7	80.0	1.1	.	.	42.3	42.4	95.9
131X AGP1	522	308	529	485	.	150	.	.	.	242	.	465	517	514	465	287	.	489	483	.	312
131X AGP2	137	48	138	113	.	73	.	.	.	20	.	112	130	127	93	68	.	129	121	.	77
131X AGP3	44	19	36	29	.	46	.	.	.	12	.	31	32	32	24	17	.	26	30	.	20
131X AGP4	20	5	10	6	.	24	.	.	.	2	.	5	8	10	5	6	.	<1	7	.	7
Number	Cu	As	Au	Bi	Cd	Fe	Ga	In	Ir	Mn	Ni	Pb	Pd	Pt	Sb	Se	Si	Sn	Te	Tl	Zn

RM SILVER ALLOYS

mounted in bakelite 25 mm Ø x 3 mm

Number	Au%	Cu%	Pb%
133X AGQ3	2.007	9.760	0.970
133X AGQ2	0.938	5.761	0.472
133X AGQ1	0.237	2.493	0.267

RM SILVER BINARY SET

set 133X AGB (1-3) only 40 mm Ø x 10 mm

Number	Ag%	Cu%
133X AGB95	94.40	5.13
133X AGB92	91.68	8.04
133X AGB88	87.60	12.26

CRM		TIN																				
		cast															analysis listed in mass % except * which is mg/kg			40 mm Ø x 15 mm		
Number	Ag	Al	As	Au	Bi	Cd	Cu	Fe	In	Ni	Pb	Sb	Te	Zn	Hg	Ga*	S*	Se*				
71X SR3	0.050	(0.0014)	0.097	0.0145	0.123	0.100	0.121	0.0203	0.104	0.0371	0.306	0.128	0.070	0.054	0.115	339	.	31				
71X SR2	0.0209	0.0010	0.043	0.0084	0.060	0.0435	0.060	0.0160	0.055	0.0192	0.112	0.061	0.030	0.007	0.144	166	(23)	97				
71X SR1	0.0121	(0.0016)	0.0102	0.0014	0.0107	0.0104	0.0111	(0.0021)	0.0120	0.0041	0.0324	0.0156	0.0112	0.0146	0.0142	49	.	(15)				
71X SR0	0.0018	0.0197	0.0008	0.0007	(0.0025)	0.0015	0.0013	0.0008	0.0047	0.0004	0.0113	0.0034	0.0009	0.0034	0.0044	27	.	5				

RM		TIN										typical analysis listed in mass %						
Number	Sn	C	Cu	Fe	Ni	Pb	Zn	Melting Pt. °C	Units									
BCS 192g	99.997	0.001	0.00007	0.0002	0.00005	0.00007	0.00006	231.9	300 g block (9.5 x 2.5 x 2 cms) or 100 g chips									

CRM		SPECIALTY TIN BASE LOW-LEAD and LEAD-FREE SOLDERS																								
		cast										analysis listed in mass % except * which is mg/kg					74X GE: 38 mm Ø x ~13 mm					all others: 40 mm Ø x 15 mm				
Number	Ag	Cu	Sb	As	Bi	Cd	Fe	Ni	Pb	Zn	Al	Au	Hg	In*	P	S*	Se									
74X CA7	4.21	0.333	0.0103	0.0095	0.0081	0.0045	0.0047	0.0007	0.0965	.	.	.	0.053	26	0.003	.	.									
74X CA5	4.00	1.094	0.133	0.0353	0.0207	0.0025	0.0019	0.0147	0.0116	0.0009	0.0003	0.0049	0.0006	111	0.0108	6	0.003									
74X CA2	3.49	0.782	0.0734	0.0100	0.0329	0.0010	0.0021	0.0308	0.0331	0.0003	0.0002	0.0014	0.0007	62	0.0055	.	0.0015									
74X CA4	3.02	0.502	0.039	0.0094	0.061	0.00075	0.0043	0.0542	0.080	(0.0011)	(0.0019)	.	Co:0.0085	41	(0.0014)	.	0.0027									
74X HA	2.66	0.612	2.06	0.0020	0.061	0.0008	0.009	0.0108	0.084	2.69	0.0185	.	.	.	(0.0024)	.	(0.0005)									
74X CA8	2.44	0.947	0.0045	0.0100	0.0032	0.0103	0.0037	0.0007	0.0403	.	.	.	0.101	41	0.0077	.	.									
74X E	0.656	3.14	0.060	0.061	0.0170	0.0029	(0.004)	0.0116	0.0146	(0.002)	(0.002)	.	.	.	0.0029	.	0.0031									
74X AM	0.562	2.97	1.06	0.045	0.175	0.0072	(0.016)	0.0203	0.119	(0.002)	(0.008)	.	.	.	0.018	.	0.0115									
74X CA1	0.440	0.682	0.0169	.	0.0131	0.0071	.	0.077	0.077	.	0.0262	0.0053									
74X WS	0.298	4.58	1.49	0.0105	0.0063	0.00140	(0.0036)	0.0048	0.037	0.0009	(0.0007)	(0.0002)	.	32	0.0122	.	.									
74X CA6	0.282	0.629	0.0078	0.0086	0.008	0.00033	0.0061	0.0194	0.0176	0.0006	0.0006	0.0106	0.0064	218	0.0046	.	0.0007									
74X HN	0.143	3.82	0.037	0.010	0.122	0.0057	0.010	0.185	0.0404	(0.0009)	0.005	.	.	.	(0.002)	.	0.0016									
74X OA	0.100	3.41	0.0098	0.080	1.065	0.00063	0.007	0.0025	0.128	(0.002)	(0.0007)	(0.0001)	.	34	0.0072	.	.									
74X GE2	0.079	0.713	.	.	.	0.0086	.	0.031	0.0467	.	0.068	Ge:0.479									
74X HB	0.070	4.56	5.40	0.028	(0.007)	0.0095	0.014	1.27	0.036	0.0117	0.0014	.	.	.	(0.002)	.	<0.001									
74X GE1	0.052	0.662	.	.	.	0.0059	.	0.0289	0.0339	.	0.065	Ge:0.046									
74X TC	0.0110	4.95	0.045	0.026	0.036	0.0145	(0.054)	0.0034	0.164	0.0097	0.0010	.	.	.	(0.029)	.	0.092									
74X BZ1	0.004	0.026	0.031	0.0119	3.03	0.0012	0.011	0.0097	0.0238	8.27	0.0021									

TIN ALLOYS

cast		# = class, where 1 = CRM and 2 = RM															40 mm Ø x 15 mm		
#	Number	Sb	Cu	Pb	Ag	Al	As	Bi	Cd	Co	Fe	In	Ni	P	S	Zn			
1	73X SC7	14.01	6.51	0.356	0.006	0.001	0.047	0.009	0.0018	0.0160	0.046	0.014	0.008	.	(0.001)	(0.003)			
1	73X SC11	12.01	11.18	0.061	0.066	0.0025	0.292	0.560	1.75	.	0.011	.	0.452	0.019	.	0.063			
1	73X SC8	9.65	3.89	0.037	(0.0015)	0.004	0.121	0.037	0.133	0.017	0.073	0.017	0.014	.	(0.011)	(0.008)			
1	73X SC9	8.18	8.47	0.20	0.004	<0.001	0.53	0.066	0.078	0.0030	0.037	0.010	0.008	.	(0.008)	(0.003)			
1	73X SC12	8.05	7.72	0.024	0.83	<0.002	0.024	0.020	0.625	.	0.051	.	0.384	.	.	0.020			
1	73X SC5	7.03	0.57	0.136	0.063	0.003	0.013	0.43	0.008	0.011	0.004	0.036	0.0058	.	(0.001)	0.001			
1	73X SC4 A	6.02	3.05	0.514	0.042	0.005	0.005	0.218	0.052	0.0035	0.011	0.011	0.017	.	(0.003)	0.008			
1	73X SC4	5.94	2.63	0.429	0.0525	(0.0015)	0.0268	0.153	0.0085	0.0020	0.0014	0.0143	0.0130	0.005	.	(0.0010)			
2	72X SA6R	6.0	0.10	0.25	.	.	0.050	0.25	0.01	.	0.050	.	.	.	0.01	0.02			
2	72X SA5R	5.04	0.009	0.067	.	.	0.042	0.01	0.022	.	0.01	0.002			
1	73X SC3	4.60	0.222	0.040	0.013	0.001	0.029	0.020	0.024	0.006	0.017	0.031	0.0136	.	(0.002)	0.001			
2	72X SA4R	4.0	0.020	0.080	.	.	0.030	0.10	0.003	.	0.10	0.007			
1	73X SC2	3.07	1.06	0.029	0.006	(0.002)	0.035	0.62	0.036	0.021	0.030	(0.002)	0.0048	.	<0.001	0.003			
1	73X SC1	1.48	2.02	0.067	0.010	0.002	0.008	0.084	0.006	<0.001	0.0025	0.008	0.0041	.	<0.002	0.003			
1	73X SC6	0.092	5.17	0.100	0.08	(0.003)	0.204	0.115	0.0125	0.0050	0.007	0.058	0.013	.	(0.004)	0.01			
1	71X PB4	0.0059	0.0014	4.00	0.0047	.	0.0045	(0.002)	0.0027	0.0063			
1	71X PB3	0.0024	0.0074	2.77	0.0011	.	0.0022	0.0103	0.0008	0.0016			

RM TIN ALLOYS

available individually		37 mm Ø x 12 mm									
Number	Type	Sb	Sn	Au	Cu	Ag	Al	As	Bi	In	Pb
NF 26	TL-50	.	50.0	Rem
NF 27	TL-55	.	55.0	Rem
NF 28	TL-60	.	60.0	Rem
NF 29	TL-65	.	65.0	Rem
NF 3	Solder	0.085	59.20	0.0045	0.0091	Rem
NF 4	Solder	0.29	60.40	0.010	0.050	Rem
NF 5	Solder	0.48	61.50	0.046	0.10	Rem
NF 6	Solder	0.11	62.50	0.10	0.25	Rem
NF 7	Solder	0.31	63.50	0.25	0.41	Rem
NF 8	Solder	0.52	64.50	0.49	0.49	Rem
NF 53	TA-12	12.4	Rem
NF 52	TA-10	10.1	Rem
NF 51	TA-8	8.00	Rem
NF 50	TA-5	5.10	Rem
NF 49	TA-3	3.10	Rem
NF 48	TA-2	2.00	Rem
NF 47	TA-1	1.00	Rem
NF 54-6	Pig tin	0.001	Rem	.	0.001	0.001	0.001	<0.01	0.000	0.001	0.007

RM BISMUTH AND SULPHUR IN TIN SETS

sold in sets only, as grouped certified analysis in bold, rest is nominal composition

37 mm Ø x 12 mm

Number	Bi	S	Ag	Al	As	Au	Cd	Cu	Fe	In	Ni	P	Pb	Sb	Sn	Zn
NF 59-1	0.008	<0.0006	3.98	<0.001	<0.01	<0.001	<0.001	0.51	0.005	0.006	0.001	<0.01	0.056	0.023	Rem	0.001
NF 59-2	0.008	0.0007	3.98	<0.001	<0.01	<0.001	<0.001	0.51	0.005	0.006	0.001	<0.01	0.056	0.023	Rem	0.001
NF 59-3	0.008	0.0048	3.98	<0.001	<0.01	<0.001	<0.001	0.51	0.005	0.006	0.001	<0.01	0.056	0.023	Rem	0.001
NF 59-4	0.008	0.0085	3.98	<0.001	<0.01	<0.001	<0.001	0.51	0.005	0.006	0.001	<0.01	0.056	0.023	Rem	0.001
NF 59-5	0.008	0.020	3.98	<0.001	<0.01	<0.001	<0.001	0.51	0.005	0.006	0.001	<0.01	0.056	0.023	Rem	0.001
NF 60-1	2.01	<0.001	0.001	<0.001	<0.01	<0.001	<0.001	0.001	<0.001	0.005	<0.001	<0.01	Rem	0.005	60	<0.001
NF 60-2	2.39	<0.001	0.001	<0.001	<0.01	<0.001	<0.001	0.001	<0.001	0.005	<0.001	<0.01	Rem	0.005	60	<0.001
NF 60-3	3.00	<0.001	0.001	<0.001	<0.01	<0.001	<0.001	0.001	<0.001	0.005	<0.001	<0.01	Rem	0.005	60	<0.001
NF 60-4	3.99	<0.001	0.001	<0.001	<0.01	<0.001	<0.001	0.001	<0.001	0.005	<0.001	<0.01	Rem	0.005	60	<0.001

CRM TIN BASE SETS

available in sets only, as grouped

Number	As	Bi	Cd	Cu	Fe	Ni	Pb	Sb	Sn	Zn	
IMN L89 1	0.019	0.012	0.19	3.20	0.18	0.010	0.072	5.66	Rem	0.099	Bearing Alloy, Rods 10 mm Ø x 100 mm
IMN L89 2	0.037	0.026	0.091	4.15	0.086	0.031	0.13	6.39	Rem	0.059	
IMN L89 3	0.065	0.052	0.041	3.49	0.058	0.090	0.29	7.41	Rem	0.042	
IMN L89 4	0.12	0.099	0.021	2.81	0.028	0.16	0.52	8.14	Rem	0.020	
IMN L89 5	0.18	0.20	0.011	2.12	0.013	0.33	1.11	8.86	Rem	.	
IMN L89 6	0.029	0.014	0.19	4.51	0.17	0.014	0.20	8.03	Rem	0.096	
IMN LA 1	0.012	0.014	1.41	2.45	0.012	0.011	3.18	6.79	Rem	0.0016	Bearing Alloy, Discs 40 mm Ø x 25 mm
IMN LA 2	0.092	0.033	0.88	3.84	0.018	0.094	2.17	7.81	Rem	.	
IMN LA 3	0.24	0.059	0.50	8.13	0.059	0.28	1.19	10.22	Rem	0.0095	
IMN LA 4	0.43	0.085	0.096	6.95	0.080	0.45	0.41	11.66	Rem	.	
IMN LA 5	0.54	0.099	0.011	5.45	0.096	0.53	0.070	13.58	Rem	0.020	
IMN L 1	0.051	0.17	0.0020	0.11	.	.	Rem	0.52	56.06	0.00093	Solder, Discs 40 mm Ø x 30 mm
IMN L 2	0.034	0.11	0.0043	0.075	(0.011)	.	Rem	0.35	59.09	0.0019	
IMN L 3	0.092	0.22	0.0065	0.034	(0.023)	.	Rem	0.14	60.18	0.0064	
IMN L 4	0.017	0.055	0.0080	0.013	(0.0085)	.	Rem	0.079	62.81	0.0011	
IMN L 5	0.0035	0.014	0.0097	0.0037	.	.	Rem	0.011	64.96	0.0056	

RM TIN BASE SETS

sold in sets only, as grouped

37 mm Ø x 12 mm

Number	Ag	As	Bi	Cd	Cu	Fe	Ge	Hg	In	Ni	P	Pb	Pd	Sb	Sn	Zn
NF 10-1	Rem	0.01	.	60	.
NF 10-2	Rem	0.05	.	60	.
NF 10-3	Rem	0.10	.	60	.
NF 10-4	Rem	0.25	.	60	.
NF 14-1	0.0050	Rem	.	.	63.0	.
NF 14-2	0.009	Rem	.	.	63.0	.
NF 14-3	0.02	Rem	.	.	63.0	.
NF 45-1	.	0.03	0.10	0.015	0.015	<0.01	0.04	.	4.0	Rem	<0.1
NF 45-2	.	0.02	0.005	0.005	0.003	<0.01	0.05	.	5.0	Rem	<0.1
NF 45-3	.	0.05	0.25	0.03	0.08	<0.01	0.20	.	6.0	Rem	<0.1
NF 58-1	0.32	.	0.12	.	0.69	.	.	0.0003	.	.	0.001	0.085	.	.	Rem	.
NF 58-2	0.21	.	0.095	.	0.79	.	.	0.0024	.	.	0.006	0.008	.	.	Rem	.
NF 58-3	0.51	.	0.077	.	0.59	.	.	0.0043	.	.	0.010	0.040	.	.	Rem	.
NF 63-1	0.74	.	.	.	0.077	.	0.079	.	0.200	0.068	.	0.009	.	.	Rem	.
NF 63-2	1.02	.	.	.	0.104	.	0.052	.	0.005	0.027	.	0.18	.	.	Rem	.
NF 63-3	1.18	.	.	.	0.53	.	0.005	.	0.053	0.066	.	0.024	.	.	Rem	.
NF 63-4	1.50	.	.	.	0.194	.	0.025	.	0.027	0.12	.	0.012	.	.	Rem	.
NF 63-5	1.01	.	.	.	0.51	.	0.010	.	0.11	0.065	.	0.018	.	.	Rem	.
NF 63-6	2.56	.	.	.	0.50	.	0.042	.	<0.001	0.0073	.	0.009	.	.	Rem	.
NF 56-1	2.54	.	0.006	.	0.91	.	.	0.018	.	.	0.020	0.10	.	.	Rem	.
NF 56-2	3.77	.	0.50	.	0.60	.	.	0.0004	.	.	0.009	0.051	.	.	Rem	.
NF 56-3	3.53	.	.	.	0.4	.	.	0.014	.	.	0.003	0.009	.	0.50	Rem	.
NF 56-4	3.26	.	0.20	.	0.30	.	.	0.0045	.	.	0.021	0.22	.	.	Rem	.
NF 56-5	4.49	.	0.029	.	0.54	.	.	0.0024	.	.	0.006	0.26	.	.	Rem	.
NF 56-6	4.24	.	0.096	.	0.80	.	.	0.009	.	.	0.012	0.024	.	.	Rem	.
NF 57-1	3.00	.	0.004	.	0.49	.	.	0.0016	.	.	0.004	0.076	.	.	Rem	.
NF 57-2	4.01	.	.	.	0.46	.	.	0.0002	.	.	0.006	<0.001	.	.	Rem	.
NF 46-1	3	0.01	0.05	.	0.20	0.02	.	0.20	Rem	0.01
NF 46-2	4	0.02	0.10	.	0.10	0.05	.	0.10	Rem	0.0025
NF 46-3	5	0.05	0.25	.	0.03	0.10	.	0.05	Rem	0.005

Number	Ag	As	Bi	Cd	Cu	Fe	Ge	Hg	In	Ni	P	Pb	Pd	Sb	Sn	Zn
--------	----	----	----	----	----	----	----	----	----	----	---	----	----	----	----	----

RM TIN BASE SETS

sold in sets only, as grouped

37 mm Ø x 12 mm

Number	Ag	Al	As	Au	Bi	Cd	Co	Cu	Fe	In	Ni	Pb	Sb	Sn	Zn
NF 54-1	0.005	0.005	<0.1	.	0.002	0.0002	0.002	0.01	<0.1	0.005	0.002	0.03	0.005	Rem	<0.1
NF 54-2	0.01	0.01	<0.1	.	0.005	0.0005	0.005	0.05	<0.1	0.01	0.005	0.15	0.01	Rem	<0.1
NF 54-3	0.03	0.03	<0.5	.	0.01	0.001	0.01	0.15	<0.1	0.02	0.01	0.40	0.02	Rem	<0.1
NF 54-4	0.06	.	<0.5	.	0.02	0.005	0.02	0.30	<0.1	0.04	0.02	0.70	0.04	Rem	<0.1
NF 54-5	0.10	.	<0.75	.	0.035	0.01	.	0.50	.	0.08	.	1.0	0.08	Rem	<0.1
NF 1-1	0.0006	<0.1	<0.001	0.001	<0.001	0.0006	.	0.0005	<0.1	<0.001	<0.1	Rem	0.003	60.0	<0.1
NF 1-2	0.001	<0.1	0.001	0.005	0.005	0.002	.	0.001	<0.1	0.001	<0.1	Rem	0.02	62.0	<0.1
NF 1-3	0.005	<0.1	0.005	0.01	0.01	0.005	.	0.005	<0.1	0.01	<0.1	Rem	0.05	63.0	<0.1
NF 1-4	0.01	<0.1	0.015	0.02	0.02	0.01	.	0.01	<0.1	0.04	<0.1	Rem	0.10	65.0	<0.1
NF 2-1	0.015	<0.1	0.01	0.05	0.04	0.005	.	0.05	<0.1	0.005	0.001	Rem	0.10	63.0	<0.1
NF 2-2	0.03	<0.1	0.02	0.10	0.10	0.01	.	0.10	<0.1	0.015	0.005	Rem	0.30	63.0	<0.1
NF 2-3	0.10	<0.1	0.03	0.25	0.25	0.02	.	0.30	<0.1	0.03	0.01	Rem	0.50	63.0	<0.1
NF 61-1	1.54	Rem	.	62.0	.
NF 61-2	1.81	Rem	.	62.0	.
NF 61-3	2.33	Rem	.	62.0	.
NF 61-4	2.58	Rem	.	62.0	.
NF 9-1	3.00	.	.	.	0.048	.	.	0.073	.	.	.	Rem	0.51	59.90	.
NF 9-2	2.00	.	.	.	0.093	.	.	0.040	.	.	.	Rem	0.38	61.90	.
NF 9-3	1.00	.	.	.	0.25	.	.	0.010	.	.	.	Rem	0.23	63.60	.

CRM TITANIUM

= class, where 1 = CRM and 2 = RM

#	Number	Al	B	C	Co	Cr	Cu	Fe	H	Mn	Mo	N	Nb	Ni	O
1	IARM 311A	0.32	.	0.009	.	0.013	0.0013	0.060	0.0021	0.0013	0.0012	0.012	(0.002)	0.014	0.083
1	BS T-80	0.0746	0.0040	0.0166	0.0146	0.0050	0.0375	0.0093	0.0059	0.0244	0.0100	0.0041	0.0367	0.0156	0.0768
1	BCR 090	(0.074)	0.00282	.	0.0501	0.0533	0.0513	0.0563	.	0.0314	0.0488	.	(0.0492)	0.0667	.
1	BS T-81	0.0664	0.0082	0.0161	0.0395	0.0294	0.0244	0.1144	0.0035	0.0404	0.0279	0.0037	0.0191	0.0090	0.0669
1	BS T-4A	0.040	.	0.014	.	0.026	(0.001)	0.19	(0.0027)	0.003	0.0006	0.005	.	0.014	(0.37)
1	IARM 303A	0.008	.	0.011	.	0.021	(0.002)	0.051	0.0011	0.002	(0.001)	0.0069	<0.0005	0.022	0.134
1	IARM 312A	0.006	.	0.004	(0.001)	(0.002)	(0.002)	0.028	0.0049	(0.001)	(0.002)	0.0023	.	(0.002)	0.066
1	BS T-2A	0.005	.	(0.007)	.	0.018	(0.001)	0.156	(0.0020)	0.003	0.002	(0.0044)	.	0.021	(0.12)
1	IARM 174C	(0.003)	.	0.0057	(0.001)	0.009	0.0015	0.28	0.0027	0.0019	0.002	0.004	(0.004)	0.007	0.34
2	BS T-26	0.002	.	0.005	.	0.037	0.037	0.055	.	0.006	0.028	(0.005)	.	0.002	(0.069)

BCR: HIP; 090A: 40mm Ø x 20mm; 090B: ~25g of 0.2g cubes BS: 32mm Ø x 12mm IARM: 31mm Ø x 2 or 18mm

Number	P	Pd	Ru	S	Si	Sn	V	W	Y	Zr	Grade
IARM 311A	0.005	0.0020	0.004	(0.002)	(0.0002)	0.012	BT1-0
BS T-80	.	0.1424	0.0469	.	(0.0035)	0.0257	0.0446	0.0174	0.0010	0.0178	Ti Cp 11
BCR 090	(0.071)	(0.057)	(0.057)	.	.	(0.0436)	.
BS T-81	.	0.0398	0.0310	.	0.0474	0.0155	0.0186	0.0372	0.0017	0.0163	Ti Cp 17
BS T-4A	(0.001)	.	(0.0004)	.	0.011	0.005	(0.001)	<0.002	.	<0.002	Ti Cp 1
IARM 303A	.	0.139	.	.	0.004	<0.005	0.005	.	(0.0003)	(0.001)	Ti Cp 7
IARM 312A	.	(0.004)	.	(0.001)	0.006	0.0012	(0.002)	.	(0.0004)	(0.001)	Ti CP 4.1
BS T-2A	.	.	(0.0004)	.	0.002	0.006	<0.002	<0.002	.	<0.003	Ti Cp 1
IARM 174C	.	.	(0.0005)	(0.006)	0.023	(0.002)	.	(0.0004)	(0.003)	(0.003)	Ti CP 1.4
BS T-26	.	.	(0.001)	(0.01)	0.025	0.020	0.57	.	.	0.005	Ti 0.5W

RM TITANIUM ALLOY XRF SAMPLES

cast typical analysis XRF ONLY 32 mm Ø x 8 mm buttons

Number	Al	Cu	Fe	Mo	Nb	Pd	Si	Sn	V	Zr
101P 811	8.0	.	0.03	1.0	1.0	.
101P 6242	6.12	.	0.014	2.06	.	.	0.08	2.01	.	3.98
101P 6246	6.05	.	0.055	5.99	.	.	0.06	2.00	.	3.92
101P 685	6.0	.	0.03	0.5	.	.	0.3	.	.	5.0
101P 318	6.0	.	0.2	4.0	.
101P 367	6.0	.	0.1	.	7.0
101P 829	5.53	.	0.005	0.28	1.01	.	0.29	3.50	.	3.03
101P 550	4.09	.	0.036	4.18	.	.	0.41	2.09	.	.
101P 551	4.0	.	0.05	4.0	.	.	0.5	4.0	.	.
101P 679	2.42	.	0.018	1.07	.	.	0.22	11.08	.	4.92
101P 205	.	.	<0.01	15.3
101P 230	.	2.30	0.065
101P 260	.	.	0.05	.	.	0.15

TITANIUM ALLOYS

= class, where 1 = CRM and 2 = RM

* Provisional Analysis

#	Number	Al	Cr	Fe	Mn	Mo	Nb	Sn	V	W	Zr	C	H	N	O	S	
1	SRM 2062	30.31	10.78	.	.	4.38	
1	IARM 269A	7.79	0.010	0.133	(0.001)	1.02	<0.005	(0.01)	1.00	.	0.0010	0.015	0.0059	0.0039	0.104	(0.002)	
1	IARM 262A	7.1	0.007	0.21	0.007	4.18	.	(0.02)	0.011	.	<0.005	0.012	0.0072	0.008	0.094	(0.002)	
2	CT 6AL4V	6.39	.	0.14	4.01	
1	SRM 654b	6.34	0.025	0.23	.	0.013	.	0.023	4.31	.	0.008	.	(0.002)	.	(0.017)	(0.001)	
1	IARM 175C	6.33	0.054	0.34	0.0074	0.011	0.009	0.006	3.95	(0.002)	0.0027	0.014	0.0038	0.0081	0.150	.	
1	BS T-5A	6.33	0.013	0.170	<0.002	0.004	.	0.009	4.10	<0.01	0.003	0.011	(0.0028)	0.008	0.190	<0.001	
2	BS T-15	6.23	1.02	1.02	0.02	3.1	.	0.015	(0.01)	(0.52)	<0.002	0.007	.	(0.007)	(0.08)	(0.002)	
1	101X Ti3	6.14	0.0194	0.104	.	0.0213	.	0.0215	4.00	.	0.0152	0.0619	0.0034	0.010	0.198	.	
1	IARM 177C	6.02	0.012	0.033	0.0015	1.96	.	2.02	0.020	.	3.99	0.005	0.0014	0.0022	0.107	.	
1	101X Ti2	6.02	0.0054	0.053	.	2.08	.	2.05	.	.	3.97	0.016	0.0076	0.0053	0.143	.	
1	101X Ti6	5.99	0.0636	0.221	0.0623	0.063	0.0639	0.067	3.95	0.066	0.0653	0.0340	0.0043	0.0137	0.0171	0.0061	
1	BCR 089	5.97	.	.	0.029	.	.	.	3.976	
1	IARM 300A *	5.97	0.009	0.19	(0.001)	(0.001)	6.9	(0.01)	(0.01)	.	.	0.006	0.0019	0.004	0.16	.	
1	IARM 285A	5.81	(0.001)	0.037	(0.001)	0.77	2.00	(0.004)	(0.004)	(0.01)	(0.002)	0.007	0.0038	0.0043	0.076	(0.0004)	
1	IARM 178B	5.58	0.015	0.56	0.003	0.008	.	2.00	5.56	.	0.004	0.030	0.0028	0.008	0.157	(0.001)	
1	IARM 314A	5.50	3.09	0.46	0.002	4.78	.	(0.01)	4.98	.	0.002	0.008	0.004	0.0034	0.155	.	
1	101X Ti5	5.328	2.996	0.162	0.073	3.978	.	2.093	0.0779	0.084	2.093	0.089	0.0039	0.0148	0.172	0.0114	
1	IARM 271A	5.28	0.016	0.31	(0.002)	0.011	.	2.49	0.09	.	0.015	0.026	0.013	0.012	0.16	(0.002)	
2	BS T-14	4.94	1.98	1.90	0.02	1.72	.	0.03	0.013	0.48	(0.01)	(0.010)	.	0.006	(0.091)	(0.003)	
1	IARM 315A	4.58	0.016	0.065	0.008	0.008	.	0.004	1.84	.	0.0044	0.011	0.0016	0.0052	0.099	.	
1	IARM 280A	4.11	0.0055	0.044	(0.002)	4.01	(0.001)	2.07	0.023	.	(0.002)	0.005	0.0015	0.0014	0.19	(0.001)	
1	101X Ti4	3.95	0.0688	0.125	0.0653	0.301	0.070	0.072	0.044	0.072	0.0668	0.115	0.0050	0.0195	0.199	.	
1	IARM 286A	3.25	6.3	0.09	(0.002)	4.15	.	(0.003)	8.1	.	4.08	0.010	0.0039	0.010	0.089	(0.001)	
1	IARM 297A	3.12	0.007	1.86	0.007	0.004	(0.06)	0.006	9.71	.	(0.002)	0.014	0.0045	0.008	0.109	(0.001)	
1	SRM 1128	3.06	2.96	0.134	.	.	.	3.04	15.13	.	.	0.011	
1	101X Ti1	3.08	.	0.035	.	14.98	2.75	0.0417	.	0.0069	0.005	0.169	(0.0025)
1	IARM 261A	3.00	0.013	0.19	0.0011	(0.003)	.	0.008	2.48	.	(0.002)	0.007	0.0023	0.007	0.10	(0.001)	
1	SRM 643	.	.	.	11.6	
1	SRM 642	.	.	.	9.0	
1	SRM 641	.	.	.	6.6	
2	BS T-24	0.002	0.54	0.54	4.7	0.51	.	0.019	1.22	0.37	(0.001)	0.005	.	0.006	(0.09)	(0.002)	
2	BS T-23	0.003	0.91	0.93	3.70	0.91	.	0.025	0.93	0.87	(0.002)	0.006	.	(0.007)	(0.13)	(0.002)	
2	BS T-22	0.004	1.22	1.19	2.02	1.15	.	0.019	0.50	0.51	(0.01)	0.005	.	(0.01)	(0.09)	(0.002)	

#	Number	Al	Cr	Fe	Mn	Mo	Nb	Sn	V	W	Zr	C	H	N	O	S	
	Number	B	Co	Cu	Ni	P	Pd	Ru	Si	Ta	Ti	Y	Units				
	SRM 2062	53.92	24 mm Ø x 2 mm (thin)
	IARM 269A	.	.	0.003	0.010	.	.	.	0.080	31 mm Ø x 2 or 18 mm
	IARM 262A	0.001	.	.	0.006	(0.005)	.	.	0.047	.	.	(0.0004)	31 mm Ø x 2 or 18 mm
	CT 6AL4V	30-35 mm Ø x 20-25 mm
	SRM 654b	.	.	0.004	0.028	.	.	.	0.045	31 mm Ø x 19 mm
	IARM 175C	0.0006	(0.001)	0.005	0.028	.	.	.	0.024	.	.	(0.0002)	31 mm Ø x 2 or 18 mm
	BS T-5A	.	.	0.0025	0.012	.	.	.	0.02	38 mm Ø x 12 mm
	BS T-15	.	.	0.03	0.007	.	.	.	0.02	32 mm Ø x 12 mm
	101X Ti3	.	.	0.0047	0.0303	.	.	.	0.013	.	.	0.0101	40 mm Ø x 13 mm
	IARM 177C	(0.001)	(0.001)	(0.003)	0.011	.	(0.004)	.	0.086	.	.	(0.0002)	31 mm Ø x 2 or 18 mm
	101X Ti2	.	.	(0.003)	0.0073	.	.	.	0.110	.	.	0.0002	40 mm Ø x 13 mm
	101X Ti6	0.0080	0.0621	0.0632	0.0421	0.0069	0.141	0.062	0.054	0.084	.	0.0087	40 mm Ø x 13 mm
	BCR 089	40 mm Ø x 20 mm
	IARM 300A *	.	.	(0.003)	0.008	.	.	.	0.019	.	(86.7)	31 mm Ø x 2 or 18 mm
	IARM 285A	(0.002)	(0.002)	0.008	0.006	.	.	.	0.009	0.97	.	0.0024	31 mm Ø x 2 or 18 mm
	IARM 178B	.	.	0.51	0.017	.	.	.	0.025	31 mm Ø x 2 or 18 mm
	IARM 314A	.	(0.003)	(0.002)	0.022	(0.005)	.	.	0.02	.	.	(0.0003)	31 mm Ø x 2 or 18 mm
	101X Ti5	0.0098	.	0.277	0.047	0.0095	.	.	0.092	.	.	0.0111	40 mm Ø x 13 mm
	IARM 271A	.	.	.	0.035	(0.002)	.	.	0.021	31 mm Ø x 2 or 18 mm
	BS T-14	.	.	0.022	0.012	.	.	.	0.04	32 mm Ø x 12 mm low supply
	IARM 315A	.	(0.004)	0.005	0.012	(0.001)	(0.003)	.	0.014	.	.	(0.0002)	31 mm Ø x 2 or 18 mm
	IARM 280A	.	(0.002)	0.003	0.012	.	(0.002)	.	0.47	.	.	(0.0003)	31 mm Ø x 2 or 18 mm
	101X Ti4	0.0093	0.066	0.0645	0.779	0.0076	0.145	0.054	0.072	0.096	.	0.0079	40 mm Ø x 13 mm
	IARM 286A	.	(0.006)	(0.004)	0.013	.	(0.02)	.	0.030	.	.	(0.001)	31 mm Ø x 2 or 18 mm
	IARM 297A	(0.003)	.	(0.002)	0.0041	.	.	.	0.022	(0.01)	31 mm Ø x 2 or 18 mm
	SRM 1128	35 mm Ø x 19 mm
	101X Ti1	.	.	0.05	0.0099	.	.	.	0.201	.	.	0.0030	40 mm Ø x 13 mm
	IARM 261A	.	.	.	0.006	.	.	.	0.012	.	.	(0.001)	31 mm Ø x 2 or 18 mm
	SRM 643	32 mm Ø x 19 mm
	SRM 642	32 mm Ø x 19 mm
	SRM 641	32 mm Ø x 19 mm
	BS T-24	.	.	0.020	(0.007)	.	.	.	(0.01)	32 mm Ø x 12 mm
	BS T-23	.	.	0.012	0.004	.	.	.	(0.01)	32 mm Ø x 12 mm
	BS T-22	.	.	0.04	0.008	.	.	.	(0.02)	32 mm Ø x 12 mm

Number	B	Co	Cu	Ni	P	Pd	Ru	Si	Ta	Ti	Y	Units
--------	---	----	----	----	---	----	----	----	----	----	---	-------

ZINC

= class, where 1 = CRM and 2 = RM analysis listed in mass % Trace = informational values such as (<0.001) or lower

#	Number	Pb	Al	Cd	Cu	Fe	In	Mg	Mn	Ni	Sb	Sn	Tl
1	41X Z6	0.031	0.0096	0.0093	0.0088	(0.002)	0.0228	<0.0005	0.0002	0.0002	.	0.0038	.
1	41X Z5	0.0275	0.041	0.0310	0.0296	0.011	0.0050	0.0098	0.0138	0.00054	0.0098	0.0275	0.0073
1	ERM-EB325	0.0142	.	0.00947	0.00475	0.00561	0.00461	0.00368
1	41X Z4	0.0091	0.0096	0.0066	0.0047	0.003	0.0015	0.0019	0.0012	0.0069	0.005	0.0070	(0.003)
1	41X Z3	0.0080	0.0164	0.0050	0.0066	0.0022	0.0010	0.0138	0.0029	0.0029	0.0045	0.0029	0.0012
1	41X Z11	0.0077	0.0261	0.0155	0.0116	0.0019	0.0345	.	.	.	0.0026	0.0072	(0.0010)
2	BS SP-5	0.005	0.0003	<0.0004	<0.001	<0.001	.	<0.002	.	.	<0.001	0.0010	.
1	ERM-EB323	0.00486	.	0.000651	0.00189	0.00113	0.00187	0.00108
1	BCR 327	0.004094	.	0.03014	(0.000056)	0.01440
1	BCR 326	0.003070	Trace	0.02030	0.01048	0.02648
2	BS SP-A	0.003	0.051	.	<0.0005	0.011	0.099	<0.001	.
1	ERM-EB324	0.00261	.	0.00489	0.000987	0.00585	0.00098	0.00199
1	41X Z2	0.0024	0.0104	0.0021	0.0020	(0.0014)	Trace	0.00035	0.0016	0.00040	(0.001)	0.0038	0.0021
2	BCS 194e	0.002	.	.	.	0.001
1	41X Z1	0.00164	0.00009	0.00059	0.00098	0.00239	0.00023	(0.00008)	0.00021	0.00032	0.00021	0.00052	0.00077
1	BAM M601	0.00157	<0.00005	0.000055	0.000189	0.000220	<0.000005	0.000225
1	ERM-EB322	0.00150	.	0.001508	0.000589	0.00191	0.00056	0.000528
1	SRM 683	0.00111	.	0.00011	0.00059	0.00022	Trace	.	Trace	.	.	(0.000002)	(0.00002)
1	SRM 631	(0.001)	0.50	0.0002	0.0013	0.005	0.0023	Trace	0.00015	Trace	.	0.0001	.
1	BCR 321	0.000485	<0.00007	(0.000023)	(0.000097)	(0.000222)	<0.00002	<0.00005	0.000078
1	SRM 682 *	.	(<0.000003)	(0.00001)	0.0000042	(0.00001)	.	(<0.00001)	Trace	(<0.00001)	.	(0.000002)	(<0.00002)

Number	Ag	Bi	Cr	Ga	Ge	Hg	Si	Ti	Zn	Melt °C	Units
41X Z6	.	0.0122	(0.0001)	50 mm Ø x 20 mm
41X Z5	(0.002)	0.00044	.	.	50 mm Ø x 20 mm
ERM-EB325	60 mm Ø x 30 mm
41X Z4	(0.0014)	<0.0005	.	.	50 mm Ø x 20 mm
41X Z3	.	0.0022	.	.	.	(0.0013)	50 mm Ø x 20 mm
41X Z11	.	0.0189	.	.	.	(0.0009)	50 mm Ø x 20 mm
BS SP-5	37 mm Ø x 12 mm
ERM-EB323	60 mm Ø x 30 mm
BCR 327	80 mm Ø x 20 mm
BCR 326	80 mm Ø x 20 mm
BS SP-A	38 mm Ø x 14 mm
ERM-EB324	60 mm Ø x 30 mm
41X Z2	.	Trace	.	.	.	0.0019	50 mm Ø x 20 mm
BCS 194e	99.99	419.5	300 g(4.5 x 3.5 x 3 cms)
41X Z1	.	0.00027	.	.	.	0.00013	50 mm Ø x 20 mm
BAM M601	45 mm Ø x 30 mm
ERM-EB322	60 mm Ø x 30 mm
SRM 683	0.00013	.	.	Trace	Cylinder segment 57mm Ø x 25mm x 19mm
SRM 631	Trace	.	0.0001	(0.0002)	(0.0002)	45 mm x 45 mm x 19 mm
BCR 321	80 mm Ø x 20 mm
SRM 682 *	(0.000002)	.	(<0.000006)	.	.	.	(<0.00005)	.	.	.	Cylinder segment 57mm Ø x 25mm x 19mm

* SRM 682 has trace informational B, Be, C, Ca, Cl, F, K, Li, N, and Nb.

CRM ELECTROLYTIC ZINC SETS

available in sets only, as grouped

Number	Al	Cd	Cu	Fe	Pb	Sn	Zn	
IMN ZA 1	.	0.0042	(0.0032)	0.00167	0.025	0.0038	Rem	Rods 10 mm Ø x 100 mm
IMN ZA 2	.	0.0029	0.0013	0.0061	0.011	0.0012	Rem	
IMN ZA 3	.	0.00092	0.00011	0.00078	0.0028	0.00036	Rem	
IMN ZA 4	.	0.00049	0.00032	0.00040	0.0016	0.00011	Rem	
IMN ZE 1	0.012	0.0019	0.011	0.020	0.018	0.0018	Rem	Discs 40 mm Ø x 25 mm
IMN ZE 2	0.0035	0.0031	(0.00037)	0.0052	0.0078	0.0074	Rem	
IMN ZE 3	0.025	0.0050	0.0032	.	0.0052	0.015	Rem	
IMN ZE 4	.	0.00023	0.013	(0.00035)	0.0012	0.0017	Rem	
IMN ZE 5	0.0011	0.0060	0.0049	0.011	0.0004	0.00045	Rem	

CRM ZINC RoHS MONITOR

cast 50 mm Ø x 20 mm

Number	Cd	Cr	Hg	Pb
41X ZSC6	0.215	<0.0002	0.029	0.0077
41X ZSC3	0.119	0.0148	0.0021	0.0273
41X ZSC5	0.0502	<0.0002	0.147	0.0137
41X ZSC1	0.0288	0.0039	0.026	0.0621
41X ZSC4	0.0131	0.0299	0.050	0.156
41X ZSC2	0.0016	0.0036	0.0053	0.111

CRM ZAMAK (MAZAK) SPECIFICATIONS AND SUGGESTED SAMPLES

42X, 43X: 50 mm Ø x 20 mm BCR: 80 mm Ø x 20 mm SRM: 44 mm x 44 mm x 19 mm

Number	Al	Cu	Mg	Ni	Cd	Cr	Fe	Mn	Pb	Sn
Zamak 2	3.9-4.3	2.6-2.9	0.025-0.05	.	<0.003	.	<0.075	.	<0.004	<0.002
43X Z4	4.76	3.21	0.043	0.0286	0.0025	0.0063	(0.064)	0.088	(0.0024)	(0.0023)
43X Z7	3.68	3.14	0.062	0.0005	0.00092	0.0003	0.029	0.0025	0.0058	0.0031
43X Z6	4.02	2.72	0.0256	0.029	0.0016	0.0006	0.019	0.0006	0.0016	0.0053
Zamak 5	3.9-4.3	0.75-1.25	0.030-0.06	.	<0.003	.	<0.075	.	<0.004	<0.002
Zamak 6	3.9-4.3	0.75-1.25	<0.05	.	<0.003	.	<0.075	.	<0.004	<0.002
43X Z3	3.64	1.58	0.0143	0.0061	0.0132	0.004	0.061	0.0125	0.01	0.0125
BCR 360	3.427	1.234	0.0705	0.0267	0.00595	.	.	.	0.00739	0.00330
BCR 359	3.711	0.989	0.0557	0.00926	0.00298	.	0.01197	.	0.00362	0.001693
SRM 630	4.30	0.976	0.030	0.0027	0.0048	0.0031	0.023	0.0106	0.0083	0.0040
43X Z2	3.53	0.949	0.093	0.00037	0.0044	(0.00015)	0.012	0.0025	0.0088	0.0061
BCR 361	4.068	0.798	.	.	(0.000080)	.	0.001034	.	0.000531	0.00463
SRM 628	4.59	0.611	0.0094	0.030	0.0040	0.0087	0.066	0.0091	0.0045	0.0017
BCR 357	4.227	0.5849	0.0273	0.000982	0.000283	.	0.00257	.	0.00138	0.000351
43X Z1	4.50	0.501	0.0145	0.0010	0.00037	0.0009	0.0058	0.0005	0.0017	(0.0007)
Zamak 3	3.9-4.3	<0.10	0.025-0.05	.	<0.003	.	<0.075	.	<0.004	<0.002
Zamak 7	3.9-4.3	<0.10	0.010-0.020	0.005-0.02	<0.002	.	<0.075	.	<0.002	<0.001
BCR 356	4.434	0.3944	0.01323	0.000343	0.000073	.	0.00315	.	0.000987	(0.000032)
42X Z6	3.67	0.238	0.177	0.00030	0.0039	0.0034	0.008	0.0157	0.0093	0.0057
42X Z3	3.72	0.159	0.0288	0.0102	0.0048	0.0020	(0.047)	0.0252	0.0060	0.0030
42X Z12	4.717	0.156	0.0488	0.0413	0.00277	0.00063	0.0457	0.0483	0.0079	0.0022
SRM 627	3.88	0.132	0.031	0.0029	0.0051	0.0038	0.023	0.014	0.0082	0.0042
BCR 355	3.443	0.1035	0.0786	0.0268	0.00581	.	.	.	0.00569	0.00291
42X Z5	4.25	0.085	0.050	0.040	0.00264	0.0012	(0.0095)	0.026	0.0065	0.0021
42X Z4	3.55	0.063	0.058	0.0177	0.0076	.	0.012	0.0077	0.0113	0.0060
SRM 626	3.56	0.056	0.020	0.047	0.0016	0.0395	0.103	0.048	0.0022	0.0012
SRM 625	3.06	0.034	0.070	0.0184	0.0007	0.0128	0.036	0.031	0.0014	0.0006
BCR 354	3.726	0.03123	0.0602	0.00831	0.00297	.	.	.	0.00308	0.00141
42X Z2 *	4.12	0.031	0.014	0.0035	0.0020	0.0013	0.007	0.0060	0.007	0.006
BCR 353	3.949	0.01000	0.04525	.	0.001044	.	.	.	0.00244	0.00056
BCR 352	4.150	0.003126	0.02830	0.000674	0.000288	.	.	.	(0.00064)	0.00030
42X Z1	4.61	0.0019	0.0041	0.0017	0.0005	<0.0005	0.0024	0.0007	0.0022	0.0006
BCR 351	4.355	0.001213	0.01310	(0.00019)	(0.000021)	.	.	.	0.000450	<0.0001

Number	Be	Bi	Ce	In	La	Sb	Si	Ti	Tl
Zamak 2
43X Z4	.	0.012	.	.	.	0.0043	(0.0065)	0.0017	.
43X Z7	0.0194	(0.0009)	.	.	.	0.0016	.	0.067	.
43X Z6	.	0.0049	.	.	.	0.0045	0.012	0.0013	.
Zamak 5
Zamak 6
43X Z3	.	0.018	.	(0.0019)	.	(0.0030)	0.005	.	(0.0035)
BCR 360	.	.	.	0.00298	0.00259
BCR 359	.	.	.	0.00155	0.001334
SRM 630	0.022	.	.
43X Z2	.	0.0015	.	.	.	0.0112	0.0102	0.0010	.
BCR 361	.	.	.	(0.00002)	0.00374
SRM 628	0.008	.	.
BCR 357	.	.	.	0.000330	0.000276
43X Z1	.	0.0031	.	.	.	0.0016	(0.0037)	0.0014	.
Zamak 3
Zamak 7
BCR 356	.	.	.	<0.00002	0.000079
42X Z6	.	.	(0.012)	0.00191	(0.011)	0.0169	(0.010)	.	0.0021
42X Z3	.	.	(0.0003)	.	(0.0003)	0.003	0.015	.	.
42X Z12	.	.	0.0116	0.0068	0.0084	0.0070	.	.	0.0076
SRM 627	0.021	.	.
BCR 355	.	.	.	0.00246	0.002325
42X Z5	.	.	0.0183	0.0049	0.0137	0.0130	.	.	0.0064
42X Z4	.	.	0.020	0.0016	0.020	(0.0029)	.	.	(0.0025)
SRM 626	0.042	.	.
SRM 625	0.017	.	.
BCR 354	.	.	.	0.00098	0.001101
42X Z2 *	.	.	0.006	.	0.003	0.001	0.012	.	.
BCR 353	.	.	.	0.000255	0.000395
BCR 352	.	.	.	0.000302	0.00032
42X Z1	.	.	0.0027	.	0.0026	(0.0009)	0.0046	.	.
BCR 351	.	.	.	<0.00002	0.000074

* Provisional Analysis

CRM ZAMAK SET

SOLD IN SET/5 ONLY

30 mm x 35 mm x 45 mm

Number	Al	Cd	Cu	Mg	Pb	Sn
GBW 02705	4.72	0.00081	0.165	0.0224	0.0026	0.00058
GBW 02706	3.92	0.0014	0.256	0.159	0.0032	0.00104
GBW 02707	3.91	0.0031	0.412	0.075	0.0057	0.0021
GBW 02708	2.92	0.0072	0.773	0.0368	0.0120	0.0040
GBW 02709	2.64	0.0138	1.37	0.0085	0.0235	0.0077

CRM ZAMAK SET

SOLD IN SET/4 ONLY

40 mm Ø x 25 mm

Number	Al	Cd	Cu	Fe	Mg	Ni	Pb	Si	Sn
IMN ZG 1	3.07	0.00048	1.34	0.0083	0.074	0.0067	0.009	0.036	0.0068
IMN ZG 2	3.56	0.0049	0.72	.	0.048	0.0025	0.0065	0.024	0.0048
IMN ZG 3	4	0.0028	0.11	0.011	0.028	0.001	0.0033	0.01	0.00067
IMN ZG 4	4.64	0.011	0.0089	0.016	0.00055	0.00042	0.0013	0.0047	0.0021

ZINC BINARY AND TERNARY SAMPLES

= class, where 1 = CRM and 2 = RM analysis listed in mass % cast

#	Number	Al	Mg	Mn	Pb	Sb	Units
1	SRM 1742	0.7917	.	.	(0.0029)	.	50 mm Ø x 12 mm
1	SRM 1737	0.6302	.	.	0.0029	.	50 mm Ø x 12 mm
1	SRM 1741	0.5242	.	.	0.1571	.	50 mm Ø x 12 mm
1	SRM 1740	0.4177	.	.	0.0691	.	50 mm Ø x 12 mm
1	SRM 1736	0.3076	.	.	0.0029	.	50 mm Ø x 12 mm
1	SRM 1739	0.2049	.	.	0.0302	.	50 mm Ø x 12 mm
1	SRM 1738	0.1014	.	.	0.0101	.	50 mm Ø x 12 mm
2	41X ZMg1	.	1.13	.	.	.	40 mm Ø x 15 mm
2	41X ZMg3	.	2.80	.	.	.	40 mm Ø x 15 mm
1	41X ZMn1	.	.	1.07	.	.	50 mm Ø x 20 mm
2	41X ZSb1	1.03	40 mm Ø x 15 mm
2	41X ZSb4	3.78	40 mm Ø x 15 mm
2	41X ZSb8	7.68	40 mm Ø x 15 mm

RM ZINC - ALUMINUM - ANTIMONY ALLOYS

cast some Sb segregation in below series, typical analysis listed 40 mm Ø x 15 mm

Number	Al	Sb	Bi	Cd	Cu	Fe	Mg	Pb	Sn
44X Z5	20.4	5.2	0.004	0.001	0.001	0.010	<0.001	0.010	0.003
44X Z4	20.3	6.7	0.016	0.011	0.007	0.011	0.008	0.032	0.018
44X Z3	17.8	8.1	0.013	0.012	0.011	0.009	0.005	0.020	0.019
44X Z2	12.6	9.5	0.030	0.005	0.003	0.007	0.035	0.053	0.018

CRM ZINC ALLOY SETS

available in SETS ONLY, as grouped

ZI: 40 mm Ø x 30 mm

ZF, ZH: 40 mm Ø x 25 mm

Number	Al	Cd	Cu	Fe	Mg	Mn	Ni	Pb	Sb	Sn	Ti	Zn
IMN ZF 1	0.018	0.0041	0.013	0.020	.	.	.	0.0012	.	0.013	0.0014	Rem
IMN ZF 2	0.011	0.0055	0.46	0.011	.	.	.	0.0082	.	0.0077	0.11	Rem
IMN ZF 3	0.0033	.	0.098	0.0018	0.0022	0.021	Rem
IMN ZF 4	0.0058	0.00053	0.86	0.00045	.	.	.	0.0091	.	0.0017	0.20	Rem
IMN ZF 5	.	0.0088	0.011	0.0081	.	.	.	0.026	.	.	0.013	Rem
IMN ZH 1	1.05	0.00079	0.063	0.0038	0.0014	1.39	0.0064	0.0072	0.0012	0.0072	.	.
IMN ZH 2	0.74	0.006	0.15	0.00042	0.0094	0.95	0.05	0.051	0.011	0.05	.	.
IMN ZH 3	.	0.018	0.3	.	0.049	0.49	.	0.31	0.03	0.11	.	.
IMN ZH 4	0.037	0.3	0.41	.	.	0.049	0.93	0.63	0.048	0.14	.	.
IMN ZH 5	0.005	0.41	.	.	0.097	0.0047	1.37	0.91
IMN ZH 6	0.45	.	.	0.053
IMN ZI 1	0.00309	0.00137	0.182	0.00137	.	.	.	0.0006	.	0.0003	0.0508	Rem
IMN ZI 2	0.0151	0.00106	0.204	0.00139	.	.	.	0.00152	.	0.00081	0.206	Rem
IMN ZI 3	0.00859	0.00206	0.0337	0.0019	.	.	.	0.00113	.	0.00058	0.263	Rem
IMN ZI 4	0.00431	0.00143	0.11	0.00131	.	.	.	0.00328	.	0.00215	0.118	Rem
IMN ZI 5	0.0108	0.00049	0.288	0.00135	.	.	.	0.00135	.	.	0.0229	Rem
IMN ZI 6	0.00151	.	0.135	0.0834	Rem

ZINC ALLOYS, chart 1 of 2														
X: 50 mm \varnothing x 20 mm CAN: 50 mm \varnothing x 12 mm SRM: 44 mm x 44 mm x 19 mm														
CRM	Al	Bi	Cd	Cr	Cu	Fe	Mg	Mn	Ni	Pb	Sb	Si	Sn	Ti
43X Z23	30.9	.	0.0043	0.0144	3.15	0.16	0.0207	0.0132	0.0156	0.0045	.	0.061	0.0055	0.0030
CAN NZA-1	28.70	.	0.00098	.	1.51	0.046	0.020	.	.	0.0030	.	.	0.0069	.
43X Z22	27.4	.	0.0050	0.019	2.32	.	0.022	0.0096	0.027	0.0060	.	0.038	0.0061	0.0065
CAN NZA-4	26.65	.	0.0029	.	2.45	0.027	0.0106	.	.	0.0101	.	.	0.0087	.
CAN NZA-3	25.99	.	0.0064	.	2.00	0.066	0.0049	.	.	0.0045	.	.	0.0034	.
CAN NZA-2	23.81	.	0.0047	.	3.00	0.021	0.029	.	.	0.0076	.	.	0.0045	.
43X Z21	23.5	.	0.027	0.0087	1.81	.	0.047	0.0104	0.043	0.012	.	0.022	0.0140	0.013
CAN NZA-7	13.17	.	0.00020	.	0.212	(0.016)	0.052	.	.	0.0136	.	.	0.0116	.
43X Z11	11.61	0.0035	0.0224	0.0010	0.515	.	0.053	0.0089	0.0014	0.0305	0.0091	0.020	0.0206	0.013
CAN NZA-5	10.85	.	0.0095	.	1.04	(0.016)	0.021	.	.	0.0012	.	.	0.0017	.
43X Z12	10.05	(0.003)	0.0115	0.0022	0.80	.	0.027	0.0061	0.004	0.0136	(0.004)	(0.006)	0.0089	0.0053
43X Z13	9.55	.	0.0100	.	0.981	.	0.0204	0.0070	0.0109	0.0125	0.009	(0.0048)	0.0111	.
43X Z14	8.05	0.0096	0.0083	0.0047	1.13	0.031	0.0133	0.0050	0.0066	0.015	0.0089	0.016	0.0054	0.0014
CAN NZA-6	7.54	.	0.0147	.	3.17	(0.0105)	0.00037	.	.	0.0809	.	.	0.0051	.
43X Z15	7.36	(0.005)	0.0030	0.0024	1.54	.	0.0022	0.0020	0.0019	0.0060	(0.005)	(0.007)	0.004	0.002
42X Z8	7.03	.	0.0003	(0.0002)	0.0215	.	0.0033	0.0014	0.0019	0.0025	.	0.013	(0.0023)	(0.0001)
42X Z9	5.58	.	0.0054	.	0.0070	.	0.0464	0.0006	(0.0003)	0.0021	.	(0.004)	(0.00035)	0.020
SRM 629	5.15	.	0.0155	0.0008	1.50	0.017	0.094	0.0017	0.0075	0.0135	.	0.078	0.012	.
42X Z7	4.8	.	0.030	(0.0001)	0.0249	.	0.0095	0.0042	0.0067	0.0097	.	0.006	0.012	(0.0001)
42X Z1	4.61	.	0.0005	<0.0005	0.0019	.	0.0041	0.0007	0.0017	0.0022	(0.0009)	0.0046	0.0006	.
42X Z5	4.25	.	0.00264	0.0012	0.085	(0.0095)	0.050	0.026	0.040	0.0065	0.0130	.	0.0021	.
42X Z6	3.67	.	0.0039	0.0034	0.238	.	0.177	0.0157	0.00030	0.0093	0.0169	(0.010)	0.0057	.
42X Z4	3.55	.	0.0076	.	0.063	.	0.058	0.0077	0.0177	0.0113	(0.0029)	.	0.0060	.
42X Z11	3.19	.	0.0020	0.0016	0.093	(0.036)	0.0329	0.0196	0.0241	0.0058	0.0047	.	0.0017	.
43X Z9	3.17	0.0033	0.0034	0.0034	4.82	0.073	0.0472	0.0108	0.0027	0.0078	0.0033	.	0.0020	0.0012
43X Z5	3.05	.	0.0111	0.0010	6.05	.	0.041	0.0030	0.0021	0.0045	.	0.003	0.0032	0.0009
43X Z8	2.51	.	0.00090	0.00024	0.481	(0.0017)	0.00155	0.00021	0.00033	0.0027	.	.	(0.0005)	.
41X 0336 Zn2	1.55	0.0099	0.145	.	0.354	(0.01)	0.099	0.0212	0.0137	0.486	0.0007	.	0.038	.
41X 0336 Zn4	1.39	0.027	0.638	.	0.874	.	0.179	0.038	0.0074	2.87	0.048	.	2.38	.

Number	Al	Bi	Cd	Cr	Cu	Fe	Mg	Mn	Ni	Pb	Sb	Si	Sn	Ti
43X Z23
CAN NZA-1
43X Z22
CAN NZA-4
CAN NZA-3
CAN NZA-2
43X Z21
CAN NZA-7
43X Z11
CAN NZA-5
43X Z12
43X Z13
43X Z14
CAN NZA-6
43X Z15
42X Z8	.	.	.	0.0081	.	0.0079
42X Z9	.	.	.	0.0047	.	0.0044	.	0.011
SRM 629
42X Z7	.	.	.	0.053	.	0.047
42X Z1	.	.	.	0.0027	.	0.0026
42X Z5	.	.	.	0.0183	0.0049	0.0137	0.0064
42X Z6	.	.	.	(0.012)	0.00191	(0.011)	0.0021
42X Z4	.	.	.	0.020	0.0016	0.020	(0.0025)
42X Z11	.	.	.	0.0014	0.0037	(0.0009)	0.0047
43X Z9	.	.	0.0010
43X Z5
43X Z8
41X 0336 Zn2	0.0102	0.0009	0.0012
41X 0336 Zn4	0.0023	0.0005	.	.	0.0035	.	(0.004)

Number	Ag	As	Be	Ce	In	La	Tl	Zr
--------	----	----	----	----	----	----	----	----

CRM		ZINC ALLOYS, chart 2 of 2										41X CGL: 42 - 48 mm Ø x 20 mm				other X: 50 mm Ø x 20 mm	
Number	Al	Bi	Cd	Cr	Cu	Fe	Mg	Mn	Ni	Pb	Sb	Si	Sn	Ti			
41X GLV6	0.474	0.0248	0.0053	0.0029	0.039	.	.	0.0013	0.0008	0.120	0.0112	.	0.0152	.			
41X 4380 Zn4	0.446	0.0101	0.086	0.0029	0.0284	0.017	0.118	0.0092	0.0172	0.310	0.0156	.	0.0416	(0.0003)			
41X 0336 Zn3	0.43	.	0.341	.	0.36	.	0.134	0.0058	.	0.019	.	.	0.111	.			
41X GLV7	0.399	(0.0108)	0.00056	0.0010	0.023	.	.	0.0025	0.0060	0.082	0.0031	.	(0.0006)	.			
41X GLV3	0.334	0.0016	0.0188	0.00084	0.0260	0.0031	0.00145	0.0111	0.0300	0.0091	0.058	.	0.0060	.			
41X 4380 Zn9	0.295	0.00046	0.0032	0.0015	0.0416	0.0113	0.0153	0.0018	0.0009	0.0139	0.0060	.	0.0008	.			
41X CGL	0.28	.	(0.0015)	.	(0.0005)	0.046	.	.	(<0.001)	.			
41X GLV8	0.263	0.0005	0.0003	0.0012	0.0139	0.0062	0.0012	0.0012	0.0006	0.0037	0.0057	.	0.0005	.			
41X 4380 Zn8	0.225	0.011	0.0079	0.0019	0.020	.	0.007	0.0015	0.024	0.73	0.016	(0.005)	0.011	0.012			
41X GLV1	0.197	0.0046	0.0139	.	0.0191	0.038	.	.	0.0182	0.0391	(0.0003)	.	0.0140	.			
41X GLV4	0.514	0.0061	0.0006	0.0007	0.0321	0.0028	0.0034	0.0089	0.0441	0.0062	0.0287	.	0.0024	.			
41X 4380 Zn7	0.137	.	0.015	0.0045	0.012	.	0.0028	.	0.012	1.25	0.090	.	0.0047	0.009			
41X 0336 Zn6	0.105	0.123	0.0140	.	0.0203	.	0.0008	0.0010	0.0018	1.82	0.234	.	0.0023	.			
41X 2951 Zn3	0.078	.	0.0062	0.184	1.89	.	0.0164	0.0018	0.0010	0.0065	.	.	(0.006)	0.133			
41X GLV2	0.070	0.017	0.0026	.	0.0053	.	.	.	0.0071	0.214	0.007	.	0.003	.			
41X GLV2 A	0.068	0.017	0.0025	.	0.0052	0.048	.	.	0.0070	0.214	0.006	.	0.003	.			
41X 4380 Zn1	0.055	0.0017	0.376	0.002	0.175	.	0.0011	0.0015	0.0029	0.068	0.002	0.006	0.049	(0.001)			
41X ZNiBi	0.050	0.502	0.0020	.	0.0132	0.0133	.	.	2.02	0.0187	.	.	0.154	.			
41X 0336 Zn5	0.035	(0.001)	0.056	.	0.023	.	<0.0005	(0.0001)	(0.0005)	0.91	0.008	.	0.21	.			
41X 2951 Zn2	0.032	.	0.0037	0.142	1.37	.	0.0123	0.0011	0.0027	0.0040	.	.	(0.0015)	0.209			
41X 2951 Zn1	0.029	.	0.0005	0.083	0.79	.	0.0029	0.0013	0.0038	0.0042	.	.	(0.0007)	0.278			
41X 4380 Zn5	0.0215	0.0308	0.0571	0.0075	0.071	.	0.00165	0.035	0.00147	0.140	0.0061	.	0.0101	0.339			
41X 4380 Zn3	0.0203	0.0103	0.0950	0.0029	0.073	.	0.0220	0.0180	0.0120	0.180	0.0046	.	0.080	0.125			
41X 4380 Zn2	0.0153	0.0076	0.284	0.0027	0.0288	.	0.0243	0.0087	0.0023	0.268	0.0093	.	0.0021	0.0251			
41X GLV5	0.014	0.0109	0.0138	.	0.0116	0.076	.	.	0.0030	0.0187	0.162	.	0.020	.			
41X 0336 Zn1	0.014	.	0.0056	.	0.0070	.	0.0049	0.0035	(0.0006)	0.95	.	.	0.0053	.			
41X ZNi2	0.0135	0.0050	0.0010	.	0.0056	0.0061	.	.	1.97	0.0172	.	.	0.141	.			
41X 4380 Zn6	0.0051	0.00109	0.0423	0.0022	0.022	.	0.0043	0.024	0.00058	0.411	0.0359	.	0.110	0.062			
44X ZnCd30	.	0.051	31.0	.	0.046	0.0015	.	.	0.0014	0.089	1.03	.	0.053	.			

Number	Al	Bi	Cd	Cr	Cu	Fe	Mg	Mn	Ni	Pb	Sb	Si	Sn	Ti
41X GLV6	.	0.0014	0.0047
41X 4380 Zn4	.	.	0.0018
41X 0336 Zn3
41X GLV7	.	0.0016
41X GLV3	.	(0.0007)	0.00150
41X 4380 Zn9
41X CGL	.	.	.	(<0.001)	(<0.001)
41X GLV8
41X 4380 Zn8
41X GLV1	.	(0.0003)
41X GLV4	.	(0.0003)	0.0037
41X 4380 Zn7
41X 0336 Zn6	0.0055	0.0020	.	0.0123	0.0132
41X 2951 Zn3
41X GLV2	.	<0.001
41X GLV2 A	.	<0.001
41X 4380 Zn1
41X ZNiBi
41X 0336 Zn5
41X 2951 Zn2
41X 2951 Zn1
41X 4380 Zn5
41X 4380 Zn3
41X 4380 Zn2
41X GLV5	.	0.0041
41X 0336 Zn1
41X ZNi2
41X 4380 Zn6	.	.	.	<0.00005	0.0003
44X ZnCd30	0.046

Number	Ag	As	Co	In	Tl
41X GLV6
41X 4380 Zn4
41X 0336 Zn3
41X GLV7
41X GLV3
41X 4380 Zn9
41X CGL
41X GLV8
41X 4380 Zn8
41X GLV1
41X GLV4
41X 4380 Zn7
41X 0336 Zn6	0.0055	0.0020	.	0.0123	0.0132
41X 2951 Zn3
41X GLV2	.	<0.001	.	.	.
41X GLV2 A	.	<0.001	.	.	.
41X 4380 Zn1
41X ZNiBi
41X 0336 Zn5
41X 2951 Zn2
41X 2951 Zn1
41X 4380 Zn5
41X 4380 Zn3
41X 4380 Zn2
41X GLV5	.	0.0041	.	.	.
41X 0336 Zn1
41X ZNi2
41X 4380 Zn6	.	.	.	<0.00005	0.0003
44X ZnCd30	0.046

last of stock

These globally recognized standards have been used in national mints and precious metal mines across the world. They originate from the Rand Refinery Ltd. in South Africa.

All of these reference materials will be accompanied by a Certificate of Analysis indicating the values of all elements. The XRF standards are mounted in bakelite TSP with a 31 mm Diameter. Other diameters and sizes are available on request.

Please note that with precious metals, market fluctuations will affect pricing. Quoted prices will be extended for a 30-day period. Prepayment is necessary. Delivery in 8 - 12 weeks.

HIGH PURITY GOLD - three forms - certified Au, informational impurities

Number	Au	Impurities reported as found present	Available forms, which must be specified
RAN AuHP1	99.99(5)	Al Ag As Bi Cd Cr Cu	80 g optical emission disc, custom sizes available
RAN AuHP2	99.99	Fe Mg Mn Ni Pb Pd Pt	18 mm x 2 mm XRF disc
RAN AuHP3	99.9(7)	Rh Sb Se Ti Te Zn	15 g or 25 g of small balls, each 200 mg +/- 5 mg

REFINED GOLD GLOBULES

Number	Al	Ag	As	Bi	Cd	Co	Cr	Cu	Fe	Mg	Mn	Ni	Pd	Pb	Pt	Rh	Sb	Se	Te	Ti	Zn
RAN AuP1	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5
RAN AuP2	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10
RAN AuP3	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25
RAN AuP4	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50
RAN AuP5	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100
RAN AuP6	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150

These standards are units of 75 globules at 200 mg +/- 5 mg each. The concentration of each impurity can be custom added and certified. Otherwise the certified impurities fall within 20% of the following values.

JEWELRY - XRF DISCS

Number	Au %	Ag %	Cu %
RAN AuA1	98	2	.
RAN AuA2	96	2	2
RAN AuA3	91	.	8.5
RAN AuA4	88	8	4
RAN AuA5	75	18	7
RAN AuA6	50	20	30
RAN AuA7	37	10	53

Gold, Silver, and Copper will be certified within 1% of the stated values. These standards are available individually or as a set of 7 standards. 11 possible trace elements are then reported as informational, custom added as impurities to the alloys. Certified values will be given for all elements including trace elements. The size is 18 mm Ø x 2 mm H discs mounted on a 31 mm Ø bakelite TSP.

The following elements may be customized in mg/kg
 Bi Cd Fe Mn Pd Pt Pb Sb Se Te Zn

BULLION - XRF discs

Optical emission discs are 80 g custom sizes, XRF discs are 21.7 mm Ø x 2 mm H discs mounted on a 31 mm Ø bakelite TSP. RAN REFBull is produced from high purity gold, silver, and copper, and are available as 3 different standards:

- Certified values for Au, Ag, and Cu
- Certified values for Au, Ag, and Cu with 6 trace elements (*) including Pt and Pd
- Certified values for Au, Ag, and Cu with 19 trace elements

Note that the Au and Ag values for RAN Bull are mass percent, while Cu and Pd are listed as mg/kg.

Au %	Ag %	Cu	Pd*
99.63	0.329	238	14

The 19 trace elements are all less than 10 mg/kg.

- Pt* Sn Pb Sb Bi* Zn Rh* Ni* Cr Mn Fe* Ti Se Co Cd Mg Zn As Al

TERNARY ALLOYS - XRF discs

Number	Au %	Ag %	Cu
RAN TA1	98.0	1.5	0.5
RAN TA2	96.0	3.0	1.0
RAN TA3	95.0	2.5	2.5
RAN TA4	93.0	4.5	2.5
RAN TA5	90.0	4.0	6.0
RAN TA6	83.3	4.0	12.7
RAN TA7	81.7	7.2	11.1
RAN TA8	80.0	12.5	7.5
RAN TA9	58.3	8.0	33.7
RAN TA10	58.3	20.0	21.7
RAN TA11	58.3	30.0	11.7
RAN TA12	50.0	20.0	30.0
RAN TA13	37.5	2.0	60.5
RAN TA14	37.5	10.0	52.5
RAN TA15/01	37.5	16.0	46.5
Number	Au %	Ag %	Cu

These standards are available as a set of 15 standards. The concentrations of the 3 major elements and the 10 trace elements will be certified over the ranges specified. The concentrations of major elements Au, Ag, and Cu in each alloy will fall within 1% of the values specified. Values listed are the mean of the range. Concentrations of custom added trace elements will be included and certified over the range of 1 - 150 mg/kg. Standards can be produced to order on receipt of detailed requirements listing concentration ranges of the trace elements.

The size is 18 mm Ø x 2 mm H discs mounted on a 31 mm Ø bakelite TSP.

The following elements may be customized in mg/kg: Bi Fe Mn Ni
Pb Pd Pt Sb Sn Zn

REFINED SILVER GLOBULES

Number	Al	As	Au	Bi	Cd	Co	Cr	Cu	Fe	In	Mn	Ni	Pb	Pd	Pt	Rh	Sb	Se	Sn	Te	Ti	Zn
RAN AgP1	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5
RAN AgP2	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10	10
RAN AgP3	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25	25
RAN AgP4	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50	50
RAN AgP5	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100	100
RAN AgP6	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150	150
RAN AgP6	200	200	200	200	200	200	200	200	200	200	200	200	200	200	200	200	200	200	200	200	200	200

These standards are units of 75 globules at 200 mg +/- 5 mg each. The concentration of each impurity can be custom added and certified. Otherwise the certified impurities fall within 20% of the following values.

SILVER ALLOYS - XRF only

Number	Ag %	Cu
RAN AgA1	97	3
RAN AgA2	94	6
RAN AgA3	91.5	8.5
RAN AgA4	80	20
RAN AgA5	60	40

These standards are available individually or as a set of 5 standards. These contain silver and copper in a variety of ranges with certified values for nine custom trace elements. The size is 18 mm Ø x 2 mm H discs mounted on a 31 mm Ø bakelite TSP.

The following elements may be customized in mg/kg

Au Pt Pd As Bi Cd Sb Ni Fe

HALLMARK - XRF only

Entirely customized, these are made to the customer specifications. Certified values will be given for Au, Ag, and Cu. Discs are 22 mm Ø x 2 mm H mounted on a 31 mm Ø bakelite TSP. Any desired mix of Au, Ag, or Cu may be supplied with a certificate of analysis. Chosen compositions do not need to use all three of the possible elements.