

Brammer Standard Company, Inc.

Certificate of Analysis

BS 74D

Certified Reference Material for Lead Steel Grade 12L14 - UNS Number G12144

	Certified Value ¹	Estimate of Uncertainty ²	Certified Values³	Certified Value ¹	Estimate of Uncertainty ²
As	0.0047	0.0009		Mo	0.0008
B	0.0009	0.0003		N	0.0004
C	0.072	0.002		Ni	0.0009
Co	0.0043	0.0008		P	0.004
Cr	0.0185	0.0008		Pb	0.009
Cu	0.0057	0.0008		S	0.02
Fe	98.2	0.1		V	0.0004
Mn	1.00	0.05			

	Reference Value ¹	Estimate of Uncertainty ²	Reference Values^{3,4}	Reference Value ¹	Estimate of Uncertainty ²
Al	0.008	0.006		Si	0.002
Ca	<0.001			Sn	0.0009
Mg	0.0003	0.0002		Ta	0.002
Nb	0.0018	0.0009		Ti	0.0005
O	0.028	0.008		W	<0.005
Sb	<0.05			Zr	0.0005

¹ For each element, the certified value listed is the present best estimate of the true value based on the mean of the weighted results of an interlaboratory testing program. See page 3-4 for more information on its calculation.

² For each element, the uncertainty listed is based on a statistical evaluation of the contributions of homogeneity and the interlaboratory testing program. See page 3-4 for more information on its calculation.

³ Values are given in weight percent. Values in brackets are reported by difference.

⁴ Reference values are not certified and are provided for information only.

Trace element information values for Be, Cl, Ga, Ge, Na, and Zn are shown on page 4.

The requirements of ISO Guides 30, 31, and 35 were followed for the preparation of this Certified Reference Material and certificate of analysis.

Analysis	*	As	*	B	*	C	*	Co	*	Cr	*	Cu	*	Fe	*	Mn	*	Mo	*	N
1	12	0.003667	11	0.0002	1	0.0677	4	0.002533	10	0.015833	12	0.003533	16	[98.14]	4	0.964	3	0.0042	2	0.0028067
2	3	0.0038	5	0.000667	1	0.07	12	0.003167	4	0.017733	4	0.004963	16	[98.150267]	4	0.973667	12	0.00463333	2	0.0036
3	5	0.0040	7	0.000813	1	0.070333	5	0.0037	4	0.017967	4	0.0052	16	[98.1755]	4	0.9815	3	0.00555	2	0.003625
4	3	0.00405	4	0.000867	11	0.0704	5	0.003967	10	0.0180	4	0.005337	4	98.18	4	0.985	4	0.00576667	2	0.0036567
5	4	0.004267	3	0.000875	3	0.0708	5	0.00412	8	0.018	5	0.0054	4	98.1859667	10	0.991	4	0.00583333	2	0.0036667
6	5	0.00433	4	0.0009	1	0.071	4	0.004133	4	0.018	4	0.005433	16	[98.195]	11	0.9945	4	0.00586667	2	0.004
7	15	0.004373	4	0.001033	1	0.071033	4	0.0043	4	0.0182	11	0.0057	16	[98.2]	10	1.00	4	0.006	2	0.0040167
8	5	0.004633	3	0.00155	3	0.07155	3	0.00455	3	0.01835	14	0.005733	14	98.2	14	1.00	5	0.00616667	2	0.0040333
9	4	0.005067			1	0.071567	11	0.00455	3	0.01835	4	0.005867	16	[98.202]	4	1.002	4	0.00619333	2	0.0042333
10	9	0.0052			1	0.071667	3	0.0046	11	0.01855	5	0.005867	10	98.2033333	4	1.003167	4	0.0063	2	0.0042667
11	9	0.005333			1	0.071733	4	0.0049	4	0.018767	3	0.00595	16	[98.22]	4	1.003233	10	0.00653333	2	0.0043
12	4	0.005733			1	0.072367	4	0.005033	5	0.0189	3	0.00595	16	[98.2533]	4	1.006167	10	0.0068	2	0.0043733
13	4	0.0060			1	0.073	4	0.0051	14	0.019033	4	0.0060			4	1.006267	4	0.00686667	2	0.0044
14	5	0.0060			1	0.073033	14	0.005333	4	0.019567	8	0.006			3	1.01	5	0.00696667	2	0.0047667
15					1	0.07315	10	0.0054	4	0.019567	10	0.006033			4	1.013333	14	0.0077		
16					1	0.0768			5	0.0213	4	0.006467			8	1.02	11	0.00785		
17					1	0.0768					10	0.0085			3	1.025				
18															10	1.055				
Average		0.004747		0.000875		0.0718		0.00432		0.01853		0.00568		98.190		1.001880		0.00631		0.00402
Std Dev		0.000085		0.000035		0.0018		0.00014		0.00062		0.00021		0.031		0.000075		0.00020		0.00014
H		0.00079		0.00041		0.0027		0.00076		0.0014		0.00085		0.19		0.011		0.00089		0.00074
U ₁		0.00079		0.00041		0.0032		0.00077		0.0016		0.00087		0.19		0.011		0.00091		0.00075
t-statistic		2.16		2.36		2.12		2.14		2.13		2.12		2.20		2.11		2.13		2.16
U ₂		0.0017		0.0010		0.0069		0.0017		0.0033		0.0019		0.43		0.023		0.0019		0.0016
U ₃		0.00046		0.00034		0.0017		0.00043		0.00083		0.00045		0.12		0.0054		0.00049		0.00043
Certified		0.0047		0.0009		0.072		0.0043		0.0185		0.0057		98.2		1.00		0.0063		0.0040
Uncertainty		0.0009		0.0003		0.002		0.0008		0.0008		0.0008		0.1		0.05		0.0008		0.0004
Tolerance		0.0027		0.0008		0.007		0.0024		0.0033		0.0024		0.4		0.15		0.0024		0.0016

Analysis	*	Ni	*	P	*	Pb	*	S	*	V										
1	12	0.008033	12	0.065667	9	0.268667	12	0.236667	12	0.000707										
2	4	0.010367	10	0.066	5	0.269	1	0.259	5	0.000967										
3	4	0.0106	5	0.066067	11	0.2755	11	0.2625	4	0.000967										
4	5	0.010867	10	0.069233	4	0.277133	1	0.264	4	0.001033										
5	4	0.010967	4	0.072633	4	0.279233	1	0.269	5	0.00111										
6	3	0.0111	3	0.0729	10	0.28	1	0.27	4	0.001233										
7	11	0.0116	4	0.0745	4	0.280133	1	0.270667	5	0.0013										
8	4	0.011933	4	0.074567	8	0.282	1	0.271	11	0.00135										
9	3	0.01195	3	0.07465	3	0.282	1	0.272	4	0.001467										
10	14	0.011967	13	0.074733	3	0.2835	1	0.272333	4	0.0015										
11	4	0.012	4	0.074967	4	0.284333	1	0.275	14	0.001533										
12	8	0.012	4	0.075567	4	0.286433	1	0.278333	3	0.0016										
13	4	0.012133	4	0.075967	4	0.286467	1	0.283333	3	0.00165										
14	4	0.012133	4	0.076167	4	0.2885	3	0.2875												
15	10	0.012333	4	0.076333	10	0.291	10	0.29												
16	10	0.014	11	0.07725	4	0.292333	1	0.297267												
17							1	0.298333												
18							10	0.307												
19							1	0.3133												
Average		0.011499		0.072950		0.2816		0.2779		0.001227										
Std Dev		0.000079		0.000079		0.0032		0.0037		0.000037										
H		0.0012		0.0027		0.0054		0.0054		0.00046										
U ₁		0.0012		0.0027		0.0063		0.0065		0.00046										
t-statistic		2.13		2.13		2.13		2.10		2.18										
U ₂		0.0025		0.0058		0.013		0.014		0.0010										
U ₃		0.00061		0.0014		0.0034		0.0032		0.00028										
Certified		0.0115		0.073		0.282		0.28		0.0012										
Uncertainty		0.0009		0.004		0.009		0.02		0.0004										
Tolerance		0.0027		0.012		0.027		0.06		0.0011										

Analysis	*	Al	*	Ca	*	Mg	*	Nb	*	O	*	Sb	*	Si	*	Sn	*	Ta	*	Ti
1	14	0.003667	11	0.000123	3	0.000165	4	0.000733	2	0.018933	12	0.000197	4	0.00316667	12	0.00014	11	0.00205	12	0.0000127
2	4	0.004067	4	0.0006	4	0.000217	10	0.0011	2	0.0204	9	0.0002	4	0.00426667	5	0.000173	14	0.00386667	5	0.0002167
3	12	0.005067	4	0.00082	3	0.0003	11	0.00185	2	0.023033	5	0.000207	5	0.00503333	5	0.000193	4	0.00483333	4	0.0004333
4	5	0.0052			11	0.0003	4	0.0019	2	0.025133	5	0.00023	12	0.0057	9	0.0007	4	0.0053	3	0.00065
5	5	0.005567			4	0.0003	4	0.00267	2	0.026367	5	0.0003	4	0.00616667	4	0.0010	4	0.00583333	11	0.0009
6	4	0.0057			4	0.0003	3	0.0028	2	0.0277	9	0.0007	4	0.0067	9	0.001067	5	0.00646667	4	0.0009333
7	4	0.006267			4	0.0003			2	0.029	11	0.00155	10	0.007	4	0.0011	3	0.00775	14	0.0009333
8	11	0.0075							2	0.0298	4	0.007233	11	0.0072	3	0.00115			4	0.0009333
9	4	0.013433							2	0.031567	4	0.007533	4	0.00793333	11	0.0015			4	0.0015333
10	4	0.0137							2	0.033567			7	0.00813333	4	0.0016				
11	4	0.013933							2	0.0339			14	0.00826667	5	0.0021				
12									2	0.036767			3	0.0087						
13													4	0.00873333						
14													4	0.00876667						
15													3	0.0088						
Average		0.007645		0.000486		0.000269		0.00184		0.028014		0.00202		0.006971		0.000955		0.00516		0.000724
Std Dev		0.000095		0.000067		0.000033		0.00013		0.000091		0.00011		0.000082		0.000027		0.00012		0.000036
H		0.00096		0.00033		0.00027		0.00054		0.0017		0.00056		0.00093		0.00042		0.00082		0.00038
U ₁		0.00097		0.00033		0.00027		0.00055		0.0017		0.00057		0.00093		0.00042		0.00082		0.00038
t-statistic		2.23		4.30		2.45		2.57		2.20		2.31		2.14		2.23		2.45		2.31
U ₂		0.0022		0.0014		0.00066		0.0014		0.0038		0.0013		0.0020		0.00094		0.0020		0.00088
U ₃		0.00065		0.00083		0.00025		0.00058		0.0011		0.00044		0.00051		0.00028		0.00076		0.00029
Reference		0.008		<0.001		0.0003		0.0018		0.028		<0.05		0.007		0.0010		0.005		0.0007
Uncertainty		0.006				0.0002		0.0009		0.008				0.002		0.0009		0.002		0.0005
Tolerance		0.007				0.0002		0.0017		0.024				0.006		0.0009		0.004		0.0006

Analysis	*	W	*	Zr
1	12	0.000113	12	0.000011
2	5	0.000263	3	0.0005
3	11	0.0004	10	0.0009
4	4	0.0010	4	0.0009
5	4	0.001167	4	0.000967
6	3	0.00235	3	0.0014
7	5	0.0028	4	0.001627
Average		0.00116		0.00090
Std Dev		0.00012		0.00012
H		0.00045		0.00041
U ₁		0.00047		0.00043
t-statistic		2.45		2.45
U ₂		0.0011		0.0010
U ₃		0.00043		0.00039
Reference		<0.005		0.0009
Uncertainty				0.0005
Tolerance				0.0008

For each element, in accordance with the requirements of ISO 17034 and Guide 35, an effort must be made to account for the effects on the certified value of the uncertainty estimate from homogeneity testing (H) and the uncertainties of the contributing laboratories. The average (A) is calculated using a weighted mean where the reciprocal of the square of each laboratory's combined uncertainty (C_L), calculated from its standard deviation (S_L) and its uncertainty estimate (U_L), is used as the weight (W_L) for its mean (M_L). The standard deviation (S) is calculated as the square root of the reciprocal of the sum of the weights. U₁ is the combined uncertainty from homogeneity and labs. U₂ is U₁ multiplied by the coverage factor (95 % t-statistic). U₃ is U₂ divided by the square root of the number of determinations (n). Thus:

$$C_L = \sqrt{S_L^2 + U_L^2} \quad W_L = \frac{1}{C_L^2} \quad A = \frac{\sum_{i=1}^n W_L M_L}{\sum_{i=1}^n W_L} \quad S = \frac{1}{\sqrt{\sum_{i=1}^n W_L}} \quad U_1 = \sqrt{H^2 + S^2} \quad U_2 = t \times U_1 \quad U_3 = \frac{U_2}{\sqrt{n}}$$

All but the final reported values are taken to two significant figures as determined by each quantity's uncertainty estimate. The final reported Uncertainty is U₃ rounded to one significant figure and represents the half width of the 95 % confidence interval for the **Certified** value. The final reported **Certified** value is A rounded to the same decimal place as the Uncertainty. The Uncertainty is a measure of the quality of the **Certified** value.

The Tolerance is a measure of the expected performance of an analysis. This involves further expanding the sample uncertainty to include instrument and operator uncertainty, for those without access to such calculations.

For further information regarding the confidence interval for the certified value see ISO Guide 35:2006 section 6.

BS 74D * Code for analytical method Trace analysis listed as mg/kg (ppm)

Analysis	*	Be	*	Cl	*	Ga	*	Ge	*	Na	*	Zn								
1	12	0.006	12	0.04	12	4	12	25	12	0.01	12	0.72								
2	12	0.01			12	4.2	12	25	12	0.03	12	0.72								
3	12	0.01			12	4.3	12	25	12		12	0.74								

Analytical Method Codes:

- | | | | | | |
|---|-------------------------|----|-------------------------|----|------------------------|
| 1 | Combustion (ASTM E1019) | 7 | Photometric | 13 | Titrimetric |
| 2 | Fusion (ASTM E1019) | 8 | Flame Atomic Absorption | 14 | DCP Atomic Emission |
| 3 | Spark Atomic Emission | 9 | GF Atomic Absorption | 15 | HG Atomic Fluorescence |
| 4 | ICP Atomic Emission | 10 | X-Ray Fluorescence | 16 | Difference |
| 5 | ICP Mass Spectrometry | 11 | GD Atomic Emission | | |
| 6 | Gravimetric | 12 | GD Mass Spectrometry | | |

ICP = Inductively Coupled Plasma GF = Graphite Furnace GD = Glow Discharge
 DCP = Direct Current Plasma HG = Hydride Generation

Lab Name	Location	Registrar	Accreditation
Brammer Standard Company, Inc.	Houston, TX	A2LA	17025, 17034
NSL Analytical	Cleveland, OH	ANAB	17025
Dirats Laboratories	Westfield, MA	ANAB	17025
Vitkovice Testing Center	Hulvaky, Ostrava	Czech Accreditation Institute	17025
Element Materials Technology	Glendale Heights, IL	A2LA	17025
Eurofins EAG Materials Science, LLC	Liverpool, NY	A2LA	17025
National Analysis Center For Iron And Steel	Beijing, China	CNAS	17025
Instituto Metalurgii Zelaza	Gliwice, Poland	PCA	17025
Shiva Analyticals Private Limited	Hoskote, Bangalore	NABL	17025
Luvak Inc.	Boylston, MA	PRI	17025
TUV Rheinland Pvt Ltd	Bangalore, India	NABL	17025
Element Materials Technology	Santa Fe Spring, CA	A2LA	17025
Laboratory Testing, Inc.	Hatfield, PA	PRI	17025

A2LA = American Association for Laboratory Accreditation
 ANAB = ANSI-ASQ National Accreditation Board
 CNAS = China National Accreditation Service
 NABL = National Accreditation Board for Testing and Calibration Laboratories
 PCA = Polish Center For Accreditation
 PRI = Performance Review Institute

Analysis: Chemical analyses were made on solid pieces and chips prepared by an end mill from representative samples for the certified portion of the lot in accordance with ASTM Standard Practice E1806. The laboratories participating in the testing followed the requirements of ISO Standard 17025.

Traceability: The following Certified Reference Materials were used to validate the analytical data: 12X15253, 12XLA10, 12XLA90, 13XNSA8, 14X12144A, 23X80010; AR 511, 513, 514B, 614A, 644, 650, 657, 659, 662, 668, 675, 881, 882, 885, 890, 892, 960, 1650, 1651, 1652, 1653; BAS 8-1, 61, 152/2, 159/3, 258-1, 345, 346A, 405/1, 408/1, 409, 451/1, 454, 464/1; BS CCS-2, H8, H230A, 45B, 56H, 66B, 66J, 73C, 74A, 74B, 74C, 75G, 80F, 82F, 88D, 179C, 183C, 431, 625D, 800A, 825E, 1045, 2931A, 2931B, 2942, 4820A, 4942A, 8620E, 9325A; CKD 166B, 167B, 168A, 169A, 182A, 185A, 189A; CZ 2025A; ECRM 037-1, 082-1, 184-1; IARM 38A, 59A, 625E, 67B, 156A, 183A, 189A, 190A; IMZ 51/1, 55/1, 55/1A; IPT 12A, 17A, 31, 39, 97; JSS 168-7, 172-7, 173-5, 174-5, 175-7; LECO 501-024, 501-504, 501-505, 501-506, 501-510, 501-644, 501-646, 501-676, 501-677, 502-195, 502-280, 502-414, 502-416, 502-712, 502-855, 502-873, 502-874, 502-986; NCS NS11019; SRM 133B, 153, 160B, 293, 361, 362, 363, 898, 1263; Y41340b.

Homogeneity: This Certified Reference Material (CRM) was tested for homogeneity using ASTM Standard Method E826 and found acceptable. It was also examined by spark atomic emission spectrometry and found to be compatible with the following Reference Materials: BS CCS-2, 56H, 66B, 66J, 74A, 74B, 74C, 75G, 2931B, 2942.

Validity statement: ISO Guide 31 states that the certification should contain an expiration date for all materials where instability has been demonstrated or is considered possible, after which the certified value is no longer guaranteed by the certifying body. The certification of BS 74D is valid indefinitely. The certification is nullified if this CRM is damaged, contaminated, or otherwise modified.

Storage: This CRM must be stored in a cool, dry, non-corrosive environment.

Source: The bar stock for this CRM was produced by a source unknown.

Form: This CRM is machined in the form of a disc, approximately 41mm in diameter and 19mm thick by Brammer Standard Company, Inc.

Use: This CRM is intended for use in spark atomic emission, glow discharge, and x-ray spectrometric methods of analysis. Refer to ISO Guide 33 for information about the use of Certified Reference Materials.

Certified Area: The entire depth of the CRM may be used.

Caution: As with any bar material, avoid spark atomic emission spectrometric burns in the center of the CRM (5 mm radius), as some segregation may be present.

Sample Preparation: For best analytical results, use the same method for preparing the analytical surface on all reference materials as used for production specimens. Avoid overheating the sample during surface preparation.

Caution: CRM contains significant insoluble soft metal inclusions. Surface smearing may occur. Spark atomic emission spectrometers may require extended preburns to compensate.

Certificate Number: The unique identification number for this certificate of analysis is 74D-120321. You may obtain information on revisions of certificates from the internet at www.brammerstandard.com.

Safety Notice: A Safety Data Sheet (SDS) is not required for this material. This material will not release or otherwise result in exposure to a hazardous chemical, under normal conditions of use. Inquiries concerning this Reference Material should be directed to:

Brammer Standard Co., Inc.
14603 Benfer Road
Houston, Texas 77069-2895 USA

Phone: (281) 440-9396
Fax: (281) 440-4432

Web: www.brammerstandard.com
Email: contact@brammerstandard.com

Brammer Standard Company, Inc., is accredited by the American Association For Laboratory Accreditation (A2LA) to ISO Standard 17034 as a Reference Material Producer for the production of Certified Reference Materials and Reference Materials (Certificate Number 656.02)

Brammer Standard Company's Chemical Laboratory is accredited by A2LA to ISO Standard 17025. (Certificate Number 656.01)

By Certificate Number 10539, the Quality System of Brammer Standard Company, Inc., is registered to ISO 9001 by National Quality Assurance (NQA), U.S.A.

The scopes of accreditation are listed on the website: www.brammerstandard.com

References:

Versions used were those available at the time of testing and characterization

- E826 Standard Practice for Testing Homogeneity of a Metal Lot or Batch in Solid Form by Spark Atomic Emission Spectrometry
- E1019 Standard Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Fusion Techniques
- E1806 Standard Practice for Sampling Steel and Iron for Determination of Chemical Composition

ISO Standard 17025:2017 General requirements for the competence of testing and calibration laboratories

ISO Standard 9001:2015 Quality Management Systems - Requirements

ISO Guide 30:2015 Terms and definitions used in connection with reference materials + 2008 amendment

ISO Guide 31:2015 Reference materials - Contents of certificates and labels

ISO Guide 33:2015 Uses of certified reference materials

ISO Standard 17034:2016 General requirements for the competence of reference material producers

ISO Guide 35:2017 Reference Materials - General and statistical principles for certification

ASTM documents available from ASTM, 100 Barr Harbor Dr., West Conshohocken, PA 19428.

ISO Guides and Standards available from Global Engineering - www.global.ihs.com

Other useful documents available from NIST, U.S. Department of Commerce, Gaithersburg, MD 20899.

NIST Special Publication 260-100, Handbook for SRM Users

NIST Special Publication 829, Use of NIST Standard Reference Materials for Decisions on Performance of Analytical Chemical Methods and Laboratories

Certified by: _____ on December 03, 2021.

Beau R. Brammer
President