

**Brammer Standard Company, Inc.**

**Data Sheet for Setting-up Material**

**BS SU 4130**

**AISI Grade 4130 Low Alloy Steel**

(UNS Number G41300)

**Estimated  
Analysis<sup>1</sup>**

**Estimated  
Analysis<sup>1</sup>**

Analysis listed as percent by weight

<b>C</b>	<b>0.29</b>	<b>Co</b>	<b>0.006</b>
<b>Mn</b>	<b>0.55</b>	<b>N</b>	<b>0.0057</b>
<b>P</b>	<b>0.015</b>	<b>O</b>	<b>0.002</b>
<b>S</b>	<b>0.020</b>		
<b>Si</b>	<b>0.25</b>		
<b>Cu</b>	<b>0.104</b>		
<b>Ni</b>	<b>0.090</b>		
<b>Cr</b>	<b>0.97</b>		
<b>Mo</b>	<b>0.16</b>		
<b>Al</b>	<b>0.030</b>		

<sup>1</sup> The above chemistry is supplied as an approximate guide to the composition and must not be regarded as the certified analysis. The analysis is based on the results of a Proficiency Testing Program. According to ASTM Standard Practice E 2027, the data from proficiency testing programs must never be used to assign certification values to the materials used in the program. This material may be used for instrument drift control. It must not be used for instrument calibration.

See the following pages for more information.

**Data Sheet Number SU-4130-091201p1**

**Analytical data:** This material was used as an unknown test specimen number 3002 in a nationally recognized Proficiency Testing Program (PTP) for low alloy steel. Most of the participating laboratories used one or more of the ASTM Standard Test Methods E 322, E 415, E 1019, and E 1085. The data shown below are the results from the PTP.

Combustion Instrument Analysis using ASTM Standard Test Method E 1019

	C	S	N	O
Number of Labs	48	44	47	24
Grand Average	0.2943	0.0198	0.0057	0.0020
Standard Deviation	0.0049	0.0012	0.0003	0.0005

Optical Emission Spectrometric Analysis using ASTM Standard Test Method E 415

	C	Mn	P	S	Si	Cu	Ni	N
Number of Labs	65	74	74	66	75	72	74	27
Grand Average	0.3011	0.5460	0.0151	0.0198	0.2546	0.1040	0.0902	0.0057
Standard Deviation	0.0094	0.0092	0.0012	0.0017	0.0080	0.0040	0.0042	0.0006

	Cr	Mo	Al	Co
Number of Labs	72	73	68	38
Grand Average	0.9636	0.1630	0.0304	0.0055
Standard Deviation	0.0152	0.0056	0.0022	0.0009

X-ray Emission Spectrometric Analysis using ASTM Standard Test Method E 322

	Mn	Cu	Ni	Cr	Mo
Number of Labs	6	6	5	6	6
Grand Average	0.5425	0.1050	0.0912	0.9760	0.1628
Standard Deviation	0.0105	0.0042	0.0059	0.0269	0.0045

X-ray Emission Spectrometric Analysis using ASTM Standard Test Method E 1085

	Mn	P	Si	Cu	Ni	Cr	Mo
Number of Labs	7	3	6	7	7	7	7
Grand Average	0.5456	0.0151	0.2603	0.1072	0.0894	0.9684	0.1610
Standard Deviation	0.0037	0.0029	0.0060	0.0037	0.0018	0.0217	0.0042

Other Analytical Methods such as AA, ICP, and GDOES spectrometric analysis and combustion methods

	C	Mn	P	S	Si	Cu	Ni	Cr	Mo
Number of Labs	3	5	9	4	7	5	5	6	5
Average	0.3003	0.5578	0.0150	0.0193	0.2536	0.1051	0.0897	0.9757	0.1652
Standard Deviation	0.0197	0.0108	0.0011	0.0017	0.0094	0.0031	0.0055	0.0306	0.0080

	Al	Co
Number of Labs	6	8
Average	0.0320	0.0061
Standard Deviation	0.0013	0.0010

ICP Spectrometric Analysis

	Mn	Si	Cu	Cr	Mo
Number of Labs	3	3	4	4	3
Average	0.5567	0.2557	0.1057	0.9650	0.1664
Standard Deviation	0.0166	0.0080	0.0091	0.0322	0.0097

**Overall Summary**

	C	Mn	P	S	Si	Cu	Ni	Cr	Mo
Robust Mean	0.2978	0.5467	0.0151	0.0198	0.2549	0.1043	0.0902	0.9655	0.1630
Robust. Std. Deviation	0.0081	0.0097	0.0012	0.0015	0.0082	0.0042	0.0043	0.0183	0.0054
	Al	Co	N	O					
Robust Mean	0.0305	0.0056	0.0057	0.0020					
Robust. Std. Deviation	0.0022	0.0009	0.0004	0.0005					

**Homogeneity:** This Setting-up Material was tested for homogeneity using ASTM Standard Method E 826 and found acceptable. It was also examined by optical emission spectrometry using ASTM Standard Test Method E 1086 and found to be compatible with the following Reference Materials: NIST SRM 1261A, 1262A, 1263A, 1763, 1764; JSS 170-6; BS CSN-2D, 54E.

**Source:** This material was melted by North Star Steel Company. It was melted by an electric arc furnace, vacuum degassed, bottom poured into ingots, aluminum killed, hot rolled, and annealed.

**Form:** This Setting-up Material is in the form of a disc, approximately 44 mm (1.75 inches) diameter and 40 mm (1.57 inches) thick.

**Use:** This material is intended for use in optical emission and x-ray spectrometric methods of analysis.

**Analytical area:** The entire depth of the disc may be used.

**Caution:** As with any bar material, avoid optical emission spectrometric bumps in the center of the disc (5 mm radius), as some segregation may be present.

**Sample Preparation:** For best analytical results, use the same method for preparing the analytical surface on all setting-up samples as you use for production specimens. Avoid overheating the bar during surface preparation.

**Data Sheet Number:** The unique identification number for this data sheet is SU-4130-091201-px, where x indicates the page number. Refer to future Brammer Standard Company catalogs for information on any revisions to this or other Brammer Standard materials. You may also obtain information on revisions from the internet at [brammerstandard.com](http://brammerstandard.com).

**Safety Notice:** A Material Safety Data Sheet (MSDS) is not required for this material. This material will not release or otherwise result in exposure to a hazardous chemical under normal conditions of use. Inquiries concerning this Setting-up Material should be directed to:

Brammer Standard Co., Inc. 14603 Benfer Road Houston, Texas 77069-2895 USA	Phone: (281) 440-9396 Fax: (281) 440-4432	web <a href="http://brammerstandard.com">brammerstandard.com</a> e-mail <a href="mailto:bramstan@netropolis.net">bramstan@netropolis.net</a>
--	--	---

Prepared by: \_\_\_\_\_ on September 12, 2001.  
G. R. Brammer

**Brammer Standard Company, Inc., is accredited to ISO Guide 34 as a Reference Material Producer for the production of Certified Reference Materials and Reference Materials by A2LA (Certificate Number 656.02) The scope of accreditation is listed on the website: [www.brammerstandard.com](http://www.brammerstandard.com)**

**By Certificate Number 10539, the Quality System of Brammer Standard Company, Inc., is registered to ISO 9002:1994 by National Quality Assurance, U.S.A.**

**Brammer Standard Company's Chemical Laboratory is accredited to ISO Guide 25 by A2LA. (Certificate Number 656.01)**

### **References:**

*ASTM documents available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, Telephone: 610-832-9500 Fax: 610-832-9555 e-mail: [service@astm.org](mailto:service@astm.org) Website: [www.astm.org](http://www.astm.org)*

E 322 - 96 Standard Test Method for X-Ray Emission Spectrometric Analysis of Low-Alloy Steels and Cast Irons

E 415 - 85 (Reapproved 1999) Standard Test Method for Optical Emission Vacuum Spectrometric Analysis of Carbon and Low-Alloy Steel

E 826 - 85 (Reapproved 1996) Standard Practice for Testing Homogeneity of Materials for the Development of Reference Materials

E 1019 - 2000 Standard Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel and in Iron, Nickel, and Cobalt Alloys

E 1085 - 95 Standard Test Method for X-Ray Emission Spectrometric Analysis of Low-Alloy Steels

E 2027 - 99 Standard Practice for Conducting Proficiency Tests in the Chemical Analysis of Metals, Ores, and Related Materials