BRAMMER STANDARD COMPANY, INC.

Data Sheet for Setting-up Sample BS SU LAS-13

Setting-up Sample for Low Alloy

	Estimated Analysis¹			Estimated Analysis ¹
		Analysis listed as percent by weight		
Al	0.261		Ni	0.149
As	0.03		Р	0.067
В	0.0053		Pb	0.0009
Bi	0.027		S	0.0009
С	0.088		Sb	0.005
Ca	0.0002		Si	0.097
Со	0.20		Sn	0.055
Cr	1.30		Ta	0.044
Cu	0.425		Те	0.012
Fe	[94.1]		Ti	0.095
Mg	0.0005		V	0.386
Mn	1.68		W	0.107
Мо	0.78		Zn	0.0021
N	0.020		Zr	0.024
Nb	0.10			

¹ The above chemistry is supplied as an approximate guide to the composition of this setup sample and must not be regarded as a certified analysis. The analysis is based on the results of the homogeneity testing performed on the sample lot. This sample was found to be suitable for use as a setting-up sample and may be used for instrument drift control. It must not be used for instrument calibration.

The requirements of ISO Guides 31, 34, and 35 were followed for the preparation of this setting-up sample and data sheet.

Brammer Standard Company, Inc. 14603 Benfer Road, Houston, TX 77069-2895 Telephone: (281) 440-9396 Fax: (281) 440-4432 Website: www.brammerstandard.com

Data Sheet Number SU LAS-13-071913 Page 1/3

<u>Homogeneity:</u> This setting-up sample (SUS) was tested for homogeneity using ASTM Standard Method E 826 and found acceptable. It was also examined by spark atomic emission spectrometry and found to be compatible with the following Reference Materials — SRM 1262A, 1762, 1763; BS LAS-3, LAS-9, 40B, 53D.

<u>Validity statement:</u> ISO Guide 31 states that the data sheet should contain an expiration date for all samples where instability has been demonstrated or is considered possible, after which the stated values are no longer guaranteed by the producing body. The stated values for BS SU LAS-13 are valid indefinitely. However, they are nullified if this SUS is damaged, contaminated, or otherwise modified.

Source: The stock for this SUS was produced by Ulrich Nell, Oberhausen, Germany.

Form: This SUS is machined in the form of a disc, approximately 40 mm in diameter and 40 mm thick by Brammer Standard Company, Inc.

<u>Use:</u> This SUS is intended for use in spark atomic emission and x-ray spectrometric methods of analysis. Refer to ISO Guide 33 for information about the use of setting-up samples. It is intended as a setup standard to be used for controlling instrument drift.

Analytical Area: The entire depth of the SUS may be used.

<u>Sample Preparation:</u> For best analytical results, use the same method for preparing the analytical surface on all setting-up samples as you use for production specimens. Avoid overheating the sample during surface preparation.

<u>Data Sheet Number:</u> The unique identification number for this data sheet is SU LAS-13-071913. You may obtain information on revisions of data sheets from the internet at <u>www.brammerstandard.com</u>.

<u>Safety Notice:</u> A Material Safety Data Sheet (MSDS) is not required for this sample. This sample will not release or otherwise result in exposure to a hazardous chemical, under normal conditions of use. Inquiries concerning this setting-up sample should be directed to:

Brammer Standard Co., Inc. Phone: (281) 440-9396 Web: www.brammerstandard.com

14603 Benfer Road

Houston, Texas 77069-2895 USA Fax: (281) 440-4432 Email: contact@brammerstandard.com

Brammer Standard Company, Inc., is accredited by the American Association For Laboratory Accreditation (A2LA) to ISO Guide 34 as a Reference Material Producer for the production of Certified Reference Materials and Reference Materials (Certificate Number 656.02)

Brammer Standard Company's Chemical Laboratory is accredited by A2LA to ISO Standard 17025. (Certificate Number 656.01)

Brammer Standard Company, Inc. 14603 Benfer Road, Houston, TX 77069-2895 Telephone: (281) 440-9396 Fax: (281) 440-4432 Website: www.brammerstandard.com

Data Sheet Number SU LAS-13-071913 Page 2/3

References:

	Versions used were those available at the time of testing and characterization			
E 826	Standard Practice for Testing Homogeneity of a Metal Lot or Batch in Solid Form by Spark Atomic Emission Spectrometry			
E 1019	Standard Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel and Cobalt Alloys by Various Combustion and Fusion Techniques			
E 1806	Standard Practice for Sampling Steel and Iron for Determination of Chemical Composition			
ISO Standard 1	17025:2005 General requirements for the competence of testing and calibration laboratories			
ISO Standard 9	0001:2008 Quality Management Systems - Requirements			
ISO Guide 30:1	1992 Terms and definitions used in connection with reference materials + 2008 amendment			
ISO Guide 31:2	2000 Reference materials - Contents of certificates and labels			
ISO Guide 33:2	2000 Uses of certified reference materials			
ISO Guide 34:2	2009 General requirements for the competence of reference material producers			
ISO Guide 35:2	2006 Reference Materials - General and statistical principles for certification			
ASTM docume	nts available from ASTM, 1916 Race Street, Philadelphia, PA, 19103.			
ISO Guides and	d Standards available from Global Engineering - <u>www.global.ihs.com</u>			
Other useful do	ocuments available from NIST, U.S. Department of Commerce, Gaithersburg, MD 20899.			
NIST Special P	ublication 260-100, Handbook for SRM Users			
	bublication 829, Use of NIST Standard Reference Materials for Decisions on Performance of Analytical ods and Laboratories			
Certified by: _	on July 19, 2013. Beau R. Brammer			
	Deau K. Diaminei			