

INDEX

ALUMINUM IN STEEL [7](#)

BORON [3](#)

CALCIUM IN STEEL [7](#)

CARBON STEEL [3, 4](#)

CAST IRON [20, 21, 22, 23, 24](#)

GRAPHITIC CARBON [20](#)

HIGH ALLOY STEEL [19](#)

HIGH NICKEL STEEL [15](#)

IRON [2](#)

LEADED STEEL [7](#)

LOW ALLOY STEEL [5, 6, 7, 9, 10](#)

LOW NICKEL STAINLESS STEEL [16](#)

MANGANESE STEEL [15](#)

MARAGING STEEL [15](#)

MILD STEEL [7, 8, 9](#)

NICKEL BINARY [7](#)

NICKEL STEEL [15](#)

NITROGEN IN STEEL [7](#)

POWDER [2, 13, 17, 19, 25](#)

RARE EARTHS [21](#)

RESULFURIZED STEEL [11](#)

SILICON STEEL [11, 12](#)

SOLUBLE BORON [3](#)

STAINLESS STEEL [16, 17, 18](#)

TOOL STEEL [13, 14](#)

IRON CHIPS AND POWDER

= class, where 1 = CRM and 2 = RM analysis listed in mass %

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	N	Al	Co	Mo	Nb	O	Sn	Ti	V	W	
1	NCS HC15014	0.0208	0.246	0.0121	0.007	0.0922	0.020	0.0202	0.013	.	0.046	0.0012	.	.	.	
1	SRM 2165	(0.0063)	0.144	0.0052	0.003643	(0.0040)	0.0013	0.155	0.050	.	(0.0060)	0.0012	0.0055	0.0004	.	0.002	0.0051	0.0040	.	
1	IARM 27G	(0.003)	(0.003)	(0.003)	0.0011	(0.07)	0.040	0.045	0.043	(0.0003)	(0.0013)	(0.0009)	(0.002)	(0.002)	0.025	(0.001)	<0.005	(0.001)	<0.005	
1	NCS HC11011b	0.0023	0.013	0.0014	0.0014	0.0023	0.0045	0.0027	0.0066	0.0045	(<0.0001)	0.0012	0.00030	(0.00004)	.	0.00015	(<0.0001)	(<0.0001)	(0.00004)	
1	VS S1/4	0.0023	0.0009	0.0010	0.0021	0.0160	0.0048	0.0210	0.0025	0.025	0.041	0.0007	0.00054	.	.	0.00021	0.00019	.	.	
2	TL 1669C	0.00226	0.0955	0.0137	0.0100	0.0093	0.0217	0.0160	0.0246	0.0024	0.03553	0.0019	0.0011	0.00046	.	0.0071	0.0504	(0.0006)	.	
1	Y TSC101	0.0013	0.00018	(0.0001)	0.0010	0.0014	0.00024	0.0052	0.00019	.	0.00065	(0.0001)	0.0033	.	Cd: (0.0001)	(0.0001)	(0.0001)	(0.0001)	(0.0001)	
1	ECRM 088-2	0.0006	0.0809	0.0048	0.0070	0.0052	0.0163	0.0275	0.0244	.	.	0.0061	0.00029	.	
1	JSS 003-8	0.00040	0.00109	0.00040	0.00016	0.00064	0.00039	0.00007	0.00012	0.00068	0.00667	0.000046	0.000020	0.000048	.	0.000020	<0.00006	(0.000006)	(0.00001)	
1	JSS 003-7	0.00034	0.00054	0.00038	0.00016	0.00052	0.00032	0.00007	0.00013	0.00061	0.00682	0.000047	0.000017	<0.0002	.	0.000017	<0.00006	trace	trace	
1	SRM 937	99.90% Fe
1	ECRM 097-2C	.	0.012	0.00538	0.00181	0.00285	0.00793	0.0241	0.0213	0.00294	.	0.0139	0.00370	.	.	0.00043	.	0.00011	0.00386	

analysis listed in mg/kg except

Number	Ag	As	B	Bi	Ca	Mg	Pb	Sb	Se	Ta	Te	Zn	Zr	Units
NCS HC15014	.	2	.	.	.	0.85	5	100 g chips
SRM 2165	2	10	9.44	(<1)	.	(<1)	3	10	150 g chips
IARM 27G	.	(16)	(6)	<70	(2)	(2)	(20)	<100	.	<200	.	<50	(30)	100 g chips
NCS HC11011b	.	26	2.3	(<0.1)	3	.	(0.2)	2.9	<0.1	(<0.1)	<0.1	1.5	<0.1	50 g chips also trace Cd, Ce, Hf, La, and Mg
VS S1/4	.	2.8	.	.	.	1.2	2.2	.	100 g chips
TL 1669C	.	17	3.8	.	1.7	(1.6)	1.3	4.9	.	.	.	2.7	(2.1)	100 g chips
Y TSC101	.	(1)	.	(1)	17	2.2	(1)	(1)	.	.	.	(1)	.	15 g powder Fe > 99.984%
ECRM 088-2	7.2	100 g chips
JSS 003-8	.	(0.1)	(0.26)	<0.7	<1	<1	0.04	<2	<1	<0.7	<1	(0.2)	<0.5	150 g chips also trace Cd, Ce, and La
JSS 003-7	.	<1	0.18	<0.7	<1	<1	(0.02)	<2	<1	<0.7	<1	(0.2)	<0.5	150 g chips
SRM 937	50 g chips
ECRM 097-2C	.	28.1	1.2	1.2	.	1.5	.	1.4	.	100 g chips

There are also purity iron powders in our
Geological catalog, Iron Ore section

<http://brammerstandard.com/pdf/geological.pdf>

CRM IRON CHIPS AND POWDER

analysis listed in mass %

Number	C	Mn	P	S	Si	Cu	Ni	Cr	N	Al	Ins.Al	As	B	Co	Mo	Ti	Units
GBW 01407a	0.080	0.358	0.036	0.031	0.506	0.254	0.203	0.170	0.018	0.432	50 g chips
NCS HC15017	0.061	0.319	0.04	0.005	0.166	0.02	0.02	0.022	0.0146	0.284	50 g chips
BAM 031-3	0.055	0.329	0.014	0.021	0.037	0.020	.	.	0.0050	0.054	.	0.013	100 g chips
BAM 031-2	0.0344	0.296	0.053	(0.052)	.	0.083	.	0.012	.	.	.	0.061	100 g chips
NCS HC15005a	0.030	0.106	0.0061	0.025	0.182	0.123	0.162	0.147	0.011	0.205	50 g chips
ECRM 083-1	0.028	0.289	0.0077	0.0100	.	0.016	0.014	.	0.00189	100 g chips
NCS HC15004	0.0272	0.246	0.0094	0.012	0.0994	0.031	0.0202	0.013	.	0.37	100 g chips
NCS HC15004a	0.027	0.195	0.014	0.0063	0.018	0.089	0.116	0.048	0.016	0.290	50 g chips
NCS HC15016	0.022	0.201	0.0072	0.0027	0.199	0.066	0.066	0.032	0.0123	0.217	50 g chips
NCS HC15003a	0.012	0.034	0.0019	0.020	0.017	0.021	0.030	0.016	0.015	0.060	50 g chips
NCS HC13013	0.0041	0.126	0.0085	0.021	0.018	150 g powder
IPT 73	0.0034	0.044	0.0034	0.0049	0.0028	0.076	0.033	0.030	0.0076	0.004	.	TEMPORARILY UNAVAILABLE	

Number	C	Mn	P	S	Si	Cu	Ni	Cr	N	Al	Ins.Al	As	B	Co	Mo	Ti	Units
--------	---	----	---	---	----	----	----	----	---	----	--------	----	---	----	----	----	-------

last

BRAMMER STANDARD ONLINE CATALOG-IRON CHIPS

CRM		CARBON STEEL CHIPS WITH NITROGEN													analysis listed in mass %										JSS: 150 g units		all others: 100 g units		
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Mo	N	Nb	Ti	V	W	As	B	Ca	Co	O	Pb	Sn	Zr						
ECRM 090-1C *	1.054	0.226	0.013	0.0095	0.281	.	0.053	0.121	.	0.009	0.0146	0.00043	.	0.204	0.00239	.	.						
VS U7/9	1.02	0.255	0.0080	0.0158	0.156	.	0.102	0.123	.	.	0.0094	.	.	.	(0.01)						
JSS 066-5	0.835	0.853	0.0145	0.0035	0.244	0.0106	.	.	0.0218	.	0.0031	last						
JSS 066-7	0.830	0.732	0.0151	0.00548	0.199	0.0103	.	.	0.0277	.	0.00524						
VS UNL4/3	0.736	0.851	0.0200	0.028	0.220	0.037	0.055	0.023	.	.	0.0041	0.127						
VS UNL4/4	0.734	0.853	0.0200	0.0268	0.221	0.037	0.055	0.023	.	.	0.0041	0.123						
VS U23	0.665	0.560	0.0197	0.0277	0.300	0.038	0.024	0.055	.	.	0.0050						
JSS 061-10	0.638	0.490	0.0214	0.0121	0.166	0.0085	.	.	0.00134	.	0.00283						
JSS 061-8	0.630	0.484	0.0099	0.0050	0.243	0.0238	.	.	0.030	.	0.0037	last						
IARM 373A	0.63	0.70	0.0123	0.031	0.22	0.107	0.048	0.096	0.002	0.0176	0.0088	0.001	0.0017	0.023	(0.002)	0.0046	0.0003	0.0005	0.005	0.002	(0.001)	0.0069	(0.003)						
VS U24	0.563	0.611	0.0129	0.0214	0.334	0.0129	0.0138	0.059	.	.	0.0079						
DSZU CX04	0.559	0.607	0.0133	0.0216	0.327	0.0147	(0.017)	0.0573	(0.004)	.	0.0079	.	(0.002)	(0.005)	.	(0.002)	.	.	(0.002)	.	(0.0001)	(0.0009)	250 g						
JSS 057-9	0.529	0.759	0.0164	0.0199	0.182	0.0128	.	.	0.0272	.	0.0052	last						
IARMFel050-18	0.499	0.79	0.0045	0.027	0.223	0.179	0.068	0.100	(0.003)	0.018	0.0097	(0.0013)	0.0008	0.0270	.	(0.0030)	(0.0005)	.	0.0056	0.0026	.	.	0.0103						
IARM 200C	0.453	0.775	0.007	0.020	0.241	0.236	0.094	0.100	0.002	0.023	0.0079	0.0014	0.0011	0.025	(0.002)	0.006	0.0003	0.0020	0.007	0.0037	.	.	0.0090	(0.004)					
IARM 210D	0.412	0.73	0.0052	0.030	0.230	0.273	0.122	0.096	(0.002)	0.034	0.011	0.001	0.0104	0.024	(0.002)	0.0059	0.0004	0.0009	0.007	0.0034	0.001	0.010	(0.001)						
JSS 050-8	0.410	0.762	0.0119	0.00278	0.207	0.0118	.	.	0.0307	.	0.00442	.	Sol.Al: 0.0295						
IARM 349A	0.41	1.49	0.011	0.025	0.192	0.300	0.178	0.189	0.0020	0.059	0.0100	0.0012	0.0013	0.027	0.004	0.005	0.0003	0.0015	0.0085	0.003	(0.001)	0.015	(0.002)						
JSS 050-6	0.38	0.50	0.013	0.0057	0.19	0.008	.	.	0.023	.	0.0029	last						
JSS 050-7	0.378	0.498	0.0129	0.0058	0.190	0.0075	.	.	0.0233T	.	0.0028	.	Sol.Al: 0.0224	last						
IARM 360A	0.331	0.733	0.008	0.023	0.260	0.235	0.078	0.113	0.0016	0.024	0.0102	0.0015	0.0010	0.039	(0.001)	0.0060	0.0004	0.0017	0.0067	0.004	(0.001)	0.010	(0.001)						
IARM 209D	0.322	0.68	0.0084	0.021	0.268	0.243	0.079	0.137	(0.003)	0.037	0.0107	0.0014	0.0011	0.042	(0.002)	0.0060	0.0002	0.002	0.007	0.005	0.001	0.012	.						
BCS 434/2	0.275	1.54	0.061	0.0141	0.51	.	0.037	0.238	.	.	0.0104	0.038						
IARM 359A	0.267	0.686	0.0094	0.020	0.233	0.186	0.068	0.121	0.002	0.023	0.0094	0.002	0.0009	0.027	(0.001)	0.0073	0.0003	0.0013	0.0069	0.0044	(0.001)	0.0100	(0.001)						
IARMFel020-18	0.226	0.547	0.006	0.024	0.235	0.198	0.078	0.125	(0.003)	0.0252	0.0098	(0.0012)	.	0.036	.	0.0044	.	(0.002)	0.0065	(0.007)	.	.	0.0080	.					
JSS 030-10	0.210	0.528	0.0175	0.0166	0.224	0.0091	.	.	0.00278	.	0.00426	.	Sol.Al:0.00185						
IARM 213C	0.201	0.922	0.007	0.025	0.25	0.149	0.068	0.099	0.0019	0.022	0.0116	0.0011	0.0010	0.035	(0.002)	0.0058	0.0003	0.0014	0.0074	0.0042	0.0011	0.0081	(0.0004)						
IMZ 1.18/5	0.20	1.43	0.023	0.030	0.44	0.11	0.077	0.073	0.098	.	0.0051	.	Sol.Al: 0.091						
JSS 030-9	0.195	0.750	0.0237	0.0076	0.237	0.0239	.	.	0.0227	.	0.00312	.	Sol.Al: 0.0218	last						
IARM 28B	0.18	0.75	0.010	0.029	0.23	0.36	0.13	0.13	0.003	0.029	0.0094	0.002	0.002	0.002	(<0.001)	0.008	0.0002	.	0.011	0.0070	(<0.01)	0.014	.						
IARM 28D	0.1700	0.80	0.010	0.016	0.27	0.11	0.090	0.081	0.0110	0.025	0.0079	0.002	0.001	0.019	(0.003)	0.0039	0.0002	.	0.009	0.006	.	0.008	.						
VS U1/12	0.109	0.541	0.0217	0.0249	0.214	0.063	0.056	0.045	.	.	0.0072						
VS UNL3/4	0.105	0.897	0.101	0.130	0.221	0.135	0.096	0.076	.	.	0.0038	(0.005)						
VS U1/11	0.101	0.578	0.0233	0.0267	0.218	0.064	0.067	0.049	.	.	0.0076						
JSS 057-11	0.578	0.803	0.0148	0.0161	0.185	0.0139	.	.	0.0340	.	0.00490						
ECRM 057-2C	0.0507	0.246	0.0120	0.0127	.	0.0146	0.0096	0.0114	0.059	.	0.0023						
IARMFel1215-18	0.043	0.96	0.059	0.29	(0.006)	0.164	0.055	0.051	.	0.016	0.0109	0.0012	0.0007	0.0020	.	0.0043	.	.	0.0055	.	Sb:0.0018	0.0083	.						
ECRM 083-2C	0.0315	0.2160	0.0106	0.00561	0.00747	0.0127	0.0116	0.0219	0.0784	.	0.00157	0.00177	.	.	0.00236	.	.	.	0.00439						
DSZU CX01	0.029	0.086	0.0063	0.0085	0.146	0.209	0.147	0.222	(0.014)	(0.031)	0.0160	.	(0.003)	(0.003)	(0.007)	(0.01)	(0.0002)	.	(0.011)	.	(0.009)	(0.012)	200 g						
BCS 111	0.0258	0.155	0.0033	0.0054	0.0253	0.0171	0.0387	0.0197	0.0348	0.0008	0.0034	(0.0005)	0.0004	0.0009	.	0.0021	.	.	0.0144	.	.	0.0015	.						
BCS 431/2	0.0249	0.902	0.121	0.0065	0.015	.	0.040	0.049	.	.	0.0052	0.0040						
IMZ 1.7/4	0.017	0.13	0.013	0.032	(0.005)	0.016	0.012	0.004	0.0040	0.0017	0.0044	Sb:0.001	0.001	0.001	0.0005	0.0045	0.001	Sol.Al: 0.0022	Zn:0.001	.	0.0005	0.0021	.						
VS U18/1	0.0122	0.130	0.0038	0.0089	0.036	0.018	0.0163	0.026	.	.	0.0145						
VS UNL1/2	0.012	0.131	0.0036	0.0091	0.033	0.019	0.16	0.026	.	(0.001)	0.0151	0.0028						
GBW 01403a	0.012	0.034	0.0019	0.020	0.017	0.021	0.030	0.016	0.060	.	0.015	last						
VS S2/5	0.0077	0.028	0.0032	0.0054	0.046	0.069	0.072	0.047	0.319	.	0.0070	0.0026						
BCS 111/1	0.0070	0.1623	0.0045	0.0049	0.0039	0.0089	0.0161	0.0055	.	0.0005	0.0025	.	0.0004	0.0002	.	0.0011	.	.	0.0053	.	.	0.0006	.						
BCS 432/2	0.0065	0.712	0.017	0.036	0.082	.	0.0196	0.016	.	.	0.0066	0.0174						
VS U25	0.0025	0.104	0.0053	0.0054	0.032	0.0075	0.0061	0.0147	.	.	0.0063	(0.001)						

* ECRM 090-1C also contains Ga: 0.00228 and Zn: 0.00209

CRM BORON IN STEEL

Number	Type	Total Boron%	Soluble Boron%	Units
VS 5-3/1	Low Alloy	0.0096	0.0058	100 g
VS 5-2/1	Carbon Steel	0.0030	0.0017	100 g
VS 5-1/1	Low Alloy	0.0012	0.0007	100 g
IMZ 1.30	Steel	0.0002	.	100 g

BRAMMER STANDARD ONLINE CATALOG-IRON CHIPS

CRM	LOW ALLOY STEEL CHIPS WITH NITROGEN																						IPT 96: 120 g		JK, JSS, NCS, SRM: 150 g		all others: 100 g		
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn	Other						
BCS 401/2	0.935	1.19	0.026	0.0078	0.60	0.101	0.019	0.138	0.074	.	0.0042	0.49	0.0159	.	.	0.496						
IMZ C-119	0.93	1.15	0.018	0.006	0.16	0.042	0.049	0.062	0.010	0.007	.	.	0.0086	.	(0.0007)	0.006	Ca: (0.0002)						
BAM 036-1	0.858	0.327	0.0074	0.0095	0.194	0.065	(0.058)	(0.091)	(0.015)	.	.	.	0.010	.	.	(0.019)	.	0.0233						
ECRM 182-1	0.790	0.389	0.0076	0.011	0.368	0.141	0.152	0.591	0.020	.	.	.	0.0102	.	.	0.1770	.	0.0202						
JK 3B	0.742	0.803	0.0101	0.0071	0.251	0.0175	0.0591	0.0529	0.0036	.	0.0048	0.0051	0.0054	.	.	(0.002)	0.0044						
ECRM 059-2C	0.721	0.495	0.0046	0.0084	0.188	0.0074	0.0198	0.0090	0.00045	0.00020	.	0.0018	0.0051						
IPT 29A	0.614	0.565	0.012	0.0076	0.372	0.012	0.794	0.845	.	0.028	.	0.276	0.0039	.	.	0.080	0.077	0.008	Sb: 0.031					
IMZ C-120	0.60	0.40	(0.049)	0.026	0.34	0.10	0.085	0.20	0.033	.	.	.	0.0115	0.065	.	.	.	0.007	0.008	Sb: 0.031					
ECRM 079-2	0.596	0.743	0.0233	0.192	0.247	0.046	0.022	0.0379	0.021	.	.	.	0.0074	0.004	0.0037						
ECRM 055-2C	0.5199	0.687	0.0102	0.0205	0.3094	0.2089	0.3121	0.3217	.	.	0.0257	0.0960	0.01069	.	0.00104	0.00245	0.0166	0.0187	0.0162	Sb: 0.00376					
ECRM 091-1	0.518	0.310	0.312	.	.	.	0.098	0.0111						
IARMe6150-22	0.512	0.813	0.026	0.0024	0.303	0.135	0.098	0.912	0.027	.	0.0081	0.0170	0.0100	.	0.0014	0.161	0.007	0.0060	.	0.0014	Sb:0.0016	0.0069	Ca: 0.0014						
IARM 299A	0.469	0.70	0.008	0.002	0.22	0.100	0.57	1.03	0.092	.	0.0054	0.99	0.0028	0.006	0.0038	0.120	0.010	0.003	0.0003	(0.002)	(0.001)	0.0055	0.0055						
BAM 030-4	0.456	0.603	0.018	0.021	0.318	0.061	0.042	0.117	0.042	.	.	.	0.0051	0.012	0.0055						
ECRM 080-1	0.452	1.116	0.028	0.024	0.317	.	.	0.025	0.0073	(0.006)	last					
IARM Fe300M22	0.431	0.735	0.0046	(0.0008)	1.65	0.0713	1.90	0.773	0.051	.	0.033	0.393	0.0018	.	0.0018	0.075	0.0115	0.0038	0.0050						
IARM 30H	0.425	0.937	0.015	0.022	0.253	0.131	0.063	0.97	0.020	.	0.0071	0.199	0.0081	(0.003)	(0.0024)	(0.0040)	(0.007)	0.0046	(0.0007)	(0.0016)	(0.0005)	0.008	Sb: 0.0013						
IARM 305B	0.425	0.58	0.011	0.014	0.349	0.214	0.156	1.63	0.92	.	0.007	0.32	0.0044	0.002	0.0044	0.004	(0.004)	(0.006)	0.0006	0.0006	(0.0003)	0.011	Ca: 0.0007						
IARM 252D	0.423	0.842	0.0075	0.0128	0.256	0.270	0.424	0.468	0.024	.	0.0078	0.204	0.0068	0.0013	0.0012	0.0022	(0.004)	0.0053	(0.0002)	(0.0013)	(0.0004)	0.012	Sb: 0.0024						
IARM 252C	0.416	0.92	0.025	0.008	0.248	0.109	0.505	0.501	0.017	.	0.008	0.205	0.0083	0.002	0.001	0.005	<0.005	0.004	(0.0001)	(0.002)	0.001	0.007	last						
SRM 12h	0.407	0.842	0.018	0.027	0.235	0.073	0.032	0.074	.	.	.	0.006	0.006	.	.	0.003						
IARM 252F	0.406	0.88	0.011	0.009	0.247	0.182	0.412	0.463	0.026	.	0.0086	0.210	0.0059	0.0016	0.0010	(0.003)	(0.003)	(0.006)	0.006						
SRM 139b	0.403	0.778	0.013	0.019	0.242	0.097	0.510	0.488	.	.	.	0.182	0.007	.	.	(0.004)						
IARM 31G	0.40	0.689	0.0136	(0.013)	0.262	0.183	1.814	0.820	0.0214	.	0.0083	0.223	0.0069	(0.0023)	0.0015	0.0036	(0.004)	(0.004)	0.0004	.	.	.	0.0077						
SRM 100b	0.397	1.89	0.023	0.028	0.210	0.064	0.030	0.063	.	.	.	0.237	0.004	.	.	0.003						
JSS 502-7	0.396	0.759	0.0187	0.0106	0.248	0.150	0.110	1.048	0.0234	0.0222	.	0.218	0.0079	.	.	0.0056						
IARM 31F	0.39	0.70	0.012	0.018	0.258	0.181	1.78	0.83	0.026	last	0.008	0.204	0.0058	(0.002)	0.0017	0.0028	(0.005)	(0.005)	0.0003	(0.001)	(0.001)	0.015	Ca: 0.0005						
IARM 322A	0.317	1.40	0.009	0.021	0.42	0.33	0.28	0.159	0.002	Sb:0.0027	0.006	0.021	0.023	(0.001)	0.0016	0.124	0.003	0.005	0.0009	0.006	(0.001)	0.016	Ca:0.0019 last						
IARM 143F	0.308	0.573	(0.011)	0.0177	0.23	0.221	0.088	0.865	0.026	.	0.010	0.163	0.0098	(0.0015)	(0.0012)	0.0046	(0.003)	0.0051	.	(0.003)	.	.	0.010						
IPT 142	0.304	0.801	0.022	0.025	0.242	0.226	0.421	0.505	0.029	0.027	0.008	0.179	0.0133	0.020						

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn	Other
BAM 032-2	0.271	0.556	0.0129	0.0254	0.282	0.085	(0.040)	(0.088)	0.0044	0.020	(0.006)
ECRM 017-1	0.261	0.725	0.015	0.022	0.266	0.062	0.085	0.044	0.0091
IARM FeF1-21	0.235	0.811	0.012	0.0060	0.278	0.0125	0.058	0.188	0.028	.	0.0095	0.48	0.0070	0.0087	0.0021	0.0191	0.0022	0.0021	0.0010	0.0024	0.0009	0.0016	Zr: 0.0014
IARM 195B	0.255	1.84	0.018	0.005	1.16	0.52	1.00	0.216	0.029	.	0.101	0.052	0.0070	0.007	0.002	0.082	0.38	0.021	0.0039	0.0017	0.002	0.084	last
ECRM 197-1C	0.219	0.792	0.0073	0.0232	0.275	0.152	0.148	0.451	0.0313	.	0.0135	0.402	0.0114	.	.	0.0005	.	0.0083	0.0097
JSS 030-11	0.213	0.528	0.0179	0.0166	0.226	0.0092	.	.	0.00267	0.00174	.	.	0.00427
ECRM 187-2C	0.2038	1.257	0.0066	0.0300	0.2111	0.1288	0.1755	1.132	0.0223	.	0.0112	0.0623	0.0105	.	.	0.0122	.	0.0057	0.00048	.	.	.	0.0237
JSS 514-8	0.201	0.836	0.0166	0.0188	0.186	0.0120	0.0282	1.20	0.031	.	0.008	0.265	0.0096	.	.	0.0059	last
ECRM 192-1C	0.1875	1.377	0.0029	0.0010	0.219	0.0453	0.755	0.0717	0.0306	0.0285	0.0055	0.482	0.0118
JK 21	0.1741	1.46	0.0148	0.011	0.36	0.045	0.035	0.024	0.005*	0.032	0.008	0.004	0.008	0.0175	0.0008	0.002	* = Insoluble Aluminum				.	.	0.006
IMZ C-195	0.17	1.18	0.010	0.0008	0.29	0.11	0.18	1.04	(0.017)	.	.	0.076	0.0061	.	(0.012)	(0.005)
ECRM 194-2C	0.1694	1.282	0.0137	0.00049	0.2974	0.0313	0.3316	0.760	0.0669	.	0.00328	0.402	0.00319	0.0290	0.00322	0.00161	.	0.00208	0.00155
JSS 517-8	0.159	1.056	0.0205	0.0101	0.246	0.1507	3.02	1.61	0.0223	0.0206	.	0.517	0.0111	.	.	0.0057
ECRM 194-1C	0.1532	1.188	0.0097	0.00059	0.431	0.0751	0.3417	0.733	0.0837	.	.	0.2857	0.0115	.	.	0.0243	.	0.0042	0.0020	.	.	.	Ca: 0.0026
VS UNL17	0.139	0.436	0.0205	0.0189	0.394	0.299	0.378	0.725	0.0043
ECRM 060-1	0.122	0.45	(0.024)	(0.031)	(0.17)	(0.060)	(0.039)	(0.028)	(0.004)	.	.	(<0.005)	0.0040	(0.005)
VS UNL5/3	0.115	1.36	0.0053	0.0035	0.484	.	.	.	0.021	.	.	.	0.0194	0.066	.	0.085
IPT 96	0.109	0.845	0.017	0.0049	0.286	0.272	0.018	0.614	.	0.041	0.0048	.	0.0092	0.0072
BAM 042-1	0.108	0.666	0.007	0.024	0.037	0.041	0.029	0.016	0.010	.	.	.	0.0078	0.054
IMZ C-169	0.099	0.54	0.015	0.0155	0.35	0.128	0.073	2.20	0.075	.	0.012	1.03	0.0193	(0.0045)	0.001	(0.016)	(0.001)	0.062
IARM 37C	0.096	0.408	0.014	(0.004)	0.31	0.121	0.148	4.34	(0.010)	.	0.015	0.500	0.008	(0.004)	(0.0025)	0.017	(0.012)	(0.009)	0.009
VS UNL10/3	0.095	0.678																					

BRAMMER STANDARD ONLINE CATALOG-IRON CHIPS

CRM LOW ALLOY STEEL CHIPS

analysis listed in mass % except * which is mg/kg

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Nb	Ti	V	W	As	B	Bt	Bs	Ca*	Sn	Units	
VS UNL9/3	1.19	0.347	0.0079	0.0152	0.218	0.176	0.188	1.30	100 g	
IARM 49E	1.03	0.364	(0.006)	(0.002)	0.248	0.076	0.043	1.43	0.024	.	(0.006)	0.017	(0.003)	0.0060	0.066	.	0.0029	0.0065	100 g	
SRM 16f	0.97	0.404	0.014	0.026	0.214	0.006	0.008	0.020	.	.	(0.003)	(0.003)	.	.	(0.002)	150 g	
SRM 163	0.933	0.897	0.007	0.027	0.488	0.087	0.081	0.982	.	.	.	0.029	100 g	
SRM 155	0.905	1.24	0.015	0.010	0.322	0.083	0.100	0.485	.	.	.	0.039	.	.	(0.014)	0.517	150 g	
BCS 404/1	0.74	0.31	0.057	0.024	0.87	0.34	0.40	0.48	.	.	.	0.31	.	.	0.11	100 g	
VS UNL 12/4	0.736	0.360	0.0070	0.0034	0.276	0.387	0.316	0.794	.	.	.	0.200	.	.	0.685	100 g	
SRM 14g	0.735	0.456	0.006	0.019	0.232	0.047	0.030	0.081	0.025	.	(0.003)	0.011	.	<0.001	0.0008	150 g	
IPT 60A	0.715	.	.	0.012	100 g	
SRM 13g	0.613	0.853	0.006	0.031	0.35	0.066	0.061	0.050	0.04	0.001	150 g	
IPT 33	0.603	0.772	0.011	0.007	0.133	0.036	0.059	0.793	.	0.099	100 g	
CMSI 1184	0.558	1.47	0.0235	0.032	0.507	0.161	0.246	0.74	.	.	.	0.245	100 g	
SRM 30f	0.490	0.79	0.011	0.009	0.283	0.074	0.070	0.945	0.182	150 g	
SRM 152a	0.486	0.717	0.012	0.030	0.202	0.023	0.056	0.046	.	.	.	0.036	.	.	0.001	0.032	150 g	
SRM 20g	0.462	0.665	0.012	0.028	0.305	0.034	0.034	0.036	0.040	.	.	0.008	.	.	0.002	150 g	
VS UNL11/4	0.436	0.642	0.022	0.0127	0.320	0.198	1.39	0.692	.	.	.	0.196	.	.	0.0033	.	0.436	100 g	
IPT 12A	0.435	0.908	0.012	0.009	0.348	0.082	0.508	0.528	.	.	.	0.172	100 g	
CMSI 1111	0.43	0.18	0.018	0.036	0.685	0.035	0.020	0.020	.	0.036	.	0.28	.	0.087	0.081	0.0028	.	.	100 g	
DSZU CX08	0.410	0.533	0.0110	0.0241	0.220	0.086	0.053	0.835	150 g	
SRM 178	0.395	0.824	0.012	0.014	0.163	0.032	0.010	0.016	.	.	.	0.003	.	.	0.001	150 g	
ECRM 084-1C	0.391	0.860	0.018	0.029	0.265	0.267	0.154	0.033	0.023	100 g	
NCS HC28214	0.312	1.35	0.023	0.017	0.292	0.243	0.117	0.069	0.0421	0.040	0.013	0.010	.	0.023	0.0013	0.0022	100 g	
IARM 330B	0.302	0.82	0.0075	(0.003)	0.227	0.084	1.856	0.807	0.023	.	0.013	0.406	(0.002)	.	0.076	0.024	0.0047	100 g	
ECRM 086-1C	0.297	0.879	0.024	0.037	0.206	0.320	0.168	0.150	0.023	0.026	100 g	
NCS HC13207	0.294	1.48	0.036	0.009	0.070	0.035	0.019	0.037	.	0.029	.	0.038	.	0.023	0.025	0.011	.	.	100 g	
SRM 72g	0.278	0.492	0.009	0.014	0.223	0.011	(0.016)	0.905	.	.	.	0.170	.	.	(0.003)	150 g	
IARM 381A	0.272	1.16	0.013	0.043	0.269	0.379	0.185	0.129	0.0023	.	0.011	0.0341	0.0018	(0.002)	0.0299	(0.003)	0.0055	0.0137	100 g	
IARM 380A	0.268	1.24	0.021	0.025	0.181	0.265	0.114	0.192	0.0029	.	(0.010)	0.059	(0.0020)	.	0.0475	(0.009)	(0.007)	0.0117	100 g	
IARM 380B	0.243	1.27	0.016	0.027	0.238	0.307	0.182	0.153	(0.0021)	.	0.014	0.055	(0.0016)	0.0011	0.049	(0.003)	0.0058	0.0132	100 g	
NCS HC28210	0.224	0.764	0.026	0.0083	0.288	0.175	0.452	0.621	0.0087	0.0051	0.013	0.254	.	0.0020	0.0033	0.0018	100 g	
SRM 293	0.222	0.96	0.018	0.022	0.30	0.032	0.48	0.51	0.039	.	.	0.20	.	.	0.004	150 g	
ECRM 054-1	0.22	(0.88)	0.092	(0.10)	(0.05)	(0.21)	(0.14)	(0.17)	.	.	.	(0.02)	.	(0.01)	.	(0.03)	100 g	
IPT 16A	0.212	0.820	0.019	0.018	0.287	0.053	0.559	0.493	.	0.016	.	0.201	100 g	
SRM 19h	0.215	0.393	0.016	0.022	0.211	0.466	0.248	0.173	(0.002)	.	.	0.038	.	.	(0.003)	150 g	
ECRM 061-1	0.210	(0.61)	(0.019)	(0.034)	0.12	(0.10)	(0.21)	100 g	
CMSI 1142	0.21	1.44	0.042	0.025	0.77	0.14	0.051	0.031	100 g	
NM 223.6A	0.21	0.65	0.038	0.036	0.28	0.14	0.98	0.88	0.041	.	0.015	0.17	100 g	
CMSI 1124	0.209	0.609	0.015	0.014	0.298	0.089	0.093	0.808	.	.	.	0.0088	.	.	0.0032	100 g	
NCS HC28208	0.203	0.502	0.020	0.018	0.221	0.181	0.050	0.907	0.0142	0.012	0.013	0.194	.	0.0010	0.0025	0.0024	100 g	
NCS HC28213	0.202	1.19	0.015	0.014	0.271	0.223	0.128	0.082	0.0419	0.040	0.011	0.017	.	0.024	0.0013	0.0016	100 g	
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Nb	Ti	V	W	As	B	Bt	Bs	Ca*	Sn	Units	
VS UNL7/3	0.200	0.688	0.0037	0.0033	0.250	0.256	0.631	0.477	0.037	.	.	.	0.0020	100 g
NM 223.6	0.20	0.64	0.04	0.034	0.3	0.14	0.97	0.86	0.04	.	0.014	0.17	100 g	
IARM 155F	0.199	0.617	0.008	(0.013)	0.223	0.219	3.36	0.144	0.0356	.	0.012	0.244	0.0016	0.0020	0.0015	(0.004)	(0.006)	0.0084	100 g	
IMZ C-162	0.19	1.31	0.021	0.014	0.59	0.077	1.64	0.91	(0.040)	.	.	0.52	.	0.12	0.045	100 g	
ECRM 087-1C	0.174	0.671	0.010	0.046	0.263	0.171	0.118	0.078	.	.	0.015	0.021	0.024	0.017	100 g	
CMSI 1140	0.166	1.33	0.014	0.022	0.162	0.017	0.040	0.027	.	0.029	.	0.003	.	0.034	0.110	0.0011	.	.	100 g	
IPT 93	0.140	1.02	0.036	0.028	0.261	0.129	0.053	0.104	0.045	.	.	0.013	.	0.034	.	.	.	0.0022	100 g	
VS UNL8/4	0.134	1.19	0.041	0.189	0.047	.	0.076	0.156	Pb: 0.160	.	100 g	
IPT 47	0.122	0.959	0.013	0.020	0.273	0.245	0.221	0.573	0.032	100 g	
SS 456/3	0.1215	0.2121	0.0228	0.0246	0.267	.	0.0174	0.0257	0.0393	.	0.0520	0.0013	0.0113	.	0.0214	.	Pb:0.0153	0.0014	.	Pb:0.0153	Sb:0.0222	.	100 g	
DSZU CX011	0.120	0.562	0.0123	0.0058	0.319	0.131	0.203	0.962	0.023	.	(0.01)	0.286	(0.003)	0.0018	0.178	.	0.007	(0.0002)	.	.	10	0.006	100 g	
VS S61	0.111	0.477	0.0097	0.0089	0.318	0.147	4.84	0.221	100 g	
ECRM 096-2C	0.1050	1.320	0.0128	0.0016	0.263	0.0170	0.0253	0.0243	0.0460	.	.	0.0020	0.0252	20	.	100 g	
NCS HC28215	0.104	0.476	0.093	0.024	0.308	0.295	0.011	0.016	.	0.0015	0.0057	.	.	(0.004)	0.0034	100 g	
JSS 154-17	0.1001	1.209	0.00524	0.0052	0.606	0.200	0.502	2.01	0.0082	0.0073	.	0.394	.	.	0.298	150 g	
ECRM 081-1	0.099	0.605	0.014	0.014	0.105	0.026	0.042	.	0.023	.	(0.017)	100 g	
CMSI 1104	0.097	0.87	0.011	0.096	0.29	0.034	0.29	0.76	0.073	100 g	
SRM 8k	0.0806	0.5046	0.0956	0.0775	(0.0576)	0.0200	0.1174	0.0467	.	.	.	(0.0397)	.	.	0.0145	150 g	
IMZ C-160	0.077	0.38	0.023	0.004	0.34	0.42	0.30	2.64	0.031	.	.	0.98	.	.	0.10	0.26	100 g	
IMZ C-159	0.075	0.39	0.022	0.005	0.33	0.41	0.31	2.64	0.024	.	.	0.98	.	.	0.10	0.26	100 g	
SRM 2167	0.051	0.022	0.0031	0.008731	0.026	0.0014	(0.002)	0.0015	0.0045	.	0.0050	0.020	0.0095	0.010	0.033	.	0.0005	9.72*	Ag:7*	Sb:20*	0.006	150 g		
BCS 421	(0.049)	(0.11)	(0.012)	(0.027)	(0.07)	0.52	100 g	
CMSI 1112	0.045	0.396	0.054	0.069	0.46	0.030	0.016	0.0095	.	0.028	.	0.11	.	0.041	0.051	0.028	.	.	100 g	
JSS 171-8	0.0406	0.400	.	.	0.196	.	0.101	0.075	0.0374	0.0369	.	0.0296	.	0.0300	.	.	0.0011	.	.	.	28	0.0317	150 g	
JSS 168-8	0.0399	0.417	.	.	0.201	.	0.0226	0.0211	0.038	0.037	.	0.099	.	0										

BRAMMER STANDARD ONLINE CATALOG-IRON CHIPS

CRM		MILD STEEL CHIPS, chart 1 of 2																			analysis listed in mass % except * which is mg/kg	
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	W	As	B	Nb	Pb	Sb	Sn	Units
VS S18/4	1.42	0.199	0.0180	0.0122	0.241	0.142	0.193	0.555	0.262	4.55	100 g
ECRM 188-1	1.094	.	.	0.0113	.	.	(0.28)	1.538	.	.	(0.06)	(0.17)	.	(0.02)	100 g
NCS HC21201	1.090	0.433	0.0112	(0.0005)	0.431	0.158	0.134	1.442	0.0381	0.0363	.	0.060	0.0074	.	.	0.023	.	.	.	0.0025	0.0273	100 g
SRM 2161	(1.02)	0.680	0.0407	0.0347	0.1816	0.2973	1.999	0.2195	0.0539	Zr:0.0132	0.0256	0.1030	0.180	0.0540	(<0.005)	0.0131	21.5*	197.8*	(0.1*)	0.00548	0.0474	150 g
CMSI 1101	0.91	2.09	0.054	0.030	0.056	0.20	0.076	0.10	.	0.015	100 g
BAM 126-1	0.841	1.817	0.0092	0.0050	(0.241)	(0.098)	(0.038)	0.317	0.143	100 g
BCS 403/2	0.750	1.677	0.055	0.0381	0.209	0.221	0.223	0.463	0.0485	.	.	0.088	.	0.341	100 g
VS UNL12/4	0.736	0.360	0.0070	0.0034	0.276	0.387	0.316	0.794	.	.	.	0.200	.	0.685	100 g
IRSID 113-1	0.680	0.586	(0.013)	(0.006)	0.249	0.146	1.744	0.816	.	.	.	0.413	100 g
SRM 363	0.62	1.50	0.029	0.0068	0.74	0.10	0.30	1.31	0.24	Ca:2.2*	0.048	0.028	0.050	0.31	0.046	0.010	13.10*	0.049	0.00186	(0.002)	0.104	150 g
NCS HC28212	0.506	0.664	0.014	0.022	0.304	0.208	0.109	1.04	0.0049	0.002	0.014	0.016	0.0021	0.154	100 g
IPT 31	0.497	0.794	0.021	0.009	0.146	0.251	0.106	1.15	.	0.087	.	.	.	0.250	100 g
BCS 407/2	0.490	0.195	0.038	0.0105	0.66	0.397	0.527	3.03	0.040	.	.	0.83	.	0.19	100 g
CMSI 1183	0.476	0.675	0.0201	0.016	0.273	0.203	1.25	0.62	100 g
BCS 407/1	0.47	0.047	0.030	0.010	0.59	0.57	0.59	2.95	.	.	.	0.78	.	0.18	100 g
CMSI 1156	0.467	0.687	0.025	0.022	0.472	.	1.515	1.03	0.147	0.69	150 g
JSS 519-2	0.451	0.852	0.0089	0.0207	0.313	0.1133	0.0494	0.0941	0.087	.	150 g
VS UNL16/1	0.440	0.660	0.028	0.031	0.266	0.044	0.041	0.925	100 g
IPT 17A	0.415	0.724	0.014	0.021	0.260	0.074	1.76	0.820	.	.	0.039	0.259	100 g
VS UNL16	0.409	0.750	0.020	0.0237	0.300	0.082	0.049	0.958	100 g
CMSI 1125	0.409	0.742	0.015	0.011	0.376	0.086	0.063	1.053	.	.	.	0.0088	.	0.0023	100 g
IRSID 107-1	0.407	0.611	.	.	0.286	0.108	0.191	1.443	0.345	.	.	0.323	100 g
IPT 25	0.400	0.902	0.012	0.007	0.222	0.040	0.072	1.01	.	.	.	0.280	last	100 g
VS UNL14/3	0.400	0.369	0.0078	0.0040	0.545	0.193	0.169	1.72	0.78	0.182	0.313	100 g
ECRM 155-1	0.40	0.56	0.019	0.012	0.23	(0.17)	1.43	1.08	(0.01)	.	.	0.34	.	(<0.01)	100 g
JSS 151-20	0.397	1.638	0.0316	0.0195	0.1002	0.0998	3.05	0.1491	0.0110	0.0105	.	0.0474	.	0.0502	150 g
ECRM 190-1C	0.395	1.28	0.0112	0.0044	0.278	.	0.934	2.18	.	.	0.034	0.410	100 g
VS UNL15/4	0.392	0.668	0.0056	0.0051	0.531	.	0.713	2.07	.	.	.	0.205	.	.	0.66	0.0078	0.0041	100 g
CMSI 1153	0.39	4.25	0.0246	0.011	0.335	0.275	0.238	1.44	0.93	.	.	0.17	150 g
ECRM 152-1	0.39	1.61	0.032	0.043	0.18	0.21	0.15	0.09	.	.	.	0.26	.	(<0.01)	100 g
IRSID 102-1	0.389	0.367	0.012	(0.006)	0.281	0.169	4.40	0.261	.	.	.	1.20	100 g
IRSID 108-1	0.384	0.690	0.0176	0.017	0.340	0.118	0.215	2.92	.	.	.	0.538	100 g
SRM 361	0.383	0.66	0.014	0.0143	0.222	0.042	2.00	0.694	(0.021)Ca:1.0*	0.032	0.19	0.020	0.011	0.017	0.017	4.78*	0.022	0.000025	0.0042	0.010	150 g	
VS UNL19	0.382	0.864	0.0179	0.0207	0.238	0.154	0.703	0.741	100 g
CMSI 1155	0.375	0.691	0.026	0.032	0.345	0.164	0.26	0.999	150 g
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	W	As	B	Nb	Pb	Sb	Sn	Units
CMSI 1154	0.367	0.56	0.018	0.027	0.375	.	3.95	0.957	.	.	.	0.143	150 g
VS S21/5	0.333	0.278	0.0110	0.0059	0.281	0.183	0.193	2.65	.	.	.	0.755	.	0.71	4.93	(0.007)	.	0.067	.	.	.	100 g
CMSI 1152	0.33	1.02	0.032	0.024	0.40	0.17	0.26	0.18	.	.	.	1.37	.	0.25	0.50	.	0.034	150 g
ECRM 153-1	0.315	0.81	0.011	0.027	0.079	0.088	2.55	0.66	(0.003)	.	.	0.58	0.011	100 g
IPT 36	0.315	0.430	0.016	0.004	0.291	0.129	0.217	1.25	.	0.86	.	0.201	100 g
ECRM 154-1	(0.3)	(0.6)	(0.02)	(0.009)	(0.2)	(0.1)	3.54	(0.05)	.	.	(0.04)	(0.03)	last	100 g
BCS 408/1	0.285	0.51	0.037	0.028	0.23	0.66	4.45	0.102	.	.	.	0.09	.	0.031	last	100 g
BCS 408	0.28	0.64	0.043	0.030	0.24	0.73	4.58	0.090	.	.	.	0.14	.	0.19	100 g
JSS 152-18	0.277	0.440	0.0174	0.0056	0.387	0.500	1.98	0.584	0.021	.	.	1.010	.	0.100	last	150 g
VS S20/5	0.270	0.432	0.0080	0.0049	0.304	0.136	1.61	1.73	0.173	1.48	(0.004)	100 g
NCS HC28211	0.265	0.934	0.013	0.014	0.312	0.148	0.082	1.13	0.0199	0.018	0.012	0.011	0.070	0.0038	100 g
VS UNL13/2	0.228	1.60	0.022	0.024	0.553	0.185	0.125	1.11	(0.005)	.	Zr:0.076	.	.	.	100 g
GBW 01356a	0.212	0.460	0.0174	0.0117	0.270	0.031	.	0.972	.	.	.	0.191	100 g
VS S10-1/1	0.209	1.04	0.0100	0.0143	0.569	0.111	0.063	0.060	(0.005)	100 g
NCS HC28209	0.202	1.02	0.017	0.011	0.225	0.141	0.047	1.21	0.0220	0.020	0.013	.	.	0.0035	100 g
SRM 33e	0.186	0.525	(0.005)	0.009	0.262	0.070	3.36	0.068	0.030	.	.	0.224	150 g
NM 221	0.18	0.39	0.013	0.014	0.18	.	3.21	0.68	.	.	.	0.23	100 g
SRM 291	0.177	0.55	0.008	0.020	0.23	0.047	0.065	1.33	(0.002)	.	.	0.53	150 g
GBW 01351	0.177	0.50	0.017	0.019	0.254	0.170	2.84	0.781	0.067	.	.	0.136	.	.	0.193	150 g
NM 212	0.154	0.51	0.046	0.035	0.287	.	3.05	0.84	100 g
ECRM 106-2	0.153	0.727	.	.	0.238	0.078	1.430	1.030	.	.	.	0.054	.	.	.	(0.057)	.	.	.	(0.0022)	(0.010)	100 g
VS S19/5	0.114	0.431	0.0062	0.0062	0.251	0.135	3.41	1.69	0.055	.	.	0.0021	100 g
VS UNL6/3	0.095	0.555	0.0162	0.0204	0.220	0.0145	0.168	1.10	(<0.01)	.	.	0.263	.	0.235	.	.	Zn:0.0011	.	0.00017	0.0004	0.0004	100 g
VS S23-1/1	0.08	0.196	0.016	0.030	.	0.068	0.193	5.03	0.0079	.	(<0.004)	100 g
SRM 2171	0.066	0.73	0.006	0.0012	0.338	1.47	3.35	0.550	0.019	.	.	0.546	.	0.003	.	.	.	0.024	.	.	.	150 g
CMSI 1102																						

CRM MILD STEEL CHIPS, chart 2 of 2

JSS: 150 g all others: 100 g

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Mo	Ti	V	W	B	Ca	Co	Nb	Sn	Zr
JSS 150-19	0.497	0.101	0.0389	0.0292	0.207	0.049	4.00	0.310	0.0157	0.0153	0.195		0.0190
IARM 170B	0.400	0.821	(0.005)	(0.004)	0.21	(0.005)	0.197	0.009	0.230	.	(0.003)	(0.19)	(0.002)	.	(0.0004)	.	(0.005)	(0.004)	(0.002)	.
IMZ 1.10/2	0.39	0.48	0.020	0.013	0.24	0.076	0.17	1.46	0.82	.	0.20
IARM Fe434022	0.382	0.739	0.0079	0.0273	0.244	0.174	1.75	0.787	0.022	As:0.0055	0.242	0.0010	0.0047	0.011	.	.	0.093	(0.003)	0.0083	.
IMZ 1.9/3	0.38	0.55	0.025	0.016	0.28	0.101	1.62	1.30	.	.	0.16
IMZ 1.11/3	0.35	0.48	0.025	0.020	0.18	0.077	0.12	1.00	.	.	0.19
JSS 152-19	0.295	0.398	0.0202	0.0392	0.412	0.496	2.00	0.507	0.0097	0.0092	0.998	.	0.1016
IARM 378A	0.274	1.38	0.018	0.037	0.307	0.299	0.142	0.187	(0.0029)	.	0.031	(0.003)	0.0844	(0.006)	(0.0006)	.	0.013	(0.003)	0.0236	.
IARM 169B	0.232	0.75	(0.004)	(0.004)	(0.32)	(0.005)	(0.010)	0.010	0.36	.	(0.004)	0.23	(0.002)	(0.003)	0.0003	.	(0.003)	(0.004)	(0.002)	.
IMZ 1.85	0.205	1.69	0.026	0.026	0.51	0.29	0.24	0.27	(0.064)	0.064	0.007	.	0.093	(0.011)	.	0.026
IMZ 1.19/2	0.20	1.00	0.020	0.017	0.30	0.11	0.096	1.10	.	.	.	0.084
JSS 153-19	0.198	0.806	0.0098	0.0102	0.305	0.307	1.003	1.010	0.0111	0.0102	0.1289	.	0.200
IMZ 1.73/1	0.18	1.24	0.014	0.029	0.34	0.56	0.095	0.15	0.043	0.036	0.056	.	0.073	0.088	.	.
IMZ 1.31	0.14	0.81	0.022	(0.025)	0.31	0.33	(0.87)	0.55	.	.	0.50	.	(0.10)	.	0.0013
IMZ 1.33	0.14	0.69	(0.022)	(0.014)	0.26	0.43	0.88	0.52	.	.	0.51	.	(0.087)	.	0.0057
IMZ 1.76/1	0.13	1.39	0.022	0.032	0.28	0.058	0.33	0.11	0.042	0.036	0.101	0.068	.	.
IMZ 1.32	0.12	0.80	0.018	0.016	(0.21)	0.37	0.83	0.55	.	.	0.53	.	(0.093)	.	0.0021
IMZ 1.72/1	0.12	0.56	0.019	0.030	0.55	0.88	0.041	0.45	0.032	0.026	.	.	(0.047)
IARM FeF11-21	0.114	0.530	0.0067	0.0141	0.679	0.123	0.069	1.349	0.018	As:0.0048	0.614	0.0015	0.0038	.	0.0004	.	0.0062	.	0.0084	Sb:0.0017
IMZ 1.74/1	0.11	1.95	0.030	0.024	0.20	0.31	0.055	0.25	0.014	(0.009)	.	.	0.094
IMZ 1.34	0.11	0.84	0.014	(0.030)	0.31	(0.05)	0.65	0.73	.	.	0.39	.	(0.005)	.	0.0084
IMZ 1.77/1	0.11	0.37	0.029	0.027	0.18	0.17	0.051	0.32	0.012	(0.008)	.	0.021	0.046
IMZ 1.82	0.10	1.11	0.017	0.020	0.27	0.069	0.085	0.21	0.060	.	0.060	.	0.101	0.058	.	(0.0015)
IMZ 1.81	0.10	0.28	0.043	0.012	0.28	0.32	0.069	0.58	0.017	0.005
JSS 154-18	0.0995	1.212	0.0046	0.00488	0.620	0.201	0.508	2.01	0.0093	0.0086	0.405	.	0.307
IARM FeT23-18	0.068	0.82	0.012	0.006	0.18	0.046	0.53	2.47	.	0:0.0044	0.261	(0.004)	0.238	1.60	0.0020	.	0.085	0.052	(0.004)	.
JSS 155-17	0.050	0.205	0.0017	0.0021	0.498	0.407	0.151	3.03	0.0102	0.0095	0.709	.	0.397

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Mo	Ti	V	W	B	Ca	Co	Nb	Sn	Zr
--------	---	----	---	---	----	----	----	----	----	-----	----	----	---	---	---	----	----	----	----	----

RM LOW ALLOY STEEL CHIPS, chart 1 of 2

analysis listed in mass % except * which is mg/kg C12X, DH: typical analysis 50 g chips BS CE: 150 g chips all others: 100 g chips

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Al.sol	Al.insol	Co	Mo	N	Nb	Ti	V
DSZU CX012	1.220	0.237	0.0159	0.0145	0.226	0.071	0.046	0.134
BS CE26 *	0.88	0.18	0.042	0.005	0.24
C12X LA50	0.81	0.98	0.057	0.015	0.67	0.09	0.13	0.12	0.19	.	.	.	0.19	.	.	.	0.58
DSZU CX014	0.802	0.212	0.129	0.0174	0.240	(0.16)	0.125	0.230
C12X LA40	0.67	0.24	0.044	0.021	0.28	0.29	0.46	0.64	0.19	.	.	.	0.46	.	.	.	0.36
BS CE24 *	0.63	0.84	0.016	0.010	0.27	0.066	0.045	0.016	0.044	.	.	0.010	0.006
IARM 34A	0.51	0.78	0.01	0.010	0.22	0.18	0.14	0.99	0.014	.	.	0.009	0.044	0.0076	0.003	0.003	0.17
DH E2208	0.4843	0.8406	0.0144	0.0013	0.2616	0.0202	0.0416	0.9596	0.0271	.	.	0.0037	0.0105	.	0.0005	0.0018	0.1325
BS CSN-2C	0.469	0.60	0.012	0.0305	0.17	0.073	0.071	0.072	(0.006)	0.0173	.	.	.
DSZU CX03a	0.206	0.369	0.029	0.033	0.014	0.020	0.0155	0.046	200 g
DH E2110	0.2035	1.483	0.0186	0.0169	0.500	0.056	0.0179	0.023	.	0.0385	0.002	0.0042	0.00249	.	.	0.0014	0.0019
C12X 3550	0.20	0.62	0.028	0.024	0.48	.	.	.	<0.01	.	.	0.05	.	.	0.02	.	0.11

Number	As	B	B.sol	Ca*	O*	Pb	Sb	Sn	W	Zn	Zr
DSZU CX012
BS CE 26 *
C12X LA50
DSZU CX014
C12X LA40
BS CE 24 *	0.0029
IARM 34A	(0.006)	(0.0002)	.	.	(14)	.	.	0.009	(0.02)	.	.
DH E2208	0.004	.	.	26	.	.	0.0005	0.0004	.	.	.
BS CSN-2C	.	.	.	33
DSZU CX03a
DH E2110	0.006	0.00006	.	3	.	0.00048	0.0008	0.00178	.	0.00053	.
C12X 3550	.	0.001	0.08	.	.	.	<0.01

* Clearance Sale Item, no uncertainties

* Clearance Sale Items

RESULFURIZED STEEL

= class, where 1 = CRM and 2 = RM

C12X, C14X typical analysis

100 g units

#	Number	S	C	Mn	P	Si	Cu	Ni	Cr	Al	Co	Mo	N	Ti	V	W	As	Pb	Sb	Sn	Zn
1	IMZ C-123	0.38	0.25	1.57	0.030	0.23	0.093	0.057	0.16	0.032	.	.	0.0171	.	.	.	0.033	0.030	0.030	(0.007)	.
1	ECRM 085-1C	0.336	0.067	0.977	0.062	0.008	0.291	.	.	.	0.019	.	.	.	0.0021	.	.	0.0010	0.0073	.	0.0025
1	IARM Fe114422	0.323	0.406	1.34	0.0091	0.171	0.115	0.036	0.061	.	0.0061	0.0112	0.0081	0.0007	0.0023	0.0017	0.0040	.	0.0017	0.0081	.
1	IRSID 022-1	0.300	0.115	0.797	0.057
1	IMZ C-124	0.28	0.10	0.60	0.082	(0.019)	0.060	0.046	0.11	0.005	.	.	0.0059	.	.	.	0.004	(0.002)	0.002	0.009	.
1	IMZ C-122	0.21	0.27	1.33	0.073	0.43	0.25	0.25	0.19	(0.027)	.	.	0.0110	.	.	.	0.007	(0.020)	0.019	0.12	.
1	VS U2/7	0.193	0.136	1.19	0.040	0.046	0.082	0.076	0.158	(0.005)	0.166	.	.	.
1	ECRM 058-2C	0.1712	0.424	1.186	0.0098	0.1080	0.261	0.199	0.1211	.	.	0.0589	0.0107	.	.	.	0.0095
1	ECRM 051-1	0.126	0.181	1.18	(0.025)	(0.11)	(0.15)	(0.14)	(0.05)
1	C12X 3520	0.125	0.30	0.63	0.067	0.33	0.14	0.33	0.415	0.145	0.050	0.255	.	0.28	0.058	0.22	0.010	.	0.022	0.106	.
1	IARM 29E	0.121	0.193	1.19	0.0157	0.239	0.253	0.082	0.105	0.0032	0.008	0.0269	0.0093	0.0014	0.0255	.	0.0085	(0.001)	(0.003)	0.0109	(0.004)
1	IARM 348A	0.102	0.384	1.46	0.0121	0.270	0.230	0.081	0.123	(0.002)	(0.010)	0.026	(0.010)	0.0015	0.0029	(0.009)	(0.007)	(0.002)	(0.003)	0.0112	<0.003
1	IMZ C-121	0.097	0.39	1.18	0.057	(0.056)	0.032	0.029	0.036	0.016	.	.	0.0125	.	.	.	0.002	0.011	0.017	0.059	.
1	IARM 307A	0.096	0.163	1.44	0.0113	0.281	0.190	0.197	0.104	0.032	(0.010)	0.045	0.0108	0.0015	(0.0028)	(0.005)	0.008	(0.002)	<0.004	0.0090	<0.002
1	IARM 307B	(0.094)	0.162	1.45	(0.012)	(0.30)	0.191	0.195	0.105	0.034	0.0101	0.045	(0.011)	(0.003)	(0.003)	0.010	.
1	IMZ C-125	(0.057)	0.029	0.95	(0.018)	0.15	0.044	0.023	0.18	(0.007)	0.065	.	0.014	0.002	.

SILICON STEEL CHIPS WITH NITROGEN

= class, where 1 = CRM and 2 = RM

100 g units

#	Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	As	Co	Mo	N	Nb	Sn	Ti	V	W
1	ECRM 191-2C	3.267	0.0043	0.1334	0.0087	0.0029	0.0165	0.0224	0.0314	0.985	.	0.0018	.	0.0020	0.00105	.	0.0050	0.0024	.	.
1	ECRM 191-3C	3.226	0.0027	0.153	0.0097	0.0005	0.0097	0.0124	0.0242	0.81	.	0.0014	.	0.00127	0.00105	.	0.0013	0.0020	0.00043	.
1	NCS HC14213	3.18	0.076	0.081	0.0090	0.023	0.066	.	.	.	0.031	.	.	.	0.0081	.	.	.	0.138	.
1	VS S9/4 **	3.12	0.040	0.066	0.0063	0.0034	0.139	0.097	0.044	0.0106	0.0074	0.0061	0.0101	0.0050	0.0130	.	0.0040	0.0057	0.0009	.
1	IMZ 1.22/1	2.02	0.090	0.24	0.019	0.026	0.071	0.039	0.045	0.014	0.011	0.020	.	.	0.0039	.	0.0076	(0.004)	.	.
1	ECRM 196-2C	1.808	0.0060	0.364	0.00369	0.00065	0.0057	0.0401	0.0282	0.2167	.	0.00033	0.0138	0.0142	0.00178	.	0.00047	0.00253	0.00368	.
1	IARM 340A	1.63	0.414	0.755	0.011	0.001	0.103	1.80	0.84	0.062	.	(0.004)	0.006	0.39	0.0020	0.015	0.005	0.0098	0.064	(0.005)
1	IMZ 1.8/4	1.31	0.35	0.99	0.020	0.018	0.11	0.16	1.18
1	IMZ 1.21/1	1.29	0.058	0.16	0.013	0.024	0.068	0.056	0.037	0.005	0.003	0.019	.	.	0.0030	.	0.0067	(0.005)	.	.
1	BCS 404/2	1.121	0.696	0.532	0.0479	0.0228	0.427	0.393	0.774	0.017	.	.	.	0.307	0.0089	.	.	.	0.107	.
1	BCS 113	0.931	0.837	1.207	0.0595	0.0294	0.179	0.0784	1.248	0.0151	.	0.0020	0.0415	0.056	0.0109	0.0487	0.0067	0.0390	0.201	0.012

Number	B	Ca	Mg	O	Pb	Sb	Zn	Zr
ECRM 191-2C
ECRM 191-3C	0.00024	.	0.0036
NCS HC14213
VS S9/4	.	.	0.0007	.	0.0029	0.0009	0.0006	.
IMZ 1.22/1	0.0028	.	.
ECRM 196-2C	0.00014	0.00071	0.00075	.	.	.	0.00019	.
IARM 340A	0.0004	.	.	(0.0010)	.	0.0021	.	.
IMZ 1.8/4
IMZ 1.21/1	0.0025	.	.
BCS 404/2
BCS 113	0.0066	0.0029	.

SILICON STEEL CHIPS

C12X: typical analysis 50 g BS CE: 150 g all others: 100 g

Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	W	As	Bt	Bs	Sn
CRM																			
VS S57/1	3.54	0.256	.	0.0051	0.0039	.	0.758	2.98	.	.
ECRM 151-1	3.49	0.028	0.085	0.015	(0.025)
CMSI 1232	3.36	0.057	0.225	0.0124	0.020	0.314	0.316	0.259	0.166	.	.	0.0036
NCS HC20210	3.36	0.057	0.225	0.012	0.020	0.314	0.316	0.259	0.1679	0.166	.	0.0036
CMSI 1432	2.91	0.400	0.437	0.0064	0.0029	0.64	0.064	0.159	.	0.113	.	0.012	.	.	1.18
SRM 125b	2.889	0.0261	0.2751	0.0276	0.0095	0.0707	0.0375	0.0198	0.329	.	(0.007)	0.0087	(0.004)	(0.0005)	.	(0.003)	.	.	0.0034
CMSI 1431	2.15	0.051	0.600	0.0149	0.0174	0.195	0.276	0.362	.	0.065	.	0.160	.	0.043	0.77
IPT 108	1.96	0.598	0.861	0.028	0.020	0.121	0.052	0.133	.	0.019	0.006	0.017	0.004
CMSI 1435	1.74	0.666	0.725	0.0144	0.0190	0.147	0.081	0.071	.	0.132	.	0.061	.	0.129	0.40	.	.	0.0013	.
ECRM 186-1C	1.72	0.610	0.870	0.022	0.035	0.281	0.190	0.218	0.014	.	.	0.048
BCS 405/1	1.71	0.032	1.28	0.018	0.069	0.013	0.22	0.15	.	.	.	0.002	.	0.28
CMSI 1433	1.69	0.599	1.14	0.0209	0.0291	0.095	0.124	1.13	.	0.018	.	0.071	.	0.081	0.028
VS S15/5	1.69	0.558	0.701	0.0140	0.0185	0.205	0.135	0.199	(0.005)	.	.	.
IARM 342A	1.63	0.257	1.37	0.006	0.0051	0.110	1.76	0.38	0.019	N:0.0102	0.008	0.42	0.0028	0.023	(0.005)	(0.006)	O:0.0006	B:0.0004	0.021
BCS 409/1	1.46	0.082	0.44	0.025	0.021	0.048	3.06	0.94	.	.	0.014	0.65	.	0.09
Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	W	As	Bt	Bs	Sn
CMSI 1108	1.42	1.086	0.308	0.013	0.004	0.036	0.021	0.045	.	0.11	.	0.89	0.30	0.50	.	.	.	0.016	.
IMZ 1.8/4	1.31	0.35	0.99	0.020	0.018	0.11	0.16	1.18
VS S22/4	1.29	0.348	0.606	0.0090	0.0060	0.167	0.850	2.83	.	.	.	0.426	.	0.189	0.8	(0.005)	.	.	.
VS S58	1.27	0.348	1.25	0.0076	0.0077	0.100	0.086	0.123
DSZU C58	1.27	0.348	1.25	0.0076	0.0077	0.100	0.086	0.123	250 g
BCS 409/2	1.18	0.086	0.559	0.0141	0.0179	0.205	3.02	1.318	0.094	.	.	0.599	.	0.008
CMSI 1434	1.10	0.706	0.875	0.0256	0.0374	0.303	0.393	0.760	.	0.158	.	0.273	.	0.168	0.176	.	.	0.0012	.
CMSI 1189	1.09	0.283	0.438	0.022	0.023	0.247	0.224	0.300	0.132	0.128	.	.	0.171	0.144	.	.	0.0045	0.0041	. last
BCS 409 *	1.07	0.11	0.48	0.025	0.015	0.23	3.14	1.22	.	.	.	0.77	.	0.028	* sale item
NCS HC28304	1.06	0.407	0.315	0.015	0.013	0.017	0.037	5.08	0.0096	0.0056	.	1.20
BCS 404	1.04	0.67	0.52	0.050	0.018	0.31	0.46	0.68	.	.	.	0.33	.	0.100 last
NCS HC20212	0.998	0.162	0.346	0.036	0.030	0.213	0.103	0.471	0.2090	0.208	.	0.0048
BAM 128-1	0.949	0.085	0.839	0.007	0.007	0.055	0.046	0.108	0.286	.	.	.	0.890	(0.008)
BCS 405/2	0.947	0.044	0.903	0.0095	0.058	0.022	0.102	0.206	0.330	.	.	0.025	.	0.411
RM																			
C12X LA90	1.07	0.47	0.58	0.074	0.065	0.51	2.04	3.10	0.05	.	0.30	1.10	.	0.39	0.007
C12X LA20	0.98	0.24	0.55	0.026	0.042	0.44	0.73	0.81	0.03	.	.	0.10	.	0.09
Number	Si	C	Mn	P	S	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	W	As	Bt	Bs	Sn

BRAMMER STANDARD ONLINE CATALOG-IRON CHIPS

CRM **TOOL STEEL CHIPS AND POWDER WITH NITROGEN** BS: 100g powder JK 49C: 35g chips other JK, JSS, NCS, SRM: 150g chips all others: 100 g chips

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn
ECRM 288-1C	2.08	0.292	0.024	(0.0012)	0.260	0.060	0.298	12.00	0.012	0.018	0.103	0.0151	.	.	0.055	(0.68)	(0.0065)
ECRM 274-1C	1.563	0.397	0.0148	0.0096	1.057	0.0281	0.077	8.036	(0.0025)	(0.0230)	1.4551	0.0769	.	(0.0011)	4.010	0.0087	(0.0013)	(0.0005)	(0.0026)	(0.000064)	(0.001)
IARM 41D	1.519	0.256	0.021	0.012	0.256	0.047	0.114	11.5	0.014	(0.020)	0.74	0.0152	(0.004)	(0.003)	0.77	0.034	(0.01)	(0.0006)	(0.003)	(0.0008)	(0.005)
IARM 45B	1.42	0.90	0.010	0.008	0.92	0.018	0.024	0.061	0.010	0.004	0.24	0.0080	(0.002)	0.002	(0.003)	(0.004)	(0.002)	(0.0001)	(0.0005)	.	0.008
JSS 609-12	0.895	0.284	0.0242	0.00061	0.250	0.0494	0.1230	3.97	.	4.71	4.83	0.0217	.	.	1.86	6.14
IARM FeM4-18	1.42	0.298	0.013	0.062	0.60	0.104	0.127	4.16	.	0.080	5.07	0.042	.	0.0018	3.97	5.55	0.0058	Fe:79.0	.	.	0.0050
IARM FeM62-18	1.32	0.27	0.016	0.015	0.37	0.115	0.129	3.86	(0.006)	0.105	10.2	0.045	(0.017)	(0.003)	2.02	6.31	.	(0.003)	(0.003)	.	.
JSS 602-12	1.256	0.298	0.0173	0.0086	0.250	0.1513	0.1579	0.355	.	.	0.0501	0.0116	.	.	0.219	3.68
JSS 610-11	1.252	0.301	0.0171	0.00014	0.310	0.0239	0.046	4.04	.	9.72	3.05	0.0349	.	.	3.32	9.22
ECRM 283-1	1.219	0.217	0.022	0.029	0.345	.	.	4.15	.	10.27	3.41	0.033	.	.	3.28	9.66	.	0.0003	.	.	.
ECRM 268-1C	1.134	0.293	0.0209	0.0154	0.373	0.123	0.143	4.57	.	0.0290	3.20	2.03	.	.	8.47	3.70	0.0062	0.0009	.	Sb:0.0017	0.0078
IMZ C-172	1.03	0.71	0.018	0.047	0.21	0.128	0.12	4.47	0.062	0.012	0.96	0.0192	.	(0.002)	0.20	0.011	0.010
BS CSONH	1.02	(0.4)	(0.05)	0.011	(0.4)	(0.11)	(0.2)	(4.3)	H:0.0008	(0.5)	(5.8)	0.025	O:0.116	.	(3.3)	(5.7)	17025
IARM 39E	0.99	0.54	.	0.35	0.004	0.10	.	4.79	0.006	0.014	1.01	0.0096	0.006	0.0044	(0.026)	0.14	.	.	0.017	0.003	0.003
IARM 39C	0.99	0.45	0.019	0.007	0.28	0.077	0.144	4.99	0.017	0.013	0.97	0.011	0.0040	0.0029	0.21	0.011	(0.005)	0.001	0.001	(0.0001)	0.005
BAM 227-1	0.950	0.236	0.016	0.022	0.272	0.124	0.114	4.25	.	.	2.64	0.040	.	.	2.44	3.03
IARM 320A	0.93	0.33	0.021	(0.0015)	0.36	0.091	0.204	4.22	0.023	4.90	4.79	(0.014)	(0.015)	0.0032	1.76	6.01	0.013	0.0011	(0.0021)	.	0.008
ECRM 290-1C	0.91	0.24	0.016	0.016	0.08	0.081	0.33	4.18	.	5.12	4.81	0.0325	.	.	1.92	6.24
JSS 609-11	0.897	0.287	0.0246	0.00059	0.252	0.0494	0.1234	3.96	.	4.72	4.83	(0.0215)	.	.	1.87	6.15
JSS 611-12	0.888	0.335	0.0213	0.00063	0.263	0.0495	0.1114	4.00	.	0.206	5.00	0.0181	.	.	1.86	6.15
JK 12A	0.886	0.312	0.020	0.023	0.30	0.062	0.191	4.04	.	0.189	4.85	0.0259	.	.	1.94	6.42	.	.	.	0.0004	0.007
IARM 304A	0.857	0.260	0.019	0.0016	0.36	0.14	0.133	3.55	0.009	0.278	8.04	0.034	0.021	0.002	1.23	1.65	(0.01)	0.002	0.002	.	0.006
IARM FeM2-18	0.853	0.337	0.025	(0.0010)	0.26	0.098	0.182	4.23	(0.014)	0.28	4.92	0.0148	(0.021)	(0.0016)	1.90	5.81	(0.008)	Fe:81.4	(0.0016)	.	(0.007)
IARM FeM1-18	0.85	0.318	0.013	(0.003)	0.44	0.091	0.104	3.67	0.007	0.226	8.0	0.037	.	0.0044	1.19	1.98	.	.	Zr:0.0013	.	0.0041
IARM 306B	0.84	0.24	0.006	(0.001)	0.21	0.058	0.095	4.12	0.08	0.010	4.2	0.0049	0.007	(0.002)	0.98	(0.01)	(0.003)	(0.001)	Sb:0.0025	(0.001)	0.004
IARM FeT1-18	0.80	0.295	0.026	(<0.0010)	0.30	0.034	0.14	3.98	0.054	0.096	0.124	0.0195	(0.004)	0.026	1.05	18.0	.	.	(0.0027)	.	(0.010)
JSS 607-10	0.787	0.313	0.0155	0.00161	0.196	0.0325	0.0591	3.96	.	4.78	0.456	0.00328	.	.	0.849	17.25
IARM 281A	0.74	0.30	0.015	0.019	0.29	0.096	0.15	3.89	0.007	4.8	0.49	0.0064	0.094	0.004	0.90	17.6	(0.02)	(0.003)	(0.003)	.	0.02
IARM 40C	0.72	1.91	0.014	0.012	0.32	0.142	0.255	0.99	0.019	0.010	1.27	0.0083	0.003	0.008	0.010	0.009	0.008	0.0009	0.0013	.	0.008
SRM 50c	0.7193	0.3417	0.0222	0.006367	0.3102	0.0792	0.0686	4.128	.	(0.035)	0.0821	0.0117	.	.	1.158	18.445	0.0225	.	.	.	0.0183
IARM 40B	0.68	1.98	.	0.39	0.004	0.050	(0.0014)	1.04	(0.006)	0.015	1.22	0.0107	0.005	0.014	0.013	0.096	.	(0.0010)	0.012	0.003	0.003
IARM 47B	0.59	0.79	0.017	0.006	1.96	0.17	0.090	0.23	0.014	0.007	0.20	0.0092	(0.002)	0.010	0.17	(0.016)	.	(<0.001)	(0.0014)	(0.0003)	0.008
JSS 605-11	0.554	0.758	0.0197	0.0109	0.256	0.155	1.661	1.008	.	.	0.457	0.0192	.	.	0.1014	0.0104
JSS 605-12	0.543	0.750	0.0192	0.0101	0.250	0.1493	1.64	0.984	.	.	0.451	0.0175	.	.	0.1017	0.0105
IARM FeS7-18	0.51	0.271	0.021	0.0032	0.47	0.128	0.170	3.28	(0.015)	0.0106	1.39	0.0102	(0.005)	0.0014	0.233	(0.016)	(0.005)	Fe: (93.6)	0.0023	0.0003	(0.006)
IARMFed6AC-22	0.471	0.82	0.0068	(0.0019)	0.260	0.036	0.539	1.02	0.035	0.0050	0.98	0.0038	0.0037	0.0021	0.108	0.0026	0.0031	0.00023	0.0010	(0.0020)	0.0019
IARM 46B	0.45	0.27	0.019	0.0040	0.89	0.147	0.108	1.09	0.011	0.013	0.222	0.0069	0.003	0.007	0.170	1.96	(0.01)	0.0003	0.002	<0.002	0.016
ECRM 276-2C	0.399	0.365	0.0093	0.0189	1.034	0.183	0.203	4.975	.	.	1.134	0.0116	.	.	0.296	0.0133
IARM 42C	0.382	0.40	0.022	0.0037	0.85	0.066	0.051	4.86	0.018	0.022	1.29	0.0201	(0.004)	0.0125	0.84	0.32	(0.01)	0.0011	0.003	0.0007	(0.06)
ECRM 271-1C	0.3698	0.437	0.0120	0.00045	0.923	0.1371	0.1552	5.002	0.0234	0.0139	1.247	0.0137	.	0.0020	0.850	0.0054	0.0057	Ca: 0.0009	.	.	0.0084
IMZ C-174	0.33	0.32	0.029	0.023	0.93	0.17	0.13	5.10	0.080	0.011	1.24	0.0288	.	(0.001)	0.98	0.021	0.010
IMZ C-173	0.30	0.43	0.029	0.020	1.15	0.32	0.42	5.52	0.060	(0.013)	1.50	0.0342	.	(0.002)	0.47	0.10	0.012
JSS 603-8	0.30	0.31	0.012	0.012	0.32	0.055	0.084	2.32	.	.	0.13	0.0250	.	.	0.46	5.47
IARM 341A	0.298	0.226	0.0038	0.0008	0.10	0.143	7.16	0.99	0.032	4.4	1.01	0.0025	(0.005)	0.003	0.086	(0.01)	Ca:0.0011	0.0005	0.0008	(0.001)	(0.005)
IMZ C-178	0.29	0.65	0.016	0.003	0.28	0.140	2.09	1.26	0.051	0.015	0.20	0.0160	0.105	.	0.011	0.017	0.011
IMZ C-171	0.195	0.42	0.020	0.014	0.21	0.116	0.59	11.44	0.036	0.024	1.23	0.057	.	(0.001)	0.26	0.008
IMZ C-170	0.155	0.50	0.018	0.014	0.32	0.285	0.63	8.82	0.11	(0.022)	0.88	0.065	0.087	(0.002)	0.24	(0.19)	0.007
IMZ C-176A	0.15	0.75	0.018	0.003	0.35	0.103	3.62	0.41	(0.058)	(0.010)	0.027	0.0129	.	.	(0.061)	(0.015)	0.009
IMZ C-179	0.114	0.83	0.016	0.003	0.375	0.164	9.98	0.20	0.061	0.016	0.12	0.0108	(0.004)	.	0.023	(0.023)	(0.007)	.	.	.	0.010
IARM FeF9-18	0.104	0.459	(0.011)	0.0036	0.345	0.093	0.148	8.72	.	0.013	0.94	0.0323	0.078	0.0028	0.214	0.0030	0.006	.	0.0025	.	0.0062
IMZ C-175	0.099	0.25	0.016	0.0040	0.22	0.130	3.12	0.515	0.043	(0.013)	0.025	0.0099	.	.	0.014	(0.019)	0.011
IMZ C-157	0.095	0.63	0.015	0.010	0.59	0.066	0.50	9.51	0.26	.	0.71	0.051	.	.	0.26
IMZ C-177	0.076	0.32	0.013	0.003	0.24	0.110	8.33	0.18	0.043	(0.017)	0.022	0.0089	.	.	0.010	0.008

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn
--------	---	----	---	---	----	----	----	----	----	----	----	---	----	----	---	---	----	---	---	----	----

TOOL STEEL CHIPS

= Class, where 1 = CRM and 2 = RM C14X: typical analysis 50g IPT 50: 120g NCS HC174xx, HC23503: 100g other NCS, SRM: 150g others: 100g

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Nb	Ti	V	W	Sn
1	IARM Fe15V-18	3.51	0.39	0.022	0.010	0.89	0.084	0.123	5.5	.	.	0.018	1.24	.	0.0027	15.6	0.08	0.0054
1	CMSI 1406	2.00	0.294	0.049	0.0053	.	.	0.113	11.71	0.96	150g
1	IMZ 1.25/3	1.48	0.26	0.018	0.025	0.28	.	.	0.48	0.29	4.97	.
1	IPT 67	1.27	0.256	0.036	0.007	0.26	0.092	0.32	4.33	.	.	9.79	4.39	.	.	2.58	8.03	.
1	CMSI 1405	1.14	0.287	0.014	0.0046	.	0.040	0.073	0.183	2.31	150g
1	VS S26/5	1.0	0.4	0.02	0.01	0.4	0.14	0.2	4.0	.	.	5.5	0.3	.	.	2.3	10.0	.
1	NCS HC17405	0.941	0.441	0.023	0.028	0.521	.	0.095	1.99	.	.	0.122	.	.	.	0.18	19.22	.
1	IPT 50	0.916	0.280	0.031	0.015	0.326	0.091	0.33	4.49	.	.	0.260	5.54	.	.	2.00	6.40	.
1	VS S24/5	0.9	0.4	0.02	0.01	0.2	0.2	0.2	3.0	.	.	0.07	3.4	.	.	2.2	5.5	.
1	ECRM 254-1	0.88	0.30	0.023	0.029	0.19	0.09	0.12	5.12	.	.	0.32	4.92	.	.	1.94	6.97	0.019 last
1	SRM 132b	0.864	0.341	0.012	0.004	0.185	0.088	0.23	4.38	.	.	0.029	4.9	.	.	1.83	6.28	.
1	CMSI 1401	0.855	0.275	0.0261	0.011	0.232	0.041	0.046	4.08	.	.	.	4.84	.	.	2.02	5.99	100g
1	BCS 484	0.85	0.21	0.030	0.024	0.20	.	.	5.17	.	.	10.2	1.07	.	.	0.93	22.4	.
1	NCS HC28402	0.847	0.296	0.023	0.012	0.190	0.122	0.096	3.99	.	0.0020	0.023	5.06	.	0.0013	1.93	6.14	.
2	C14X HS30	0.84	0.59	0.019	0.020	0.58	0.04	0.33	4.65	.	.	10.1	1.06	.	.	1.17	19.1	.
1	ECRM 251-1	0.84	0.27	0.024	0.025	0.21	0.08	0.15	5.35	.	.	5.70	0.53	.	.	1.59	19.9	0.025
1	IMZ 1.14/4	0.83	0.33	0.028	(0.005)	0.35	.	0.16	4.09	.	.	.	0.45	.	.	1.23	17.30	.
1	NCS HC21401	0.828	0.283	0.028	0.0072	0.226	0.140	0.083	4.08	.	0.013	0.018	3.13	.	0.0044	1.33	9.23	0.017
1	SRM 134a	0.808	0.218	0.018	0.007	0.323	0.101	0.088	3.67	.	.	.	8.35	.	.	1.25	2.00	.
2	C14X HS10	0.79	0.29	0.020	0.022	0.195	0.05	0.10	3.93	.	.	0.51	1.11	.	.	0.90	16.8	.
1	NCS HC17406	0.78	0.427	0.024	0.020	0.230	.	0.134	3.64	.	.	.	0.176	.	.	0.44	18.72	.
1	VS S27/4	0.772	0.317	0.0154	0.0138	0.397	0.045	0.288	4.23	.	.	0.017	0.353	.	.	1.19	17.62	.
1	CMSI 1404	0.762	0.280	0.0241	0.026	.	0.038	0.040	4.03	.	.	.	0.245	.	.	1.30	18.16	100g
1	NCS HC20505	0.73	0.26	0.009	0.004	0.25	3.98	100g
1	NCS HC17407	0.710	0.268	0.029	0.0064	0.183	.	0.187	4.29	.	.	.	0.266	.	.	1.05	17.64	.
1	VS S25/4	0.702	0.192	0.0057	0.0053	0.276	0.143	0.242	3.31
1	BCS 482	0.70	0.28	0.021	0.025	0.13	.	.	4.09	.	.	0.24	0.27	.	.	0.98	18.1	.
1	BCS 481	0.69	0.29	0.021	0.027	0.14	.	.	3.56	.	.	0.21	0.22	.	.	0.52	14.2	.
1	BCS 483	0.67	0.29	0.019	0.025	0.11	.	.	3.21	.	.	1.94	0.17	.	.	0.54	10.8	.
1	NCS HC17408	0.577	0.233	0.015	0.0043	0.383	.	0.231	2.70	.	.	.	0.330	.	.	0.81	16.24	.
1	IPT 145	0.558	0.716	0.016	0.011	0.259	0.051	1.61	1.14	0.023	0.021	0.024	0.494	.	.	0.094	.	.
1	IPT 117	0.515	0.557	0.019	0.011	0.349	0.070	3.01	1.03	.	0.026	0.014	0.292	.	.	0.015	0.060	.
1	VS S28/5	0.503	0.339	0.0091	0.0044	0.888	0.024	0.605	6.02	1.59	.	0.0073	0.599	Pb:0.00015	.	0.64	3.46	Sb: 0.0004 Zn: 0.0012
1	CMSI 1182	0.503	0.326	0.0212	0.015	0.592	0.028	0.140	1.14	2.22	.
1	NCS HC17409	0.493	0.343	0.304	0.0048	0.493	.	0.278	4.78	.	.	.	0.411	.	.	1.49	14.96	.
1	VS S60	0.405	0.634	0.0206	0.0071	0.932	0.120	0.405	13.10	.	.	.	0.135	.	.	0.137	.	.
1	IARM 255B	0.389	0.317	0.010	(0.002)	0.91	0.073	0.062	4.82	0.032	.	0.0090	1.30	(0.006)	.	0.515	.	(0.006)
1	IPT 114	0.388	0.361	0.021	0.0023	1.02	0.064	0.165	5.20	.	0.028	0.018	1.29	.	.	0.89	0.174	.
1	CMSI 1402	0.359	0.298	0.0211	0.021	.	0.030	0.0208	2.48	.	.	.	0.055	.	.	0.27	8.39	100g
1	IRSID 112-1	0.348	0.191	.	.	1.00	0.115	0.234	4.78	.	.	.	1.21	.	.	0.604	1.78	.
1	IMZ 1.13/3	0.33	0.38	0.023	0.007	0.23	0.13	1.52	2.61	0.29	8.31	.
1	IMZ 1.26/2	0.31	0.48	0.021	0.009	0.29	0.14	4.05	1.87	.	.	.	0.11	.	.	.	1.70	.
1	CMSI 1254	0.177	0.509	0.021	0.005	0.27	0.083	4.06	1.51	1.34	.
1	IMZ 1.43	0.14	0.66	(0.010)	0.013	0.60	.	1.06	10.83	.	.	.	0.82	(0.43)	.	0.69	0.92	last of stock
1	SRM 133b	0.128	1.07	0.018	0.328	0.327	0.080	0.230	12.63	<0.005	.	.	0.052	.	.	0.071	.	(0.004)
1	VS S23/5	0.047	0.216	0.0062	0.0066	0.445	0.024	0.054	5.02	0.515	0.74	.
1	BCS 422	(0.036)	(0.09)	(0.015)	(0.025)	(0.06)	1.28	.
1	BCS 423	(0.030)	(0.07)	(0.017)	(0.027)	(0.05)	2.06	.
1	BCS 424	(0.024)	(0.09)	(0.02)	(0.024)	(0.05)	3.02	.

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Nb	Ti	V	W	Sn
---	--------	---	----	---	---	----	----	----	----	----	-----	----	----	----	----	---	---	----

LOW NICKEL STAINLESS STEEL CHIPS WITH NITROGEN

= Class, where 1 = CRM and 2 = RM analysis listed in mass % except * which is mg/kg C13X: typical analysis 100g CMSI, JK, JSS, SRM: 150 g chips all others: 100 g chips

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	As	B	Ca*	O	Pb*	Sn	W
1	IARM 13D	1.040	0.697	0.0195	0.0012	0.614	0.184	0.256	16.36	(0.006)	0.0212	0.488	0.0492	0.0074	0.0035	0.058	(0.008)	0.0005	(7)	0.0031	.	0.011	0.046
1	IARM 353A	0.98	0.95	0.019	0.025	0.49	0.13	0.265	17.01	0.0018	0.032	0.50	0.027	(0.011)	0.0015	0.116	(0.004)	(0.0006)	(3)	(0.005)	Se:0.17	0.0056	0.041
1	ECRM 291-1C	0.90	0.81	0.017	0.0088	0.91	0.071	0.56	17.15	.	0.0233	2.10	0.1142	.	.	0.39
1	IARM Fe16-18	0.718	0.605	0.013	0.0017	0.264	0.027	1.34	0.71	0.020	0.007	0.237	0.0064	(0.003)	0.0033	0.008	0.0033	(0.0008)	.	0.0012	.	.	.
1	IPT 22	0.628	0.804	0.029	0.009	0.449	0.050	0.143	16.21	.	.	.	0.008
1	BAM 226-1	0.416	0.434	0.0207	0.0094	0.514	.	0.139	13.67	.	.	0.024	0.0362	.	.	0.022
1	IARM 352A	0.341	1.13	0.0182	0.21	0.357	0.148	0.269	13.11	(0.0025)	(0.016)	0.38	0.029	(0.012)	0.0015	0.028	(0.005)	(0.0007)	.	(0.005)	.	0.0046	(0.005)
1	IARM 154C	0.339	0.423	0.0174	0.0043	0.37	0.120	0.215	12.41	(0.0034)	0.016	0.036	0.054	0.014	0.0015	0.043	(0.004)	0.0007	.	(0.0042)	.	0.0058	(0.005)
1	ECRM 272-1C	0.2815	0.600	0.0156	0.0196	0.420	0.0192	0.2445	11.927	0.0046	0.0145	0.0030	0.0508	0.0028	0.00096	0.0167	0.0116	0.0018	9.0
1	IMZ C-168	0.24	1.36	0.019	0.012	1.12	0.093	0.17	13.91	(0.004)	(0.019)	0.026	(0.057)	.	(0.003)	0.053	0.009	.
1	IARM 205D	0.232	0.736	0.0209	0.0028	0.257	0.122	0.841	12.18	0.0021	0.043	1.002	0.0484	0.013	0.0022	0.319	0.004	0.0007	(20)	0.0053	(20)	0.0047	1.07
1	IMZ C-167	0.175	1.16	0.016	0.0025	0.755	0.106	0.16	13.07	(0.018)	(0.021)	0.024	0.053	.	(0.002)	0.054	0.009	.
1	IARM Fe418-18	0.168	0.429	0.016	(0.0005)	0.32	0.22	2.00	12.4	(0.004)	0.029	0.104	0.031	(0.019)	.	0.046	.	.	.	(0.004)	.	(0.005)	2.63
1	IARM 12C	0.155	0.55	0.022	0.0032	0.34	0.33	2.23	15.78	(0.004)	0.048	0.125	0.056	0.020	(0.002)	0.040	(0.004)	0.0004	7	(0.005)	(5)	0.008	0.015
1	IARM Fe410-18	0.132	0.50	0.017	0.0014	0.29	0.046	0.280	12.2	(0.003)	0.012	0.146	0.046	0.0021	.	0.065	.	.	.	(0.009)	.	.	(0.008)
1	ECRM 296-1C	0.1166	0.676	0.0178	0.0026	0.242	0.1498	2.790	11.82	0.0275	0.0218	1.700	0.0214	.	.	0.363	0.0139	(0.0003)	.	.	1.6	0.0131	.
1	IARM Fe416-22	0.114	0.83	0.019	0.37	0.39	0.064	0.230	12.98	(0.0016)	0.019	0.027	0.036	(0.004)	0.0015	0.038	(0.003)	.	.	(0.008)	.	0.0041	(0.004)
1	IARM 291A	0.11	0.71	0.016	0.009	0.23	0.060	2.62	11.3	(0.004)	0.021	1.61	0.035	0.022	0.0011	0.29	.	0.001	.	0.014	.	0.004	(0.01)
1	IARM 14C	0.061	0.385	0.021	0.0015	0.63	0.19	0.364	24.9	0.0041	0.043	0.101	0.058	0.013	0.013	0.078	(0.003)	0.0005	.	(0.006)	(1)	0.004	0.031
1	JSS 670-4	0.0480	1.489	0.0201	0.0093	0.731	0.1093	0.201	11.15	0.0278	.	0.0996
1	SRM 345b	(0.043)	0.4902	0.0176	(0.0008)	0.7821	3.000	4.054	16.03	(0.013)	0.0660	0.1541	(0.013)	0.2143	(0.007)	0.0662	(0.0031)	<0.001	.	(0.014)	(20)	0.00568	0.0394
1	JSS 650-15	0.0356	0.487	0.0369	0.00411	0.257	0.0311	0.215	16.11	0.00203	0.0166	0.0939	0.0446	.	.	0.0239	last
1	JSS 650-16	0.0334	0.493	0.0268	0.00387	0.238	0.0153	0.1191	16.27	0.00143	0.0110	0.0330	0.0454	.	.	0.0267
1	IARM 355A	0.0274	0.47	0.0186	0.31	0.435	0.083	0.427	17.81	0.0016	0.047	0.337	0.0439	0.0095	0.0020	0.038	(0.004)	(0.0011)	.	(0.010)	(2)	(0.005)	(0.018)
1	IARM 317A	0.025	1.26	0.028	0.0007	0.39	0.21	4.19	22.5	0.005	0.064	0.249	0.123	(0.004)	(0.002)	0.061	(0.006)	0.0019	(3)	0.0032	.	0.008	0.015
1	NCS HC41318	0.023	1.25	0.030	0.0013	0.421	0.136	4.85	22.26	.	0.047	3.11	0.175	0.014	0.0014	0.038	0.0085	0.0032	0.011
1	IARME155PH-18	0.015	0.616	0.021	(0.0004)	0.430	3.35	4.79	15.13	0.014	0.024	0.129	0.0494	0.273	.	0.055	(0.0026)	(0.00005)	.	0.0028	.	0.0021	0.019
1	IARM Fe409-20	0.010	0.387	0.021	(0.0007)	0.52	0.0655	0.110	11.28	0.017	0.019	0.011	0.010	0.0041	0.141	0.075	0.0026	.	Zn:0.010	.	Sb:0.0011	0.0053	0.0036
1	JSS 670-3	0.008	0.53	0.020	(0.0005)	0.55	0.044	0.21	11.23	(0.005)	.	0.020	0.0064	.	0.26

LOW NICKEL STAINLESS STEEL CHIPS

= Class, where 1 = CRM and 2 = RM C13X: typical analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Ti	V	As	B	Ce	Pb	Sn	Units	
1	IMZ 1.38	1.08	1.14	0.010	0.016	0.94	0.34	0.63	19.12	.	0.021	.	.	.	0.033	0.0023	100 g	
1	ECRM 278-1	0.903	0.405	0.0154	0.0052	0.336	0.077	0.236	18.11	.	.	1.040	.	.	0.077	100 g	
1	IMZ 1.44	0.43	0.86	0.015	0.013	0.87	0.077	1.08	17.07	.	.	1.29	100 g	
1	IRSID 201-1	0.291	0.363	.	.	0.843	0.099	0.202	12.33	.	.	0.050	100 g	
1	BCS 339	0.29	0.41	0.022	0.022	0.36	(0.08)	0.37	12.40	100 g	
1	BCS 469	0.279	0.598	0.015	0.020	0.421	(0.02)	0.246	11.93	(0.02)	100 g	
1	BCS 472	0.227	1.02	0.032	0.029	1.05	(0.02)	1.95	15.82	.	.	0.661	.	.	(0.02)	100 g	
1	IPT 26	0.201	0.713	0.022	0.012	0.306	0.029	0.413	13.69	.	.	0.070	100 g	
2	C13X 150240	0.20	0.66	0.042	0.035	0.77	0.36	3.00	14.9	.	0.10	0.26	0.17	50 g	
1	BCS 342	0.18	0.91	0.030	0.026	0.92	(0.08)	2.16	16.15	.	.	0.69	100 g	
1	BCS 340	0.18	0.38	0.024	0.020	0.35	(0.06)	0.40	16.35	100 g	
1	BCS 473	0.172	0.494	0.019	0.030	0.604	(0.03)	(0.06)	9.06	.	.	0.95	.	.	(0.02)	100 g	
1	BCS 470	0.153	0.235	0.024	0.035	0.335	(0.02)	0.369	17.68	(0.02)	100 g	
1	VS S32/4	0.136	0.368	0.0115	0.0141	0.338	0.152	2.97	13.73	.	.	0.050	.	.	0.205	.	.	.	W:1.82	.	100 g	
1	NCS HC28318	0.134	0.456	0.027	0.0067	0.505	0.127	1.78	16.26	.	0.051	0.152	.	(0.002)	0.074	0.0064	.	.	(0.0001)	0.0058	50 g	
2	C13X 147750	0.13	1.47	0.060	0.074	0.59	0.22	1.79	17.84	.	0.16	0.51	0.72	50 g	
1	VS S34/5	0.106	0.232	0.0135	0.0035	0.519	0.159	3.97	15.52	.	.	.	0.089	.	0.511	0.58	100 g	
1	IMZ C-156	0.101	0.84	0.031	0.008	1.11	0.071	0.64	16.96	(0.034)	(0.033)	0.035	.	(0.032)	0.073	100 g	
1	BCS 341	0.100	0.43	0.016	0.024	0.31	(0.10)	0.56	24.00	100 g	
1	BCS 471	0.095	0.417	0.018	0.023	0.326	(0.02)	0.96	23.85	(0.03)	100 g	
1	IMZ C-158	0.091	1.34	0.015	0.007	2.23	0.097	0.24	25.51	1.56	.	0.025	.	0.12	0.078	100 g	
1	ECRM 279-2	0.088	0.258	.	.	0.516	0.107	1.603	15.642	100 g
1	IMZ C-155	0.078	0.84	0.018	0.012	0.49	0.084	0.77	11.07	(0.20)	.	0.056	.	0.19	0.045	W:(0.095)	100 g	
1	IMZ C-161	0.074	0.29	0.023	0.023	0.65	0.56	0.55	12.90	.	.	1.10	.	.	0.33	W:1.05	100 g	
1	NCS HC28319	0.046	0.742	0.027	0.013	0.643	3.24	3.85	15.88	.	0.115	0.259	0									

STAINLESS STEEL CHIPS AND POWDER WITH NITROGEN

# = Class, where 1 = CRM and 2 = RM		analysis listed in mass % except * which is mg/kg											Cl3X: typical analysis		JK, JSS, VS S44-2: 150 g chips										NILAB: 150 g powder all others: 100 g chips				
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	As	B	Ca*	O	Pb*	Sn	W						
1	IARM 241D	0.125	1.94	(0.003)	0.0023	1.00	0.242	8.98	18.12	0.022	0.022	(0.02)	(0.008)	0.028	0.018	0.031	(0.001)	0.0016	(12)	(0.005)	(3)	(0.0022)	(0.012)						
1	IMZ C-166A	0.108	1.99	0.019	0.005	2.51	0.025	21.93	25.53	0.036	0.030	(0.025)	0.077	0.003	0.038	(0.0026)	(0.0035)	.						
1	IMZ C-164	0.100	1.77	0.019	0.002	0.82	0.26	6.75	20.96	0.040	0.035	3.48	0.249	0.049	(0.003)	0.053	(0.005)	(0.003)	(0.025)						
1	IARM 234C	0.092	1.93	0.0090	(0.0027)	0.88	3.41	9.00	18.15	0.035	0.034	0.012	(0.01)	0.053	0.026	0.055	(0.001)	0.0023	(17)	(0.005)	(10)	0.0017	(0.006)						
1	VS S41/5	0.085	1.51	0.018	0.0069	1.41	0.155	8.85	18.65	.	.	.	0.142	.	.	2.04	(<0.005)						
1	IMZ C-165	0.082	0.98	0.017	0.007	1.42	0.040	19.01	23.28	0.038	0.029	0.025	0.105	.	(0.002)	0.042	(0.003)	0.003	.						
1	IARMF177PH-18	0.080	0.730	0.020	(0.0005)	0.51	0.36	7.11	17.08	1.09	0.048	0.350	0.0153	0.009	0.083	0.062	.	(0.0017)	.	.	.	(0.006)	(0.011)						
1	ECRM 270-1C	0.0742	0.540	0.0196	0.0007	1.517	0.1076	10.86	20.88	(0.0023)	0.0685	0.2099	0.1417	.	(0.0019)	0.0256	(0.0034)	Ce: 0.0487	La: 0.0154	.	.	.	(0.0244)						
1	IARM 316A	0.070	0.61	0.023	0.0011	1.50	0.19	10.81	21.07	0.006	0.118	0.250	0.16	(0.003)	(0.002)	0.042	0.007	Ce: 0.064	17	0.0052	(1)	0.006	0.022						
1	BAM 237-1	0.068	1.443	0.032	0.012	0.482	0.123	10.32	17.24	.	0.221	0.306	0.035	0.660	.	0.057						
1	BCS 465/1	0.066	1.380	0.021	0.012	0.405	0.098	9.24	17.31	0.026	0.053	0.092	0.010	.	0.40	0.102	.	0.0006						
1	ECRM 286-2	0.0640	1.919	0.0306	0.305	0.394	0.370	8.436	17.65	.	0.1490	0.413	0.0350	.	.	0.0951	0.0097	.						
1	IARM Fe304H-18	0.052	1.82	0.031	0.027	0.298	0.460	8.35	18.4	(0.005)	0.136	0.43	0.072	(0.010)	.	0.075	0.0076	.	.	(0.008)	.	(0.014)	0.027						
1	JSS 651-16	0.0514	0.925	0.0353	0.00384	0.557	0.350	8.04	18.12	0.0017	0.217	0.278	0.0604	.	.	0.074						
1	IARM 253B	0.051	1.61	0.13	0.011	0.46	0.44	9.11	17.64	(0.004)	0.145	0.59	0.031	0.021	0.0027	0.092	0.0052	0.0007	.	0.007	Se:0.13	(0.012)	(0.05)						
1	IPT 98 **	0.050	1.88	0.042	0.016	0.26	0.292	11.01	16.75	0.073	0.125	1.92	0.0112	.	0.41	0.053	0.019	0.053						
1	ECRM 269-1C	0.0499	1.262	0.0313	0.0010	0.441	0.366	8.044	18.150	.	0.1116	0.397	0.0460	0.0242	0.0006	0.0991	0.0061	0.0099	0.0306						
1	IARM 8H	0.049	1.81	0.0250	(0.002)	0.40	0.192	9.08	17.14	(0.005)	0.083	0.237	0.027	0.48	0.0027	0.049	.	(0.0002)	.	(0.004)	.	(0.008)	(0.016)						
1	IARM 6i	0.049	1.76	0.0208	(0.023)	0.31	0.202	9.20	17.76	0.084	0.052	0.133	(0.013)	(0.018)	0.60	0.048	(0.005)	0.0034	0.0012	.	.	(0.0060)	(0.023)						
1	JSS 654-16	0.0486	0.924	0.0210	0.00051	0.663	0.0634	19.16	24.61	0.00230	0.0996	0.0603	0.0345	.	.	0.0552						
1	IPT 24A	0.048	1.53	0.035	0.020	0.510	0.32	11.12	17.37	.	(0.16)	2.47	(0.036)						
1	IARM Fe321-22	0.048	1.46	0.0288	0.024	0.54	0.299	9.24	17.4	0.114	0.220	0.214	0.0115	0.018	0.56	0.096	0.0061	(0.0012)	.	.	.	0.0057	0.024						
1	ECRM 281-1	0.048	0.786	0.012	0.016	0.929	0.076	9.37	18.17	.	0.023	.	0.023	.	0.216	5	.	.						
1	IARM 4F	0.047	1.17	0.0195	0.0015	0.494	0.146	20.1	24.5	0.015	0.067	0.142	0.056	0.007	0.0031	0.146	(0.003)	(0.0012)	(20)	(0.004)	.	(0.005)	0.012						
1	IARM Fe303-18	0.046	1.55	0.033	0.35	0.47	0.61	8.12	17.2	.	0.140	0.42	0.069	0.015	.	0.072	0.007	(0.0012)	.	(0.006)	.	(0.015)	0.029						
1	JSS 651-14	0.046	1.19	0.027	0.0058	0.67	0.12	9.03	18.26	(0.002)	0.17	0.11	(0.0426)	last of stock						
1	IARM 4G	0.0454	1.36	0.027	0.0008	0.630	0.320	19.2	24.9	0.008	0.085	0.580	0.058	0.008	0.029	0.092	(0.005)	0.0032	(10)	(0.003)	(5)	0.008	0.017						
1	JSS 655-10	0.045	0.96	0.024	(0.0005)	0.63	0.045	9.75	17.53	(0.003)	(0.073)	0.033	0.0072	0.49						
1	IARM 4E	0.044	1.07	0.0224	0.0006	0.514	0.234	20.18	24.25	0.004	0.066	0.32	0.038	0.024	Ta:0.005	0.052	(0.005)	0.0011	.	0.0021	.	0.0060	0.046						
1	IARM 8i	0.0424	1.395	0.0352	0.0118	0.38	0.441	9.01	17.08	(0.0030)	0.301	0.416	0.052	0.60	(0.008)	0.057	.	(0.0005)	.	(0.004)	.	(0.012)	0.060						
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	As	B	Ca*	O	Pb*	Sn	W						
1	IARM 8G	0.042	1.468	0.0327	0.0126	0.36	0.390	9.02	17.20	0.0030	0.162	0.359	0.046	0.53	0.0024	0.062	(0.007)	(0.0005)	(5)	(0.003)	.	0.0107	0.032						
1	IARM 17D	0.041	4.15	0.026	0.0018	0.416	0.412	11.83	21.06	0.0032	0.23	1.52	0.311	0.14	0.010	0.118	0.005	0.001	(20)	0.003	(2)	0.0044	0.056						
1	NILAB 500HAC	0.041	1.541	0.024	0.012	0.720	0.182	11.00	16.93	.	0.139	2.73	0.1154	0.023	.	0.074						
1	IARM 6G	0.040	1.39	0.030	0.0006	0.37	0.41	9.14	17.15	0.030	0.150	0.330	0.011	0.013	0.440	0.089	.	0.0004	.	0.0017	.	0.014	0.033						
1	JSS 653-16	0.0387	1.426	0.0252	0.00034	0.610	0.106	14.26	23.18	0.022	0.167	0.119	0.0384	.	.	0.071						
1	JSS 652-16	0.0369	0.938	0.0327	0.00148	0.628	0.272	10.06	16.80	0.0022	0.209	2.06	0.0224	.	0.089						
1	ECRM 292-1C	0.0367	1.744	0.0175	0.0055	0.402	0.0391	10.09	18.00	(0.002)	0.0255	0.0464	0.0640	0.571	.	.	(0.008)	.	(6)						
1	JSS 652-17	0.0345	0.961	0.0314	0.00189	0.678	0.284	10.05	18.80	0.00249	0.192	2.04	0.0327	.	0.0843						
1	IARM 21D	0.032	0.052	0.008	(0.0014)	0.039	0.017	8.29	12.69	1.03	0.078	2.23	0.0037	(0.005)	0.016	0.017	(0.012)						
1	IARM 15C	0.032	0.760	0.019	0.0018	0.26	1.54	6.35	14.39	(0.005)	0.024	0.722	0.0148	0.63	(0.002)	0.041	0.0044	(0.0006)	.	(0.003)	(0.003)	0.009	(0.020)						
1	IARM FeN50-18	0.030	5.27	0.026	(0.0013)	0.24	0.28	11.90	21.0	(0.006)	0.081	2.01	0.26	0.18	(0.002)	0.121	.	.	.	(0.006)	.	(0.007)	0.023						
2	TL 2001C	0.0244	0.679	0.022	0.0006	0.27	0.612	7.5	25.58	.	0.046	3.49	0.279	0.024	.	0.079	0.57						
1	ECRM 297-1C	0.0223	0.897	0.0137	0.0101	0.344	0.204	12.33	18.37	0.0195	0.0413	0.290	0.0152	(0.0089)	0.0072	0.0535	0.0040	1.146	(2)	.	.	.	(0.0057)						
1	ECRM 284-2C	0.0201	1.745	0.0258	0.0237	0.537	0.1831	10.72	16.811	0.0027	0.0525	2.111	0.0151	.	0.191	0.0425	0.0063	0.0026	.	0.0099	.	0.0047	.						
2	TL 2003D	0.0193	1.068	0.0274	0.0169	0.5020	0.2773	9.231	18.25	.	0.1270	0.2871	0.0556	0.0150	.	0.0711	0.0150						
1	BCS 463/1	0.019	1.400	0.0025	0.019	0.270	0.276	10.20	18.46	.	0.116	0.265	0.063	0.0022						
1	IARM Fe2205-18	0.018	1.18	0.023	(0.0013)	0.46	0.208	5.57	22.6	(0.007)	0.104	3.20	0.17	0.011	(0.003)	0.063	.	.	.	(0.004)	.	(0.006)	0.024						
1	BCS 476	0.0171	1.755	0.0302	0.0234	0.323	0.3026	10.17	16.88	.	0.162	2.04	0.0794	0.0107	.	0.066	0.0053	.	28	.	.	0.0059	0.041						
1	IARM 239C	0.017	0.87	0.023	(0.0010)	0.38	1.49	6.14	25.8	0.007	0.039	3.33	0.228	(0.006)	(0.004)	0.083	(0.004)	0.0014	.	(0.007)	.	(0.003)	(0.05)						
1	IARM Fe2100-18	0.017	0.52	0.026	(0.0009)																								

STAINLESS STEEL CHIPS AND POWDER

= Class, where 1 = CRM and 2 = RM

C13X: typical analysis

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Ti	V	As	B	Ce	Pb	Sn	Units
1	IMZ 1.45	0.34	0.84	0.028	0.012	2.67	0.38	5.23	27.89	.	.	0.59	100 g
1	VS S30/4	0.293	0.510	0.0117	0.0053	2.51	.	6.39	12.74	.	.	.	0.060	100 g
1	BCS 468/1	0.143	1.70	0.014	0.020	1.41	.	8.90	17.96	.	0.018	100 g
1	NCS HC28315	0.110	0.841	0.024	0.0082	0.780	0.089	18.02	23.71	0.0056	0.102	0.115	0.016	(0.003)	0.077	0.0042	.	0.0004	0.0025	.	50 g
1	BCS 462	0.092	0.74	0.010	0.018	0.46	.	12.55	12.35	0.007	.	.	0.0005	.	100 g last of stock
2	C13X 190030	0.09	1.60	0.063	0.029	0.59	0.08	13.1	18.9	.	.	2.50	0.11	50 g
2	C13X 180040	0.09	1.53	0.077	0.017	1.30	0.02	11.98	21.84	.	0.16	0.60	0.78	50 g
1	BCS 463	0.088	0.77	0.015	0.017	0.51	.	9.65	18.29	(0.0004)	.	.	.	100 g
1	ECRM 282-1	0.086	1.64	0.019	0.0042	0.734	0.109	10.86	16.72	.	.	2.19	.	0.488	100 g
1	NM 220A	0.086	1.35	0.031	0.014	0.57	0.13	8.74	19.21	.	0.15	100 g
1	IMZ 1.12/4	0.084	1.47	0.040	0.013	0.30	.	10.14	17.41	.	.	1.96	.	0.52	100 g
1	NM 220	0.084	1.35	(0.030)	0.013	0.56	0.12	8.70	19.26	.	0.16	100 g last
1	DSZU CX06	0.082	1.20	0.026	0.0118	0.64	0.16	10.23	18.40	(0.1)	(0.04)	(0.13)	.	0.56	(0.03)	(0.01)	100 g
1	IMZ C-154	0.076	2.18	0.040	0.16	0.89	0.33	9.86	17.71	(0.16)	0.105	2.58	.	1.00	0.073	100 g
1	VS S62	0.071	0.064	(<0.001)	0.0128	0.032	0.0083	13.00	17.24	(0.02)	.	.	.	0.030	.	.	Ca:0.058	.	O:(0.35)	.	100 g powder
2	C13X 190020	0.07	1.05	0.031	0.053	0.76	0.105	9.18	17.1	.	.	1.99	0.07	50 g
1	NCS HC28316	0.067	1.10	0.028	0.021	0.435	0.166	10.39	16.80	0.012	0.063	2.01	0.027	(0.006)	0.048	0.0037	.	.	0.0005	0.0034	50 g
1	IARM Fe309-18	0.066	1.61	0.029	(0.002)	0.30	0.430	12.2	22.42	.	0.248	0.357	0.021	W:0.063	0.073	0.0065	.	.	Sb:0.0018	0.012	100 g
1	IMZ C-152	0.065	1.42	0.010	0.0025	0.52	0.061	9.48	18.04	.	.	0.017	.	.	0.030	100 g
1	BCS 332	0.063	0.80	0.015	0.020	0.44	(0.10)	12.45	12.80	.	(0.037)	.	.	.	(0.02)	100 g
1	BCS 333	0.066	0.79	0.016	0.020	0.45	.	9.49	18.7	100 g
1	VS S43/4	0.058	0.408	0.0153	0.0048	0.717	0.122	10.20	19.69	.	.	5.02	0.78	0.686	.	(0.004)	100 g
1	VS S38/6	0.056	1.60	0.0135	0.0030	0.970	0.096	8.47	17.06	0.445	100 g
1	IRSID 202-1	0.055	.	.	.	0.68	.	9.8	16.	.	.	2.30	.	0.54	100 g last of stock
1	IMZ 1.40	0.054	1.60	0.011	0.017	0.93	0.098	16.10	17.59	.	.	3.70	.	0.47	100 g
1	NCS HC41317	0.053	1.03	0.032	0.00071	0.571	0.383	9.19	17.17	.	0.132	0.154	0.0095	0.309	0.059	0.0047	.	.	W:0.018	0.013	50 g
1	SRM 339	0.052	0.738	0.129	0.013	0.654	0.199	8.89	17.42	.	0.096	0.248	.	.	0.058	Se:0.247	150 g
1	NCS HC28313	0.039	1.07	0.037	0.016	0.425	0.399	8.19	18.31	.	0.208	0.027	.	(0.002)	0.106	0.0035	.	.	(0.0001)	0.0051	50 g
1	VS S39/4	0.037	0.97	0.0092	0.0048	0.526	0.019	9.91	18.04	Se:0.213	.	100 g
1	BCS 462/1	0.0345	0.722	0.0053	0.0041	0.463	0.0112	12.85	11.8	.	.	0.0304	100 g
1	NCS HC28314	0.021	0.940	0.034	0.0028	0.414	0.043	8.11	18.21	.	0.216	0.025	.	0.006	0.089	0.0025	.	.	(0.0001)	(0.0001)	50 g
1	VS S37/5	0.018	1.43	0.0067	0.0079	0.696	0.133	12.28	17.39	.	0.0069	.	1.03	100 g
1	NCS HC28317	0.018	1.17	0.042	0.0057	0.317	0.334	10.34	16.61	.	0.185	2.05	.	(0.002)	0.070	0.0055	.	.	(0.0001)	0.0073	50 g
1	VS S29/4	0.017	0.636	0.0099	0.0026	0.751	0.018	19.02	11.39	0.149	.	.	.	2.88	0.0099	.	Sb:0.00027	.	0.00017	0.0006	100 g Zn: 0.0017
1	NCS HC28320	0.013	1.17	0.033	0.0021	0.464	1.49	24.23	19.67	0.024	0.096	4.47	0.042	(0.002)	0.086	0.0053	.	.	(0.0001)	0.0043	50 g
1	BCS 461/1	0.0103	0.686	0.0053	0.0051	0.374	0.0091	6.124	14.727	.	(0.004)	0.0138	100 g
1	IARM 99D	(0.006)	(0.013)	(0.004)	0.0011	(0.03)	(0.045)	18.4	(0.12)	0.117	9.24	4.8	(0.011)	0.67	(0.037)	.	0.0026	.	(0.010)	.	100 g
1	JK 25	.	(1.7)	(11.3)	(22.3)	.	.	(0.1)	0.096	.	.	150 g

#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	Nb	Ti	V	As	B	Ce	Pb	Sn	Units
---	--------	---	----	---	---	----	----	----	----	----	----	----	----	----	---	----	---	----	----	----	-------

HIGH ALLOY STEEL CHIPS AND POWDER

# = Class, where 1 = CRM and 2 = RM		C13X: typical analysis 50 g chips										CMSI, JSS, JK, and SRM 126c: 150 g chips					NILAB: 150 g powder			all others: 100 g chips				
#	Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Ti	V	W	As	B	O	Pb	Sn	Other	
1	BAM 327-2	0.152	1.289	0.0228	0.0046	2.052	0.060	19.72	24.35	0.070	0.159	0.174	0.059	.	.	0.044	
1	BCS 464/1	0.086	0.791	0.020	0.028	0.57	.	20.05	25.39	.	0.054	(0.003)	.	.	0.0004	.	.	
1	BCS 467/1	0.082	0.788	0.018	0.019	0.52	.	9.21	18.09	0.99	.	.	.	0.004	.	.	0.004	.	.	
2	C13X 142110	0.08	0.70	0.006	0.016	1.72	0.31	12.4	26.05	.	0.08	0.30	3.29	
1	NCS HC41503	0.071	0.807	0.015	0.0006	0.36	0.038	32.27	20.72	0.299	0.050	0.297	.	.	0.49	
1	BCS 479	0.0529	0.680	0.0029	0.0030	0.553	0.0052	24.87	19.922	(0.013)	(0.002)	(0.003)	0.0057	0.625	0.0306	0.0052	.	(0.002)	<0.0005	
1	BCS 475	0.050	0.89	0.037	0.008	0.21	1.94	5.66	14.14	0.013	0.22	1.59	.	0.22	0.015	.	
1	ECRM 289-1C	0.0489	1.016	0.0114	0.0027	0.531	.	24.68	14.63	0.199	0.065	1.102	.	.	2.01	0.260	.	.	0.0044	.	.	0.111	.	
1	IARM 15B	0.047	0.39	0.013	0.001	0.33	1.53	6.94	14.53	0.006	0.24	0.82	0.0355	0.65	0.005	0.033	0.12	.	.	.	0.0039	.	0.009 last	
1	VS S47/4	0.036	0.402	0.0062	0.0083	0.366	0.686	30.84	.	.	4.06	
1	ECRM 273-1	0.0336	0.785	0.0131	0.0004	0.378	3.046	4.85	14.747	.	0.0391	0.2462	0.0444	0.221	.	0.0512	.	0.0030	.	.	.	0.0021	.	
1	CMSI 1320	0.032	0.578	0.013	0.0036	0.238	0.030	22.43	4.04	0.0024	0.011	0.0019	(0.011)	.	0.0018	0.0047	(0.001)	0.0026	.	.	.	0.0022 last	.	
1	SRM 126c	0.02540	0.4684	(0.00350)	(0.0050)	0.1936	(0.0396)	36.054	(0.0625)	.	(0.0080)	(0.0110)	.	.	.	(0.001)	
1	BCS 474	0.022	1.70	0.008	0.020	0.17	0.35	14.74	19.06	.	(0.02)	3.55	.	.	.	0.30	.	0.030	
1	SRM 868	0.022	0.052	<0.003	0.0025	0.097	0.022	37.78	0.077	0.99	16.1	0.014	.	2.99	1.48	0.077	.	.	0.0078	
1	VS S33/4	0.020	0.733	0.0095	0.0058	0.354	.	22.48	15.25	1.38	.	4.38	.	0.0079	
1	VS S64	0.017	0.147	0.0023	0.0037	0.267	0.044	33.20	0.146	.	16.57	
1	ECRM 295-1C	0.0166	1.758	0.0167	0.0004	0.418	1.481	24.40	19.51	0.0203	0.0450	3.996	0.0615	.	.	0.0453	.	0.0041	0.0018	.	.	0.0025 last	.	
1	IARM 157D	0.0154	0.626	0.016	0.0005	0.28	0.196	23.9	20.31	0.020	0.102	6.08	0.203	0.149	0.009	0.050	0.036	.	0.0007	.	.	0.0036	Fe: 48.0	
1	ECRM 299-1C	0.0154	0.2678	0.0152	0.00022	0.299	0.0382	0.172	22.32	5.33	0.0187	0.0186	0.0198	.	0.1289	0.0329	.	0.0054	0.0002	.	.	.	Zr: 0.1775	
1	NILAB 501HAC	0.014	0.858	0.020	0.003	.	0.761	17.69	19.79	0.003	0.159	6.14	0.2243	0.007	.	0.044	
1	VS S42/4	0.014	0.604	0.0105	0.0049	0.958	2.85	26.43	23.30	0.0140	.	2.68	.	.	0.270	
1	VS S66	0.0124	0.0270	.	0.0054	0.050	3.30	28.28	17.54	.	1.78	.	.	.	0.486	.	.	Ca:0.202	
1	ECRM 379-1D	0.0121	1.804	0.0166	0.0006	0.393	0.984	30.83	26.79	(0.00246)	0.0390	3.290	0.0550	(0.0028)	(0.0014)	0.0663	(0.0091)	(0.0018)	0.00190	(0.0027)	(0.000038)	0.0021	Sb: 0.00057	
1	BCS 477	0.0102	1.623	0.0209	0.00039	0.473	1.340	25.07	20.38	0.0303	0.0875	4.23	0.0562	.	.	0.0527	.	0.00399	0.00198	.	Mg:0.00053	0.00453	Sb: 0.0078	
1	VS S46/5	0.01	0.4	0.002	0.003	0.1	.	29.3	.	.	17.2	
2	DH E2401	0.0048	0.0203	0.0013	0.0026	0.0222	0.0161	18.85	0.0405	.	11.46	4.64	Ca:0.0002	0.0023	1.28	0.0029	.	0.0038	.	Sb:0.0003	<0.0001	0.0016	Al.s:0.1013	
1	VS S63	0.0024	0.402	0.0166	0.0113	0.175	0.284	27.73	0.016	.	18.63	

* ECRM 295-1C also contains Fe: 48.36, Mg: (0.0003), and Sb: 0.0007

** Provisional Analysis

CAST IRON CHIPS WITH GRAPHITIC CARBON

analysis listed in mass %

IPT: 80 g

SRM: 150 g

all others: 100 g

Number	C	C.Grph	Mn	P	S	Si	Cu	Ni	Cr	Mo	Ti	V	As	Sn	Mg	N
IPT 75A	3.4	2.7	0.722	0.250	0.033	1.98	0.433	0.425	0.487	0.438	0.022	0.030
IPT 69	3.34	2.50	0.715	0.267	0.018	2.07	0.47	0.272	0.353	(0.004)	0.019
IPT 37B	3.37	2.85	0.737	0.148	0.069	1.66	0.052	0.074	0.088	.	0.034	last of stock
SRM 4L	3.21	2.66	0.82	0.149	0.043	1.33	0.240	0.042	0.118	0.040	.	0.024
NM 73 **	3.07	2.55	0.82	0.22	0.014	1.21	.	** Combined Carbon:	0.52%	last
VS Ch15/1	3.04	(0.2)	1.08	0.211	0.040	1.49	0.606	0.256	2.04	.	0.70	.	(0.006)	.	.	.
VS Ch6/11	3.01	(1.0)	0.776	0.289	0.031	2.38	.	0.79	0.261	0.318	0.028	.	Co:0.048	.	.	.
SRM 107c	2.99	1.98	0.480	0.079	0.059	1.21	0.205	2.20	0.693	0.83	(0.019)	(0.015)
VS Ch1/9	2.94	(2.1)	0.271	0.0125	0.0290	0.293	.	0.061	.	.	0.046	.	(0.004)	.	.	.
DSZU CH02X	2.90	(1.5)	1.08	0.006	0.013	1.36	(0.04)	0.66	0.59	0.23	0.16	.	.	(0.015)	.	.
SRM 6g	2.85	2.01	1.05	0.557	0.124	1.05	0.502	0.135	0.370	0.035	0.059	0.056	(0.042)	.	.	0.005
VS Ch19	2.73	1.73	0.250	0.074	0.028	0.202	.	0.081	0.067	.	0.038	.	0.0125	.	.	.
SRM 115a	2.62	1.96	1.00	0.086	0.064	2.13	5.52	14.49	1.98	0.050	0.020	0.014
ECRM 454-1	(2.53)	(1.96)	1.16	0.046	0.068	2.00	(0.07)	(0.21)	.	.	0.052	.	(0.025)	.	.	.
ECRM 453-1	(2.44)	(2.37)	0.72	1.63	0.049	3.17	0.10	0.068	0.053	.	(0.040)	0.050	0.019	.	.	.
VS Ch5/7	2.27	1.02	1.27	0.0115	0.0044	1.86	0.069	0.061	0.327	.	.	.	(0.005)	.	0.042	.
SRM 342a	1.86	1.37	0.274	0.018	0.00214	2.73	0.134	0.058	0.033	0.005	0.020	.	.	.	0.070	.
SRM 341	1.81	1.23	0.92	0.024	0.007	2.44	0.152	20.32	1.98	0.010	0.018	0.012	.	.	0.068	.
VS Ch17/1	1.66	(0.8)	1.32	0.0313	0.0087	2.08	0.0197	0.039	0.299	.	.	.	(0.002)	.	0.044	.

CRM CAST IRON CHIPS

Number	C	Mn	P	S	Si	As	Units
NCS HC18009	3.83	0.74	0.186	0.023	1.88	0.025	100 g
NCS HC16023	3.8	0.929	0.171	0.016	1.42	.	150 g
NCS HC11003	3.77	0.659	0.230	0.129	1.47	.	100 g
NCS HC37011	3.73	0.565	0.117	0.067	2.58	.	100 g
NCS HC18010	3.66	0.59	0.145	0.041	2.399	0.036	100 g
NCS HC16024	3.59	0.514	0.315	0.033	1.96	.	150 g
NCS HC18011	3.43	0.729	0.079	0.0082	1.93	0.036	100 g
NCS HC18013	3.40	0.79	0.049	0.0087	2.12	0.013	100 g
NCS HC18014	3.36	0.792	0.049	0.0087	2.136	0.012	100 g
NCS HC11003a	3.36	0.561	0.166	0.176	1.39	.	100 g
NCS HC11003b	3.36	0.386	0.135	0.154	1.82	.	100 g
NCS HC18012	3.23	0.74	0.079	0.0080	1.93	0.037	100 g
NCS HC16026	3.22	0.726	0.085	0.059	2.25	.	150 g
NCS HC18016	3.20	0.42	0.104	0.0092	2.91	0.092	100 g
NCS HC11006	3.11	0.850	0.270	0.130	1.37	.	100 g
NM 18A	3.06	0.43	0.05	0.11	2.67	.	100 g last
NCS HC13016	2.99	1.30	0.278	0.100	1.29	.	150 g
NCS HC39003	2.95	0.26	0.142	0.085	1.49	.	100 g
NCS HC18005	2.89	0.733	0.108	0.0058	2.01	0.091	100 g
NCS HC39001	2.85	0.38	0.081	0.096	2.48	.	100 g
NCS HC16022	2.83	0.721	0.094	0.067	2.19	.	100 g
NCS HC39002	2.81	0.57	0.062	0.134	1.71	.	100 g
NCS HC39004	2.78	0.78	0.066	0.082	2.17	.	100 g
NCS HC11004	2.72	0.359	0.124	0.115	2.56	.	100 g
NCS HC18002	2.67	1.36	0.051	0.031	2.94	.	150 g
NCS HC18006	2.65	0.75	0.114	0.0057	1.99	0.092	100 g
NCS HC39010	2.65	0.331	0.113	0.134	1.29	.	100 g
NCS HC39008	2.59	0.859	0.187	0.093	2.17	.	100 g
NCS HC15011	2.58	1.00	0.087	0.068	2.76	.	100 g
NCS HC13015	2.51	0.62	0.104	0.020	4.08	.	150 g
CTIF FG20	2.487	0.571	1.440	0.109	1.726	.	100 g
NCS HC39009	2.47	1.56	0.318	0.057	3.33	.	100 g
CTIF FG10	2.322	1.098	0.111	0.016	2.467	.	100 g
NCS HC11005	2.19	0.219	0.047	0.048	3.07	.	100 g

Number	C	Mn	P	S	Si	As	Units
--------	---	----	---	---	----	----	-------

CRM CAST IRON CHIPS WITH MAGNESIUM AND RARE EARTHS

unit sizes have been abbreviated as follows: A = 80 g, B = 100 g, and C = 150 g

Number	C	Mg	T.RE	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	As	Ce	La	Sn	Units	Other
NCS HC18011	3.43	0.030	.	0.729	0.079	0.0082	1.93	0.036	.	.	.	B	Re: 0.024
NM 207.3	3.13	0.026	.	0.83	0.21	0.016	1.23	0.029	1.90	0.37	0.036	.	.	.	B	
NCS HC37019	3.06	0.054	0.049	6.72	0.11	0.0041	5.80	A	
BS CE207 *	3.05	0.003	.	1.20	0.090	0.016	2.07	0.222	0.048	0.039	0.005	.	0.031	(0.001)	0.079	0.034	0.004	0.016	0.004	.	C	
ECRM 480-1	3.029	0.0172	.	0.1514	0.0021	0.0086	2.407	(0.0052)	0.4826	.	0.0163	B	
NCS HC28054	3.01	0.047	.	0.645	0.188	0.011	2.03	.	1.19	0.619	.	.	.	0.355	B	Nb: 0.095
NCS HC37020	2.88	0.068	0.047	6.40	0.11	0.0035	3.75	A	
NCS HC37021	2.79	0.028	0.045	8.77	0.10	0.0060	6.58	A	
NCS HC37018	2.78	0.049	0.041	6.80	0.12	0.0027	5.96	A	
NCS HC19017	2.77	0.070	0.070	0.570	0.015	0.014	2.52	0.046	0.031	0.042	.	.	0.037	.	0.072	0.356	B	
NCS HC11015	2.74	0.012	0.036	0.473	0.022	0.0009	2.32	0.031	0.627	0.040	.	0.021	0.011	0.0016	0.015	0.031	0.011	0.019	0.013	0.0037	A	N: 0.0047
NCS HC19018	2.70	0.083	0.083	0.625	0.024	0.011	3.10	0.049	0.031	0.043	.	.	0.035	.	0.125	0.405	B	
NCS HC19010	2.69	0.028	0.040	0.79	0.029	0.023	2.92	0.042	0.025	0.227	.	.	.	0.0016	0.109	0.236	B	
BS CE206 *	2.64	0.0006	.	0.99	0.145	0.018	2.76	0.45	0.048	0.068	0.004	.	0.029	0.007	0.078	0.038	0.004	0.011	0.004	.	C	
NCS HC37008	2.59	0.014	0.011	0.373	0.042	0.012	3.08	0.288	0.514	A	
CKD 230 *	2.55	0.040	.	0.31	0.049	0.024	1.04	1.05	1.11	0.09	.	0.01	0.01	0.05	0.01	0.02	0.005	0.01	(0.005)	0.010	B	Sb: 0.006
BS CE209 *	(2.47)	0.0013	.	0.39	0.167	0.027	2.13	0.211	0.045	0.010	0.006	.	0.030	(0.001)	0.062	0.030	0.003	0.026	0.008	.	C	
BS CE208 *	2.41	0.0008	.	0.34	0.118	0.041	1.63	0.212	0.047	0.007	0.003	.	0.031	(0.001)	0.048	0.024	0.004	0.018	0.007	.	C	
NCS HC19016	2.21	0.099	0.099	0.420	0.014	0.012	3.78	0.047	0.032	0.040	.	.	0.037	.	0.066	0.310	B	
NCS HC37005	1.92	0.073	0.059	0.955	0.041	0.0064	3.36	0.181	0.128	A	

Number	C	Mg	T.RE	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	Ti	V	As	Ce	La	Sn	Units	Other
--------	---	----	------	----	---	---	----	----	----	----	----	-----	----	----	----	---	----	----	----	----	-------	-------

* Clearance Sale Item

ALLOYED CAST IRON

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Als	Co	Mo	Ti	V	W	As	B	Bi	Pb	Sb	Sn	Units	Other	
CRM																							
CMSI 1571	3.95	0.27	0.130	0.233	1.30	0.011	0.029	4.31	.	.	0.36	0.016	0.012	100 g	
NCS HC37001	3.40	0.99	0.060	0.054	1.35	1.22	0.63	13.54	.	.	1.03	50 g	
NCS HC13010	3.35	0.699	0.147	0.045	2.44	0.018	0.300	0.96	.	.	2.39	100 g	
SRM 892	3.33	0.76	0.054	0.015	1.83	0.270	5.53	10.18	.	0.31	0.20	.	0.041	150 g	
NCS HC13011	3.23	1.20	0.310	0.045	4.30	0.243	0.919	1.36	.	.	0.639	100 g	
CKD 227 *	3.2	0.95	0.66	0.037	1.67	0.33	0.05	0.68	0.04	0.03	0.60	0.07	0.11	0.06	0.01	0.007	0.0005	0.001	0.03	0.07	100 g	Zn: 0.01	
NCS HC28034	3.15	0.795	0.321	0.082	1.67	1.04	.	0.464	.	.	0.515	0.053	150 g	
NCS HC37003	2.95	1.72	0.062	0.034	1.32	1.06	1.05	15.39	.	.	1.12	50 g	
CMSI 1569	2.86	1.07	0.058	0.028	0.36	0.42	0.25	22.52	.	.	1.14	0.005	0.039	100 g	
ECRM 482-2	2.599	0.728	0.0974	0.0491	1.815	1.231	2.284	0.675	.	.	0.454	100 g	
CMSI 1568	2.46	1.63	0.383	0.013	0.32	0.73	1.20	12.95	.	.	0.76	0.0089	0.026	100 g	
NCS HC37002a	2.42	0.71	0.058	0.064	1.05	0.90	0.23	8.93	.	.	1.74	80 g	
NCS HC11013	2.35	1.05	0.010	0.0094	1.05	.	.	15.06	.	.	2.84	0.062	0.16	100 g	
CMSI 1570	2.31	0.83	0.064	0.043	0.59	0.36	0.49	26.50	.	.	2.71	0.0051	0.039	100 g	
ECRM 451-2	2.059	1.079	0.0593	0.0315	2.092	6.26	14.01	1.097	100 g	
CTIF FA10	1.976	1.063	0.045	.	1.480	0.492	20.05	1.986	100 g	
NCS HC11012	1.95	0.926	0.0084	0.0079	0.59	.	.	13.11	.	.	0.52	0.064	0.137	100 g	
VS Ch18	1.91	4.27	0.095	0.0147	1.167	0.257	0.168	15.61	100 g	
CTIF FA20	0.643	0.368	0.045	.	1.519	.	.	28.30	100 g	
RM																							
BS CE 216 *	.	0.80	0.193	0.043	2.60	0.68	0.24	0.41	.	0.014	0.68	0.097	0.032	.	0.0070	0.00043	.	150 g	
BS CE 217 *	.	1.07	0.356	0.029	3.15	0.13	0.002	1.08	.	0.014	0.002	0.093	0.036	0.00041	.	150 g	
BS CE 219 *	.	1.23	0.505	0.038	2.47	0.415	0.228	0.31	.	0.014	0.283	0.080	0.034	0.00050	.	150 g	
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Als	Co	Mo	Ti	V	W	As	B	Bi	Pb	Sb	Sn	Units	Other	

* BS and CKD Clearance Sale Items, BS CE items have no uncertainties

CAST IRON CHIPS AND POWDER WITH CARBON OVER 3%

unit sizes have been abbreviated so that: A = CRM, 100g and B = CRM, 150g and C = RM, 50g

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	As	B	Cd	Ga	Pb	Sb	Sn	Tl	Units
ECRM 490-1	4.813	10.83	0.0267	0.0040	(0.03)	0.0088	(0.02)	0.0183	.	.	0.0030	0.0035	0.0152	A
JSS 102-10	4.66	0.244	0.127	0.0303	0.703	0.0053	0.0525	B
VS Ch13/1	4.16	1.11	0.067	0.034	2.90	0.91	0.454	1.30	.	1.16	.	.	.	(<0.002)	powder	A
NCS HC16027	4.06	0.094	0.038	0.029	0.725	0.0023	0.0023	0.010	.	0.0027	.	0.026	0.0064	0.0011	.	.	.	<0.0002	0.00013	0.00014	.	A
ECRM 478-2	4.003	0.321	0.201	0.0460	2.411	0.1276	0.151	0.251	.	.	0.0023	0.0328	0.0113	(0.0018)	0.0006	A
NCS HC16028	4.00	0.634	0.046	0.0073	1.55	0.0051	0.0045	0.036	.	0.0089	.	0.084	0.018	0.0012	.	.	.	<0.0002	0.00016	0.00018	.	A
ECRM 488-2	3.956	0.201	0.0111	0.1173	0.374	0.0256	0.1247	0.303	.	.	0.0052	0.0636	0.0545	0.0013	.	A
BCS 535	3.875	0.456	0.1438	0.0276	2.702	0.1397	1.349	0.0501	.	0.0037	.	Al:0.0087	.	As:0.0049	powder	A
BCS 527	3.873	0.316	0.1269	0.0366	1.000	0.0104	0.0229	0.0187	A
VS Ch14/2	3.81	1.05	0.061	0.034	2.09	0.427	1.52	0.724	0.265	0.625	.	.	.	(<0.005)	powder	A
NCS HC16010c	3.76	0.206	0.35	0.049	0.84	0.026	0.036	A
VS Ch2/7	3.61	0.079	0.078	0.071	0.836	0.142	0.222	0.218	0.124	0.444	.	0.293	0.521	(<0.002)	powder	A
NCS HC28015	3.58	0.97	0.080	0.014	3.02	0.091	0.0125	0.0075	B
ECRM 487-2 *	3.5730	0.0491	0.0065	0.0031	0.0898	0.0136	0.0219	0.0248	0.0151	0.0034	0.004	0.0022	0.0117	0.0045	last	A
CTIF FB20-2	3.557	(0.39)	(0.07)	0.0614	(0.935)	.	.	(0.10)	A
CTIF FB20-1	3.552	(0.39)	(0.07)	0.059	(0.935)	.	.	(0.10)	A
CMSI 1503B	3.53	1.10	0.066	0.048	1.83	0.258	0.025	A
NCS HC16004c	3.50	1.00	0.128	0.024	2.33	0.257	0.027	A
SRM 122i	3.47	0.530	0.28	0.087	0.89	0.033	0.047	0.151	0.28	0.008	.	0.024	0.012	B
CMSI 1572	3.46	1.05	0.252	0.062	3.15	0.263	0.132	0.202	.	0.047	.	0.047	0.007	A
NCS HC16008b	3.45	1.84	0.046	0.018	1.44	0.015	0.019	A
GBW 01108b	3.45	1.84	0.046	0.018	1.44	0.015	0.019	A
ECRM 476-3	3.390	0.987	0.0908	0.0493	1.813	0.2445	0.0549	0.0648	.	.	0.0038	0.0222	0.0115	0.0145	A
ECRM 485-2	3.308	0.190	0.610	0.165	0.508	0.0303	0.0742	0.0845	.	.	0.0058	A
ECRM 487-1	3.27	0.094	0.0020	0.0007	0.0060	.	0.040	0.063	0.0088	.	0.0042	.	.	0.011	last	A
ECRM 492-1	3.258	.	.	0.0854	0.0048	A
ECRM 484-1	3.20	0.395	0.121	0.230	0.717	.	.	0.155	A
CMSI 1530	3.16	0.335	0.066	0.103	0.461	0.065	0.027	0.030	0.033	.	.	.	0.56	.	.	.	0.0078	.	.	last	0.225	A
NCS HC28035	3.15	0.685	0.49	0.076	1.44	0.915	B
NCS HC28028	3.11	0.605	0.250	0.088	1.71	1.03	.	0.280	.	.	.	0.0494	0.023	B
NCS HC28014	3.05	0.57	0.300	0.079	2.67	0.194	0.018	0.022	B
GBW 01101B	3.04	1.22	0.072	0.052	1.34	0.025	0.008	A
CMSI 1501B	3.04	1.22	0.072	0.052	1.34	0.025	0.008	A
CMSI 1533	3.00	0.869	0.048	0.145	1.42	0.066	0.027	0.033	0.033	.	.	.	0.29	.	.	.	0.0077	.	.	.	0.254	A

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Co	Mo	N	Ti	V	As	B	Cd	Ga	Pb	Sb	Sn	Tl	Units
--------	---	----	---	---	----	----	----	----	----	----	---	----	---	----	---	----	----	----	----	----	----	-------

* ERM 487-2 also contains: Al: 0.079, As: 0.0063, Te: 0.0064, and Zn: 0.0012

CAST IRON CHIPS WITH CARBON UNDER 3%

analysis listed in mass % except * which is mg/kg

unit sizes have been abbreviated as follows: A = 80 g, B = 100 g, C = 150 g, and D = 200 g

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Ti	V	As	B	Bi*	Ga*	Pb*	Sb*	Sn	Tl	Units
CRM																								
NM 201.8	2.99	0.44	0.054	0.11	2.64	0.035	0.024	0.030	B
JSS 120-3	2.99	0.218	0.0124	0.0088	1.31	0.00752	(0.0278)	(0.0983)	.	.	.	0.00253	0.0057	0.00421	0.0075	C
NCS HC28025	2.98	0.698	1.80	0.087	1.80	0.201	.	0.081	C
NCS HC39011	2.96	0.57	0.082	0.058	1.67	0.061	B
VS Ch1-1	2.94	0.271	0.0125	0.0290	0.293	0.101	0.061	0.051	0.046	B
NCS HC28026	2.90	0.702	1.91	0.124	1.81	0.245	.	0.086	C
ECRM 489-1	2.860	(0.510)	0.815	0.155	1.524	0.274	(0.0056)	B
NCS HC39013	2.86	0.56	0.106	0.052	2.35	0.0101	B
NCS HC28029	2.85	0.85	0.086	0.0995	1.91	0.865	.	0.316	0.033	0.017	C
JSS 120-1	2.85	0.70	0.053	0.0095	1.32	0.29	0.12	0.28	.	.	.	(0.007)	0.0058	0.006	0.007	last of stock	C
VS Ch6/1	2.82	0.803	0.267	0.037	2.76	.	0.716	2.73	.	.	0.096	0.215	.	0.093	B
CMSI 1506A	2.809	1.48	0.039	0.062	0.856	0.045	0.0118	C
VS Ch4/7	2.78	0.742	0.194	0.0276	1.60	0.221	0.525	0.706	(0.006)	B
ECRM 428-2	2.747	0.750	0.0691	0.1105	1.751	0.0996	0.0358	0.0366	0.0311	0.0120	0.0156	B
GBW 01106b	2.71	0.98	0.077	0.089	1.14	0.036	0.007	B
NCS HC16006b	2.71	0.98	0.077	0.089	1.14	0.036	0.007	B
NCS HC11007	2.70	1.66	0.201	0.102	1.72	0.031	.	0.589	0.014	0.0067	B
NCS HC28013	2.65	0.575	0.450	0.098	2.29	0.086	0.0675	0.041	0.041	C
VS Ch16/1	2.64	1.23	0.0237	0.049	0.864	0.242	4.15	1.77	(0.007)	B
NCS HC41010	2.64	0.540	0.086	0.029	1.49	0.056	0.030	0.086	.	.	.	0.021	.	0.024	0.011	C
NCS HC41011	2.64	0.725	0.177	0.033	2.23	0.146	0.035	0.151	.	.	.	0.105	.	0.031	0.014	C
SRM 5m	2.59	0.74	0.32	0.133	1.83	0.89	0.041	0.080	.	.	.	(0.029)	(0.006)	(0.097)	0.033	C
NCS HC41012	2.52	1.24	0.635	0.032	3.86	0.114	0.037	0.115	0.017	0.071	0.033	.	.	.	8	11	.	.	.	C
VS Ch20	2.41	1.84	1.46	0.053	0.594	0.050	0.157	0.170	0.0040	(0.015)	0.089	B
CMSI 1534	2.38	1.28	0.069	0.077	2.12	0.070	0.028	0.030	.	.	0.034	.	.	.	0.40	.	.	.	73	.	.	.	0.314	B
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Ti	V	As	B	Bi*	Ga*	Pb*	Sb*	Sn	Tl	Units
GBW 01109b	2.31	0.509	0.025	0.100	0.28	0.038	0.030	B
NCS HC16009b	2.31	0.509	0.025	0.100	0.28	0.038	0.030	B
NCS HC37030	2.22	0.869	0.339	0.101	2.20	0.501	.	0.142	B
NCS HC37041	2.22	0.869	0.339	0.101	2.20	0.501	.	0.142	B
ECRM 486-1	2.21	0.841	1.00	0.023	2.43	0.548	0.057	0.104	0.020	0.074	.	B
CMSI 1509A	2.202	0.528	0.0226	0.080	0.378	0.063	0.0094	C
NCS HC37029	2.15	1.08	0.451	0.068	2.69	0.752	.	0.221	B
NCS HC37040	2.15	1.08	0.451	0.068	2.69	0.752	.	0.221	B
BCS 170/4 *	2.15	0.78	0.70	0.080	2.45	0.60	B
CTIF FB20	2.114	0.464	0.039	0.128	1.012	.	.	0.035	B
NCS HC37013	2.11	0.353	0.167	0.139	1.70	.	.	0.119	25	A
IPT 49	2.11	0.272	0.012	0.019	0.78	0.040	0.021	0.020	A
NCS HC37028	2.04	1.34	0.479	0.038	3.37	0.642	.	0.197	B
NCS HC37039	2.04	1.34	0.479	0.038	3.37	0.642	.	0.197	B
NCS HC37042	2.04	0.670	0.226	0.103	1.86	0.176	.	0.054	B
NCS HC37038	2.01	0.677	0.057	0.115	1.44	.	.	0.113	15	B
NCS HC11008	1.90	1.96	0.060	0.097	2.72	0.041	.	0.766	0.013	0.0075	B
NCS HC37037	1.90	0.780	0.110	0.055	2.34	.	.	0.024	38	B
NCS HC37036	1.67	1.05	0.085	0.024	1.90	.	.	0.055	34	B
RM																								
VS Ch12-1	2.83	1.32	0.049	0.006	2.41	B
CKD 215 *	2.46	0.76	0.087	0.17	3.08	0.43	0.081	0.15	.	0.01	.	0.05	.	0.04	0.05	0.02	0.048	.	D
Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Als	Co	Mo	N	Ti	V	As	B	Bi*	Ga*	Pb*	Sb*	Sn	Tl	Units

* Clearance Sale Item

CRM OTHER IRON BASE CHIPS AND POWDER

100 g

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Sn	Ti	V	W	As	B	O	Sb	Other
IARM Fe5140H-18	0.37	0.93	0.014	0.022	0.187	0.253	0.266	0.67	0.13	0.0081	0.031	0.007	(0.0015)	0.0069	0.0015	(0.0024)	(0.003)	(0.011)
IARM Fe422-22	0.239	0.687	0.021	0.0095	0.44	0.126	0.616	12.22	0.0024	0.022	0.97	0.050	0.013	0.0035	0.0017	0.210	1.03	0.0039	0.0006	0.0073	0.0009	Ca: 0.0029
IARM FeA100-18	0.222	(0.013)	(0.004)	(<0.0010)	(0.039)	(0.010)	11.2	2.98	(0.007)	13.4	1.19	(0.0010)	(0.003)	.	(0.008)	(0.007)	(0.006)	.	.	(0.0009)	.	.
IARM Fe8620-18	0.211	0.857	0.012	0.026	0.23	0.197	0.446	0.536	0.0246	0.0085	0.197	0.007	(0.0014)	0.0090	0.0015	0.0061	(0.004)	0.009
IARM Fe4820-18	0.192	0.541	(0.011)	0.0018	0.26	0.167	3.51	0.144	0.022	0.0107	0.287	0.007	(0.002)	0.0089	(0.0011)	0.0015	(0.004)	(0.006)	.	(0.003)	.	.
IARM FeE9310-18	0.121	0.62	0.009	0.0128	0.256	0.158	3.07	1.09	0.036	0.009	0.086	0.0070	.	0.0072	.	0.0030	.	.	.	(0.0017)	.	.
IARM FeDP1080-18	0.110	1.88	0.014	(0.006)	0.11	0.042	0.554	0.554	(0.002)	0.069	0.445	(0.009)	0.014	(0.0064)	(0.0013)	(0.0043)	(0.030)	.	.	(0.0055)	.	.
IARM Fe91-18	0.099	0.453	0.015	(0.002)	0.27	0.041	0.187	8.24	(0.006)	0.013	0.94	0.046	0.070	(0.004)	(0.0021)	0.198	(0.003)	.	.	(0.003)	.	.
IARM FeP92-18	0.092	0.737	(0.005)	(0.005)	0.20	0.074	0.82	9.4	(0.005)	0.036	0.52	(0.0036)	0.096	(0.006)	(0.003)	0.188	1.97	.	0.0026	(0.013)	.	.
IARM FeINVR36-22	0.0497	0.78	0.0041	0.0019	0.307	0.058	36.0	0.094	0.0023	0.010	0.012	0.0021	(0.0016)	0.0042	(0.0020)	0.0013	(0.0328)	0.0029	0.0019	(0.0042)	(0.0006)	Se: 0.21
IARM Fe174PH-18	0.041	0.47	0.024	(<0.0040)	0.52	3.33	4.73	15.10	0.007	0.047	0.315	0.0436	0.285	0.008	.	0.051	0.015	.	.	0.0035	.	.
IARM FeKovar-18	0.024	0.26	(0.004)	(0.0055)	(0.09)	0.077	29.0	0.068	.	17.3	0.062	.	.	0.0021	.	.	(0.020)
IARM FE2507-21	0.019	0.85	0.024	0.0005	0.36	0.125	7.12	25.2	(0.0051)	0.039	3.76	0.27	0.022	0.0034	0.0019	0.067	0.026	0.004	0.0024	(0.0048)	0.0015	Zr: 0.0013
IARM Fe254SMO-21	0.017	0.892	0.022	0.0010	0.301	0.77	18.1	19.7	0.022	0.118	6.09	0.200	(0.0083)	0.0041	0.004	0.052	0.041	0.0044	0.0009	0.0025	0.0017	Ca: 0.0024
IARM Fe2205-18	0.018	1.18	0.023	(0.0013)	0.46	0.208	5.57	22.6	(0.007)	0.104	3.20	0.17	(0.011)	(0.006)	(0.003)	0.063	0.024	.	.	(0.004)	.	.
IARM Fe415-21	0.018	0.640	0.028	0.013	0.42	0.198	3.55	11.64	0.0018	0.065	0.537	0.073	0.0049	0.0104	0.0013	0.086	0.042	0.0036	0.0008	0.0075	0.0019	.
IARM Fe904L-22	0.0133	1.14	0.020	0.0007	0.654	1.30	24.0	19.3	0.036	0.126	4.03	0.045	0.017	0.0051	0.0020	0.064	0.024	0.0044	(0.0005)	0.0018	0.0018	Ca: 0.0041
IARM Fe316LP-18	(0.006)	1.56	(0.011)	0.0041	0.29	0.0031	13.9	17.9	(0.006)	(0.006)	2.81	(0.081)	.	.	.	(0.006)	.	.	.	(0.043)	.	POWDER 75g
IARM FeC250-21	0.0028	0.022	0.0033	0.0006	0.0091	(0.0041)	18.6	(0.0093)	0.101	7.92	4.93	0.0004	0.0019	(0.0015)	0.418	(0.0074)	(0.0069)	(0.0011)	0.0029	0.0006	(0.0044)	.

Number	C	Mn	P	S	Si	Cu	Ni	Cr	Al	Co	Mo	N	Nb	Sn	Ti	V	W	As	B	O	Sb	Other
--------	---	----	---	---	----	----	----	----	----	----	----	---	----	----	----	---	---	----	---	---	----	-------